



Standard Test Method for Determination of the Nonvolatile Content in Silanes, Siloxanes and Silane-Siloxane Blends Used in Masonry Water Repellent Treatments¹

This standard is issued under the fixed designation D5095; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a procedure for the determination of the nonvolatile content (N_s) of silanes, siloxanes, and blended silane-siloxane materials used in masonry water repellent treatments and is applicable to both solvent- and waterborne materials.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement, see Section 7.

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

D3980 Practice for Interlaboratory Testing of Paint and Related Materials (Withdrawn 1998)³

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

3. Summary of Test Method

3.1 A designated quantity of test material is weighed into a preweighed aluminum dish containing the catalyst solution, mixed, allowed to stand for 60 min at room temperature, and then heated in an oven at $110 \pm 5^\circ\text{C}$ for 60 min. The

nonvolatile content of the test material is calculated by subtracting the solids of the catalyst solution from the total solids by weight of the test solution.

4. Significance and Use

4.1 This test method is used to determine the nonvolatile content of silanes, siloxanes, and silane-siloxane blended materials used in masonry water-repellent treatments. It can be used for the purpose of calculating the volatile organic compound (VOC) content of these materials under specified test conditions.

5. Apparatus

5.1 *Aluminum Dishes*, 58-mm diameter by 18-mm high with a smooth (planar) bottom surface. Precondition the dishes for 30 min in an oven at $110 \pm 5^\circ\text{C}$ and store in a desiccator prior to use.

5.2 *Forced Draft Oven*, Type IIA or Type IIB as specified by Specification E145.

5.3 *Syringes*, 1-mL and 5-mL.

5.4 *Analytical Balance*, capable of weighing to 0.1 mg.

6. Reagents

6.1 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV of Specification D1193.

6.2 *p-Toluenesulfonic Acid*, monohydrate.⁴

6.3 *Alcohol*, technical grade ethanol or isopropanol.

7. Hazards

7.1 In addition to other precautions, provide adequate ventilation, consistent with accepted laboratory practice, to limit the accumulation of solvent vapors.

⁴ The sole source of supply of the solution of *p*-Toluenesulfonic acid known to the committee at this time is King Industries, Science Road, Norwalk, CT 06852. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.47 on Concrete, Stone and Masonry Treatments.

Current edition approved June 1, 2013. Published June 2013. Originally approved in 1990. Last previous edition approved in 2007 as D5095 – 91 (2007). DOI: 10.1520/D5095-91R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

8. Procedure

8.1 *Catalyst Solution*—Prepare a catalyst solution containing a mixture of 0.5 % *p*-Toluenesulfonic acid in either ethanol or isopropanol. Thoroughly mix the solution. Prepare sufficient catalyst solution to perform all tests.

8.1.1 The nonvolatile content of the test material can be calculated only if the same catalyst solution is used throughout the test. Each time a new batch of catalyst solution is used, its nonvolatile content must be determined.

8.2 Determine the nonvolatile matter, in triplicate, of the catalyst solution as follows:

8.2.1 Weigh an aluminum dish to 0.1 mg. Record the weight as W_1 .

8.2.2 Using a 5-mL syringe, weigh 3 ± 1.0 g, to 0.1 mg, by difference, of the catalyst solution into the preweighed aluminum dish. Record the weight of catalyst solution as W_3 .

8.2.3 Heat the aluminum dish containing the catalyst solution in a forced draft oven for 60 min at $110 \pm 5^\circ\text{C}$.

8.2.4 Remove the dish from the oven and immediately place in a desiccator. Seal the desiccator and allow the dish to cool to ambient temperature.

8.2.5 Reweigh the dish to 0.1 mg. Record the weight as W_2 .

8.2.6 Calculate the nonvolatile matter of the catalyst solution, N_c , in accordance with 9.1.

8.3 Determine the percent nonvolatile content, in triplicate, of the test specimen as follows:

8.3.1 Thoroughly mix the test materials before use.

8.3.2 Weigh an aluminum dish to 0.1 mg. Record the weight as W_4 .

8.3.3 Using a 5-mL syringe, weigh 3 ± 1.0 g, to 0.1 mg, by difference, of the catalyst solution into the preweighed aluminum dish. Record the weight as W_6 .

8.3.4 Using a 1-mL syringe, weigh 1.0 ± 0.1 g, to 0.1 mg, by difference, of the test specimen into the weighing dish containing the catalyst solution. Record the weight of the test specimen as S .

8.3.4.1 Weighings must be done quickly to limit weight loss due to volatilization. If there is insufficient moisture present when testing solvent-borne silane materials, it is advisable to add up to 0.3 g of reagent grade water to the dish containing the mixture of catalyst and test solutions.

8.3.5 Gently swirl the dish to mix the materials. Allow the materials to stand at room temperature for 60 min.

8.3.6 Heat the dish containing the mixture of catalyst and test solutions in a forced-draft oven for 60 min at $110 \pm 5^\circ\text{C}$.

8.3.7 Remove the dish from the oven and immediately place in a desiccator. Seal the desiccator and allow the dish to cool to ambient temperature.

8.3.8 Reweigh the aluminum dish to 0.1 mg and record the weight as W_5 .

8.3.9 Calculate the nonvolatile content, N_s , of the test specimen in accordance with 9.2.

9. Calculation

9.1 Calculate the nonvolatile matter, N_c , in the catalyst solution as follows:

$$N_c = (W_2 - W_1)/W_3 \quad (1)$$

where:

N_c = nonvolatile matter of catalyst solution expressed as a decimal fraction,

W_1 = weight of aluminum dish, g,

W_2 = weight of dish plus catalyst solution after heating, g, and

W_3 = weight of catalyst solution before heating, g.

9.2 Calculate the nonvolatile content, N_s , in the test specimen as follows:

$$N_s = 100 \frac{[(W_5 - W_4) - (W_6)(N_c)]}{S} \quad (2)$$

where:

N_s = nonvolatile content of test specimen, percent,

W_4 = weight of the aluminum dish, g,

W_5 = weight of aluminum dish plus the catalyzed test material after heating, g,

W_6 = weight of catalyst solution used in test specimen before heating, g,

N_c = nonvolatile matter of catalyst solution, decimal fraction, (average of two determinations), and

S = weight of test specimen before heating, g.

10. Report

10.1 Report the following information:

10.1.1 The average values obtained for the nonvolatile content of the catalyst solution, N_c .

10.1.2 The average values obtained for the percent nonvolatile content of the test specimen, N_s .

11. Precision and Bias

11.1 The precision estimated for this test method is based on an interlaboratory study in which one operator in each of five laboratories tested in triplicate on two different days four water repellent materials containing between 14 to 65 % nonvolatiles. The results were analyzed statistically in accordance with Practice D3980. The intralaboratory standard deviation was found to be 0.283 % absolute with 17 df and the interlaboratory coefficient of variation 7.02 % relative with 16 df. Based on the standard deviation and coefficient of variation, the following criteria should be used for judging at the 95 % confidence level, the acceptability of results.


11.1.1 *Repeatability*—Two results, each the mean of triplicates, obtained by the same operator should be considered suspect if they differ by more than 0.84 % absolute.

11.1.2 *Reproducibility*—Two results, each the mean of triplicates, obtained by operators in different laboratories should be considered suspect if they differ by more than 7.02 % relative.

11.2 *Bias*—Bias has not been established for this test method.

12. Keywords

12.1 masonry water repellents; nonvolatile matter content; silanes; siloxanes

 **D5095 – 91 (2013)**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).