



Standard Test Method for Rubber Property—Pusey and Jones Indentation¹

This standard is issued under the fixed designation D531; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the indentation of rubber or rubber-like materials by means of the Pusey and Jones type of plastometer. This apparatus is used to measure the depth of indentation of an indenter, under fixed force into the surface of a specimen.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D1349 Practice for Rubber—Standard Conditions for Testing](#)

[D1415 Test Method for Rubber Property—International Hardness](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

NOTE 1—The specific dated edition of the practice that prevails in this document is referenced in the Section 9.

3. Significance and Use

3.1 The Pusey and Jones indentation value is the depth of indentation, expressed in hundredths of a millimetre, of a ball 3.175 mm (0.1250 in.) in diameter under an expressed force of 9.8 N (2.2 lbf). This value may be used to compare the indentation resistance of rubber and rubber-like materials.

¹ This test method is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.10 on Physical Testing.

Current edition approved Aug. 1, 2015. Published January 2016. Originally approved in 1939. Last previous edition approved in 2010 as D531 – 00 (2010). DOI: 10.1520/D0531-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 The indentation value obtained should not be confused with hardness as measured by Test Method [D1415](#), since in the latter test the rubber immediately adjacent to the indenter is precompressed.

4. Apparatus

4.1 *Plastometer*, an instrument consisting of an indenter, a mass for applying the stated force on the indenter, a micrometer for indicating the depth of the indentation, a specimen holder and support.

4.1.1 *Indenter*, for indenting the specimen, consisting of a vertical steel shaft attached, at the upper end to a depth indicator gage, and terminating in a steel sphere having a diameter of 3.175 ± 0.015 mm (0.1250 ± 0.0005 in.) of polished, noncorrosive hard metal treated to resist wear.

4.1.2 *Mass*, the mass shall be 1000 ± 0.01 g.


4.1.3 *Depth Indicator Gage*, a micrometer attached to the plastometer, either an electronic digital gage or analog dial gage, capable of displaying indenter movement (indentation) in increments of at least 0.01 mm (0.0004 in.) and having travel of 0 (zero) to no less than 3 mm (0.12 in).

4.1.4 *Support*, a support frame, or fixture, for the plastometer, shall be configured so that the specimen holder and hence, the specimen, are perpendicular to the indenter support shaft and that the mass may be independently raised or lowered vertically, permitting the indenter to rest on the surface of the specimen and the mass to be subsequently applied.

4.1.5 *Specimen Holder*, for the standard, or reference specimen described in [5.1](#), shall consist of a clamping fixture of two metal plates secured by two threaded bolts. The uppermost plate shall have a hole and a slot, as depicted in [Fig. 1](#), to allow for the unencumbered introduction of the indenter to the specimen.

4.1.5.1 The purpose of the specimen holder is to support the specimen in a manner that reduces, or eliminates, relative positioning or movement that may adversely affect test determinations.

4.1.5.2 In routine testing, a specimen holder, a support, or both, of other, but similar, configurations may be employed to accommodate specimens other than those described in [5.1](#), refer to [5.1.1](#).



mm		in.
A, min	80	3.15
B, min	30	1.2
D	17 to 18	0.67 to 0.70
E	11 to 12	0.43 to 0.47
F	60	2.36

FIG. 1 Holder for Test Specimens

5. Test Specimens

5.1 The standard, or reference, test specimen shall be a uniform molded rectangular block a minimum of 13 mm (0.51 in.) in thickness, 30 mm (1.18 in.) in width, and 75 mm (2.95 in.) in length. The upper and lower surfaces, those opposite surfaces with the largest area, shall be parallel to within ± 0.5 mm (± 0.20 in.).

5.1.1 The standard, or reference, test specimen shall be used when the plastometer is employed for the purpose of determining a standard, or reference, either within or between laboratories, that is, in other than routine testing.

5.2 In routine testing, specimens may be used with a configuration other than those of the standard, or reference, test specimen described in 5.1.

6. Procedure

6.1 *Measurement of Indentation of Standard, or Reference Specimens:*

6.1.1 When measuring the indentation on a standard, or reference specimen as described in 5.1, secure it in the specimen holder (refer to Fig. 1 and Section 4.1.5) with the bolts tightened sufficiently to hold it firmly without measurable compression.

6.1.2 Place the specimen holder on the support.

6.1.3 Mount the plastometer over the specimen so that the indenter shaft is perpendicular to the support and hence the specimen holder, to within ± 0.05 mm (± 0.002 in.).

6.1.4 The plastometer and support shall be placed upon a flat surface in a manner that prevents unsteadiness or movement other than described in 6.3.

6.1.5 Lower the indenter shaft until the indenter is at the moment of contact with the specimen.

6.1.5.1 Adjust the depth indicator gage to record indentations up to 3 mm (0.12 in.).

6.1.5.2 Adjust the depth indicator gage so the display indicates zero.

6.1.6 Lower the mass onto the indenter, in a fashion that eliminates shock, until the mass rests fully on the indenter.

6.1.7 The amount of indentation displayed on the depth indicator gage 60 s (± 1 s) after the application of a total force of 9.8 N, shall be recorded.

6.1.8 Make no less than 3 such determinations on the specimen at least 13 mm (0.51 in) apart and from any edge.

6.1.9 The median of the determinations, expressed as a whole number indicating hundredths of millimetres, shall be reported as the Pusey and Jones Indentation Value, refer to 8.1.1.

6.2 *Measurement of Indentation of Specimens for Routine Tests (Nonstandard Specimens):*

6.2.1 When making determinations on specimens other than those described in 5.1, specimen holders, supports or other suitable fixturing, similar to those previously described, may be employed and the procedure in 6.1 may be followed, otherwise:

6.2.2 Mount the plastometer over, or directly upon, the specimen, so that the indenter shaft is vertical and perpendicular to the specimen surface and both are level, as determined by means of a spirit level or similar device.

6.2.3 Position curved (convex or concave) or irregularly shaped specimens, so that the center line of the indenter shaft is perpendicular to the tangent of the specimen at the point of contact of the indenter and that determinations shall be made in accordance with 6.2.8.

6.2.4 The plastometer and specimen, or any fixtures employed, shall be secure and situated in a manner that prevents unsteadiness or movement other than described in 6.3.

6.2.5 Lower the indenter shaft until the indenter is at the moment of contact with the specimen.

TABLE 1 Special Precision Results—Pusey and Jones Indentation

Material	Mean Level	Within Instrument ^A			Between Instrument ^A		
		$S(w)$	$r(w)$	$(r)(w)$	$S(B)$	$r(B)$	$(r)(B)$
1	11.7(a)	0.265	0.750	6.4	0.374	1.06	9.1
2	20.9	0.296	0.838	4.0	0.309	0.875	4.2
3	38.1	0.379	1.073	2.8	0.668	1.89	5.0
4	63.0	0.192	0.543	0.86	1.67	4.73	7.5

^A $S(w)$ = within instrument, standard deviation.

$r(w)$ = repeatability (within instrument) measurement units.

$(r)(w)$ = repeatability (within instrument), %.

$S(B)$ = between instrument, standard deviation.

$r(B)$ = repeatability (between instrument) measurement units.

$(r)(B)$ = repeatability (between instrument), %.

(a) = Pusey and Jones indentation number.

6.2.5.1 Adjust the depth indicator gage to record indentations up to 3 mm (0.12 in).

6.2.5.2 Adjust the depth indicator gage so the display indicates zero.

6.2.6 Lower the mass onto the indenter, in a fashion that eliminates shock, until the mass rests fully on the indenter.

6.2.7 The amount of indentation displayed on the depth indicator gage 60 s (± 1 s) after the application of a total force of 9.8 N, shall be recorded.

6.2.8 Make no less than 3 such determinations on the specimen at least 13 mm (0.51 in) apart and from any edge.

6.2.9 The median of the determinations, expressed as a whole number indicating hundredths of millimetres, shall be reported as the Pusey and Jones Indentation Value, refer to 8.1.1.

6.2.10 When tests are performed on specimens other than those described in 5.1 and without the specimen holder and support the results shall be compared only to those obtained on similarly configured specimens under similar conditions.

6.3 *Vibrator*—A small vibrator that is activated prior to the mass being applied to the indenter and operates continuously during a test to overcome any friction in the apparatus. An instrument that vibrates approximately 120 times per s, with an amplitude of vibration of the fixed platform of the tester varying from approximately 0.002 to 0.005 mm (0.0001 to 0.0002 in.), has been found satisfactory.

6.4 Such a vibrator may consist of a simple-cored solenoid fastened to the top of a C-shaped piece of strap steel. The lower part of the solenoid core is a loose cylindrical piece of steel with a shoulder at its lower end. When the current is off, the loose-cored section rests on a screw projecting from the bottom of the C-shaped support. When the current is on, the loose-cored section is attached to the solenoid but is restrained by a flat split ring of spring brass through which the cored section passes, and which bears on the shoulder of the cored section. The cored section is caused to vibrate by the alternating forces of attraction by the solenoid and repulsion by the flat ring acting as a spring. A small plate bearing a toggle switch for closing the circuit to the solenoid is fastened to the top of the C-shaped piece of strap steel by means of the same bolt that holds the solenoid. The bottom of the C-shaped piece is fastened by screws to a portion of a brass nut that serves to clamp the vibrator to one upright post of the tester.

7. Laboratory Atmosphere and Test Specimen Conditioning

7.1 The tests shall be conducted in the standard laboratory atmosphere as defined in Practice D1349, Terminology: “standard laboratory atmosphere.”

7.2 Test specimen conditioning shall be in accordance with Practice D1349, Section 5 Conditioning of Materials for Testing.

7.3 These conditions may be modified if agreed upon between laboratories or between supplier and user and are in accord with the alternative procedures described in Practice D1349.

7.4 When tests are conducted, within a laboratory, for purposes of research, development, or empirical study and reported beyond that laboratory, the conditions shall be reported in accordance with Practice D1349.

8. Report

8.1 State that the test was made in accordance with this designation and include the following information:

- 8.1.1 The Pusey and Jones indentation number,
- 8.1.2 Description of test specimen including dimensions,
- 8.1.3 Date of vulcanization, if known,
- 8.1.4 Duration and temperature of vulcanization, if known,
- 8.1.5 Temperature of test room, and
- 8.1.6 Date of test.

9. Precision and Bias³

9.1 These precision statements have been prepared in accordance with Practice D4483. Refer to Practice D4483 for terminology and other testing and statistical concepts.

9.2 The Pusey and Jones Indentation Plastometer is used mainly in the rubber roll industry. In this program no inter-laboratory precision data were obtained due to the limited use of this test method. The precision program consisted of tests by one operator on three different (in-house) instruments on three different days. Four materials were tested. A test result is the median value of three separate (determinations) indentation measurements.

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D11-1028.

9.3 **Table 1** gives the within and among “instrument” precision. Repeatability refers to within instrument variation; reproducibility refers to among (between) instrument variation, with the same operator for both.

9.4 *Bias*—In test method statistical terminology, bias is the difference between an average test value and the reference or true test property value. Reference values do not exist for this test method since the value or level of the test property is exclusively defined by the test method. Bias, therefore, cannot be determined.

10. Keywords

10.1 hardness; indentation hardness; relative hardness; plastometer

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>