



Designation: D5356 – 17

Standard Test Method for pH of Chrome Tanning Solutions¹

This standard is issued under the fixed designation D5356; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the pH of chrome tanning solutions.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3898 Test Method for Chromic Oxide in Basic Chromium Tanning Liquors

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *pH, of a solution*—the negative logarithm of the hydrogen ion activity.

3.1.1.1 *Discussion*—A solution of pH 7 is neutral at 24 °C. Lower numbers indicate increasing acidity, higher numbers indicate increasing alkalinity.

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.06 on Chemical Analysis

Current edition approved May 15, 2017. Published May 2017. Originally approved in 1993. Last previous edition approved in 2015 as D5356 – 10(2015). DOI: 10.1520/D5356-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 The chrome tanning liquor is diluted to a concentration of 25.0 ± 0.5 g chromic oxide equivalent per litre, allowed to come to equilibrium and the pH is then measured with the appropriate meter.

5. Significance and Use

5.1 This test method is designed to measure the pH of a chrome tanning solution which has been diluted to a specific concentration. This is considered to be a measure of the acidity or alkalinity of the solution.

5.2 This test method is suitable for quality control in the manufacture of leather.

6. Apparatus

6.1 *pH Meter*, either battery or line-operated equipped with appropriate electrodes. The meter shall have a maximum scale division of 0.1 pH unit and reproducibility of 0.05 pH unit.

7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled water, deionized water, or water of equal purity.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

7.3 *Buffer Solutions*—Commercially available buffer solutions of 2.00 ± 0.02 pH and 4.00 ± 0.02 pH shall be used for meter standardization, in accordance with the manufacturer's recommendations.

8. Standardization

8.1 Standardize the meter against the pH 4.00 standard, in accordance with the manufacturer's recommendations. The buffer standard shall be at room temperature and the temperature compensator shall be set at this temperature.

8.2 Read the pH of the 2.00 standard with no adjustment of the meter. The standard shall be at a temperature no more than 2 °C different from that at which the meter was standardized against the pH 4.00 standard, and the temperature compensator set accordingly.

8.3 If the reading of the pH 2.00 buffer does not differ by more than 0.05 pH from the published value under the temperature conditions, the standardization is satisfactory and the meter ready for use. If the error exceeds 0.05 pH, the meter and electrodes must be checked and the necessary adjustments made to obtain conformity.

9. Procedure

9.1 The sample shall be representative of the chrome tanning liquor to be tested. It shall be adjusted to an equivalent chromic oxide concentration of 25.0 ± 0.5 g/L (**Note 1**) and allowed to stand at room temperature for at least 60 min before measuring pH in order to attain dilution equilibrium (**Note 2**).

NOTE 1—The concentration adjustment shall be based on the analysis of the liquor for chromium as based on Test Method **D3898**. In most cases, the concentration of the sample will be above 25 g chromic oxide per litre and measurement of the appropriate quantity of liquor in a graduated

cylinder or weighed quantity shall be transferred to a 100-mL volumetric flask. Diluting with water at room temperature will give sufficiently accurate dilution. Spent chrome tanning liquor does not require dilution.

NOTE 2—If the dilution described in **Note 1** takes place essentially at room temperature, the change in pH is sufficiently slight that 60-min equilibration will suffice. If the pH is measured before 60 min has elapsed, report the time. If it is necessary to concentrate the solution by boiling, or the original solution was hot, then the diluted sample should be allowed to reach room temperature before testing, or the pH test may be repeated until constant to 0.1 pH are obtained.

NOTE 3—If measuring the pH of spent chrome tanning solutions, it may be necessary to remove grease and sediment prior to measurement.

9.2 After standardization of the meter (**Section 8**), rinse the electrodes three times with water and remove surplus water with a soft, nonabrasive tissue. Do not let the electrodes dry. Immediately immerse the electrodes in the prepared sample to a depth recommended by the manufacturer, set the temperature compensator to the temperature of the solution (25 ± 5 °C), allow the meter to equilibrate, and read the pH to the nearest pH unit of the meter.

10. Report

10.1 Report the following information:

10.1.1 pH of sample = A (25 g Cr₂O₃ per litre)

where:

A = pH reading obtained in **Section 9**.

10.1.2 pH of spent chrome tanning liquor = B (*undiluted*)

where:

B (*undiluted*) = pH reading obtained in **Section 9**.

11. Keywords

11.1 chrome tanning solutions; pH; spent tanning liquor

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/