



# Standard Test Method for Moisture Resistance of Electrical Insulating Varnishes<sup>1</sup>

This standard is issued under the fixed designation D5637; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the mechanical performance of electrical insulating varnishes subjected to high humidity conditions.

1.2 The values stated in SI units are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See 7.1.*

NOTE 1—There is not ISO or IEC equivalent.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D2519 Test Method for Bond Strength of Electrical Insulating Varnishes by the Helical Coil Test](#)

2.2 *IEEE Standard:*

[IEEE 117 Standard Test Procedure for Evaluation of Systems of Insulating Materials for Random-Wound AC Electric Machinery](#)<sup>3</sup>

## 3. Terminology

3.1 See Test Method [D2519](#).

## 4. Summary of Test Method

4.1 Flexural strength tests are made on varnish-treated helical coils to determine the force required to break the coil under specified conditions both before and after exposure to high humidity conditions.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders and Encapsulating Compounds.

Current edition approved Jan. 1, 2012. Published January 2012. Originally approved in 1994. Last previous edition approved in 2005 as D5637 – 05. DOI: 10.1520/D5637-05R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from Institute of Electrical and Electronics Engineers, Inc., 3 Park Avenue, 17<sup>th</sup> Floor, New York, NY 10017.

## 5. Significance and Use

5.1 This test method is useful for the evaluation of insulating varnish performance in high humidity exposure.

## 6. Apparatus

6.1 *Tensile Testing Machine*—See Test Method [D2519](#).

6.2 *Test Fixture*—See Test Method [D2519](#).

6.3 *Exposure Chamber*—A chamber capable of maintaining a minimum of 100 % relative humidity with condensation, at  $30 \pm 1^\circ\text{C}$ .

NOTE 2—The exposure chamber described in IEEE 117 has been found suitable.

## 7. Safety Precautions

7.1 It is unsafe to use liquid varnish at temperatures above the flash point without adequate ventilation, especially if the possibility exists that flames or sparks are present. Store varnish in sealed containers.

## 8. Test Specimens

8.1 Prepare a minimum of ten test specimens in accordance with Test Method [D2519](#) using a wire mutually agreed upon by interested parties.

## 9. Procedure

9.1 Condition half of the test specimens in the exposure chamber maintaining a minimum of 98 % relative humidity for  $336 \pm 1$  h.

9.2 Test specimens both conditioned and unconditioned as described in Test Method [D2519](#) at standard laboratory conditions. If possible, test conditioned specimens in the exposure chamber. When specimens are not tested in the exposure chamber, they should be removed one at a time from the chamber and tested as soon as possible. The time after removal from the chamber and room conditions will possibly affect test results. Take care to minimize any change in humidity within the cabinet during testing.

## 10. Report

10.1 Report the following information:

10.1.1 Description of varnish,

10.1.2 Identification of wire used,

10.1.3 Cure time and temperature and number of dips used to prepare the coils,

10.1.4 Average bond strength in newtons (pounds-force) of unconditioned coils,

10.1.5 Average bond strength in newtons (pounds-force) of conditioned coils, and

10.1.6 Percent retention of bond strength after conditioning:

$$\text{Percent retained bond strength} = \frac{\text{average bond strength (conditioned)}}{\text{average bond strength (unconditioned)}} \times 100 \quad (1)$$

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*

## 11. Precision and Bias

11.1 *Precision*—No information has been presented to ASTM upon which to base a statement of precision. No activity has been planned to develop such information.

11.2 *Bias*—This test method has no bias because the value for moisture resistance is determined solely in terms of this test method itself.

## 12. Keywords

12.1 bond strength; helical coils; moisture resistance; varnish