



Standard Test Method for Sealed Tube Chemical Compatibility Test¹

This standard is issued under the fixed designation D5642; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers procedures for evaluating the interaction of electrical insulation components used, or intended to be used, in electrical insulation systems.

1.2 This test method is useful for determining compatibility but additional testing will potentially be required for some applications.

1.3 This test method also provides useful information about the behavior of selected insulating materials when compared to a reference value as opposed to a reference system.

1.4 This test method does not cover systems which operate in liquids or gases other than air.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* See also 8.2.4, 8.3.1 and 8.3.2.1

2. Referenced Documents

2.1 *ASTM Standards:*²

D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies

D1676 Test Methods for Film-Insulated Magnet Wire

D1711 Terminology Relating to Electrical Insulation

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.17 on Fire and Thermal Properties.

Current edition approved Nov. 1, 2016. Published November 2016. Originally approved in 1994. Last previous edition approved in 2009 as D5642 – 09. DOI: 10.1520/D5642-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 *magnet wire*—See Terminology D1711 for the definition of this term.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *aging test, n*—a process of exposure, to a specified set of conditions for a defined period of time, which results in an irreversible change in one or more physical, chemical, electrical, or thermal characteristics of a material.

3.2.2 *candidate system, n*—the proposed electrical insulation system to be evaluated.

3.2.3 *electrical insulation system, n*—an intimate combination of insulating materials with conductors, as used in electrical equipment.

3.2.4 *insulation system class, n*—a standardized designation of the temperature capability of the electrical insulation system. It is expressed by both numbers and letters as follows:

System	Class
105	(A)
120	(E)
130	(B)
155	(F)
180	(H)
200	(N)
220	(R)
240	(S)

3.2.5 *reference system, n*—an electrical insulation system which has been previously evaluated and found acceptable.

3.2.6 *twisted pair, n*—film-insulated round magnet wire that has been prepared in accordance with Test Methods D1676.

4. Summary of Test Method

4.1 A combination of specific materials is sealed in a limited space and subjected to a specific elevated temperature for a specified time. Following this exposure the dielectric breakdown voltage of the insulated conductors is used as a basis for judging the compatibility of the candidate system.

5. Significance and Use

5.1 This test method is useful for evaluating a combination of materials for potential use in an electrical insulation system.

6. Apparatus

6.1 *Oven*, capable of maintaining the required exposure temperature within ± 3 °C.

*A Summary of Changes section appears at the end of this standard

6.2 *Glass Tubes* with inside volume not exceeding 900 mL that can be sealed. Two general types are described as follows:

6.2.1 *Flanged High Temperature Glass Tubes* which are designed to be sealed with metal rings and gaskets are preferred.

6.2.2 *Glass Tubes*, which can be fusion sealed after the addition of all materials are acceptable alternatives.

6.3 *Gasket Materials* for use with tubes described in 6.2.1.

6.3.1 Type TFE (Tetrafluoroethylene) or FEP (Perfluoroethylene Propylene) Fluorocarbon.

6.3.2 *Hexafluoropropylene*—vinylidene fluoride elastomer can be used for exposure temperatures not exceeding 155 °C.

6.4 Apparatus in conformance with Test Method **D149** to measure dielectric breakdown voltage.

7. Material Specimens

7.1 The specific list of materials to be tested is to be established by agreement between interested parties.

7.2 Represent each of the non-metallic components of the electrical insulation system, with the exception of an impregnating varnish and insulated conductors, with a specimen having a minimum mass of 250 mg.

7.3 *Insulated Conductor Specimens:*

7.3.1 Use film insulated magnet wire twisted pairs constructed in accordance with Test Methods **D1676**; 18 AWG heavy build is preferred.

7.3.2 For conductors not suitable for constructing twisted pairs, use specimens having a minimum length of 200 mm.

NOTE 1—An example of conductors not suitable for constructing twisted pairs is fibrous wrapped conductors. They shall be represented as described in 7.3.2.

7.4 Apply impregnating varnish to the insulated conductors and cure per manufacturer's recommendations.

8. Procedures

8.1 *Tube Loading and Sealing:*

8.1.1 Clean and dry tubes as needed prior to use.

8.1.2 Prepare one tube with the materials that represent the reference system. Insert all materials as specified in Section 7 into the tube. For each magnet wire type insert a minimum of five twisted pairs or three straight lengths prepared in accordance with Section 7.

NOTE 2—It is acceptable to place a stainless steel screen as a barrier to restrict physical contact of the insulated conductors from the other materials in the tube, to avoid damage to the insulated conductor specimens.

8.1.3 Prepare one tube for each candidate system in the same manner in which the reference system tube was prepared.

8.1.4 Condition each unsealed tube and its contents for 1 h at 105 °C. The purpose of this procedure is to minimize the moisture content of all materials in the tube. It is an acceptable procedure to condition materials outside the tube to allow sufficient drying prior to 8.1.2 and 8.1.3. Concurrently condition tubes and gaskets.

8.1.5 Certain materials, including but not limited to hygroscopic papers, require additional conditioning to remove moisture. If agreed upon by interested parties, the use of higher

temperatures and times for drying is acceptable. Select a time and temperature that do not cause loss of other volatile materials or cause thermal decomposition.

8.1.6 Seal tubes within 3 min after conditioning, and leak test immediately thereafter in accordance with 8.1.6.2.

8.1.6.1 Seal flanged glass tubes by applying a sufficient torque to ensure a seal that is leak free. A torque of 3.4 N·m (30 inch-pounds) in increments of 0.56 N·m (5 inch-pounds), alternating between bolts to tighten evenly and securely has been found acceptable for this purpose.

8.1.6.2 Check glass tubes for leaks using the following procedure: Submerge the still warm tubes into room temperature tap water for a minimum of 2 min. Observe the tubes after they have reached room temperature for condensation on the inner walls. Condensation is a result of leakage.

8.1.6.3 Do not use tubes that exhibit leakage.

8.2 *Aging:*

8.2.1 Place the tubes into an oven that is at room temperature.

8.2.2 Apply power to the oven and allow it to attain the aging temperature.

8.2.2.1 Place sealed tubes into a heated oven but be aware that the thermal shock will cause stresses that have the potential to result in cracking of the glass tubes. Do not use any tubes that crack as a result of such treatment.

8.2.3 The aging temperature shall be 25°C greater than the numerical insulation system class of the reference system.

8.2.4 After a minimum of 336 h exposure to the aging temperature, remove the tubes from the oven. As an alternative, to reduce the extent of thermal shock, turn off the power to the oven and allow the oven and tubes to cool to room temperature. (**Warning**—Use protective equipment including safety glasses or face shield and high temperature gloves when handling heated glass tubes. It is feasible that glass tubes will shatter upon being subjected to thermal shock.)

8.3 *Procedures for Testing:*

8.3.1 Open the tubes within 72 h of the completion of aging. Remove the insulated conductor specimens. (**Warning**—Use adequate ventilation when opening the tubes. It is likely that fumes emitted from the tube will be toxic.)

8.3.2 Determine the dielectric breakdown voltage of twisted pair conductors in accordance with Test Methods **D1676**.

8.3.2.1 **Warning**—*It is feasible that lethal voltages will be present during this test. It is essential that the test apparatus, and all associated equipment potentially electrically connected to it, be properly designed and installed for safe operation. Solidly ground all electrically conductive parts that any person might come in contact with during the test. Provide means for use at the completion of any test to ground any parts which: were at high voltage during the test; have the potential to have acquired an induced charge during the test; have the potential to retain a charge even after disconnection of the voltage source. Thoroughly instruct all operators in the proper way to conduct tests safely. When making high voltage tests, particularly in compressed gas or in oil, it is feasible that the energy released at breakdown will be sufficient to result in fire, explosion, or rupture of the test chamber. Design test equipment, test chambers, and test specimens so as to minimize*

the possibility of such occurrences and to eliminate the possibility of personal injury.

8.3.3 For straight conductor specimens prepare electrodes by applying 6 mm wide thin metal foil to the center of a 13 mm wide, 75 mm long strip of pressure sensitive tape. Apply two electrodes at right angles to each specimen at intervals approximately $\frac{1}{3}$ the length of the specimen and wrap smoothly and firmly around the specimen a minimum of 1 and $\frac{1}{2}$ complete turns, with the metal surface of the foil in contact with the insulation.

8.3.4 If necessary, modify the electrode configuration as necessary for specific applications: Such modification shall be as agreed between interested parties.

8.3.5 Record the results.

9. Interpretation of Results

9.1 For each type of conductor taken from each tube, calculate the average of at least five dielectric breakdown voltage values using all of the dielectric breakdown voltages obtained. The criteria to be used for eliminating any one dielectric breakdown voltage value from the calculation of the average is to be determined by agreement between interested parties prior to testing.

9.2 A comparison of the average dielectric breakdown voltage values obtained for the conductor specimens taken from the candidate and reference tubes is the basis for

determining the compatibility of the materials in a candidate system. The maximum acceptable difference between the average values shall be established by agreement between interested parties.

10. Report

10.1 Report the following information:

10.1.1 Designation and description of the reference and candidate system including all components,

10.1.2 Pre-conditioning or drying conditions,

10.1.3 Aging temperature, and

10.1.4 Length of exposure time.

10.1.5 For each type of conductor taken from each tube,

10.1.5.1 Individual dielectric breakdown voltage values, and

10.1.5.2 Average dielectric breakdown voltage value.

11. Precision and Bias

11.1 No statement is made about either the precision or bias of this test method since the result merely states whether there is conformance to the criteria for acceptability defined in terms of this test method.

12. Keywords

12.1 chemical compatibility; electrical insulation system; sealed tube

SUMMARY OF CHANGES

Committee **D09** has identified the location of selected changes to this standard since the last issue (D5642 – 09) that may impact the use of this standard. (Approved Nov. 1, 2016.)

(1) Revised **1.2, 1.3, 8.1.5, 8.2.2.1, 8.2.4, 8.3.1, 8.3.2.1,** and **8.3.4** to remove non-mandatory language (“may” and “should”).

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/