



Standard Specification for Poly (Vinyl Chloride) (PVC) Gaskets for Drain, Waste, and Vent (DWV), Sewer, Sanitary, and Storm Plumbing Systems¹

This standard is issued under the fixed designation D5926; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification describes material and physical requirements for nonrigid poly (vinyl chloride) (PVC) preformed molded and spliced gaskets used in mechanical couplings. These couplings are used in gravity flow drain, waste, and vent (DWV), sewer, sanitary, and storm plumbing systems. They include couplings to join similar and dissimilar piping sizes and piping material.

1.2 It is acceptable to use recycled materials in this product in accordance with the requirements in Section 4.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—There is no known ISO equivalent to this standard.

1.4 The following safety hazards caveat pertains only to the test method portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

[C717 Terminology of Building Seals and Sealants](#)

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

[D471 Test Method for Rubber Property—Effect of Liquids](#)

[D573 Test Method for Rubber—Deterioration in an Air Oven](#)

[D618 Practice for Conditioning Plastics for Testing](#)

[D624 Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers](#)

[D746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact](#)

[D883 Terminology Relating to Plastics](#)

[D1149 Test Methods for Rubber Deterioration—Cracking in an Ozone Controlled Environment](#)

[D1203 Test Methods for Volatile Loss From Plastics Using Activated Carbon Methods](#)

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D2240 Test Method for Rubber Property—Durometer Hardness](#)

[D2287 Specification for Nonrigid Vinyl Chloride Polymer and Copolymer Molding and Extrusion Compounds](#)

[D3892 Practice for Packaging/Packing of Plastics](#)

[D4968 Guide for Annual Review of Test Methods and Specifications for Plastics](#)

[D6147 Test Method for Vulcanized Rubber and Thermoplastic Elastomer—Determination of Force Decay \(Stress Relaxation\) in Compression](#)

[D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products \(Withdrawn 2015\)³](#)

3. Terminology

3.1 *General*—Definitions are in accordance with Terminologies [C717](#), [D883](#), and [D1600](#), unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *flash*—the excess material protruding from the surface of a molded article at the mold junction.

4. Materials and Manufacture

4.1 This specification covers preformed gaskets made principally from virgin nonrigid PVC molding compound conforming to the requirements of Specification [D2287](#) for general purpose, electrical requirements excluded class PVC 30267, 40366 or 50465. Refer to Table 1 in Specification [D2287](#).

³ The last approved version of this historical standard is referenced on www.astm.org.

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.24 on Plastic Building Products.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1996. Last previous edition approved in 2011 as D5926-11. DOI: 10.1520/D5926-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4.1.1 This class compound has the following material property requirements:

with the dimensions and tolerances of the specific piping materials and sizes to which it is designed to join.

TABLE 1 Material Property Requirements

Properties Tested	ASTM Method	Requirement	Requirement	Requirement
Durometer hardness, A scale	Test Method D2240	55 to 64	65 to 74	75 to 84
Tensile strength, min, psi (MPa)	Test Method D412	1000 (6.9)	1285 (8.8)	1575 (10.8)
Volatile loss at 105°C, max, %	Test Method D1203	6.0	6.0	6.0
Brittleness temperature, max	Test Method D746	−40°C	−30°C	−20°C
Heat Aging :	Test Method D573			
Hardness increase, max, pts. Shore A		10	10	10
Loss in tensile strength, max, %		25	25	25
Loss in elongation, max, %		35	35	35
Water Absorption, Weight increase,max, %	Test Method D471	20	20	20
Ozone Resistance, No Cracks at 2 times Magnification	Test Method D1149	No Cracks	No Cracks	No Cracks
Oil Immersion in IRM 903 Oil:	Test Method D471			
Max volume increase, %		10	10	10
Max volume decrease, %		50	50	50
Tear Strength, min, lbf/in. (N/cm)	Test Method D624	150	150	150
Stress Relaxation, Min. % Force Retention	Test Method D6147	30	30	30

4.2 The molding compound shall have a minimum percent elongation by Test Method **D412** of 250 %.

4.3 The molding compound shall have a minimum tear strength by Test Method **D624** of 150 lb/in. (268.5 N/cm).

4.4 Recycled materials, as defined in Guide **D7209**, shall meet all the requirements in Sections 4 and 5 when used in this product.

4.5 Qualification testing for material physical requirements shall be conducted by the material manufacturer on the specific compound supplied and not on the molded gaskets, since the physical properties do not change on molding.

NOTE 2—The material manufacturer shall reassess the need for requalification of the specific compound supplied any time the compound formulation is changed or the PVC resin or any compound ingredient is changed.

4.6 The compound manufacturer shall certify in writing to the gasket manufacturer that the compound supplied meets all the requirements of this specification.

5. Requirements

5.1 *Dimensions*—Gaskets shall conform to the dimensions and dimensional tolerances as agreed upon between the supplier and the purchaser. All dimensions shall be compatible

5.2 *Spliced Gaskets, Stretch Test*—The splice shall withstand the splice test in 7.1 with no visible separation or peeling.

5.2.1 The observance of any peeling or separation in a spliced seam shall be followed by immediate correction of the temperature/time functions in the heat welding operation.

5.3 Gaskets selected for sampling (6.1) shall meet all dimensional requirements (5.1) and workmanship requirements (5.4).

5.4 Workmanship:

5.4.1 The surface of preformed gaskets shall be smooth and free from pitting, cracks, blisters, air marks, or any other imperfections that have the potential to affect product performance in service.

5.4.2 Neither the flash thickness nor the flash extension shall exceed 1/32 in. (1 mm).

6. Sampling

6.1 Sample using a statistically acceptable procedure.

6.2 A shift of production on a molding line shall be considered as a unit of manufacture for sampling purposes.

6.3 Spliced gasket production shall be sampled at a level of 100 % of total spliced units produced during the trimming and inspection operation.

7. Test Methods

7.1 *Spliced Gasket Stretch Test*—Gasket specimens shall be stretched during the seam trimming operation by inverting the spliced section 180°, while carefully inspecting the seam for separation and peeling and the seam area for workmanship imperfections (5.4.1).

7.2 The physical properties enumerated herein shall be determined on the non-rigid PVC compound in accordance with the following methods:

7.2.1 *Test Specimens*—Unless otherwise specified, test specimens shall be prepared of sheets 0.075 ± 0.010 in. (1.9 ± 0.2 mm) thick. Specimens shall be of the shape and dimensions specified in the individual test methods.

7.2.2 *Conditioning*—Test specimens of non-rigid PVC plastics shall be conditioned in accordance with Procedure A of Practice D618.

7.2.3 Unless otherwise specified, tests shall be conducted in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$) and $50 \pm 10\%$ relative humidity.

7.2.4 *Durometer Hardness*—Test Method D2240 using a 15 s interval as described in 9.2 of that method.

7.2.5 *Tensile Strength and Percent Elongation*—Test Methods D412, using specimens prepared with Die C.

7.2.6 *Volatile Loss*—Test Method D1203 using Method A, except that the test temperature shall be 105°C .

7.2.7 *Brittleness Temperature*—Test Method D746, using Procedure A.

7.2.8 *Tear Strength*—Test Method D624, using Die C.

7.2.9 *Heat Aging*—Test Method D573 for 96 h at $70 \pm 2^\circ\text{C}$ ($158 \pm 4^\circ\text{F}$).

7.2.10 *Water Absorption*—Test Method D471 for 7 days at $70 \pm 2^\circ\text{C}$ ($158 \pm 4^\circ\text{F}$).

7.2.11 *Ozone Resistance*—Test Method D1149, using test specimen A for 100 h at $40 \pm 2^\circ\text{C}$ ($104 \pm 4^\circ\text{F}$) with ozone concentration of 1.5 ppm.

7.2.12 *Oil Immersion*—Test Method D471 for 70 h at $100 \pm 2^\circ\text{C}$ ($212 \pm 4^\circ\text{F}$).

7.2.13 *Stress Relaxation*—Test Method D6147, using Method B, and test specimen as defined in section 7.1.2 of D6147. The test temperature and duration shall be 168 h at $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$).

8. Certification

8.1 The gasket manufacturer shall keep appropriate production and testing records, including certification documentation from the PVC compound producer, required to certify, when requested by the purchaser, that the product meets all requirements of this specification.

9. Product Marking

9.1 Each gasket shall be marked with the manufacturer's name or trademark, or both.

9.2 The type and size of pipe for which the gasket is intended or the manufacturer's product identification shall be marked on or attached to each gasket.

9.3 All gaskets shall be marked with the designation ASTM D5926 showing compliance to this specification.

10. Packaging and Package Marking

10.1 *Packaging*—The gaskets shall be packaged in standard commercial containers so constructed as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery, unless otherwise specified in the contract or order.

10.2 All packing, packaging, and marking provisions of Practice D3892 shall apply to this specification.

11. Keywords

11.1 DWV piping gaskets; pipe couplings; plumbing gaskets; poly(vinyl chloride) (PVC); recycle usage; sanitary piping gaskets; sewer piping gaskets; storm piping gaskets

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D5926 – 11) that may impact the use of this standard. (October 1, 2015)

(1) Revised Table 1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/