



# Standard Specification for Liquid Paint Driers<sup>1</sup>

This standard is issued under the fixed designation D600; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope\*

1.1 This specification covers liquids for use in paints, varnishes, enamels, and similar organic coatings and are solutions of metallic salts of:

1.1.1 *Class A*—2-Ethyl hexanoic acids in petroleum spirits.

1.1.2 *Class B*—Naphthenic acids in petroleum spirits.

1.1.3 *Class C*—Neodecanoic acids in petroleum spirits.

1.1.4 *Class D*—Tall oil fatty acids in petroleum spirits.

1.1.5 *Class E*—Any of the above acids or acid blends, but containing additives that make the liquid drier water dispersible. Some other driers may also contain complexing agents.

1.1.6 *Class F*—Other acids and acid blends unidentified by their producers.

1.2 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit in accordance with the rounding-off method of Practice E29.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 For specific hazard information and guidance, see the supplier’s Material Safety Data Sheets for materials listed in this specification.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D564 Test Methods for Liquid Paint Driers

D1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved July 1, 2012. Published September 2012. Originally approved in 1941. Last previous edition approved in 2007 as D600–07. DOI: 10.1520/D0600-07R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

D1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 *U.S. Federal Specification*:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>3</sup>

## 3. Chemical and Physical Requirements

3.1 *Quantitative Requirements*—The drier shall conform to the quantitative requirements as specified in Table 1 for metallic content, color, and viscosity.

3.2 *Physical Appearance*—Each type of drier shall be a mobile liquid free of sediment and suspended matter and shall be stable and miscible with oil as listed in Test Methods D564.

## 4. Significance and Use

4.1 This specification covers the general requirements for liquid paint driers used in paints, varnishes, enamels, and similar organic coatings.

4.2 The values listed should be considered as general guides to the character of the products, rather than reproducible constants.

## 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with Test Methods D564, except as otherwise provided in this specification.

## 6. Packaging and Package Marking

6.1 Package size shall be agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

## 7. Keywords

7.1 liquid paint driers

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

\*A Summary of Changes section appears at the end of this standard

TABLE 1 Typical Requirements of Liquid Paint Driers<sup>A</sup>

Class	Metal	Metal Concentration, %		Nonvolatile Matter, %	Typical Specific Gravity 25/25°C		Color, <sup>B</sup> Gardner (Test Method D1544)	G-H Viscosity (Test Method D1545)
		min	max	max	min	max		
A	Calcium	3.9	4.1	50	0.884 <sup>C</sup>	—	3	A
A	Calcium	4.9	5.1	60	0.894	0.912	5	C
B	Calcium	3.9	4.1	70	0.902	0.937	10	D
B	Calcium	4.9	5.1	85	0.932	0.970	11	T
C	Calcium	4.9	5.1	46	0.888	—	2	A
D	Calcium	3.9	4.1	66	0.890	0.918	9	B
E	Calcium	3.9	4.1	63	0.905	0.930	8	G
E	Calcium	5.9	6.1	76	0.922	0.960	5	N
F	Calcium	3.9	4.1	50	0.850	0.884	3	A
F	Calcium	4.9	5.1	60	0.900	0.936	4	B
F	Calcium	5.9	6.1	74	0.873	0.948	6	N
F	Calcium	7.9	8.1	70	0.958	—	5	B
F	Calcium	9.9	10.1	65	1.000	1.030	7–8	K
A	Cerium	5.9	6.1	30	0.856	—	8	A
B	Cerium	5.9	6.1	57	0.925	—	17	A1
A	Cobalt	5.9	6.1	45	0.875	0.900	blue/purple	A
A	Cobalt	11.8	12.2	90	1.008	1.060	blue/purple	J
B	Cobalt	5.9	6.1	67	0.918	0.970	blue/purple	B
C	Cobalt	11.8	12.2	65	0.984	—	blue	A
D	Cobalt	5.9	6.1	72	0.912	0.956	purple	C
E	Cobalt	4.9	5.1	60	0.926	—	red/purple	A
E	Cobalt	5.9	6.1	71	0.945	0.960	blue/purple	I
F	Cobalt	5.9	6.1	70	0.870	0.958	blue/violet	A
F	Cobalt	11.8	12.2	80	1.014	1.040	blue/violet	J
A	Iron	5.9	6.1	50	0.900	0.930	dark brown	A
B	Iron	5.9	6.1	67	0.960	0.990	dark brown	M
F	Iron	5.9	6.1	50	0.905	0.930	brown	A
F	Iron	8.9	9.1	78	0.950	0.985	brown	A
F	Iron	11.8	12.2	75	1.068	—	brown	A
A	Lead	23.8	24.2	65	1.090	1.110	3	A
B	Lead	23.8	24.2	67	1.125	1.160	11	B
C	Lead	23.8	24.2	61	1.100	—	2	A2
D	Lead	23.8	24.2	66	1.100	1.125	10	A
E	Lead	23.8	24.2	71	1.125	1.150	7	A
F	Lead	23.8	24.2	67	1.080	1.140	10	A
F	Lead	35.8	36.2	81	1.350	1.393	8	H
A	Manganese	5.9	6.1	50	0.888	0.920	red/brown	A
B	Manganese	5.9	6.1	66	0.930	0.965	17	D
C	Manganese	5.9	6.1	50	0.870	—	10	A
D	Manganese	5.9	6.1	72	0.942	0.972	brown	E
E	Manganese	4.9	5.1	42	0.911	—	brown	A
E	Manganese	5.9	6.1	69	0.942	0.965	brown	E
F	Manganese	5.9	6.1	55	0.870	1.020	18	A
F	Manganese	8.9	9.1	80	0.950	1.020	18	H
F	Manganese	11.8	12.2	75	1.044	—	16	C
A	Nickel	9.9	10.1	70	1.032	—	sh. green	A
A	Rare earth <sup>D</sup>	5.9	6.1	30	0.630	0.880	6	E
A	Rare earth	11.8	12.2	55	0.977	—	yel.-green	C
B	Rare earth	3.9	4.1	35	0.840	0.855	10	A
C	Rare earth	5.9	6.1	35	0.876	—	8	A5
A	Zinc	7.9	8.1	50	0.880	0.906	6	G
A	Zinc	17.8	18.2	90	1.068	1.130	7	Z
B	Zinc	7.9	8.1	70	0.915	0.960	9	A
B	Zinc	9.9	10.1	75	0.980	1.044	8	L
D	Zinc	7.9	8.1	70	1.008	—	11	D
E	Zinc	7.9	8.1	42	0.946	—	2	A
F	Zinc	7.9	8.1	60	0.855	0.963	7	C
F	Zinc	15.8	16.2	80	1.020	1.100	3	B
A	Zirconium	5.9	6.1	30	0.860	0.864	2	A
A	Zirconium	11.8	12.2	56	0.960	0.992	4	A
A	Zirconium	17.8	18.2	55	1.070	1.074	3	A
A	Zirconium	23.8	24.2	77	1.240	—	2	J
C	Zirconium	5.9	6.1	23	0.864	—	2	A5
C	Zirconium	11.8	12.2	46	0.976	—	2	A
E	Zirconium	5.9	6.1	31	0.864	—	4	A
E	Zirconium	11.8	12.2	55	0.975	1.020	4	A
F	Zirconium	5.9	6.1	28	0.855	0.870	2	A5
F	Zirconium	11.8	12.2	55	—	—	—	—
F	Zirconium	17.8	18.2	80	1.090	1.130	4	Z
F	Zirconium	23.8	24.2	93	1.240	1.260	6	J

<sup>A</sup> Source: "Raw Material Index," *National Paint and Coatings Association Guide*, Chemical Specialties Section, April 1978. Available from National Paint and Coatings Assn., 1500 Rhode Island Ave. NW, Washington, DC 20005.

<sup>B</sup> Per Gardner Test Method **D1544**. If off the scale, as observed by the unaided eye.

<sup>C</sup> Only one drier was listed in this category.

<sup>D</sup> The metal content represents total rare earth metals calculated as cerium, but the drier contains cerium and lanthanum, as well as minor amounts of other rare earth metals.

## SUMMARY OF CHANGES

Committee D01.35 has identified the location of selected changes to this standard since the last issue (D600 - 90 (2001)) that may impact the use of this standard. (Approved June 1, 2007.)

(1) Added reference to Practice **E29** in Scope section.

(2) Added Practice **E29** to list of Referenced Documents.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org](http://www.astm.org)/COPYRIGHT/).*