



Standard Test Methods for Physical Properties of Smooth-Wall, Coilable, Polyethylene (PE) Conduit (Duct) for Preassembled Wire and Cable¹

This standard is issued under the fixed designation D6070; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover procedures for determining the environmental performance properties of smooth-wall, coilable, medium-density and high-density polyethylene (MDPE and HDPE) conduit (duct) for preassembled wire and cable.

1.2 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)

3. Significance and Use

3.1 Environmental performance test values for smooth-wall, coilable, medium density and high density polyethylene (MDPE and HDPE) conduit (duct) for preassembled wire and cable may provide data for research and development, engineering design, quality control, and acceptance or rejection under specifications.

4. Procedure

4.1 *Performance Tests*—Remove electrical wire or cables, or both, from the duct before performing the following tests.

¹ These test methods are under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and are the direct responsibility of Subcommittee F17.40 on Test Methods.

Current edition approved Aug. 1, 2010. Published November 2010. Originally published as D6070-96. Last previous edition approved in 2002 as D6070-02. DOI: 10.1520/D6070-02R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4.2 *Compression and Recovery*—Flatten three specimens of duct 6 in. (150 mm) long, that have been conditioned at $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$) and $50 \pm 5\%$ relative humidity for not less than 48 h, between parallel plates at a rate of 0.5 in./min (13 mm/min) in a suitable press until the distance between the parallel plates has been decreased by 50 % of the original inside diameter of the duct. Be sure the specimens, the test apparatus, and the surrounding air are in thermal equilibrium with one another at a temperature of $23 \pm 2^\circ\text{C}$ during the test. The minimum force required to compress the specimens to the 50 % deflection is shown in **Table 1**. Within 10 min after removal of the force, the specimens shall recover as specified in the individual product specification.

4.3 Impact Test:

4.3.1 *Room-Temperature Test*—Cut ten 6-in. (150-mm) specimens, from finished lengths of each size of coilable PE duct to be tested. The surfaces shall not have cracks, tears, or other imperfections. The specimens, the test apparatus, and the surrounding air are to be in thermal equilibrium with one another at a temperature of $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$) during the test. Use the test apparatus and method described in **4.3.3**.

4.3.2 *Low-Temperature Test*—Cut ten 6-in. (150-mm) specimens, from finished lengths of each size of coilable PE duct to be tested. The surfaces shall not have cracks, tears, or other imperfections. Condition the specimens at a temperature of $-20 \pm 2^\circ\text{C}$ ($-4 \pm 4^\circ\text{F}$) for 5 h. Condition the test apparatus at a temperature of $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$). The test apparatus and method are described in **4.3.3**. Remove the samples from the cold chamber and complete the impact test within 30 s.

4.3.3 *Test Method*—Test each specimen separately while it is resting on a solid, flat steel plate that has a nominal thickness of at least 0.5 in. (12.5 mm) and that is firmly anchored with its upper surface horizontal. It is recommended that a protective cage surround the plates and specimens to prevent injury from pieces of broken duct in the event that the duct shatters. Allow a 20-lb (9-kg) Type B tup as described in Test Method **D2444** to fall freely through a vertical guide from the heights indicated in **Table 2**. Allow the face of the tup to strike the center of the specimen once (provide for preventing the tup from striking the specimen more than once). A crack or tear longer than 0.031 in. (0.8 mm) is considered a failure.

TABLE 1 Minimum Load for Compression and Recovery Test

Nominal Inside Diameter, in. (mm)		Type II Medium Density		Type III High Density	
		lb/ft	kN/m	lb/ft	kN/m
1/2	(12.7)	250	3.6	300	4.4
3/4	(19.3)	250	3.6	300	4.4
1	(25.4)	275	4.0	350	5.1
1 1/4	(31.8)	300	4.4	375	5.5
1 1/2	(38.1)	375	5.5	475	6.9
2	(50.8)	500	7.3	600	8.8
2 1/2	(63.5)	700	10.2	700	10.2
3	(76.2)	700	10.2	700	10.2

TABLE 2 Height for Dropping Tup

Nominal Inside Diameter, in. (mm)		Type II Medium Density		Type III High Density	
		ft	m	ft	m
1/2	(12.7)	4	1.2	2.5	0.8
3/4	(19.3)	4	1.2	4	1.2
1	(25.4)	5	1.5	5	1.5
1 1/4	(31.8)	6	1.8	6	1.8
1 1/2	(38.1)	7.5	2.3	7.5	2.3
2	(50.8)	9.5	2.9	9.5	2.9
2 1/2	(63.5)	10.5	3.2	10.5	3.2
3	(76.2)	11	3.4	11	3.4

5. Precision and Bias

5.1 *Precision*—These test methods have been in use for many years, but no statements of precision have been made and no activity is planned to develop such a statement.

5.2 *Bias*—A statement of bias is not possible due to a lack of a standard reference material.

6. Keywords

6.1 compression and recovery; conduit; duct; high-density polyethylene; impact test; medium-density polyethylene

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/