



Standard Specification for Chemically Modified Asphalt Cement for Use in Pavement Construction¹

This standard is issued under the fixed designation D6154; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers asphalt cements that have been modified by the addition of a chemical gellant. It was developed to provide a reference for specifying chemically modified asphalt cement and reflects the properties of currently available commercial products. The tests are intended to measure degree of modification not performance characteristics. This is not intended to be a performance-based specification.

1.2 Chemically modified asphalt cements are normally produced by addition of a chemical stabilizer. However, any asphalt modifier may be used that will give the required test results when blended with the desired asphalt.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 The following precautionary statement pertains to the test method portion only, Section 5, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

- D5 Test Method for Penetration of Bituminous Materials
- D36 Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)
- D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved Jan. 1, 2015. Published February 2015. Originally approved in 1997. Last previous edition approved in 2014 as D6154 – 09 (2014). DOI: 10.1520/D6154-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D140 Practice for Sampling Bituminous Materials

D1754 Test Method for Effects of Heat and Air on Asphaltic Materials (Thin-Film Oven Test)

D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

D4957 Test Method for Apparent Viscosity of Asphalt Emulsion Residues and Non-Newtonian Bitumens by Vacuum Capillary Viscometer

D7553 Test Method for Solubility of Asphalt Materials in N-Propyl Bromide

3. Materials and Manufacture

3.1 The asphalt cement used to prepare the chemically modified asphalt cement shall be prepared by the refining of crude petroleum by suitable methods.

4. Physical Properties

4.1 The chemically modified asphalt cement shall be homogeneous, free from water, and shall not foam when heated to 180°C.

4.2 The chemically modified asphalt cement shall conform to the requirements of Table 1.

5. Methods of Sampling and Testing

5.1 Sample and test the chemically modified asphalt cement in accordance with the following methods:

5.1.1 *Sampling*—See Practice D140.

5.1.2 *Penetration*—See Test Method D5.

5.1.3 *Viscosity at 60°C*—See Test Method D4957.

5.1.4 *Viscosity at 135°C*—See Test Method D4957.

5.1.5 *Flash Point, Cleveland Open Cup*—See Test Method D92.

5.1.6 *Solubility*—See Test Method D2042 or Test Method D7553.

5.1.7 *Softening Point*—See Test Method D36.

5.1.8 *Thin-Film Oven Test*—See Test Method D1754.

6. Keywords

6.1 chemical gellant; chemical stabilizer; Chemically Modified Asphalt Cement; viscosity

TABLE 1 Requirements for Chemically Modified Asphalt Cement

Test ^A	Grade			
	CM 5-10	CM 10-20	CM 20-30	CM 30-40
Viscosity ^{B,C} , 60°C, min, Pa·s, 1 s ⁻¹	50.0	100.0	200	300
Viscosity ^{C,D} , 135°C, Pa·s, 10 s ⁻¹	0.2 to 2.0	0.4 to 4.0	0.7 to 6.0	1.0 to 8.0
Penetration, 4°C, 200 g, 60 s, dmm	40 to 100	30 to 65	20 to 45	12 to 35
Penetration, 25°C, 100 g, 5 s, dmm	140 to 185	100 to 140	65 to 100	35 to 65
Flash Point, Cleveland open cup, min, °C	246	246	246	246
Softening Point, min, °C	50	55	60	65
Solubility, min, % ^E	99.0	99.0	99.0	99.0
Tests on residue from thin-film oven test:				
Aging Index, max	2.5	2.5	2.5	2.5
Vis. ATFOT/BTFOT				

^A Handling of all samples for testing shall be in accordance with 7.2 of Test Method **D4957**, which requires heating the sample in an oven maintained at 195 ± 2°C. Stir the sample occasionally until homogenous and pour in a suitable container for testing. Pouring temperatures should be 180 ± 5°C on all tests.

^B Normally run using a No. 200 Modified Koppers Viscometer tube at 300 mm of vacuum.

^C Normally run using a No. 50 Modified Koppers Viscometer tube at 100 mm of vacuum.

^D The selection of tube size and vacuum should be varied to achieve measurement near the specified shear rate to avoid extrapolation of data.

^E Use Test Method **D2042** or Test Method **D7553**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/