



# Standard Specification for Extruded Rods and Bars Made From Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC)<sup>1</sup>

This standard is issued under the fixed designation D6263; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## INTRODUCTION

This specification is intended to be a means of calling out mechanical grade plastic product used in the fabrication of end items or parts.

### 1. Scope\*

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded shapes of rods and bars made from poly(vinyl chloride) (PVC), and chlorinated poly(vinyl chloride) (CPVC).

1.2 The properties included in this specification are those required for the compositions covered. Use the classification system given in Section 4 to describe requirements necessary to identify particular characteristics important to specialized applications.

1.3 This specification allows for the use of regrind and recycled plastics as defined in Guide D7209 providing: products produced from regrind or recycled PVC material can be shown to meet the requirements of this standard with regard to material classification, physical performance, dimensions and workmanship; and the regrind or recycled plastics used have not been subjected to severe environments in post consumer applications (such as chemical service) which could adversely affect the end products performance when subjected to machining or critical applications or both.

1.4 The values are stated in inch-pound units and are regarded as the standard in all property and dimensional tables. For reference purposes, SI units are also included in Table 1 only.

1.5 The following safety hazards caveat pertains only to the test method portions section of this specification: *This standard does not purport to address all of the safety concerns, if any,*

*associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D883 Terminology Relating to Plastics

D1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds

D3892 Practice for Packaging/Packing of Plastics

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)<sup>3</sup>

2.2 *ANSI Standard*:

Z1.4-1993 Sampling Procedures and Tables for Inspection by Attributes<sup>4</sup>

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.20.02).

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1998. Last previous edition approved in 2011 as D6263 - 11. DOI: 10.1520/D6263-15.

\*A Summary of Changes section appears at the end of this standard

2.3 *NSF Standard:*  
**NSF Standard 61**<sup>5</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology **D883** or Guide **D7209**.

3.1.2 *regrind plastic, n*—a product or scrap such as sprues and runners and edge trim that have been reclaimed by shredding and granulating for use in-house.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *rod, n*—an extruded solid cylindrical shape with a minimum diameter of 0.125 in. (3.2 mm).

3.2.2 *tubular bar, n*—an extruded annular shape with minimum inside diameter of 0.375 in. (9.5 mm) and minimum wall thickness of 0.0625 in. (1.6 mm).

### 4. Classification and Material

4.1 Product shape and size as defined in the applicable purchase order.

4.2 This specification covers extruded product as listed in Tables S-PVC-I and S-PVC-II. Products included in the designations reference Specification **D1784** callouts where applicable.

4.2.1 Categorize the type of poly(vinyl chloride), and chlorinated poly(vinyl chloride) shape product by type, grade, and class depending on resin composition as defined in Table S-PVC-II.

4.3 The type, class and grade is further differentiated based on dimensional stability (elevated temperature excursion test). See Table S-PVC-II and dimensional requirements, Table A.

#### 4.4 Property Tables:

4.4.1 Use Tables S-PVC-I and S-PVC-II to describe extruded products.

4.4.2 Use Table 1 also to describe extruded products not included in Table S-PVC-I or S-PVC-II via a cell callout that includes the applicable material type and specific properties (Designations 1 through 7).

4.4.3 To facilitate the incorporation of future or special materials not covered by Tables S-PVC-I and S-PVC-II, the “as specified” category (00) for type, class and grade is shown in the applicable table with the basic properties to be obtained from Table 1 as they apply.

4.5 *Callout Designation*—A one-line system shall be used to specify poly(vinyl chloride), or chlorinated poly(vinyl chloride) materials covered by this specification. The system uses pre-defined cells to refer to specific aspects of this specification as illustrated below:

#### 4.5.1 Examples:

4.5.1.1 *Example 1*—Product made from general purpose poly(vinyl chloride):

CELL CALLOUT: S-PVC0111  
 S-PVC01 = Product made from PVC in accordance with Table S-PVC-I and Table S-PVC-II  
 1 = Unfilled class  
 1 = General purpose grade product

4.5.1.2 *Example 2*—Product made from general purpose chlorinated poly(vinyl chloride):

CELL CALLOUT: S-CPVC0211  
 S-PVC02 = Product made from CPVC in accordance with Tables S-PVC-I and S-PVC-II  
 1 = Unfilled class  
 1 = General purpose grade product

4.5.2 These two examples illustrate how a one-line, alphanumeric sequence can identify the product composition, commercial parameters and physical characteristics of extruded product. A space must be used as a separator between the specification number and the type designation. No separators are needed between type, class, and grade. When special notes are to be included, such information shall be preceded by a comma. Special tolerances must be noted at time of order and are inserted after the grade in parenthesis and preceded by a comma.

4.5.2.1 The material used in the manufacture of PVC and CPVC shapes intended for contact with or the transport of potable water, or both, must be evaluated and certified as safe for this purpose by a testing agency acceptable to the local health authority. The evaluation shall be in accordance with the requirements for chemical extraction, taste, and odor, that are no less restrictive than those included in the National Sanitation Foundation (NSF) Standard 61.

### 5. Ordering Information

5.1 All shapes covered by this specification shall be ordered using the proper callout designation (see 4.5).

### 6. Physical Property Requirements

6.1 The physical property values listed within this specification’s tables are to be considered minimum specification values. Any requirement for specific test data for a given production lot shall be specified at the time of order. Use Table 1 to specify physical properties for extruded products not yet included in Table S-PVC-I or S-PVC-II.

### 7. Dimensional Requirements

7.1 The type, class, and grade is differentiated based on dimensional stability (elevated temperature excursion test) as indicated in Table S-PVC-II.

7.2 Products shall be produced within the commercial tolerances and with the lowest stress levels for machined parts as delineated in Table A.

7.3 Tubular bar dimensions shall be supplied in the unfinished condition, unless otherwise specified at time of order, sufficient to finish to the nominal dimensions ordered.

7.4 The maximum allowable camber at final inspection at the factory shall be within the limits referenced in Table A.

### 8. Workmanship, Finish, and Appearance

8.1 *Appearance*—The resin material color for poly(vinyl chloride) shall be dark gray. The resin material color for

<sup>5</sup> Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.

chlorinated poly(vinyl chloride) shall be light gray. All shapes shall be uniform in color throughout the thickness. Specific colors and color matching only as agreed to by order.

8.1.1 It is possible that physical properties will be affected by other colors. Regardless of color, minimum properties of 4.4 must be met.

8.2 *Finish*—All products shall be free of blisters, wrinkles, cracks, gouges and defects that restrict commercial use of the product. Special surface finish shall be supplied only when specified in the purchase order or contract.

8.3 *Defects*—All products shall be free of visual voids, dirt, foreign material and embedded particles exceeding 0.040 in. (1 mm) maximum diameter as defined in 8.3.1

8.3.1 The criteria for determining the cleanliness shall be external visual inspection. A maximum number of two defects per one foot length of rod and tubular bar are allowed. Clusters of defects less than 0.040 in. (1 mm) diameter are to be counted as a single defect.

8.4 *Extrusion Quality*—Products shall not flake or disintegrate when tested in accordance with the test method for degree of fusion as defined in 12.6.

## 9. Sampling

9.1 Sampling shall be statistically adequate to satisfy the requirements of this specification as applicable (see ANSI Z1.4-1993).

9.2 For purposes of sampling, an inspection lot for examination and tests shall consist of all material of the same type, class, grade and nominal size submitted for inspection at one time.

## 10. Number of Tests

10.1 Routine lot inspection shall consist of all the criteria specified in the applicable product tables.

10.2 The criteria listed in these product tables and definitions are sufficient to establish conformity of the shape to this specification. When the number of test specimens is not stated in the test method, it is acceptable to make a single determination. If more than single determinations and separate portions of the same sample are made, the results shall be averaged. The final result shall conform to the requirements prescribed in this specification.

## 11. Test Conditions

11.1 *Conditions of Specimens*—The specification values and dimensions are based on conditioning techniques outlined in Procedure A of Practice D618

11.2 *Standard Temperature*—The tests shall be conducted at the standard laboratory temperature of  $73.4 \pm 3.6^\circ\text{F}$  ( $23.0 \pm 2.0^\circ\text{C}$ ) and  $50 \pm 10\%$  relative humidity.

## 12. Test Methods

12.1 Tensile stress at break, elongation at break, and tensile modulus (tangent) are in accordance with Test Method D638, at the rate of 0.2 in. (5 mm)/min. Values obtained shall meet the requirements called out in Table S-PVC-I.

12.1.1 All rod specimens are in accordance with Test Method D638.

12.2 *Dimensional Stability:*

12.2.1 *Specimen Preparation (a Minimum of Three Test Samples Required):*

12.2.1.1 *Rods*—Prepare each specimen by cutting a 1.5 in. (35 mm) long slice from the shape to be tested. Machine the slice using a coolant and good machining practices to a length of  $1.000 \pm 0.005$  in. ( $25 \pm 0.13$  mm). Each end of the specimen shall have a machined surface.

12.2.2 *Testing Procedure*—Measure the outside diameter and thickness or length of the specimen as applicable at  $73.4 \pm 3.6^\circ\text{F}$  ( $23.0 \pm 2.0^\circ\text{C}$ ) to the nearest 0.0001 in. (0.025 mm). All measurements shall be done on the centerline. Also take measurements for thickness halfway to center and for diameter at mid-point.

12.2.2.1 Place the specimen in a bath consisting of poly-alkylene glycol or an air circulating oven heated to  $250 \pm 5^\circ\text{F}$  ( $121 \pm 3^\circ\text{C}$ ). After 6 h allow the specimen to slowly cool to room temperature at a rate not to exceed  $40^\circ\text{F}$  ( $22^\circ\text{C}$ )/h. Measure the specimen at  $73.4 \pm 3.6^\circ\text{F}$  ( $23 \pm 2^\circ\text{C}$ ) and calculate the percent change in each dimension.

12.2.3 *Reproducibility*—Interlaboratory reproducibility is being determined and will be added within one year. A precision statement will be finalized and included within two years.

12.3 *Lengthwise Camber:*

12.3.1 Make all measurements for camber using the maximum distance rod deviates from the straight line extended from edge to edge when measured in accordance with 12.3.2. The shape shall be oriented such that the weight of the product doesn't influence the results.

12.3.2 *Rod:*

12.3.2.1 *Rod*—Lay each rod on its side and measure it with concave side facing a straight edge. Measure camber from the straight edge to the maximum concave point on the rod. Camber shall not exceed the values of Table A.

12.3.3 *Reproducibility*—Interlaboratory reproducibility is being determined and will be added within one year. A precision statement will be finalized and included within two years.

12.4 Flexural modulus is in accordance with Test Method D790, specimen 0.25 in. (1.4 mm) thick maximum, testing speed 0.11 in. (2.9 mm)/min. Values obtained shall meet the requirements called out in Table S-PVC-I.

12.5 Izod impact, in accordance with Test Method D256, Method A, Fig. 4, notched 0.25 in. (1.4 mm) thick maximum specimen. Values obtained shall meet the requirements called out in Table S-PVC-I.

12.6 *Degree of Fusion of Extruded PVC and CPVC by Solvent Immersion*—Make a determination of the degree of fusion for extruded PVC as indicated by reaction to immersion in anhydrous acetone. A determination of the degree of fusion shall be made for extruded CPVC as indicated by reaction to immersion in methyl isobutyl ketone (MIBK).

12.6.1 American Chemical Society reagent grade having a maximum density of 0.7857 g/mL at  $25^\circ\text{C}$ .

12.6.2 *Specimen Preparation*—Specimen shall be a size that is convenient to immerse in the test container, but not less than 2 in. (5 cm) immersion height (depth). For small diameter rod (sizes 6 in. (15 cm) or less), the sample shall cut in half lengthwise and both halves immersed to provide a complete circumferential section. For large diameter rod the specimen can be cut into smaller pieces to facilitate testing, provided that the height of the sections meet the 2 in. (5 cm) immersion height requirements, and provide a full circumferential section.

12.6.3 *Conditioning*—Unless otherwise specified, condition the specimens in air for a minimum of 1 h at  $73.4 \pm 3.6^{\circ}\text{F}$  ( $23.0 \pm 2.0^{\circ}\text{C}$ ) prior to testing. The specimens shall not be conditioned in water because of the effect water has on the solvents.

12.6.4 *Procedure*—Place sufficient solvent in the container to ensure proper immersion (2 in. (5 cm) depth) of the test specimen. Place the test specimen in the solvent, seal the container, and do not agitate. Allow specimen to stand immersed for 30 min. After 30 min remove the specimen from the container and inspect for signs of attack. Attack is described as a lifting, raising, or removing of any material from the surfaces immersed. Swelling or softening of the test specimen shall not be considered attack.

12.6.5 *Failure Criteria*—50 % attack on any one surface immersed, or 10 % attack on more than one surface shall be considered a failure.

12.6.6 *Reproducibility*—Interlaboratory reproducibility is being determined and will be added within one year. A precision statement will be finalized and included within two years.

### 13. Certification

13.1 When requested at the time of order, the purchaser shall be furnished a certification that the lot is made from the required poly(vinyl chloride) or chlorinated poly(vinyl chloride) plastic and percent recycle (if applicable) meets the requirements of this specification.

### 14. Packing, Packaging, and Marking

14.1 All packing, packaging, and marking provisions of Practice **D3892** shall apply to this specification.

### 15. Keywords

15.1 chlorinated poly(vinyl chloride), recycled plastics; chlorinated poly(vinyl chloride), rod; chlorinated poly(vinyl chloride), shapes; poly(vinyl chloride); poly(vinyl chloride), rod; poly(vinyl chloride), shapes; poly(vinyl chloride), tubular bar

**TABLE S-PVC-I Material Requirements for Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Shapes**

Material	Cell Classification (Specification <b>D1784</b> )	Minimum Compound Property Requirements (Specification <b>D1784</b> )				Flexural Modulus, psi (MPa), min, @ 73°F (Test Method <b>D790</b> )
		Izod Impact Strength, ft-lb in. of notch (J/m of notch)	Tensile Strength, psi (MPa), min	Tensile Modulus, psi (MPa)	Deflection Temp- erature Under Load, min 264 psi, °F (°C)	
PVC	12454	0.65 (35)	7000 (48)	400 000 (2760)	158 (70)	375 000 (2590)
Other PVC	As Specified	...	...	...	...	...
CPVC	23437	1.5 (80)	7000 (48)	320 000 (2200)	212 (100)	315 000 (2170)
Other CPVC	As Specified	...	...	...	...	...

**TABLE S-PVC-II Requirements for Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Rod**

Type	Description	Class	Description	Grade	Resin/Compound Type (Cell Classification Specification <b>D1784</b> )	Description	Dimensional Stability, max, %
01	PVC	1	Unfilled	1	12454	General Purpose	1.5 %
		0	As Specified	0	As Specified	As Specified	...
02	CPVC	1	Unfilled	1	23437	General Purpose	1.5 %
		0	As Specified	0	As Specified	As Specified	...

**TABLE A Dimensional Requirements for PVC and CPVC Rod**

Size, in. <sup>A</sup>	Outside Diameter <sup>A</sup>	Diameter Tolerance <sup>A</sup>	Camber, in. <sup>A</sup>
1/4	0.250	+0.016/–0	N/A
3/8	0.375	+0.020/–0	N/A
1/2	0.500	+0.020/–0	1 1/2 in./10 ft
5/8	0.625	+0.028/–0	1 1/2 in./10 ft
3/4	0.750	+0.028/–0	1 1/2 in./10 ft
7/8	0.875	+0.028/–0	1 1/2 in./10 ft
1	1.000	+0.030/–0	1 1/2 in./10 ft
1 1/8	1.125	+0.035/–0	1 1/4 in./10 ft
1 1/4	1.250	+0.035/–0	1 1/4 in./10 ft
1 3/8	1.375	+0.040/–0	1 1/4 in./10 ft
1 1/2	1.500	+0.040/–0	1 1/4 in./10 ft
1 5/8	1.625	+0.045/–0	1 1/4 in./10 ft
1 3/4	1.750	+0.050/–0	1 in./10 ft
1 7/8	1.875	+0.055/–0	1 in./10 ft
2	2.000	+0.060/–0	1 in./10 ft
2 1/8	2.125	+0.060/–0	1/2 in./5 ft
2 1/4	2.250	+0.068/–0	1/2 in./5 ft
2 3/8	2.375	+0.071/–0	1/2 in./5 ft
2 1/2	2.500	+0.075/–0	1/2 in./5 ft
2 3/4	2.750	+0.080/–0	1/2 in./5 ft
3	3.000	+0.090/–0	1/4 in./5 ft
3 1/2	3.500	+0.105/–0	1/4 in./5 ft
4	4.000	+0.120/–0	1/4 in./5 ft
4 1/2	4.500	+0.135/–0	1/4 in./5 ft
5	5.000	+0.150/–0	1/4 in./5 ft
5 1/2	5.500	+0.165/–0	1/4 in./5 ft
6	6.000	+0.180/–0	1/4 in./5 ft
7	7.000	+0.210/–0	1/8 in./5 ft
8	8.000	+0.240/–0	1/8 in./5 ft
9	9.000	+0.270/–0	1/8 in./5 ft
10	10.000	+0.300/–0	1/8 in./5 ft
11	11.000	+0.330/–0	1/8 in./5 ft
12	12.000	+0.360/–0	1/8 in./5 ft

<sup>A</sup>To convert inches to millimetres multiply by 25.40.

**TABLE 1 Additional Detail Requirements for Extruded Poly(Vinyl Chloride) and Chlorinated(Poly Vinyl Chloride) Shapes**

Note 1—The applicable shape type (Tables S-PVC-I or S-PVC-II) must precede this table designation.

Designation	Property	0	1	2	3	4	5	6	7	8	9
Order Number											
1	Tensile Strength, Test Method <b>D638</b> , psi (MPa), min	Unspecified	6000 (41)	3000 (55)	10 000 (69)	12 000 (83)	14 000 (97)	16 000 (110)	20 000 (138)	25 000 (172)	Specify Value
2	Elongation at Break, Test Method <b>D638</b> , min, %	Unspecified	1	3	5	10	20	50	100	200	Specify Value
3	Tensile Modulus, Test Method <b>D638</b> , psi (MPa), min	Unspecified	100 000 (690)	200 000 (1379)	300 000 (2073)	400 000 (2760)	500 000 (3448)	600 000 (4137)	800 000 (5516)	1 000 000 (6895)	Specify Value
4	Dimensional Stability per <b>12.2</b> , max, %	Unspecified	0.1	0.2	0.3	0.4	0.6	0.8	1.0	1.5	Specify Value
5	Flexural Modulus, Test Method <b>D790</b> , psi (MPa), min	Unspecified	250 000 (1649)	350 000 (2400)	450 000 (3100)	550 000 (3792)	650 000 (4482)	750 000 (5171)	1 000 000 (6895)	1 500 000	Specify Value
6	Izod Impact, Test Method <b>D256</b> , ft-lb in. of notch (J/m of notch), min	Unspecified	0.5 (27)	0.75 (40)	1.0 (53)	2.5 (133)	5.0 (266)	10.0 (533)	15.0 (800)	18.0 (960)	Specify Value
7	To be determined	Unspecified	...	...	...	...	...	...	...	...	Specify Value

**SUMMARY OF CHANGES**

Committee D20 has identified the location of selected changes to this standard since the last issue (D6263 – 11) that may impact the use of this standard. (October 1, 2015)

- |  |  |
|--|--|
| (1) Changed fraction to decimal 3.2.1, 3.2.2, 12.4, 12.5.                      | (4) Added new 12.6.1 to add Acetone reference.     |
| (2) Reworded 11.2, 12.2.2, 12.2.2.1, 12.6.3(new) to bring in line with D618-13 | (5) Renumbered 12.6.1 – 12.6.5 to 12.6.2 – 12.6.6. |
| (3) Reworded 12.6 to remove Acetone reference.                                 | (6) Added left parenthesis to 13.1.                |

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*