



Standard Practice for Separation and Washing of Recycled Plastics Prior to Testing¹

This standard is issued under the fixed designation D6288; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice describes a procedure for separating recycled plastics based on their color and a procedure for washing dirty, ground plastic, which results in separation of light materials (density $<1.00 \text{ g/cm}^3$). This practice is not intended to represent generic washing procedures used in the plastics recycling industry. The described procedures are solely for preparation of plastic samples for use in other analytical tests. The procedure includes a room temperature wash step to facilitate separation of paper (for example, labels) followed by washing at an elevated temperature.

NOTE 1—Although not presented as a quantitative method, the procedure presented in this practice may be used to provide quantitative results. The user assumes the responsibility to verify the reproducibility of quantitative results.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 ASTM Standards:²

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D5814 Practice for Determination of Contamination in Recycled Poly\(Ethylene Terephthalate\) \(PET\) Flakes and Chips Using a Plaque Test](#)

[D5991 Practice for Separation and Identification of Poly\(Vinyl Chloride\) \(PVC\) Contamination in Poly\(Ethylene](#)

¹ This practice is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.95 on Recycled Plastics.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1998. Last previous edition approved in 2009 as D6288 - 09. DOI: 10.1520/D6288-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Terephthalate\) \(PET\) Flake](#)

[D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products \(Withdrawn 2015\)](#)³

[IEEE/ASTM SI-10 Standard for Use of the International System of Units \(SI\): The Modern Metric System](#)

3. Terminology

3.1 The terminology used in this practice is in accordance with Terminology [D1600](#) and Guide [D7209](#). Units and symbols are in accordance with Standard [IEEE/ASTM SI-10](#).

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *light material*—materials with densities less than 1.00 g/cm^3 .

4. Summary

4.1 Different colored plastic materials are readily distinguished by visual inspection of a sample.

4.2 Labels, glue residues and other plastics may absorb the dyes used in some procedures for identifying contaminants or these other contaminants may exhibit interfering fluorescence. Consequently, a standard procedure is provided for washing the plastic prior to examination by these tests.

4.3 This practice utilizes a room temperature wash step to facilitate separation of paper followed by washing at an elevated temperature to permit separation of plastics and other contaminants based on densities. The room temperature wash step effectively removes labels without activating some adhesives.

NOTE 3—The dye and fluorescence tests that may require plastic washed by this procedure are specifically designed to detect poly(vinyl chloride) (PVC) contamination.

4.4 Washed recycled plastic materials are then used for tests such as those described in Practices [D5814](#) or [D5991](#).

5. Significance and Use

5.1 Dirt, paper and mixtures of polymeric materials complicate the interpretation of data from procedures used to identify the contaminants in recycled plastics.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

6. Apparatus

6.1 *Bright Aluminum Tray*, shallow depth (750 mm), with minimum area of 774 cm² (120 in.²).

6.2 *Balances*, suitable for weighing 500 g of flake.

6.3 *Baffled Beaker*, stainless steel, 15.2 cm (6 in.) diameter with four 1.9 cm (0.75 in.) baffles providing a slurry height/diameter ratio of 0.9.

6.4 *Cover for Beaker* (see 6.3) which can accommodate a thermometer (or other temperature sensing device) and the stirring impeller rod.

6.5 *Overhead Stirrer*, capable of 1000 r/min.

6.6 *Stirring Impeller*, pitched three blade, 7.62 cm (3 in.) diameter.

6.7 *Plastic Pails*, 19 L (5 gal).

6.8 *Strainer*, non-aluminum to fit the pails described in 6.7.

6.9 *Hot Plate*.

6.10 *Thermometer*.

6.11 *Manual Stirring Rod*.

6.12 *Oven*, capable of drying plastic flakes at 60 ± 2°C.

7. Materials

7.1 *Water*, distilled or deionized.

7.2 *Sodium Hydroxide*, granular.

7.3 *Detergent*, nonionic surfactant.

NOTE 4—Nonylphenol or octylphenol derivatives are effective detergents for this procedure. Users of this procedure should be aware that these materials have been linked to endocrine/estrogen activity and false positive interferences with breast cancer research. Anionic detergents may also be effective.

7.4 Wash solution, consisting of 2 L of water, 0.3 % (6 g) nonionic surfactant (see 7.3), and 1 % (20 g) sodium hydroxide (see 7.2). Dissolve the surfactant in cold water prior to addition of the sodium hydroxide.

8. Procedures

8.1 *Separation of Plastics Based on Color:*

8.1.1 Spread a representative portion of the recycled plastic on an aluminum tray.

NOTE 5—Use an appropriate sampling technique to insure that the sample used for this test is representative of the entire gaylord or bale of material.

8.1.2 Visually inspect the recycled plastic and separate the materials based on color.

8.2 *Room Temperature Washing Procedure:*

NOTE 6—Although not required for all plastics, the room temperature washing procedure is useful to remove labels from some products. This step can reduce filter screen plugging from paper because the low temperature does not activate some adhesives.

8.2.1 Place the wash solution (see 7.4) in the baffled beaker (see 6.3).

8.2.2 Select and accurately weigh 500 ± 20 g of dirty plastic from the sample. Add this sample to the solution in the beaker.

8.2.3 Insert the overhead stirrer so that the impeller is 2.54 cm (1 in.) above the bottom of the beaker.

8.2.4 Turn on the overhead stirrer and adjust the speed to 1000 r/min. Continue agitation for 15 min at room temperature (25 ± 2°C).

NOTE 7—Bubbles may be attached to plastic flakes and these bubbles may cause heavy materials to float when they would otherwise sink. Using a screen to gently disturb the floating particles and cause release of the air may permit these heavy materials to sink instead of float.

8.2.5 After 15 min, turn off the overhead stirrer and remove it from the baffled beaker. Wait 5 min to allow paper and other light materials to rise to the surface and polymers such as PET and PVC to sink. Using the manual stirring rod (see 6.11), gently agitate the light materials to allow any trapped PET or PVC to sink.

8.2.6 Place a strainer (see 6.8) over a 19 L (5 gal) pail (see 6.7). Carefully pour the wash solution from the beaker through the strainer causing the light materials to be trapped on the strainer. Do not allow the heavier plastic material that settled in the beaker to be transferred to the strainer.

8.2.7 Add water to the beaker to raise the water level to within several inches of the top.

8.2.8 Agitate this plastic/water mixture with the manual stirring rod to further separate any trapped light materials. Allow any heavier polymers to sink to the bottom of the beaker, then pour the majority of the water through the strainer into the pail.

8.2.9 Rinse the light materials in the strainer for 2 min with cold water (see 7.1) while agitating the material with the manual stirring rod. Drain rinse water into the pail.

8.2.10 Transfer the trapped light materials from the strainer to paper towels and air dry.

NOTE 8—To shorten the drying time, place the isolated light materials in an oven at 60 ± 2°C.

8.3 *Elevated Temperature Washing Procedure:*

8.3.1 Place wash solution (see 7.4) into a baffled beaker (see 6.3) and heat to 88 ± 2°C (190 ± 5°F) on a hot plate. Cover the beaker (see 6.4) to minimize evaporation.

8.3.2 Select and accurately weigh 500 ± 20 g of dirty plastic from the sample. Add this sample to the solution in the beaker. If the room temperature wash procedure (see 8.2) was used to separate labels and other light materials, transfer all of the heavy plastic from the beaker (see 8.2.8) to the beaker with the wash solution at 88 ± 2°C (190 ± 5°F). Be careful to transfer all material from the first beaker.

8.3.3 Insert the overhead stirrer so that the impeller is 2.54 cm (1 in.) above the bottom of the beaker and return the solution temperature to 88 ± 2°C (190 ± 5°F).

8.3.4 Turn on the overhead stirrer and adjust the speed to 1000 r/min. Continue agitation for 15 min while maintaining the solution temperature at 88 ± 2°C (190 ± 5°F).

8.3.5 After 15 min, turn off the overhead stirrer and remove it from the baffled beaker. Remove the beaker from the hot plate.

8.3.6 Place a strainer (see 6.8) over a 19 L (5 gal) pail (see 6.7). Carefully pour the wash solution from the beaker through the strainer causing the solid material to be trapped on the strainer.

8.3.7 Add warm water ($88 \pm 2^{\circ}\text{C}$ ($190 \pm 5^{\circ}\text{F}$)) to the beaker to raise the water level to within several inches of the top. Agitate this plastic/water mixture with the manual stirring, then pour the majority of the water through the strainer into the pail.

8.3.8 Rinse the material in the strainer for 2 min with cold water (see 7.1) while agitating the material with the manual stirring rod. Drain rinse water into the pail.

8.3.9 Transfer the trapped materials from the strainer to the aluminum tray (see 6.1) and oven dry at $60 \pm 2^{\circ}\text{C}$.

9. Keywords

9.1 contamination; poly(ethylene terephthalate) (PET); poly(vinyl chloride) (PVC); recycled plastics; washing

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D6288 - 09) that may impact the use of this standard. (October 1, 2015)

(1) Reworded 1.1, 3.2.1, 4.1, 4.3, 5.1, 8.1.2, and 8.2.10.

(2) Added English conversion of 19 L pail in 8.2.6 and 8.3.6.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/