



Standard Guide for Reporting Properties for Plastics and Thermoplastic Elastomers¹

This standard is issued under the fixed designation D6436; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This guide provides recommendations for reporting the property values of plastics and thermoplastic elastomers in published literature, data sheets, presentations, comparative analysis, and so forth. It is intended to minimize confusion when comparing the data from several sources.

1.2 This standard is not intended to replace recommendations within the test methods for reporting data. Refer to the test method or use other guidance to determine the number of significant figures for reporting laboratory test results.

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 Because of the large number of ASTM test methods referenced in this guide, they will not be identified individually in this section.

2.2 *ASTM Standards*:²

[D883 Terminology Relating to Plastics](#)

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[IEEE/ ASTM SI-10 Standard for Use of the International System of Units \(SI\): The Modern Metric System](#)

2.3 *NFPA Standard*:

[NFPA 99 Standard for Health Care Facilities](#)³

¹ This guide is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.94 on Government/Industry Standardization.

Current edition approved March 1, 2014. Published March 2014. Originally approved in 1999. Last previous edition approved in 2008 as D6436 - 08. DOI: 10.1520/D6436-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

3. Terminology

3.1 *Definitions*—The terminology used in this guide is in accordance with Terminologies [D883](#), [D1600](#), and [IEEE/ ASTM SI-10](#).

4. Significance and Use

4.1 This guide is intended to provide ready access to the recommended property name, test method reference, maximum number of significant digits,⁴ and appropriate units for commonly used plastics and thermoplastic elastomer tests.

4.2 It is particularly useful for those involved in the writing and proofreading of documents containing data for a large number of tests since the need to go to each individual test method should be greatly minimized.

4.3 SI units are to be regarded as standard. U.S. Customary units and conversion factors are provided to accommodate those situations where it is necessary to report both. U.S. Customary refers to units commonly used in the United States and is not always the same as inch-pound units.

5. Procedure

5.1 Refer to [Table 1](#) for the recommended nomenclature and units for physical properties and the recommended number of significant digits for test data associated with each property.

5.2 Abbreviations not shown in [Table 1](#) that may be necessary to further clarify the conditions of testing, such as MHz and kHz for electrical tests, can be found in [IEEE/ ASTM SI-10](#).

6. Keywords

6.1 conversion factors; decimal places; properties reporting; reporting guide; significant figures

⁴ The recommended maximum number of significant digits is based on experience of experts in the plastics industry.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Reference Guide for Properties Reported

Property Reported	Units, SI (U.S. Customary)	ASTM Test Method	Maximum Number of Significant Digits	Conversion Factor (CV) (SI × CV = U.S. Customary)
Arc Resistance	s (s)	D495	2	1
Bulk Density	kg/m ³ (lb/ft ³)	D1895	3	0.06242
Charpy Impact Resistance of Notched Specimens	J/m (ft × lbf/in.)	D6110	3	0.01873
Coefficient of Friction	—	D1894	2	—
Coefficient of Linear Thermal Expansion	mm/mm × °C (in./in. × °F)	D696	2 (expressed in scientific notation)	0.5556
Color, CIE, L*, a*, b*	—	E308	3	—
Crystalline Peak Melting Point (<i>T_m</i>) 2nd Heating Cycle	°C (°F)	D3418	3	(°C × 1.8) + 32
Dart Impact	g (g)	D1709	2 (1 if value is <100)	1
Deflection Temperature @ 1.82 MPa (264 psi) @ 0.455 MPa (66 psi)	°C (°F)	D648	3	(°C × 1.8) + 32
Density	kg/m ³ (g/cm ³) g/cm ³ (g/cm ³) g/cm ³ (g/cm ³)	D792 D1505 D4883	3 3 3	0.001 1 1
Dielectric Strength (Specify Method Used)	V/mm (V/mil)	D149	3	0.0254
Dissipation Factor (Specify Test Frequency)	—	D150	2	—
Durometer Hardness Shore A Shore D	—	D2240	2	—
Elmendorf Tear Resistance	N (gf)	D1922	3	102
Elongation @ Break	% (%)	D638 D882 D412	2 2 2	1 1 1
Elongation @ Yield	% (%)	D638 D882 D412	2 2 2	1 1 1
Flammability	cm/min (in./min)	D635	2	0.394
Flexural Modulus	MPa (10 ⁵ psi)	D790	3	0.001450
Flexural Modulus, ___% Secant	MPa (10 ⁵ psi)	D790	3	0.001450
Flexural Strength	MPa (psi)	D790	3	145.0
Flexural Yield Strength	MPa (psi)	D790	3	145.0
Flow Rate, Condition ___°C/___kg	g/10 min (g/10 min)	D1238	2	1
Gardner Impact Strength @ F ₅₀	J (in. × lbf)	D5420	2	8.851
Gas Permeability, CO ₂	cm ³ × mm/m ² × 24 h × atm (cm ³ × mil/100 in. ² × 24 h × atm)	D1434	2	2.54
Gas Permeability, O ₂	cm ³ × mm/m ² × 24 h × atm (cm ³ × mil/100 in. ² × 24 h × atm)	D3985	2	2.54
Gas Transmission Rate, CO ₂	cm ³ /m ² × 24 h × atm (cm ³ /100 in. ² × 24 h × atm)	D1434	2	0.06452
Gas Transmission Rate, O ₂	cm ³ /m ² × 24 h × atm (cm ³ /100 in. ² × 24 h × atm)	D3985	2	0.06452
Glass Transition Temperature (<i>T_g</i>)	°C (°F)	D3418	3	(°C × 1.8) + 32

TABLE 1 *Continued*

Property Reported	Units, SI (U.S. Customary)	ASTM Test Method	Maximum Number of Significant Digits	Conversion Factor (CV) (SI × CV = U.S. Customary)
Gloss @ ___°	—	D2457	3	—
Haze	% (%)	D1003	2	1
Heat of Fusion	kJ/kg (cal/g)			
1st Heating Cycle		E793	2	0.2388
2nd Heating Cycle		D3417	2	0.2388
Impact Resistance (Puncture), Energy @ Maximum Load	J (ft × lbf)	D3763	2	0.7376
Impact Resistance of Plastic Film, Energy to Rupture	J (ft × lbf)	D4272	2	0.7376
Izod Pendulum Impact Resistance	J/m (ft × lbf/in.)	D256	3	0.01873
Light Transmission	% (%)	E308	2	1
Melt Density @ ___°C	kg/m ³ (g/cm ³)	D3835 D1238 (Note A, Table 2)	3	0.001
Mold Shrinkage	mm/mm (in./in.)	D955	3	1
Oxygen Index	% (%)	D2863	2	1
Permittivity (Dielectric Constant) (Specify Test Frequency)	—	D150	2	—
PPT Tear Resistance	N (lbf)	D2582	2	0.2248
Refractive Index, n_D	—	D542	4	—
Rockwell Hardness (Specify Scale)	—	D785	3	—
Soluble Matter Loss	% (%)	D570	2	1
Specific Gravity	—	D792	3	—
Specific Heat @ ___°C (°F)	kJ/kg × K (cal/g × °C or Btu/lb × °F)	E1269	3	(cal/g × °C) 0.2388 (Btu/lb × °F) 0.2388
Static Decay Rate	s (s)	D4470 NFPA 99	3	1
Surface Resistivity	ohms/square (ohms/square)	D257	2 (expressed in scientific notation)	1
Tear Propagation Resistance, Split-Tear Method	N (lbf)	D1938	2	0.2248
	N/mm (lbf/in.)		2	5.710
Tear Propagation Resistance (Specify Specimen Type)	N/mm (lbf/in.)	D624	3	5.710
Tensile Modulus	MPa (10 ⁵ psi)	D638	3	0.001450
	MPa (10 ⁵ psi)	D882	3	0.001450
	MPa (10 ⁵ psi)	D412	3	0.001450
Tensile Modulus, ___% Secant	MPa (10 ⁵ psi)	D638	3	0.001450
	MPa (10 ⁵ psi)	D882	3	0.001450
	MPa (10 ⁵ psi)	D412	3	0.001450
Tensile Stress @ Break	MPa (psi)	D638	3	145.0
	MPa (psi)	D882	3	145.0
	MPa (psi)	D412	3	145.0
Tensile Stress @ Yield	MPa (psi)	D638	3	145.0
	MPa (psi)	D882	3	145.0
	MPa (psi)	D412	3	145.0

TABLE 1 *Continued*

Property Reported	Units, SI (U.S. Customary)	ASTM Test Method	Maximum Number of Significant Digits	Conversion Factor (CV) (SI × CV = U.S. Customary)
Thickness of Film Tested	microns (mils)	D5947 ≤250 microns (≤10 mils)	2	0.03937
Thickness of Sheet Tested	mm (mils)	D5947 >0.25 mm (>10 mils)	2	39.37
Transmittance (Specify Regular Transmittance and/or Total Transmittance)	% (%)	D1003	2	1
Transparency (Clarity)	% (%)	D1746	2	1
Unnotched Cantilever Beam Impact Resistance	J/m (ft × lbf/in.)	D4812	3	0.01873
Vicat Softening Temperature	°C (°F)	D1525	3	(°C × 1.8) + 32
Volume Resistivity	ohms × cm (ohms × cm)	D257	2 (expressed in scientific notation)	1
Water Absorption	% (%)	D570	2	1
Water Vapor Transmission Rate	g/m ² × 24 h (g/100 in. ² × 24 h)	F372 (film/sheet)	2	0.06452
Yellowness Index	—	E313	2	—

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D6436 - 08) that may impact the use of this standard. (March 1, 2014)

- (1) Added D6110 to **Table 1**.
 (2) Changed labels for D256 and D4812 in **Table 1**.
 (3) Revised **Note 1** to meet requirements of Guide D4968.
 (4) Made minor editorial changes.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).