



Standard Practice for Salt-Accelerated Outdoor Cosmetic Corrosion Testing of Organic Coatings on Automotive Sheet Steel¹

This standard is issued under the fixed designation D6675; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Corrosion of painted sheet steel of auto bodies is classified according to the initial location and direction of the corrosive attack. When the corrosion starts on the visible exterior surface, mostly at nicks and scratches in the paint, it is called “cosmetic” or “outside in” corrosion. Corrosion initiated at an interior surface or within a closed or semi-closed part is called “perforation” or “inside out” corrosion.

1. Scope

1.1 This practice is designed to assist procedures to be followed when conducting outdoor exposures to evaluate cosmetic corrosion that might occur in steel panels covered with an organic coating that has been damaged. The outdoor exposures described are based on Practice [G7](#) and include periodic wetting of the test specimens with a salt solution.

1.2 The methods of preparing test specimens and the particular exposure requirements of materials are beyond the scope of this practice.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- [B117 Practice for Operating Salt Spray \(Fog\) Apparatus](#)
- [D609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and](#)

¹ This practice is under the jurisdiction of ASTM Committee [D01](#) on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee [D01.27](#) on Accelerated Testing.

Current edition approved Dec. 1, 2015. Published December 2015. Originally approved in 2001. Last previous edition approved in 2011 as D6675 – 01 (2011). DOI: 10.1520/D6675-01R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

Related Coating Products

- [D610 Practice for Evaluating Degree of Rusting on Painted Steel Surfaces](#)
- [D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels](#)
- [D1014 Practice for Conducting Exterior Exposure Tests of Paints and Coatings on Metal Substrates](#)
- [D1654 Test Method for Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments](#)
- [D1730 Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting](#)
- [D2201 Practice for Preparation of Zinc-Coated and Zinc-Alloy-Coated Steel Panels for Testing Paint and Related Coating Products](#)
- [D3170 Test Method for Chipping Resistance of Coatings](#)
- [G7 Practice for Atmospheric Environmental Exposure Testing of Nonmetallic Materials](#)
- [G50 Practice for Conducting Atmospheric Corrosion Tests on Metals](#)
- [G117 Guide for Calculating and Reporting Measures of Precision Using Data from Interlaboratory Wear or Erosion Tests](#)

3. Significance and Use

3.1 Tests of the type described in this practice may be used to evaluate the corrosion resistance of organic coatings on metal products exposed to highly salty environments, such as areas subjected to deicing salts or coastal areas. Exposure conditions are complex and changeable. Important factors include climate, time of year, presence of pollution, and so forth. Generally it is difficult, if not impossible, to define or measure precisely all the factors that influence degradation. Repeated exposure testing during different seasons and over a period of at least two years is required to obtain results representative of any given location.

3.2 Control specimens must always be used because this is a comparative test.

4. Test Site

4.1 *Location*—The preferred location for the racks is a cleared, grass covered area. Other conditions can be agreed upon between the parties involved.

4.2 *Rack Position and Type*—45° open rack facing the equator, direct weathering unless other conditions are agreed upon between the buyer and seller.

NOTE 1—Information on location, rack construction, and position are given in Practices **D1014**, **G7**, and **G50**.

5. Test Specimens

5.1 Methods for the preparation of test panels and substrates are given in Practices **D609**, **D1730** and **D2201**. Practice **D823** covers techniques for producing uniformly coated test panels.

6. Preparation of Test Specimens

6.1 Prior to exposure, the organic coating shall be subjected to damage by scribing, chipping or by a method agreed upon between all interested parties. Applicable methods for scribing are given in Practice **D1654** and for chipping in Practice **D3170**.

7. Procedure

7.1 Attach specimens to an exposure rack facing the equator. Unless otherwise specified, the rack shall be oriented at an angle of 45° to the horizontal. The panels must be electrically insulated from each other and the exposure rack. The use of insulators or painting all sides of the specimens to protect against galvanic corrosion, are suitable methods for achieving this.

7.2 Unless otherwise specified, twice weekly, at 3 to 4 day intervals, apply the electrolyte solution to test specimens. Unless otherwise specified, use a 5 % aqueous sodium chloride solution prepared in accordance with Practice **B117**. Use a hand pump atomizer or other means to spray the electrolyte solution. Make sure that each specimen is completely wetted. Since the degree of atomization and volume of solution can affect the corrosion rate, the details of the solution application must be reported. Make sure to use the same application conditions each time the electrolyte solution is applied.

NOTE 2—This test does not necessarily agree with any other accelerated test, or any other natural exposure conducted in severe locations.^{3,4,5,6}

³ Townsend, H. E., Davidson, D. D., and Ostermiller, M. R., "Development of Laboratory Corrosion Tests by the Automotive and Steel Industries of North America," *Proceedings of the Fourth International Conference on Zinc and Zinc-Alloy Coated Steel Sheet*, Iron and Steel Institute of Japan, Tokyo, 1998, pp. 659–666.

7.3 The application of electrolyte solution should be performed on the scheduled day regardless of the weather conditions such as rain or snow. Unless otherwise agreed upon, spray the panels after the evaporation of the morning dew formation. Do not remove snow and ice from the specimens prior to the electrolyte solution application.

8. Periods of Exposure

8.1 The duration of exposure should be specified on one of the following bases:

8.1.1 Exposure for a specified number of days, months or years. The report shall indicate exact dates of exposure.

8.1.2 Exposure until a specified level of corrosion or degradation has occurred.

8.1.3 Exposure until a specified amount of corrosion or degradation has occurred in a standard specimen exposed with the test specimens.

9. Evaluation of Specimens After Exposure

9.1 Evaluate the specimens in accordance with Test Method **D610** and Practice **D1654**.

9.2 Other methods for evaluating test specimens may be used as agreed upon between the buyer and seller.

10. Report

10.1 Report all the following information, if available:

10.1.1 Materials tested and number of specimens obtained,

10.1.2 Preparation of the test panel and description of the paint damage before exposure; scribe, chip or otherwise,

10.1.3 Exposure site location include ground cover, rack materials or construction and position (angle facing the equator) and possible occurrence of natural salt spray,

10.1.4 Type of electrolyte solution, application method, sprayer type and interval,

10.1.5 Duration of exposure,

10.1.6 Exposure dates, and

10.1.7 Results of the evaluation.

11. Keywords

11.1 atmospheric testing; corrosion; exposure tests-exterior

⁴ Lutze, F. W., and Shaffer, R. F., "Accelerated Atmospheric Corrosion Testing of AISI Panels," *Automotive Corrosion and Prevention Conference Proceedings, P-250*, Society of Automotive Engineers, Warrendale, PA, 1991, pp. 115–127.

⁵ Davidson, D. D., and Sumacher, W. A., "An Evaluation and Analysis of Commonly Used Accelerated Cosmetic Corrosion Tests Using Direct Comparisons with Actual Field Exposure," *Automotive Corrosion and Prevention Conference Proceedings, P-250*, Society of Automotive Engineers, Warrendale, PA, 1991, pp. 205-219.

⁶ Simpson, M. W., Van der Linde, W. B., McCune, D. C., and Townsend, H. E., "License-Plate Cosmetic Corrosion Tests of Automotive Coated Steel Sheet," Paper No. 98553 presented at the Symposium on Automotive Corrosion, NACE International, March, 1998.

 **D6675 – 01 (2015)**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>