



# Standard Guide for Selection of Test Methods for Prefabricated Vertical Drains (PVD)<sup>1</sup>

This standard is issued under the fixed designation D6917; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This guide provides recommendations for the selection of appropriate test methods for prefabricated vertical geocomposite drains (sometimes referred to as Wick Drains) used in geotechnical engineering applications to provide consistency in data reporting.

1.2 This guide includes test methods for all types of prefabricated geocomposite drains manufactured in a plant and consisting of a polymeric core structure with a synthetic fabric (geotextile) jacket for filtration.

1.3 This guide is intended to aid all personnel involved in the selection, manufacture, installation, or evaluation of prefabricated vertical drains.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- D4491 Test Methods for Water Permeability of Geotextiles by Permittivity
- D4533 Test Method for Trapezoid Tearing Strength of Geotextiles
- D4632 Test Method for Grab Breaking Load and Elongation of Geotextiles
- D4716 Test Method for Determining the (In-plane) Flow Rate per Unit Width and Hydraulic Transmissivity of a Geosynthetic Using a Constant Head
- D4751 Test Method for Determining Apparent Opening Size of a Geotextile

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee D35 on Geosynthetics and are the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.

Current edition approved Feb. 15, 2016. Published February 2016. Originally approved in 2003. Last previous edition approved in 2011 as D6917 – 03(2011). DOI: 10.1520/D6917-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D4884 Test Method for Strength of Sewn or Bonded Seams of Geotextiles
- D5101 Test Method for Measuring the Filtration Compatibility of Soil-Geotextile Systems
- D5199 Test Method for Measuring the Nominal Thickness of Geosynthetics
- D5322 Practice for Laboratory Immersion Procedures for Evaluating the Chemical Resistance of Geosynthetics to Liquids
- D5493 Test Method for Permittivity of Geotextiles Under Load
- D5567 Test Method for Hydraulic Conductivity Ratio (HCR) Testing of Soil/Geotextile Systems
- D5819 Guide for Selecting Test Methods for Experimental Evaluation of Geosynthetic Durability
- D6241 Test Method for Static Puncture Strength of Geotextiles and Geotextile-Related Products Using a 50-mm Probe
- D6364 Test Method for Determining Short-Term Compression Behavior of Geosynthetics
- D6389 Practice for Tests to Evaluate the Chemical Resistance of Geotextiles to Liquids
- D6918 Test Method for Testing Vertical Strip Drains in the Crimped Condition
- D7498 Test Method for Vertical Strip Drains Using a Large Scale Consolidation Test

## 3. Terminology

### 3.1 Definitions:

3.1.1 *geocomposite, n*—a product composed of two or more materials, at least one of which is a geosynthetic.

3.1.2 *geosynthetic, n*—a planar product manufactured from polymeric material used with soil, rock, earth, or other geotechnical engineering related material as an integral part of a manmade project, structure, or system.

3.1.3 *geotechnical engineering, n*—the engineering application of geotechnics.

3.1.4 *geotechnics, n*—the application of scientific methods and engineering principles to the acquisition, interpretation, and use of knowledge of materials of the earth's crust to the solution of engineering problems.

\*A Summary of Changes section appears at the end of this standard

3.1.5 *geotextiles, n*—any permeable textile material used in foundation, soil, rock, earth, or any other geotechnical engineering related material, as an integral part of a manmade project, structure, or system.

3.1.6 *vertical strip drain, n*—a geocomposite consisting of a geotextile cover and drainage core installed vertically into soil to provide drainage for accelerating consolidation of soils.

3.1.6.1 *Discussion*—Also known as band drain, wick drain, or prefabricated vertical drain (PVD).

#### 4. Significance and Use

4.1 To properly evaluate prefabricated vertical drains, tests must be performed according to specific test methods and procedures. Failure to follow this practice can result in data not representative of the product’s characteristics and performance.

#### 5. Test Methods

5.1 Recommended test methods for prefabricated vertical drains have been grouped into 2 categories and are listed in tables as follows:

##### 5.1.1 Table—Prefabricated Vertical Drains Index Properties

Characteristic	ASTM Standard
PVD (Geocomposite)	
Grab	Test Method <b>D4632</b>
Thickness	Test Method <b>D5199</b>
Discharge Capacity (Transmissivity)	Test Method <b>D4716</b>
Compression	Test Method <b>D6364</b>
Seam Strength	Test Method <b>D4884</b>
Geotextile (Filter)	
Permittivity	Test Method <b>D4491</b>
Permeability	Test Method <b>D4491</b>
Apparent Opening Size	Test Method <b>D4751</b>
Static Puncture	Test Method <b>D6241</b>
Trap Tear	Test Method <b>D4533</b>

##### 5.1.2 Table—Prefabricated Vertical Drains Performance Properties.

Characteristic	ASTM Standard
PVD (Geocomposite)	
Discharge Capacity (Transmissivity)	Test Method <b>D4716</b>
Chemical Resistance	Practice <b>D5322</b> / Practice <b>D6389</b>
Durability	Guide <b>D5819</b>
Crimp Test	Test Method <b>D6918</b>
Large Scale Consolidation	Test Method <b>D7498</b>
Geotextile (Filter)	
Permittivity Under Load	Test Method <b>D5493</b>
Clogging Potential by Gradient Ratio	Test Method <b>D5101</b>
Hydraulic Conductivity Ratio	Test Method <b>D5567</b>

#### 6. Keywords

6.1 geocomposite; geosynthetic; geotextile; permittivity; prefabricated vertical drain; transmissivity

### SUMMARY OF CHANGES

Committee D35 has identified the location of selected changes to this standard since the last issue (D6917 – 03(2011)) that may impact the use of this standard. (Approved Feb. 15, 2016.)

- (1) Removal of Test Method D3786, Test Method D4886, and Test Method D5261.      (2) Addition of Test Method **D6918** and Test Method **D7498**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*