



# Standard Specification for Urea-Formaldehyde Molding Compounds<sup>1</sup>

This standard is issued under the fixed designation D705; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers compression molding thermosetting, urea-formaldehyde molding compounds as further defined in 3.1.

1.2 The values stated in SI units are to be regarded as the standard.

NOTE 1—The properties included in this specification are those required to identify the types of molding compounds covered. There may be other requirements necessary to identify particular characteristics. Transfer or injection molding will usually result in different physical and electrical characteristics than compression molding.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—ISO 2112-1977(E) is similar but not equivalent to this specification. Product classification and characterization are not the same.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
- D495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation
- D570 Test Method for Water Absorption of Plastics
- D618 Practice for Conditioning Plastics for Testing
- D790 Test Methods for Flexural Properties of Unreinforced

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.16 on Thermosetting Materials.

Current edition approved Dec. 1, 2012. Published December 2012. Originally approved in 1943. Last previous edition approved in 2004 as D705 - 99(2004). DOI: 10.1520/D0705-99R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and Reinforced Plastics and Electrical Insulating Materials

- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D956 Practice for Compression Molding Specimens of Amino Molding Compounds (Withdrawn 1992)<sup>3</sup>
- D3892 Practice for Packaging/Packing of Plastics

2.2 *ISO Standard*:

- ISO 2112-1977(E) Plastics—Aminoplastic Moulding Materials—Specification<sup>4</sup>

## 3. Classification

3.1 The molding compounds covered by this specification shall be designated by types, based upon their principal characteristics and the fillers used.

3.1.1 *Type 1*—A general purpose molding compound with alpha-cellulose filler.

3.1.2 *Type 2*—A general purpose molding compound with cellulose filler other than alpha-cellulose.

## 4. General Requirements

4.1 The molding compounds shall be of uniform composition. The apparent density, bulk factor, plasticity, particle size, and color shall be compounded as to conform to the requirements prescribed in this specification.

## 5. Detail Requirements

5.1 Test specimens molded in accordance with Practice D956 shall conform to the requirements prescribed in Table 1.

## 6. Sampling

6.1 A batch of molding compound shall be considered as a unit of manufacture as prepared for shipment and may consist of a blend of two or more production runs.

6.2 Adequate statistical sampling shall be used.

## 7. Test Methods

7.1 The properties enumerated in this specification shall be determined in accordance with the following methods:

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Detail Requirements for Compression-Molded Test Specimens**

NOTE 1—ASTM Committee D20 on Plastics recognizes the existence of two types having essentially the same physical and electrical properties. The two types are continued, however, since Type 1 has unlimited color possibilities, while Type 2 is limited to a relatively few dark, opaque colors.

	Type 1	Type 2
Specific gravity, 23/23°C: min	1.45	1.45
Flexural strength, min: MPa	55.2	51.7
Impact resistance (Izod), min, J/m of notch	10.7	10.7
Water absorption, max, weight gain, %	2.0	2.0
Dielectric strength, 23°C, min, kV/mm: short-time test	11.8	11.8
step-by-step test	7.9	7.9
Arc resistance, min, s	80	...

7.1.1 *Conditioning Test Specimens*—Molded test specimens shall be conditioned in accordance with Procedure B of Practice D618, except for the tests for arc resistance and dielectric strength, where Procedure A shall be used.

7.1.2 *Test Conditions*—Tests shall be conducted in the standard laboratory atmosphere of  $23 \pm 1^\circ\text{C}$  and  $50 \pm 2\%$  relative humidity, unless otherwise specified in the testing methods or in this specification.

7.1.3 *Specific Gravity*—Method A of Test Methods D792.

7.1.4 *Flexural Strength*—Test Methods D790, Procedure A, Method I, using a 6.4 by 12.7 by 127-mm bar tested parallel to molding pressure.

7.1.5 *Impact Resistance (Izod)*—Method A of Test Methods D256, using a specimen measuring 12.7 by 12.7 by 63.5 mm and notched on the side parallel to the direction of molding pressure.

7.1.6 *Water Absorption*—Test Method D570, using the 24-h immersion procedure.

7.1.7 *Dielectric Strength*—Test Methods D149, except that the test specimens shall be compression-molded disks or plates 3.2 mm in thickness.

7.1.8 *Arc Resistance*—Test Method D495, using tungsten rod electrodes.

## 8. Packaging and Package Marking

8.1 *Packaging*—The compound shall be packaged in standard commercial containers, so constructed as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery.

8.2 *Package Marking*—Shipping containers shall be marked with the name of the compound, type, color, and the quantity contained therein, as defined by the contract or order under which shipment is made, the name of the manufacturer, and the number of the contract or order.

8.3 All packing, packaging, and marking provisions of Practice D3892 shall apply to this specification.

## 9. Keywords

9.1 formaldehyde; molding compounds (thermosetting); urea-formaldehyde

## SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue, D705 – 99(2004), that may impact the use of this standard. (December 1, 2012)

(1) Five year review. Reapproval without change.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*