



# Standard Test Method for Polyurethane Raw Materials: Determination of Acidity as Acid Number for Polyether Polyols<sup>1</sup>

This standard is issued under the fixed designation D7253; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This test method measures the acidic constituents in polyether polyols and reports the results as acid number. The typical acid number range is 0-0.1 mg KOH/g sample. (See [Note 1.](#))

1.2 The values stated in SI units are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D883 Terminology Relating to Plastics](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method see Terminology [D883](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *acid number*—the quantity of base, expressed in milligrams of potassium hydroxide, that is required to titrate acidic constituents in 1 g of sample.

## 4. Summary of Test Method

4.1 The sample is dissolved in 2-propanol. The resulting single-phase solution is titrated at room temperature with 0.02

N methanolic potassium hydroxide solution to an end point indicated by the color change (pink endpoint) of the added phenolphthalein.

NOTE 2—It is permissible to use automatic titrators using a potentiometric endpoint for the titration portion of this test provided the automatic titration method is tested to obtain at least equivalent results to the manual titration.

NOTE 3—Phenolphthalein is the indicator of choice based on published hydroxyl number methods that include an acid number correction. Other indicators can be chosen if specific acids are of interest. Bromothymol blue (green endpoint) can be used for stronger acids ( $\text{pKa}'\text{s} < \sim 4$ ) and thymolphthalein (blue endpoint) can be used for weak acids ( $\text{pKa}'\text{s} > \sim 7$ ).

## 5. Significance and Use

5.1 This test method is suitable for quality control, as a specification test, and for research. Acid numbers indicate the extent of any neutralization reaction of the polyol with acids. The results of this method measure batch-to-batch uniformity and are used as correction factors in calculating true hydroxyl numbers.

## 6. Interferences

6.1 Samples or constituents that are highly-colored will interfere with or prevent the use of this test method. In this case, a potentiometric titration using an autotitrator is recommended, see [Note 2](#).

## 7. Apparatus

7.1 *Buret, 10 mL*, can be manual or automatic.

7.2 *Graduated cylinder, 10 mL, maximum.*

7.3 *Balance, analytical with sensitivity of at least  $\pm 0.0001$  g.*

7.4 *Erlenmeyer flask, at least 250 mL capacity.*

7.5 *Stirring bars or stirring rods.*

## 8. Reagents and Materials

8.1 *Purity of Reagents*—Use reagent-grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.22](#) on Cellular Materials - Plastics and Elastomers.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 2006. Last previous edition approved in 2011 as D7253 - 11(2011) <sup>$\epsilon$ 1</sup>. DOI:10.1520/D7253-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

specifications are available.<sup>3</sup> Other grades can be used provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

8.2 *Phenolphthalein*, Indicator Grade.

8.3 *Phenolphthalein Indicator Solution*—Dissolve 1 g of phenolphthalein in 100 mL of methanol.

8.4 *Potassium Hydroxide Standard Solution (0.02 N)*—Prepare and standardize a 0.02 N methanolic potassium hydroxide solution. (1.32 g KOH pellets (85 % KOH) per 1000 mL methanol, standardized with potassium hydrogen phthalate.) The KOH solution is to remain capped to avoid the formation of carbonates due to the reaction with atmospheric CO<sub>2</sub>.

## 9. Procedure

9.1 Add 100 ± 20 mL of 2-propanol and 1 mL of phenolphthalein indicator solution to an Erlenmeyer flask.

9.2 Titrate the stirred solution with 0.02 N KOH solution to the first faint pink endpoint that persists for 30 seconds.

9.3 Weigh 50-60 g of sample into the same Erlenmeyer flask and record the weight of the sample to the nearest 0.1 g.

9.4 Stir or swirl the solution in the flask until the sample is completely dissolved.

9.5 Titrate the clear sample solution with standardized 0.02 N KOH solution to the first faint pink endpoint that persists for 30 seconds.

## 10. Calculation or Interpretation of Results

10.1 Calculate the acid number, in milligrams of KOH /gram of sample as follows:

$$\text{Acid Number} = [A \times N \times 56.1] / W \quad (1)$$

where:

A = volume of KOH solution for the titration of the sample in mL,

N = the normality of the KOH solution, and

W = the weight of the sample used in g.

## 11. Report

11.1 Report results to the nearest 0.001 mg KOH/g.

## 12. Precision and Bias<sup>4</sup>

12.1 **Table 1** is based on a round robin involving seven laboratories and conducted in 2005 in accordance with Practice

<sup>3</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K. and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

<sup>4</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D20-1244.

**TABLE 1 Round Robin Data for Acid Number (mg KOH/g) in Accordance with Practice E691**

Material	Average	$S_r^A$	$S_R^B$	$r^C$	$R^D$	$n^E$
1	0.026	0.001	0.005	0.003	0.013	7
2	0.015	0.001	0.005	0.004	0.014	7
3	0.016	0.002	0.005	0.005	0.013	7
4	0.105	0.001	0.008	0.004	0.022	6

<sup>A</sup> $S_r$  = within-laboratory standard deviation of the replicates.

<sup>B</sup> $S_R$  = between-laboratory standard deviation of the averages.

<sup>C</sup> $r$  = within-laboratory repeatability limit = 2.8\* $S_r$ .

<sup>D</sup> $R$  = between-laboratory reproducibility limit = 2.8\* $S_R$ .

<sup>E</sup>  $n$  = number of laboratories contributing valid data for this material.

**E691.** All labs used a colorimetric endpoint titration for the generation of the data used in this study. All the samples were prepared at one source, but the individual specimens were prepared at the laboratories that tested them. Each test result was the average of two individual determinations. Each laboratory made duplicate determinations on each material on each of two days. (**Warning**—The following explanations of  $r$  and  $R$  (12.2 – 12.2.3) are intended only to present a meaningful way of considering the approximate precision of this test method. The data in **Table 1** is not to be rigorously applied to the acceptance or rejection of material, as those data are specific to the round robin and are not representative of other lots, conditions, materials, or laboratories. Users of this test method are to apply the principles outlined in Practice **E691** to generate data specific to their laboratory and materials or between specific laboratories. The principles of 12.2 – 12.2.3 are then valid for such data.)

### 12.2 Precision

12.2.1 *Repeatability, (r)*—Comparing two replicates for the same material, obtained by the same operator, using the same equipment on the same day. The two replicate results are to be judged not equivalent if they differ by more than the  $r$  value for that material.

12.2.2 *Reproducibility, (R)*—Comparing two results, each the mean of replicates, for the same material, obtained by different operators, using different equipment in different laboratories on different days. The two test results are to be judged not equivalent if they differ by more than the  $R$  value for that material.

12.2.3 Any judgment in accordance with 12.2.1 and 12.2.2 has an approximate 95 % (0.95) probability of being correct.

12.3 There are no recognized standards by which to estimate the bias of this test method.

## 13. Keywords

13.1 acidity; acid number; hydroxyl number; polyether polyols

**SUMMARY OF CHANGES**

Committee D20 has identified the location of selected changes to this standard since the last issue (D7253 - 11(2011))<sup>e1</sup> that may impact the use of this standard. (September 1, 2016)

- |   |  |
|---|--|
| <p>(1) Subsection 1.2 Scope—Changed to comply with the Blue Book.</p> <p>(2) Subsection 4.1 Summary of Test Method—Added note to indicate use of automatic titrators is permissible.</p> <p>(3) Subsection 6.1 Interferences—Added recommendation for use of an autotitrator.</p> | <p>(4) Subsection 8.4 Reagents and Materials—Added to protect reagent from atmospheric CO<sub>2</sub>.</p> <p>(5) Minor editorial changes throughout the method.</p> |
|---|--|

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*