



Standard Test Method for Analysis of In-Service Lubricants Using Particular Four-Part Integrated Tester (Atomic Emission Spectroscopy, Infrared Spectroscopy, Viscosity, and Laser Particle Counter)¹

This standard is issued under the fixed designation D7417; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the quantitative analysis of in-service lubricants using an automatic testing device that integrates these varied technologies: atomic emission spectroscopy, infrared spectroscopy, viscosity, and particle counting.

1.2 This is suited for in-service lubricating oils having viscosities in the range between ISO 10 and ISO 320 and properties in the ranges given in [Tables 1 and 2](#).

1.3 This test method may be used to establish trends in wear and contamination of in-service lubricants and may not give equivalent numerical results to current ASTM test methods.

1.4 This test method is not intended for use with crude oil.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* (Specific hazard statements are given in Section 9 and [11.3](#).)

2. Referenced Documents

2.1 ASTM Standards:²

[D445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids \(and Calculation of Dynamic Viscosity\)](#)

[D2270 Practice for Calculating Viscosity Index from Kinematic Viscosity at 40 and 100°C](#)

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.96 on In-Service Lubricant Testing and Condition Monitoring Services.

Current edition approved Oct. 1, 2010. Published November 2010. DOI: 10.1520/D7417-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D2896 Test Method for Base Number of Petroleum Products by Potentiometric Perchloric Acid Titration](#)

[D4057 Practice for Manual Sampling of Petroleum and Petroleum Products](#)

[D4739 Test Method for Base Number Determination by Potentiometric Hydrochloric Acid Titration](#)

[D6595 Test Method for Determination of Wear Metals and Contaminants in Used Lubricating Oils or Used Hydraulic Fluids by Rotating Disc Electrode Atomic Emission Spectrometry](#)

[D7042 Test Method for Dynamic Viscosity and Density of Liquids by Stabinger Viscometer \(and the Calculation of Kinematic Viscosity\)](#)

[E2412 Practice for Condition Monitoring of In-Service Lubricants by Trend Analysis Using Fourier Transform Infrared \(FT-IR\) Spectrometry](#)

2.2 ISO Standards:³

[ISO 4406:99 Hydraulic Fluid Power Solid Contaminations Code](#)

[ISO 11171 Automatic Particle Counter Calibration Procedures](#)

3. Terminology

3.1 Definitions:

3.1.1 *electrode, n*—in an integrated tester, set of two (upper and lower) used in excitation of wear metals during emission spectroscopic testing.

3.1.2 *emission spectrometer, n*—component used to report elements in parts per million in lubricants. This process measures 20 different wear/additive metals that can be present in the used lubricant after the oil has been in service for a period of time. Test Method [D6595](#) can be used for reference or definition.

3.1.3 *infrared spectrometer, n*—component used to report condition and contamination of the lubricant (for example, water, oxidation, fuel dilution (gasoline and diesel), nitration, glycol, soot, calculated viscosity, and base number). Practice [E2412](#) can be used for reference or definition.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

TABLE 1 Element Test Parameters Measured, Calculated, and Reported

Element	Low Range, mg/kg	High Range, mg/kg	Element	Low Range, mg/kg	High Range, mg/kg
Aluminum	5 to 100	NA	Molybdenum	10 to 1000	NA
Barium	25 to 150	150 to 2000	Nickel	5 to 100	NA
Boron	5 to 100	100 to 1000	Phosphorous	100 to 600	600 to 4000
Calcium	25 to 500	500 to 9000	Potassium	10 to 1000	1000 to 4000
Chromium	8 to 100	NA	Silicon	5 to 150	150 to 3000
Copper	5 to 500	500 to 1000	Sodium	10 to 1000	NA
Iron	6 to 1000	1000 to 3000	Tin	6 to 100	NA
Lead	6 to 150	NA	Titanium	8 to 100	NA
Magnesium	5 to 100	100 to 3000	Vanadium	7 to 100	NA
Manganese	5 to 100	NA	Zinc	8 to 100	100 to 4000

TABLE 2 Physical Properties Parameters Measured, Calculated, and Reported

NOTE 1—Review Test Method **D4739** and **D2896** for particular lubricating oil applications.

Physical Property	Range
Water, wt%	0.1 to 3
Glycol, wt%	0.1 to 2
Soot, wt%	0.1 to 4
Fuel Dilution, wt%	0.1 to 15
Oxidation, abs.	0.1 to 50
Nitration, abs.	0.1 to 35
Calculated Viscosity - IR	4 to 35 (100° cSt)
Viscosity 40°C, cSt (optional)	30 to 320
Viscosity 100°C, cSt (optional)	5 to 25
Viscosity Index	5 to 150
Base Number, mg KOH/g	1.0 to 17

3.1.4 *integrated tester, n*—instrument used to analyze in-service lubricants for maintenance, preventative maintenance and service recommendations. This instrument utilizes any combination of the following: emission spectrometer, infrared device, viscometer, and particle counter.⁴

3.1.5 *sample transport system, n*—in an integrated tester, computer controlled assembly that directs the oil samples throughout the integrated tester.

3.1.6 *spark chamber, n*—in an integrated tester, area housing the upper and lower electrodes for emission spectrometer.

3.1.7 *viscometer, n*—in an integrated tester, a viscometer using calibrated measurements similar to a kinematic viscometer capable of reporting viscosity at 40°C or 100°C in centistokes (cSt), and providing a calculated viscosity index. The results are also used to determine fuel dilution in diesel lubricants. Reference to Test Method **D445**, Practice **D2270**, or Test Method **D7042** can be used as a reference for viscosity definition. Although the integrated tester does not print out SI units for measuring viscosity, reporting in mm²/s can be determined.

3.2 Definitions of Terms Specific to This Standard:

⁴ The sole source of supply of the apparatus (OSA Lab Four Part Analyzer and accessories) known to the committee at this time is On-Site Analysis, Inc., 7108 Fairway Drive, Suite 130, Palm Beach Gardens, FL 33418 (manufacturing division in Marlborough, MA), www.on-siteanalysis.com. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

3.2.1 *electrode gap, n*—in an integrated tester, specific distance between the upper and lower electrodes in the spark chamber.

3.2.2 *particle counter, n*—component in this particular integrated tester that is used to count particles using laser and high-resolution digital counter reporting in 4 μm(c), 6 μm(c), 14 μm(c) or 2 μm, 5 μm, 15 μm, using ISO 11171 calibration method and or ISO 4406:99 reporting method.

3.2.3 *sanitized cleaning swabs, n*—in an integrated tester, used to clean the electrodes after each sample analysis.

3.3 Abbreviations:

AES = Atomic Emission Spectroscopy
 IR = Infrared
 OEM = Original Equipment Manufacturer

4. Summary of Test Method

4.1 A sample of in-service lubricant is collected into a clean, new 120 mL sample bottle from the equipment being tested, preferably within 30 min of equipment shutdown. Lubricant description and service information should be recorded for proper evaluation. The integrated tester is prepared for analysis according to the operations manual and on-screen prompts. The lubricant sample is placed into the sample transport system and is analyzed using available integrated devices. The application software guides the entire procedure, controls the transfer of the sample, stores data, and generates on screen and printed results with a printed generic recommendation of the lubricant's physical condition.

5. Significance and Use

5.1 The integrated tester is primarily used to perform on-site analysis of in-service lubricants used in the automotive, high-way trucking, mining, construction, off-road “mining,” marine, industrial, power generation, agriculture, and manufacturing industries.

5.2 The immediate results of analysis of in-service lubricants are critical when performing proactive and preventative maintenance. On-site oil analysis, when used in conjunction with these programs, allows continuous system monitoring and contamination control potentially improving equipment “up-time” and equipment life.

6. Interferences

6.1 *Sample Size*—Using less than the required 130 mL of sample for the analysis may result in erroneous numbers.

6.2 *High Concentration*—Of a contaminant such as water and or soot in the IR device might cause other parameters to be blocked out in the IR band resulting in a default returned value of not applicable or “n/a” for these other parameters.

7. Apparatus

7.1 *Integrated Tester*—The particular integrated tester will incorporate two or more of the following sensors: an emission spectrometer, an infrared device, a viscometer, or a particle counter.

7.2 *Emission Spectrometer*—Consists of an excitation source, spark stand, and optical system.

7.3 *Infrared Device*—Consists of an infrared source, sample cell, and optical system.

7.4 *Dual Temperature Viscometer*—Consists of a temperature controlled sample reservoir and electronic control system.

7.5 *Particle Counter*—Consists of a sophisticated sensor cell using red laser light extinction technology utilizing the ISO 11171 calibration and ISO 4406:99 reporting.

7.6 *Sample Container*—Sample container of no less than 118 mL that is free of contaminants shall be used for the in-service oil samples and shall be discarded after use. The maximum dimensions of 10.8 cm high, 8.9 cm in diameter, and an opening of no less than 1.6 cm shall be used.

7.7 *Sonic Bath*—Water-filled, vibrating tool used to be sure that all of the contamination is in suspension in the lubricant sample. This is mostly used when preparing a lubricant sample for a particle count analysis procedure.

7.8 *Computer Application Software and Operations Manual*—The computer application software provides the functionality for the particular integrated tester; an electronic user with help screens and a condensed reference manual for quick reference, interface, hierarchical equipment database to store, analyze and manage data, embedded logic for data interpretation; and automatic reporting tools. A complete operations manual and troubleshooting guide accompany the software application.

8. Reagents and Materials

8.1 The particular integrated tester uses the following supplies which are available from the manufacturer to ensure accurate operation of the integrated tester:

8.1.1 *Electrodes*—A high-purity silver electrode set (upper and lower).

8.1.2 *Cleaning Fluid*—An environmentally safe mineral oil, to clean the instruments internal flow system. The cleaning solution in most cases can also be used as the base oil for the calibration of the instrument. This product is a nonflammable product consisting of technical grade Semtol White Mineral Oil.⁵

8.1.3 *Test Standard*—This solution is intended for use as a calibration standard for the integrated tester. It is a multi-element solution of Primol N352⁶ that was prepared with neutral oil as a functional antioxidant for specific concentrations. The certified concentrations are based upon the assayed concentrations of the raw materials and the gravimetric procedures used to prepare the final standard. The uncertainty associated with each certified concentration is ± 2 mg/kg (parts per million). In order to verify these certified values, the final solution was analyzed by plasma emission spectroscopy (ICP).

NOTE 1—The manufacturer guarantees the accuracy of this solution until the expiration date shown, provided it is kept tightly capped and stored in original bottle under normal laboratory conditions. Do not refrigerate or store in direct sunlight. Minimize exposure to moisture or high humidity. It is recommended that the solution be thoroughly mixed, by shaking the bottle, prior to use.

8.1.4 *High Viscosity Fluid*—For use with viscometer only. This fluid is blended with known viscosities and is periodically analyzed to confirm calibration or to recalibrate the viscometer. It consists of a highly refined mineral oil and a detergent/dispersant engine oil additive package.

8.1.5 *Low Viscosity Fluid*—For use with viscometer only. This fluid is blended with known viscosities and is periodically analyzed to confirm calibration or to recalibrate the viscometer. It consists of a highly refined mineral oil and a detergent/dispersant engine oil additive package.

8.1.6 *Reference Oil*—Used to verify accuracy of physical property test results reported by infrared device. The reference oil has known physical properties which are tested against the infrared device using the software to determine standardization. It consists of a highly refined mineral oil combined with zinc alkyl dithiophosphate.

8.1.7 *Sanitary Cleaning Swabs*—Used to clean the electrodes after each sample analysis. Operator shall use contaminant free cotton swabs that are not treated with sodium from the hypochlorite bleaching process. Check the manufacturer’s

⁵ The sole source of supply of the apparatus known to the committee at this time is Sonneborn, Inc., 771 Old Saw Mill River Rd., Tarrytown, NY 10591-6716. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ The sole source of supply of the apparatus known to the committee at this time is ExxonMobil (Corporate Headquarters), 5959 Las Colinas Blvd., Irving, TX 75039-2298. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

specifications of the cleaning swabs before use to determine if the bleaching process has been performed.

9. Hazards

9.1 Used oil can contain hazardous material from component source and or the contamination process. Wear appropriate personal protective equipment to prevent repeated or prolonged contact with used oil. Follow proper oil handling procedures during sampling and throughout analytical process. Follow applicable regulations and procedures when disposing of used oil.

10. Sampling

10.1 When possible, obtain sample within 30 min of equipment shutdown so that wear metals are retained in suspension and are removed with the sample. Use every possible method to keep the sample clear from external contamination. The integrated tester is capable of analyzing in-service lubricants having viscosities in the range of ISO 10 to ISO 320, including hydraulic, transmission, and power steering lubricants. Refer to Practice **D4057** when preparing sample for processing.

11. Preparation of Apparatus

11.1 Turn the main power switch of the integrated tester to “ON,” and push the red reset button to activate the computer and all components.

11.2 The integrated tester will run a diagnostics process while warming up. After the diagnostic page appears, it is a good practice to allow the integrated tester to have a warming up period of 10 min.

11.3 Fill the flush container with the cleaning fluid; this is a nonflammable product. (**Warning**—Empty the waste fluid into an approved waste disposal container in accordance with local laws.)

11.4 Fill the printer paper tray if using printer in conjunction with unit.

11.5 *Check Electrode Gap*—The gap between upper and lower electrodes shall be checked routinely to verify the proper operation of the emission spectrometer. A specially designed gapping tool is supplied with each integrated tester for setting the proper electrode gap. Electrode gap can **ONLY** be adjusted before elemental standardization (calibration).

11.6 *Clean Electrodes*—The outer and inner surfaces of the upper electrode, as well as the lower electrode, shall be cleaned with sanitary cleaning swabs.

11.6.1 Open the integrated tester spark chamber door. Using a clean dry cotton swab, wipe the electrodes clean of all sample residues (see **Note 2**).

11.6.2 Using another clean dry cotton swab, wipe the inside of the upper electrode holder by inserting the swab down through the center hole of the brass holder (see **Note 2**).

NOTE 2—Do not use cleaning fluid when cleaning electrodes. Always use a clean dry cotton swab when cleaning electrodes.

11.6.3 When testing for viscosity, no special requirements are needed to prepare the oil sample.

11.6.4 When particle count testing is required, the process requires placing the in-service oil sample bottle into the sonic bath for a 1 min period as mentioned in the operations manual. This will prepare the sample for processing.

12. Calibration and Standardization

12.1 *Baseline Test*—Verify system cleanliness by running a baseline test that uses the system’s cleaning fluid. This process is performed under the “Standardization” button on the main screen of the integrated tester. Baseline testing ensures that the atomic emission spectrometer is not contaminated and will give a pass or fail indication on the computer screen to let the operator know if it is acceptable to proceed with the next sample. The specifications are ± 5 mg/kg on all wear and additive metals except phosphorus which is ± 10 mg/kg.

12.2 If the baseline test fails to meet the required cleanliness range of the atomic emission spectrometer, the system will require flushing until a passing baseline test is achieved. The baseline test process should be run every 24 h.

12.3 *Standardization*—Standardize the unit’s atomic emission spectrometer by using an atomic emission test standard fluid as mentioned in **8.1.3** (see **Note 3**).

12.3.1 If any device in the particular integrated tester fails to meet the required accuracy range of the test standard, a full standardization shall be performed (see **Note 3**).

NOTE 3—A standardization check can be run at any time to verify calibration and cleanliness of the integrated tester. A detailed standardization process is located within the operations manual.

12.3.2 This process must be run when reference oil test fails as outlined in the instrument operations manual.

12.4 *Reference Oil Test*—See **8.1.6**. This process is recommended every 96 operational hours. This process will determine if the IR component of the integrated tester is clean of soot/solids and other debris from previous samples processed. The software for the particular integrated tester will determine the pass/fail criteria and will post a message on the computer screen stating whether standardization was completed successfully.

12.5 *Errors*—If the instrument returns an “error” message, refer to the troubleshooting guide in the operations manual.

12.6 *Calibration of Particle Counter*—Calibration shall be done by the manufacturer and should be done approximately every 1000 particle samples processed or every 2 years, whichever comes first.

13. Conditioning

13.1 No preconditioning is required for lubricant samples except when a particle count is required. If a particle count is required, the lubricant sample should be obtained hot and within 30 min of equipment shutdown. Lubricant sample must be shaken in a sonic bath immediately prior to testing to ensure all material is suspended uniformly.

14. Procedure

14.1 Collect lubricant sample into a clean, new sample bottle; at least 118 mL of the lubricant being tested is recommended.

14.2 Make sure the integrated tester is in the proper software/test mode for application being tested (for example, automotive, trucking, off-road, industrial, etc.).

14.3 Place the filled sample bottle underneath the sipper/extraction tube of the integrated tester. This device is located either in the middle of the unit or on the top right hand corner of the integrated tester.

14.4 Follow the on-screen instructions. Answer all screen prompts in the order that they appear on the touch screen. This process will lead the operator through the equipment and oil usage information: component type; oil type; oil viscosity; miles or hours, or both, that the oil has been in service; time on component being sampled; etc.

14.5 The accuracy of the information entered is crucial to allow the software to process the oil sample correctly. Review all of the vehicle and in-service lubricant information entered and make any necessary changes.

14.6 Press “START,” and follow any on-screen instructions, including placing lubricant sample into the sample transport system.

14.7 The integrated tester has an option of two delivery systems using internal valves and pumps. If the integrated tester has a particle counter, the delivery system runs separately from the atomic emission spectrometer, viscometer and IR delivery system.

14.8 The analysis process will take up to 15 min to complete. The instrument transfers oil automatically to the selected devices within the integrated tester. The application software guides the entire procedure, controls the transfer of the sample, stores data, and generates on screen and printed results with a printed generic recommendation of the lubricants physical condition.

15. Calculation or Interpretation of Results

15.1 Based on the information entered before sample processing and the results obtained from analysis of the test sample, the software program performs all required calculations and generates a data report. Optionally, a diagnostics and results interpretation report may be printed.

15.2 Test results can include equipment wear ratings (for example, normal, abnormal or severe) and maintenance recommendations.

16. Report

16.1 Report test results as follows:

16.1.1 *Wear Metals and Contaminant Elements*—Report to the nearest part per million.

16.1.2 *Water, Glycol, Soot, and Fuel Dilution*—Report either in whole values as weight % or in the abbreviated format of “present” or “not present.”

16.1.3 *Base Number*—Report in mg of KOH/g. Test Method **D4739** can be used for reference and definition base number.

16.1.4 *Oxidation and Nitration*—Report in absorbance units (Abs).

16.1.5 *Viscosity*—Report in centistokes (cSt) at 100°C or 40°C, or both. If viscosity results at both temperatures are measured, report viscosity index.

16.1.6 *Particle Count*—Report by particle size and number of particles found.

16.2 The computer software displays the test results on the screen. The results can then be printed automatically in one of several print format options. An example of a typical report is shown in **Appendix X1**.

17. Precision and Bias⁷

17.1 The precision statements are based on results from a four-laboratory study conducted in November 2004. The study involved five samples (five instruments; five operators), comprising used oil from various in-service applications. Statistical analysis revealed spectroscopic and instrumental differences. The differences are included in the estimated repeatability.

17.2 *Repeatability*—The difference between successive results obtained by the same operator with the same apparatus under constant operating conditions, on identical test materials would, in the long run, in the normal and correct operation of the practice, exceeds the values shown in **Table 3** in only one case in twenty.

17.3 *Reproducibility*—The reproducibility of this test method is not currently available. The reproducibility will be available within five years following the approval of this test method.

17.4 *Bias*—The measured quantity is an effective value for which there is not an established reference material available for measurement.

18. Keywords

18.1 arc-spark emission spectrometry; baseline; check flush; contaminants; electrodes; infrared spectrometry; in-line dual temperature viscometer; in-service lubricants testing; integrated tester; kinematic viscosity; particle counter; standardization; test standard; wear metals

⁷ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D02-1702.

TABLE 3 Repeatability

Element	Low Range, mg/kg (ppm)	Low Range Repeatability, mg/kg (ppm)	High Range, mg/kg (ppm)	High Range Repeatability, mg/kg (ppm)
Aluminum	5 to 100	5	NA	NA
Barium	25 to 150	25	150 to 2000	±20%
Boron	5 to 100	5	100 to 1000	±15%
Calcium	25 to 500	25	500 to 9000	±20%
Chromium	8 to 100	8	NA	NA
Copper	5 to 500	5	500 to 1000	±20%
Iron	6 to 1000	6	1000 to 3000	±20%
Lead	6 to 150	6	NA	NA
Magnesium	5 to 100	5	100 to 3000	±20%
Manganese	5 to 100	5	NA	NA
Molybdenum	10 to 1000	10	NA	NA
Phosphorous	100 to 600	40	600 to 4000	±20%
Potassium	10 to 1000	10	1000 to 4000	±20%
Silicon	5 to 150	5	150 to 3000	±15%
Sodium	10 to 1000	10	NA	NA
Tin	6 to 100	6	NA	NA
Titanium	8 to 100	8	NA	NA
Vanadium	7 to 100	7	NA	NA
Zinc	8 to 100	8	100 to 4000	±20%
Physical Property	Range	Repeatability		
Water, wt%	0.1 to 3	0.2		
Glycol, wt%	0.1 to 2	0.2		
Soot, wt%	0.1 to 4	0.2		
Fuel Dilution, wt%	0.1 to 15	0.4		
Oxidation, abs.	0.1 to 50	0.2		
Nitration, abs.	0.1 to 35	0.2		
Calculated Viscosity - IR	4 to 35 (100° cSt)	2		
Viscosity 40°C, cSt (optional)	30 to 320	2.5		
Viscosity 100°C, cSt (optional)	5 to 25	1		
Viscosity Index	5 to 150	1		
Base Number, mg KOH/g	1.0 to 17	1		

APPENDIX

(Nonmandatory Information)

X1. REPORTS GENERATED BY THE PARTICULAR INTEGRATED TESTER

X1.1 Example of Data Reports Options

X1.1.1 See [Figs. X1.1-X1.3](#).

	Company: MARLBOROUGH CONSTRUCTION	City: MARLBOROUGH	AA LUBRICANT COMPANY	Phone: 317-900-5008
	Address: 123 MAIN STREET	State/Zip: MA 01752		Fax:
	Phone: 508-555-1212	Fax:		
	Email:	INDIANAPOLIS	IN	46208
	Machine Make: CATERPILLAR	Unit ID: 2058	Machine ID: 2058	
	Machine Model: BG730	Unit Location: CENTER	Test Date: 04/29/2008	
	Sump Capacity: 30 Quarts	Description: ENGINE	Vehicle Year: NA	Equipment: Off-road Diesel Engine

Date Taken: 04/29/2008	Wear Metals In Parts Per Million	Physical Properties
Sample ID: 40	Iron	Chromium
Oil Brand: SHELL	Lead	Copper
Oil Type: ROTELLAT	Tin	Aluminum
Oil Weight: 15W40	Nickel	Molybdenum
Hours On Unit: 9,875	Titanium	Vanadium
Hours On Oil: 350	Manganese	Silicon
User Sample: UNKNOWN	Boron	Magnesium
Operator: UNKNOWN	Calcium	Barium
	Phosphorus	Zinc
	Sodium	Potassium
	Water	Oxidation
	V100C	Glycol
	Fuel	TBN
	Nitration	Soot
	V40C	Vindex
	135	135

ALL ENGINE WEAR RATES NORMAL. SAMPLE APPEARS FREE OF EXTERNAL CONTAMINATION. ANALYSIS INDICATES PROPER PERFORMANCE OF THE LUBRICANT AND UNIT. RESAMPLE AT THE NEXT OIL DRAIN INTERVAL.

ASSUMING NORMAL OIL CONSUMPTION AND BASED ON PROVIDED INFORMATION, WEAR METAL EVALUATION VARIES PER MAKE AND MODEL, TOTAL MILES/HOURS AND THE MILES/HOURS THE OIL HAS BEEN IN SERVICE.

A=ABNORMAL S=SEVERE NA=NOT APPLICABLE ND=NOT DETECTED N=NORMAL X=NOT TESTED

Rev 4.0.0.110807

FIG. X1.1 Example of Extended Metals and Wear Report

Truck Make:	Fleet Unit ID:	VIN#:
Truck Year:	Engine Make:	Sample Date:
Sump Capacity:	Engine Model:	Equipment:

Date Taken: 09/15/2004	WEAR METALS (in Parts per Million):										PHYSICAL PROPERTIES							
Sample ID: 000037	ALUMINUM	CHROMIUM	COPPER	IRON	LEAD	TIN	SILICON	POTASSIUM	SODIUM	MOLY	WATER	OXIDATION	VISC@100	GLYCOL	FUEL	TBN	NITRATION	SOOT
Oil Brand:	31	10	287	238	8	6	<2	<2	5		<0.1	9.4	14.0	-	2.7		4.3	
Oil Type:																		
Truck:																		
Oil Weight:																		
Truck:																		
Oil																		
User Sample:																		
Operator:																		

***ALL ENGINE WEAR RATES NORMAL. POSSIBLE FUEL LEVEL DETECTED. CHECK FOR INCREASED OIL LEVEL ON DIPSTICK CHECK FOR LOW OIL PRESSURE. RESAMPLE AT NEXT SERVICE INTERVAL TO MONITOR.**

Date Taken: 09/15/2004	WEAR METALS (in Parts per Million):										PHYSICAL PROPERTIES							
Sample ID: 000036	ALUMINUM	CHROMIUM	COPPER	IRON	LEAD	TIN	SILICON	POTASSIUM	SODIUM	MOLY	WATER	OXIDATION	VISC@100	GLYCOL	FUEL	TBN	NITRATION	SOOT
Oil Brand:	38	4	190	34	5	7	7	<2	<2		<0.1	11.0	12.1	-	6.5		6.9	
Oil Type:																		
Truck:																		
Oil Weight:																		
Truck:																		
Oil																		
User Sample:																		
Operator:																		

***ALL ENGINE WEAR RATES NORMAL. POSSIBLE MINOR FUEL DILUTION OCCURRING. VISCOSITY LOWER THAN TYPICAL FOR THE GIVEN OIL TYPE. CHECK FUEL SYSTEM. DRAIN OIL AND CHANGE FILTER IF NOT ALREADY DONE. RESAMPLE AT NEXT SERVICE INTERVAL TO MONITOR.**

Date Taken: 09/15/2004	WEAR METALS (in Parts per Million):										PHYSICAL PROPERTIES							
Sample ID: 000035	ALUMINUM	CHROMIUM	COPPER	IRON	LEAD	TIN	SILICON	POTASSIUM	SODIUM	MOLY	WATER	OXIDATION	VISC@100	GLYCOL	FUEL	TBN	NITRATION	SOOT
Oil Brand:	23	<2	63	100	7	4	8	7	<2		0.1	7.1	10.8	-	<2.0		9.1	
Oil Type:																		
Truck:																		
Oil Weight:																		
Truck:																		
Oil																		
User Sample:																		
Operator:																		

***ALL ENGINE WEAR RATES NORMAL. VISCOSITY LOWER THAN TYPICAL FOR THE GIVEN OIL TYPE. DRAIN OIL AND CHANGE FILTER IF NOT ALREADY DONE. RESAMPLE AT NEXT SERVICE INTERVAL TO MONITOR.**

***ASSUMING NORMAL OIL CONSUMPTION AND BASED ON PROVIDED INFORMATION, WEAR METAL EVALUATION VARIES PER MAKE AND MODEL, TOTAL MILES/HOURS AND THE MILES/HOURS THE OIL HAS BEEN IN SERVICE.**

A=ABNORMAL HN=HIGH NORMAL NA=NON APPLICABLE ND=NOT DETECTED S=SEVERE

FIG. X1.2 Example of Basic Report Option

Vehicle Make:	FleetUnitID:	VIN#:	
Vehicle Model:	Engine Size:	Sample Date:	
Sump Capacity:		Equipment:	GASOLINE ENGINE
Oil Brand:	Sample ID: 33	Vehicle:	52000 Miles
Oil Type:	User Sample:	Oil:	3250 Miles
Oil Weight: 10W-30	Operator:		

	Normal:	Monitor:	Inspect:	Reason
Air Filter	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	
Bearings	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Excessive (copper/lead/tin) levels detected.
Bushings	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	
Camshaft	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Excessive iron level detected.
Coolant Content	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	
Crankshaft	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Excessive iron level detected.
Cylinders	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Excessive iron level detected.
Engine Block	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	
Fuel Content	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Possible minor fuel dilution detected; May be due to piston/ring
Oil Condition	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Oil no longer serviceable due to additive depletion.
Piston Rings	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	High chromium level detected.
Pistons	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Excessive aluminum level detected.
Sludge Potential	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Oil no longer serviceable due to additive depletion.
Water Content	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	
Wear Metals	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	High wear rate detected.

Overall Results: Unacceptable

RESAMPLE AT 1/2 OIL CHANGE INTERVAL TO MONITOR.

Recommendation:

1. Check for: power loss; blow-by; smoking; oil consumption; etc.
2. Check for: oil pressure drop and abnormal knocking noise.
3. Change engine oil and filter.

FIG. X1.3 Example of Basic Report Option

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/