



Standard Test Methods for Determining the Organic Treat Loading of Organophilic Clay¹

This standard is issued under the fixed designation D7626; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This standard covers two index test methods that can be used in the evaluation of the amount of organic compound chemically bonded to the base clay portion of a representative sample of organophilic clay.

1.2 The values stated in SI units are to be regarded as the standard. No other units of measurement are included in this standard.

1.3 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice [D6026](#).

1.3.1 The procedures used to specify how data are collected/recorded or calculated in this standard are regarded as the industry standard. In addition, they are representative of the significant digits that generally should be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of the reported data to be commensurate with these considerations. It is beyond the scope of this standard to consider significant digits used in analysis methods for engineering design.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D653 Terminology Relating to Soil, Rock, and Contained Fluids](#)

¹ These test methods are under the jurisdiction of ASTM Committee [D18](#) on Soil and Rock and are the direct responsibility of Subcommittee [D18.21](#) on Groundwater and Vadose Zone Investigations.

Current edition approved May 1, 2010. Published June 2010. DOI: 10.1520/D7626-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D3740 Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction](#)

[D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing](#)

[D6026 Practice for Using Significant Digits in Geotechnical Data](#)

[E145 Specification for Gravity-Convection and Forced-Ventilation Ovens](#)

3. Terminology

3.1 *Definitions*—For common definitions of terms in this standard, refer to Terminology [D653](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *base clay, n*—an untreated naturally occurring clay (e.g., bentonite, kaolinite).

3.2.2 *organic treat loading, n*—the amount of organic compound chemically bonded to the base clay portion of an organophilic clay.

3.2.3 *organophilic, adj*—having a strong affinity for oil and other insoluble organic compounds.

3.2.4 *organophilic clay, n*—a manufactured oleophilic material consisting of base clay to which an organic compound has been chemically bonded to the clay surface.

4. Summary of Test Methods

4.1 *Test Method A*—Moisture content is determined by drying an organophilic clay specimen at 160 °C in an oven or muffle furnace. The moisture content is expressed as a percentage of the as-received mass. The ash content of the organophilic clay specimen is determined by igniting the dried specimen from the moisture content determination in a muffle furnace at 750 °C.

4.2 *Test Method B*—An organophilic clay specimen is heated at a controlled rate in a thermal gravimetric analyzer. Percent moisture content and ash are taken from thermal gravimetric analyzer report.

4.3 Some volatile structural matter within the base clay will be lost during the last stage of heating. Organic treat loading is determined on a dry weight basis by a calculation that accounts

for the moisture content, ash, and a nominal percent of volatile structural matter within the base clay.

NOTE 1—The supplier of the organophilic clay must be able to verify with historical data the nominal percent mass of the base clay (on a dry weight basis) remaining after similar heating. This value is typically in the range of 94 to 96 %.

5. Significance and Use

5.1 This standard test method is intended as an index test to determine the organic treat loading of organophilic clay. This standard test method can be used for manufacturing quality control and construction quality assurance material evaluation.

5.2 The percent organic treat loading of organophilic clay is a relative indicator of its adsorptive capacity. Organophilic clay is used for remediation of contaminated sediment, soil, and groundwater.

5.3 The two test methods denote different devices, a muffle furnace and a thermal gravimetric analyzer. The thermal gravimetric analyzer may be programmed to reach a higher temperature than the muffle furnace, but the organic matter will be burnt off at 750 °C.

NOTE 2—The quality of the result produced by this standard is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D3740 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice D3740 does not in itself assure reliable results. Reliable results depend on many factors; Practice D3740 provides a means of evaluating some of those factors.

6. Apparatus

6.1 *Oven*, meeting the requirements of Specification E145 and capable of being regulated to a constant temperature of 160 ± 5 °C.

6.2 *Muffle Furnace*, capable of producing constant temperature of 750 °C.

6.3 *TGA*, thermal gravimetric analyzer capable of reaching a minimum 750 °C with a balance having 0.001 mg readability.

6.4 *Balance or Scale*, a balance or scale for determining the mass of organophilic clay having a minimum capacity of 100 g and meeting the requirements of Guide D4753 for a balance or scale of 0.01 g readability.

6.5 *Porcelain Container and Cover*.

6.6 *Desiccator*.

6.7 *Mortar and Pestle*.

6.8 *Sieve*, 0.075 mm sieve opening.

6.9 *Gloves, Tongs or Other Suitable Equipment or Combinations Thereof*, to safely handle porcelain containers to and from furnace.

7. Sample

7.1 Collect a representative maximum 50 g sample of organophilic clay.

7.2 Crush organophilic clay sample with mortar and pestle and then screen through 0.075 mm sieve. Retain finer fraction of sample.

8. Procedures

8.1 *Test Method A—Oven or Muffle Furnace or Combinations Thereof*:

8.1.1 *Moisture Content Determination* :

8.1.1.1 Record to the nearest 0.01 g the mass of a clean, dry porcelain container and cover.

8.1.1.2 Place a test specimen of at least 10 g and no more than 50 g in the porcelain container and record mass to the nearest 0.01 g.

8.1.1.3 Dry uncovered in an oven or muffle furnace for at least 16 h at 160 °C or until there is no change in mass of the specimen after further drying in periods in excess of 1 h.

8.1.1.4 Remove from the oven, cover tightly, cool in a desiccator and record the mass (m_{dry}) to the nearest 0.01 g.

8.1.1.5 Calculate the moisture content as percent of as-received mass as follows:

$$M = [(m_i - m_{dry}) \times 100] / m_i \quad (1)$$

where:

M = moisture content, as percent of as-received mass,

m_i = mass of the as-received test specimen, g, and

m_{dry} = mass of the dried specimen, g.

8.1.2 *Organic Treat Loading Determination*:

8.1.2.1 Place the entire oven-dried specimen and porcelain container from the moisture content determination in a muffle furnace. Raise the temperature in the furnace to 750 °C.

8.1.2.2 Heat at 750 °C for a minimum of 1 h. Remove the container, cool in a desiccator, and weigh and record the mass.

8.1.2.3 Replace into furnace and repeat step 8.1.2.2 until weight loss is less than 0.05 % over at least 1 h of heating.

8.1.2.4 Remove the container, cool in a desiccator, and weigh and record the mass of dried ash (m_{ash}) to the nearest 0.01 g.

8.1.2.5 Determination of the Organic Treat Loading requires several computation steps:

Calculate the percent dry weight ash content as follows:

$$\% \text{ ash}_{dry} = (m_{ash} \times 100) / m_{dry} \quad (2)$$

where:

$\% \text{ ash}_{dry}$ = ash content as percent on a dry weight basis,

m_{ash} = mass of ash, g, and

m_{dry} = mass of the dried test specimen, g.

Calculate percent dry base clay as follows:

$$\% \text{ base clay}_{dry} = \frac{\% \text{ ash}_{dry}}{\% \text{ ash}_{dry} \text{ of base clay}} \times 100 \% \quad (3)$$

where:

$\% \text{ ash}_{dry} \text{ of base clay}$ = nominal percent of mass of base clay remaining as ash (on a dry weight basis) after similar heating as above, as reported by manufacturer (see 4.3, Note 1), and

$\% \text{ base clay}_{dry}$ = percent of mass attributable to base clay on a dry weight basis.

Calculate the Organic Treat loading as follows:

$$\% \text{ organic treat loading} = 100 \% - \% \text{ base clay}_{dry} \quad (4)$$

where:

$\% \text{ organic treat loading}$ = percent of organic treat loading on a dry weight basis.

8.2 Test Method B—Thermal Gravimetric Analyzer (TGA):

8.2.1 Use compressed air as the gas source. Check that air pump is connected and on. Check the gas flow rate ensuring flow is in accordance with manufacturer's standard operating procedure.

8.2.2 Tare a clean, dry porcelain container in the TGA device.

8.2.3 Remove the container from the TGA device and insert a test specimen of at least 50 mg in the container.

8.2.4 Place the container and specimen into the TGA device and allow the balance to stabilize.

8.2.5 Heat at a rate of 20 °C per minute to 160 °C and hold until no further loss of mass and record percent mass loss data as M .

8.2.6 Heat at rate of 20 °C per minute to between 750 °C and 1000 °C.

8.2.7 Hold at final temperature until weight loss is less than 0.05 % over at least 3 min and record data as $\% \text{ ash}_{wet}$.

8.2.8 Organic Treat Loading Determination:

8.2.8.1 Determination of the Organic Treat Loading requires several computation steps:

Determine the percent dry weight ash content:

$$\% \text{ ash}_{dry} = \frac{\% \text{ ash}_{wet}}{100\% - M} \times 100\% \quad (5)$$

where:

M = percent of initial mass loss determined at 160 °C as reported by TGA,

$\% \text{ ash}_{wet}$ = percent of initial mass remaining as ash after heating to between 750 °C and 1000 °C as reported by TGA, and

$\% \text{ ash}_{dry}$ = percent of mass on a dry weight basis remaining as ash after heating to between 750 °C and 1000 °C as reported by TGA.

NOTE 3— M is the moisture content as a percent of as-received mass. The moisture content analysis method with oven as described in 8.2.1 could be used to determine this value if it is difficult to obtain it from the TGA report.

Determine the percent dry base clay:

$$\% \text{ base clay}_{dry} = \frac{\% \text{ ash}_{dry}}{\% \text{ ash}_{dry} \text{ of base clay}} \times 100\% \quad (6)$$

where:

$\% \text{ ash}_{dry} \text{ of base clay}$ = nominal percent of mass of base clay remaining as ash (on a dry weight basis) after similar heating as above, as reported by manufacturer (see 4.3, Note 1), and

$\% \text{ base clay}_{dry}$ = percent of mass attributable to base clay on a dry weight basis.

Calculate the Organic Treat loading as follows:

$$\% \text{ organic treat loading} = 100\% - \% \text{ base clay}_{dry} \quad (7)$$

where:

$\% \text{ organic treat}$ = percent of organic treat loading on a dry weight basis.

9. Report

9.1 Report—Test Data Sheet:

9.1.1 The methodology used to specify how data are recorded as given below, is covered in 1.3.

9.1.1.1 Record as a minimum the following general information (data):

(1) Sample/specimen identifying information such as number, location, project, or feature.

(2) A description of the organophilic clay used in the evaluation including source, and manufacturer's codes of product identification, such as type and lot number.

9.1.1.2 Record as minimum the following test specimen data (see example test data sheet in Appendix X1):

(1) Specimen masses to 0.01 g (four significant digits).

(2) The results for moisture content and organic treat loading of the organophilic clay to the nearest 0.1 % (three significant digits).

9.1.2 Types of oven, furnace or TGA and representative temperatures used, and

9.1.3 Other reporting information not listed here, but as may be required by the referenced ASTM test methods.

10. Precision and Bias

10.1 *Precision*—Test data on precision is not presented due to the nature of the organophilic clay materials tested by this test method. It is either not feasible or too costly at this time to have ten or more laboratories participate in a round-robin testing program. In addition, it is either not feasible or too costly to produce multiple specimens that have uniform physical properties. Any variation observed in the data is just as likely to be due to specimen variation as to operator or laboratory testing variation.

10.1.1 Subcommittee D18.21 is seeking any data from the users of this test method that might be used to make a limited statement on precision.

10.2 *Bias*—There is no accepted reference value for this test method, therefore, bias cannot be determined.

11. Keywords

11.1 groundwater remediation; organic treat loading; organophilic clay

APPENDIX
(Nonmandatory Information)
X1. EXAMPLE DATA SHEET

ORGANIC TREAT LOADING OF ORGANOPHILIC CLAY TEST		
Sample No.:	Project:	Test Device:
Tested by: Date:	Computed by: Date:	Checked by: Date:
Specimen No.:		
Moisture Content Determination – Method A, Oven and/or Muffle Furnace		
(1) Container No.		_____
(2) Oven or muffle furnace drying temperature		_____ (°C)
(3) Mass of container, cover and organophilic clay		_____ (g)
(4) Mass of container, cover and dry organophilic clay		_____ (g)
(5) Mass of container and cover		_____ (g)
(6) Mass of organophilic clay, $m_i = (3) - (5)$		_____ (g)
(7) Mass of dry organophilic clay, $m_{dry} = (4) - (5)$		_____ (g)
(8) Moisture content as % of as-received mass, $M = \frac{(6 - 7)}{(6)} \times 100$		_____ (%)
Organic Treat Loading Determination		
(9) Muffle furnace ash temperature		_____ (°C)
(10) Mass of container, cover and ash		_____ (g)
(11) Mass of container and cover = (5)		_____ (g)
(12) Mass of ash, $m_{ash} = (10) - (11)$		_____ (g)
(13) Ash content, % dry weight = $\frac{(12)}{(7)} \times 100$		_____ (%)
(14) Nominal % ash for base clay*		_____ (%)
(15) Organic Treat Loading = $\frac{(13)}{(14)} \times 100$		_____ (%)
*Remarks (as reported by manufacturer):		

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).