



Standard Practice for Electromagnetic (Eddy Current) Examination of Type F-Continuously Welded (CW) Ferromagnetic Pipe and Tubing Above the Curie Temperature¹

This standard is issued under the fixed designation E1033; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers a procedure for in-line, eddy current examination of continuously welded (CW) ferromagnetic pipe and tubing at temperatures above the Curie temperature (approximately 1400°F (760°C), where the pipe is substantially nonmagnetic or austenitic.

1.2 This practice is intended for use on tubular products having nominal diameters of ½ in. (12.7 mm) to 4 in. (101.6 mm). These techniques may be used for larger- or smaller-diameter pipe and tubing as specified by the using parties.

1.3 This practice is specifically applicable to eddy current testing using encircling coils, or probe coils.

1.4 This practice does not establish acceptance criteria. They must be established by the using parties.

1.5 *Units*—The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address the safety problems associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[E309 Practice for Eddy-Current Examination of Steel Tubular Products Using Magnetic Saturation](#)

[E543 Specification for Agencies Performing Nondestructive Testing](#)

¹ This practice is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.07 on Electromagnetic Method.

Current edition approved Dec. 1, 2013. Published December 2013. Originally approved in 1985. Last previous edition approved in 2009 as E1033 - 09. DOI: 10.1520/E1033-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E1316 Terminology for Nondestructive Examinations](#)

2.2 Other Documents:

[SNT-TC-1A Recommended Practice for Personnel Qualification and Certification in Nondestructive Testing](#)³

[ANSI/ASNT-CP-189 ASNT Standard for Qualification and Certification of Nondestructive Testing Personnel](#)³

[NAS-410 NAS Certification and Qualification of Nondestructive Personnel \(Quality Assurance Committee\)](#)⁴

3. Terminology

3.1 Standard terminology relating to electromagnetic testing may be found in Terminology [E1316](#), Section C, Electromagnetic Testing.

4. Summary of Practice

4.1 In-line, automatic, eddy current examination of CW pipe utilizes probes or encircling coils, or both, mounted in the pass line to monitor the quality of pipe during production at temperatures ranging from 1600 to 2200°F (870 to 1204°C).

4.2 Eddy current instrumentation provides timely and useful information regarding the acceptability of CW pipe for quality control purposes as well as for early warning that unacceptable pipe is being produced.

5. Significance and Use

5.1 The purpose of this practice is to outline a procedure for the in-line eddy current examination of hot CW pipe for the detection of major imperfections and repetitive discontinuities.

5.2 A major advantage of in-line eddy current examination of ferromagnetic CW pipe above the Curie temperature lies in the enhanced signal-to-noise ratio and depth of penetration obtained without the use of magnetic saturation.

5.3 The eddy current method is capable of detecting and locating weld imperfections commonly referred to as open

³ Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

⁴ Available from Aerospace Industries Association of America, Inc. (AIA), 1000 Wilson Blvd., Suite 1700, Arlington, VA 22209-3928, <http://www.aia-aerospace.org>.

*A Summary of Changes section appears at the end of this standard

welds, cave welds, black spots (weld inclusions), and partial welds (incomplete penetration). In addition, it will detect pipe-wall imperfections such as slivers, laps, and ring welds (end welds).

5.4 The relative severity of the imperfections may be indicated by eddy current signal amplitude or phase, or both. An alarm level may be selected that utilizes signal amplitude or phase, or both, for automatic recording or marking, or both.

5.5 Because the responses from natural discontinuities may vary significantly from those from artificial discontinuities, care must be exercised in establishing test sensitivity and acceptance criteria.

6. Basis of Application

6.1 The following criteria may be specified in the purchase specification, contractual agreement, or elsewhere, and may require agreement between the purchaser and the supplier.

6.1.1 The diameter, wall-thickness, and temperature of the pipe being examined.

6.1.2 The extent of the examination.

6.1.3 The time of examination: the point or points in the manufacturing process where the pipe will be examined, and its throughput speed.

6.1.4 *Standardization:*

6.1.4.1 The size (length, diameter, and wall) and composition of the reference standard if applicable.

6.1.4.2 The time between standardization checks.

6.1.5 The disposition of material with indications.

6.1.6 The reporting of examination results.

6.1.7 If specified in the contractual agreement, personnel performing examinations to this practice shall be qualified in accordance with a nationally recognized NDT personnel qualification practice or standard such as ANSI/ASNT-CP-189, SNT-TC-1A, MIL-STD-410E, NAS-410, ASNT-ACCP, or a similar document and certified by the certifying agency, as applicable. The practice or standard used and its applicable revision shall be identified in the contractual agreement between the using parties.

NOTE 1—MIL-STD-410 is canceled and has been replaced with NAS-410, however, it may be used with agreement between contracting parties.

6.1.8 If specified in the contractual agreement, NDT agencies shall be qualified and evaluated in accordance with Practice E543. The applicable edition of Practice E543 shall be specified in the contractual agreement.

7. Interferences

7.1 There are some manufacturing processes that produce pipe with surface conditions that could interfere with or obscure signals related to typical pipe imperfections.

7.2 Mechanical vibrations, speed variations, and temperature changes can have an affect on test sensitivities.

8. Apparatus

8.1 The coil assembly, whether encircling or probe coils, consists of one or more electrical coils, cooling apparatus that is adequate to maintain the proper coil-operating temperature

and prevent thermal damage, and positioning mechanisms for adjusting and maintaining a constant spacing between the coil and the pipe surface. Some assemblies may include mechanical guides to prevent physical damage to the coils by contact with the product.

8.1.1 The types and sizes of coils employed are determined to a large degree by the coverage and resolution required. Through precise coil positioning, the geometries required for effective pipe inspection can be maintained.

8.1.2 The eddy current coils are cooled to maintain proper operating temperatures for test stability, and to avoid thermal damage to the windings or the associated fixturing, or both.

8.1.3 The optimum response to the variables of interest (see 5.3) can be obtained through the selection of the proper instrumentation, coil design, and operating frequency. Through signal processing, responses to variables of interest can be increased while those from such sources as scale patches, cold spots, and mechanical vibration can be suppressed.

8.1.4 Usually, the coil assembly is placed at a location where product speed is constant and vibration is minimal.

8.2 The eddy current instrumentation should be capable of energizing coils with alternating currents of selected and stable frequencies and energy levels, and of sensing the changes in eddy current flow arising from pipe imperfections.

8.2.1 Eddy current responses may be displayed on a cathode-ray tube, indicated by a meter, digital display, strip-chart recorder, or other applicable methods.

8.2.2 Automatic alarm and marking features may be included and can provide automatic classification at production-line speeds.

9. Adjustment and Standardization of Apparatus

9.1 The method of manufacture of CW pipe precludes the use of a physical reference standard for in-line system standardization as is the norm for most eddy current examinations. The continuity of product runs and the high-line speeds (up to 3000 ft/min or 15.2 m/s) requires the use of alternative calibration methods.

9.2 The industry-accepted methods for system standardization and sensitivity adjustment include either electronically generated signals to simulate responses to reference notches, or the use of eddy current noise levels to obtain repeatable sensitivities.

9.2.1 Electronic signals that simulate those obtained from actual imperfections during the examination can be induced into the coil, or the instrumentation, or both, and adjusted to the appropriate response levels.

9.2.2 The eddy current noise level is that actually generated as the pipe passes through or by the transducer. Instrument controls may be adjusted so that the material-generated noise is some predetermined fraction of full-scale response. Through experience, sensitivities suitable for detecting imperfections of interest can be obtained. It must be clearly established that the noise level is material-generated and not from the instrumentation.

9.2.3 Verification of the sensitivity levels obtained through either the electronic-signal or the system-noise may be established through other nondestructive or mechanical examination methods, or both.

9.3 If standardization with conventional reference standards is applicable, off-line standardization may be performed using pipe samples of appropriate sizes made from austenitic stainless steel.

9.3.1 Refer to Practice E309, paragraph 7.6 and Section 10, for reference standard fabrication and Section 9 for standardization procedures.

10. Operating Procedure

10.1 Standardize the system in a manner similar to that given in Section 9 at the beginning of each turn and when changing sizes.

10.2 Pipes and tubes to be examined are passed through the examination station with the apparatus adjusted in accordance with Section 9.

10.3 Any piece showing a discontinuity indication equal to or greater than an established rejection level shall be automatically marked or otherwise identified as having a potentially rejectable discontinuity.

10.4 Make no equipment adjustments other than at standardization time.

11. Keywords

11.1 Curie temperature; eddy current; electromagnetic; NDT; nondestructive testing

SUMMARY OF CHANGES

Committee E07 has identified the location of selected changes to this standard since the last issue (E1033-09) that may impact the use of this standard. (Approved December 1, 2013.)

(1) Replaced “examination” with “test” to be consistent with the preferred use of these terms.

(2) Minor editorial changes throughout document to improve readability.

(3) Replaced the term “transducer” with “coil” throughout the document.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).