



Standard Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases¹

This standard is issued under the fixed designation E 1309; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide establishes essential and desirable data elements for fiber-reinforced composite materials for two purposes: to establish the material identification component of data-reporting requirements for test reporting and to provide information for the design of material property databases.

1.1.1 This guide is the first part of a two-part modular approach. The first part serves to identify the material and the second part serves to describe testing procedures and variables and to record results.

1.1.2 For mechanical testing, the related document is Guide E 1434. The interaction of this guide with Guide E 1434 is emphasized by the common numbering of data elements. Data Elements A1 through G13 are included in this guide, and numbering of data elements in Guide E 1434 begins with H1 for the next data element block. This guide is most commonly used in combination with a guide for reporting the test procedures and results such as Guide E 1434.

1.2 These guidelines are specific to fiber-reinforced polymer-matrix composite materials. Composite materials, which also contain particulates or precipitated particles, are also included provided they can be described adequately as a filler in the matrix.

1.3 The data elements described in this guide are suggested for use in recording data in a computerized database, which is different from contractual reporting of test results. The latter type of information is described in the material specification or shown in business transactions and is subject to agreement between the vendor and the user.

1.4 This guide defines the information that is considered essential to uniquely describe a composite material. Additional data elements that are considered desirable, but not essential, are also defined. The purpose is to facilitate efficient storage and retrieval of information with a computer and to allow the meaningful comparison of data from different sources.

1.5 This guide with Guide E 1434 may be referenced by the data reporting section of a test method to provide common data

reporting requirements for mechanical tests of high-modulus fiber-reinforced polymer-matrix composite materials. This guide may also be useful for additional tests, for material identification for databases at the property levels or for other uses of material identification of composite materials.

1.6 From this information and a guide such as Guide E 1434, the database designer should be able to construct the data dictionary preparatory to developing a database schema.

1.7 Data elements in this guide are relevant to test data, data as obtained in the test laboratory and historically recorded in laboratory notebooks. Property data, data that have been analyzed and reviewed, require a different level of data elements. Data elements for property data are provided in Annex A1.

2. Referenced Documents

2.1 ASTM Standards:²

- C 274 Terminology of Structural Sandwich Constructions
- D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D 1600 Terminology for Abbreviated Terms to Plastics
- D 3410/D 3410M Test Method for Compressive Properties of Polymer Matrix Composite Materials with Unsupported Gage Section by Shear Loading
- D 3878 Terminology for Composite Materials
- D 5467 Test Method for Compressive Properties of Unidirectional Polymer Matrix Composites Using a Sandwich Beam
- D 6507 Practice for the Fiber Reinforcement Orientation Codes for Composite Materials
- E 6 Terminology Relating to Methods of Mechanical Testing
- E 1013 Terminology Relating to Computerized Systems
- E 1308 Guide for Identification of Polymers (Excluding Thermoset Elastomers) in Computerized Material Property Databases³
- E 1338 Guide for Identification of Metals and Alloys in

¹ This guide is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.01 on Editorial and Resource Standards.

Current edition approved Oct. 1, 2005. Published October 2005. Originally approved in 1992. Last previous edition approved in 2000 as E 1309 – 00.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

Computerized Material Property Databases
IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI): The Modern Metric System

E 1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases

E 1443 Terminology Relating to Building and Accessing Materials and Chemical Databases³

E 1471 Guide for the Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases

E 1484 Guide for Formatting and Use of Material and Chemical Property Data and Database Quality Indicators³

2.2 Other Documents:

ANSI X3.172-1996 Information Technology—American National Standard Dictionary of Information Technology (ANSDIT)⁴

A Glossary of Terms Relating to Data, Data Capture, Data Manipulation, and Databases, CODATA Bulletin, Vol 23, Nos 1-2, CODATA, Paris, January-June 1991⁵

ISO 8601 Data Elements and Interchange Formats—Information Interchange—Representation of Dates and Times⁶

3. Terminology

3.1 *Definitions*—Terminology in accordance with Terminologies **D 3878**, **C 274**, and **E 1443** shall be used where applicable.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *category set*—a closed listing of all possible strings which could be included in a particular field of a record.

(E 1443)

3.2.2 *composite material*—a substance consisting of two or more materials, insoluble in one another, which are combined to form a useful engineering material possessing certain properties not possessed by the constituents.

3.2.2.1 *Discussion*—A composite material is inherently inhomogeneous on a microscopic scale but can often be assumed to be homogeneous on a macroscopic scale for certain engineering applications. The constituents of a composite retain their identities; they do not dissolve or otherwise merge completely into each other, although they act in concert.

(D 3878)

3.2.3 *data dictionary*—a collection of the names of all data items used in a software system together with relevant properties of those items; for example, length of data item, mode of representation, and so forth. (CODATA)

3.2.4 *data element*—one individual piece of information used in describing a material or to record test results. For example, a variable name, test parameter, and so forth.

⁴ *MIL-HDBK-17-2D, Polymer Matrix Composites*, Vol 2, Section 1.6, Feb. 23, 1994, available from Standardization Documents Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094. Attn: NPODS Additional information on handbook availability at <http://mil-17.udel.edu/>.

⁵ *DOD/NASA Advanced Composites Design Guide*, Air Force Wright Aeronautical Laboratories, Dayton, OH, prepared by Rockwell International Corp., 1983 (distribution limited).

⁶ *MIL-HDBK-17*, Vol. 2, Section 1.6.1, available from Standardization Documents Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, and Terminology D 1600

3.2.5 *database schema*—in a conceptual schema language, the definition of the representation forms and structure of a database for the possible collection of all sentences that are in the conceptual schema and in the information base, including manipulation aspects of these forms. **(ANSI X3.172)**

3.2.6 *essential data element*—a data element in a record which must be completed in order to make the record meaningful in accordance with the pertinent guidelines or standard.

(E 1443)

3.2.6.1 *Discussion*—Data elements are considered essential if they are required to make a comparison of property data from different sources meaningful. A comparison of data from different sources may still be possible if essential information is omitted, but the value of the comparison may be greatly reduced.

3.2.7 *gel point, n (or gel time)*—a point in a cure cycle where a thermosetting polymer resin resolidifies after melting.

3.2.8 *lay-up, n*—a process or fabrication involving the placement of successive layers of materials.

3.2.9 *lay-up code, n*—a designation system for abbreviating the stacking sequence of laminated composites. **(D 3878)**

3.2.10 *matrix, n*—in composite materials, the continuous constituent of a composite material which acts as the load transfer mechanism between the discrete dispersed reinforcement constituent.

3.2.10.1 *Discussion*—A composite matrix is a bonding structure which unites, fills, and encloses the composite's reinforcement structures.

3.2.11 *ply count, n*—in laminated composite materials, the number of plies or laminae used to construct the composite.

3.2.12 *prepreg, n*—the admixture of fibrous reinforcement and polymeric matrix used to fabricate composite materials. Its form may be sheet, tape, or tow. For thermosetting matrices, it has been partially cured to a controlled viscosity call "B stage."

(D 3878)

3.2.13 *sandwich construction, n*—a structural panel concept consisting in its simplest form of two relatively thin sheets of structural material bonded to and separated by a relatively thick lightweight core.

3.2.14 *stacking sequence, n*—the arrangement of ply orientations and material components in a laminate specified with respect to some reference direction. **(D 3878)**

3.2.15 *value set*—an open listing of representative acceptable strings which could be included in a particular field of a record. **(E 1443)**

3.2.15.1 *Discussion*—A closed listing of such string is called a domain or category set.

3.2.16 *void content, n*—the percentage of voids in a composite.

3.2.17 *volatiles content, n*—the percentage of volatiles which are driven off as vapor from a plastic or an impregnated reinforcement.

3.3 Other relevant terminology can be found in Terminologies **E 6** and **E 1013**.

4. Significance and Use

4.1 This guide provides the recommended data elements for the identification of fiber-reinforced composite materials. The ASTM standards for which this guide was developed are listed

in 2.1. The recommended data elements can be used with experimental data records and analyzed property records.

4.2 The intent of this guide is to provide sufficient detail that values are known for the material parameters that may influence test results or material property values. The motivation for this guide is the steadily increasing use of computerized databases. However, these guidelines are equally appropriate for data stored in a hard-copy form.

4.3 This guide is for material identification and description only. It does not include the recommended data elements for mechanical test data or other specific types of test data. These items are covered by separate formats to be referenced in material specifications or other test standards.

4.4 Composite materials are defined as two or more materials that are combined on a macroscale. There is a gray area between composites and other material classes. Two examples of this gray area between polymer matrix composites and plastics are toughened polystyrene and liquid crystal polymer. The present guide may be used to help the database designer determine how to handle materials that fall into this gray area. The selection of which guide to use, this guide or Guide E 1308 for plastics, should depend on whether the additional data elements in this guide are required by the data user, as follows. If information on orientation and form of reinforcement is needed by the intended data/database user, the composite materials guide may be more useful since it contains data elements for this information. Appendix X1 contains a table, which provides guidelines for distinguishing between reinforced polymers and polymer matrix composites.

4.5 Composite materials consist of a matrix phase and one or more discrete reinforcements. Reinforcements may be interpreted broadly to include any macroscale second material, including fibers, particulates, precipitated particles, or structured domains of the parent material. The reinforcements covered in this guide include fibers and such particulates and precipitated particles that can be described adequately as filler within the matrix. The reinforcements may be polymers, metals, ceramics, or other materials. Sandwich constructions are not covered by this guide; data recording for test methods which use a sandwich specimen should refer to Guide E 1471 for identification of the core material. These guidelines are suitable for the identification of composites in simple shapes of constant thickness; for example, plates or tubes. For complex structures, additional information relevant to a specific application may be required.

4.6 Classification of composite materials is complicated by the fact that composites are formed by combining different materials in varying amounts and configurations; this results in an infinite number of possibilities. An effective identification scheme must be capable of possible combinations without overburdening the system with details relevant only to a limited number of material systems. This guide provides both essential data elements and data elements that are considered

desirable but not essential. Data elements are considered essential if they are required to make a meaningful comparison of property data from different sources.

4.7 Identification of constituent materials of the composites is included to the level considered necessary for identification of the composite. Additional information may be necessary when the constituent is considered independently. Guides for polymers (E 1308), metals (E 1338), and reinforcements (E 1471) should be consulted in this case.

4.8 Comparison of property data from different databases will be most meaningful if all the essential information defined by the guide is present. Comparison may still be possible if essential information is omitted, but the usefulness of the comparison may be greatly reduced.

4.9 This information should not be considered restrictive. For example, a database designer may find it useful to aggregate several data elements, such as all data elements in a test method data element set or the material and chemical classes, into a single field. This may affect search strategies and other database operations. These considerations are beyond the scope of this guide.

5. Data Reporting

5.1 This guide is intended to provide common data reporting requirements for material identification when used for reporting testing and material properties based on accumulated results from a number of tests. The data reporting section of standard test methods may reference this guide for material identification in conjunction with Guide E 1434 for recording of the test procedure, parameters, and results. In addition, such a data reporting section may identify any usage specific to that document. One example of usage specific to a test method is Test Method D 5467, which may require additional information to identify the core material for the sandwich specimen from Guide E 1471. These requirements do not mean that the information must be reported separately for each specimen or that all information must be reported separately for each batch. Any data elements that are the same for a series of specimens or for a series of batches may be reported once for the entire series, as long as it is clearly indicated that they apply to all specimens or all batches.

5.2 Five levels of requirement are defined in Section 8 and identified in Table 1. The cost of acquiring and storing the data documentation is recognized. Less extensive data reporting requirements may be established for a given program or purpose upon agreement of the parties involved.

5.3 In addition, for identifying materials, some data elements are essential only if relevant. For example, Data Element D3, fabric style is required for material traceability, but is currently used only for certain types of fiber (primarily glass). Fabric styles have not been standardized for carbon fibers.

TABLE 1 Data Elements for Identification of Composite Materials

NOTE 1—Standard Data Element Sets (third column)—enclosed in square brackets.

NOTE 2—Requirement Levels (fifth column):

ET - Essential for Test validity

RT - Recommended for Test validity

EM - Essential for Material traceability

RM - Recommended for Material traceability

O - Optional

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|---------------------------------------------------|--------------------------------------------|----------------------------------------|-----------------------------------|-------|
| A. Composite Material Identification Block | | | | |
| A1 | Material identifier | STRING | | ET |
| A2 | Data source identification | STRING | | ET |
| A3 | Composite material name | STRING | Calculated | O |
| A4 | Material class | STRING | "Composite" | O |
| A5 | Material subclass | STRING | Calculated | O |
| A6 | Material form | STRING | | EM |
| A7 | Matrix class | STRING | "Polymer" | EM |
| A8 | Reinforcement class | STRING | Table 2 | EM |
| A9 | Reinforcement subclass | STRING | Table 3 | EM |
| A10 | Material specification | [Specification] | | RM |
| A11 | Material source (if not from manufacturer) | [Organization] | | RM |
| A12 | Material maximum temperature, nominal | REAL | C(F) | O |
| A13 | Material minimum temperature, nominal | REAL | C(F) | O |
| A14 | Material MSDS and assigning organization | STRING | | O |
| A15 | Contract number | STRING | | O |
| A16 | Data restrictions | STRING | | O |
| B. Fiber Information Block | | | | |
| B1 | Fiber class | STRING | Table 4 | RM |
| B2 | Fiber chemical class | STRING | Table 5 | ET |
| B3 | Fiber chemical family | STRING | Table 6 | RM |
| B4 | Fiber modulus subfamily | STRING | Table 7 | O |
| B5 | Fiber commercial name | STRING | | EM |
| B6 | Fiber additional name information | STRING | | RM |
| B7 | Fiber manufacturer's specification | [Specification] | | RM |
| B8 | Fiber user's specification | [Specification] | | O |
| B9 | Fiber manufacturer's internal designation | STRING | | O |
| B10 | Fiber manufacturer | [Organization] | | RM |
| B11 | Fiber lot | STRING | | EM |
| B12 | Fiber date of manufacture | DATE | | RM |
| B13 | Fiber batch certification number | STRING | | O |
| B14 | Fiber density | REAL | g/cm ³ | EM |
| B15 | Fiber density test method | [Test method] | | EM |
| B16 | Tow or yarn filament count | INTEGER | | EM |
| B17 | Tow or yarn filament count test method | [Test method] | | RM |
| B18 | Tow/strand linear density | REAL | tex | O |
| B19 | Tow/strand linear density test method | [Test method] | | O |
| B20 | Tow yield | REAL | m/g | O |
| B21 | Fiber filament diameter | REAL | mm | EM |
| B22 | Fiber filament diameter test method | [Test method] | | RM |
| B23 | Filament cross-section type | STRING | Table 8 | RM |
| B24 | Surface treatment type | STRING | Table 9 | RM |
| B25 | Surface treatment detail | STRING | | RM |
| B26 | Tow or yarn sizing identification | STRING | | RM |
| B27 | Tow or yarn sizing amount | REAL | | RM |
| B28 | Tow or yarn twist amount | REAL | t/m | RM |
| B29 | Tow or yarn twist direction | STRING | Table 10 | RM |
| C. Matrix Information Block | | | | |
| C1 | Matrix subclass | STRING | Table 11 | EM |
| C2 | Matrix chemical family | STRING | Table 12 | ET |
| C3 | Matrix subfamily | STRING | Table 13 | O |
| C4 | Matrix commercial name | STRING | | EM |
| C5 | Matrix manufacturer | [Organization] | | EM |
| C6 | Matrix lot number | STRING | | RM |
| C7 | Matrix date of manufacture | DATE | | RM |
| C8 | Matrix filler type | STRING | | RM |
| C9 | Matrix filler amount | REAL | | RM |
| C10 | Matrix nominal density | REAL | g/cm ³ | RM |
| C11 | Matrix nominal density test method | [Test method] | | RM |
| C12 | Matrix internal designation | STRING | | O |
| C13 | Matrix manufacturer specification | [Specification] | | O |

TABLE 1 *Continued*

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|---------------------------------|-----------------------------------------------------------|----------------------------------------|-----------------------------------|-------|
| C14 | Gel time | [Auxiliary test] | | O |
| D. Preform Information Block | | | | |
| D1 | Preform architecture | STRING | Table 14 | EM |
| D2 | Preform identifier | STRING | | EM |
| D3 | Preform manufacturer | [Organization] | | EM |
| D4 | Preform method of manufacture | STRING | Table 15 | |
| D5 | Number of preform layers | INTEGER | | EM |
| 2-D Fabric Information Subblock | | | | |
| D6 | Fabric manufacturer | [Organization] | | EM |
| D7 | Fabric weave type | STRING | Table 16 | EM |
| D8 | Fabric style number | STRING | | EM |
| D9 | Fabric lot | STRING | | EM |
| D10 | Fabric date of manufacture | DATE | | RM |
| D11 | Fabric batch certification number | STRING | | O |
| D12 | Fabric manufacturer specification | [Specification] | | O |
| D13 | Fabric user specification | [Specification] | | O |
| D14 | Fabric sizing identification | STRING | | EM |
| D15 | Fabric sizing content | REAL | | EM |
| D16 | Fabric end count (warp) | REAL | /m | EM |
| D17 | Fabric fill fiber (if different) | STRING | | EM |
| D18 | Fabric pick count (fill) | REAL | /m | EM |
| D19 | Fabric nominal fiber areal weight | REAL | g/mm ² | O |
| D20 | Tracer warp name | STRING | | O |
| D21 | Tracer warp linear density | REAL | g/m | O |
| D22 | Tracer warp spacing | REAL | /mm | O |
| D23 | Tracer warp sizing | REAL | | O |
| D24 | Tracer fill name | STRING | | O |
| D25 | Tracer fill linear density | REAL | g/m | O |
| D26 | Tracer fill spacing | REAL | /mm | O |
| D27 | Tracer fill sizing | REAL | | O |
| 3-D Woven Materials Subblock | | | | |
| D28 | Interlock description | STRING | | EM |
| D29 | Warp fiber filament count | INTEGER | | EM |
| D30 | Weft fiber filament count | INTEGER | | EM |
| D31 | Angle fiber filament count | INTEGER | | EM |
| D32 | Weaver yarn filament count | INTEGER | | EM |
| D33 | Percentage of warp yarn | REAL | % | EM |
| D34 | Percentage of weft yarn | REAL | % | EM |
| D35 | Angle of angle yarn (positive with respect to axial yarn) | REAL | degrees | EM |
| D36 | Percentage of angle yarn | REAL | % | EM |
| D37 | Percentage of weaver yarn | REAL | % | EM |
| D38 | Percentage of through-thickness yarn | REAL | % | EM |
| D39 | Pitch length | REAL | in. | EM |
| D40 | Warp end count | REAL | tow/in. | EM |
| D41 | Weft end count | REAL | tow/in. | EM |
| D42 | Unit cell width | REAL | in. | O |
| D43 | Unit cell length | REAL | in. | O |
| D44 | Unit cell depth | REAL | in. | O |
| Stitching Information Subblock | | | | |
| D45 | Stitch type | STRING | | EM |
| D46 | Stitch thread | STRING | | EM |
| D47 | Stitch axial pitch | REAL | degrees | EM |
| D48 | Stitch row spacing | REAL | in. | EM |
| D49 | Stitch denier | REAL | denier | RM |
| D50 | Stitch filament count | INTEGER | | EM |
| D51 | Bias yarn end count | INTEGER | | EM |
| D52 | Bias yarn angle | REAL | degrees | EM |
| Braiding Information Subblock | | | | |
| D53 | Braid description | STRING | | EM |
| D54 | Axial fiber type | STRING | | EM |
| D55 | Braid fiber type | STRING | | EM |
| D56 | Axial fiber filament count | INTEGER | | EM |
| D57 | Braid fiber filament count | INTEGER | | EM |
| D58 | Braid angle | REAL | degrees | EM |
| D59 | Percentage of axial yarn | REAL | % | EM |
| D60 | Percentage of braid yarn | REAL | % | EM |
| D61 | Axial yarn spacing in braids | REAL | in. | RM |
| D62 | Unit cell width | REAL | in. | O |

TABLE 1 *Continued*

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|-----------------------------------------------------------------|--------------------------------------|----------------------------------------|-----------------------------------|-------|
| D63 | Unit cell length | REAL | in. | O |
| D64 | Braider identification | STRING | | RM |
| D65 | Number of carriers | INTEGER | | RM |
| Winding Information Block | | | | |
| D66 | Winding description | STRING | | EM |
| D67 | Winder identification | STRING | | RM |
| D68 | Mandrel identification | STRING | | EM |
| E. Prepreg Information Block Prepreg Identification Subblock | | | | |
| E1 | Prepreg type | STRING | Table 17 | EM |
| E2 | Prepreg commercial name | STRING | | EM |
| E3 | Prepreg manufacturer | [Organization] | | EM |
| E4 | Prepreg manufacturer's internal spec | [Specification] | | O |
| E5 | Prepreg source | [Organization] | | O |
| E6 | Prepreg dimension parameter | STRING | Table 18 | RM |
| E7 | Prepreg dimension value | REAL | | RM |
| E8 | Prepreg reinforcement orientation(s) | STRING | | RM |
| E9 | Scrim fiber chemical class | STRING | Table 5 | RM |
| E10 | Scrim fabric style | STRING | | RM |
| E11 | Prepreg additional information | STRING | | RM |
| Prepreg Batch Information Subblock | | | | |
| E12 | Prepreg batch number | STRING | | EM |
| E13 | Prepreg batch certification date | STRING | | O |
| E14 | Prepreg batch expiration date | DATE | | RM |
| E15 | Prepreg batch roll number | STRING | | RM |
| Prepreg Auxiliary Test Subblock | | | | |
| E16 | Prepreg fiber areal weight | [Auxiliary test] | g/m ² | EM |
| E17 | Prepreg volatile content, wt% | [Auxiliary test] | wt% | EM |
| E18 | Prepreg fiber content, vol% | [Auxiliary test] | vol% | RM |
| E19 | Prepreg matrix content, wt% | [Auxiliary test] | Wt% | RM |
| E20 | Prepreg matrix flow | [Auxiliary test] | Wt% | RM |
| E21 | Prepreg matrix gel time | [Auxiliary test] | | RM |
| E22 | Prepreg tack | [Auxiliary test] | | O |
| E23 | Prepreg drape | [Auxiliary test] | | O |
| F. Process Information Block Process Specification Subblock | | | | |
| F1 | Process specification | [Specification] | | RM |
| F2 | Process reinforcement application | STRING | Table 19 | EM |
| F3 | Process mold type | STRING | Table 20 | EM |
| F4 | Tackifier common name | STRING | | RM |
| F5 | Tackifier chemical class | STRING | Table 12 | RM |
| F6 | Tackifier form | STRING | Table 21 | RM |
| F7 | Tackifier manufacturer | STRING | | RM |
| Process Description Subblock | | | | |
| F8 | Process stage type | STRING | Table 22 | RM |
| F9 | Process stage temperature | REAL | C(F) | RM |
| F10 | Process stage pressure | REAL | psig | RM |
| F11 | Process stage vacuum | REAL | psig | RM |
| F12 | Process stage duration | REAL | min | RM |
| F13 | Process ramp rate | REAL | C/min (F/min) | RM |
| F14 | Process stage other parameter | STRING | degrees | RM |
| F15 | Processor | [Organization] | | EM |
| F16 | Process start date | DATE | | RM |
| F17 | Process end date | DATE | | RM |
| F18 | Process records reference | STRING | | RM |
| G. Part Information Block Part Description Subblock | | | | |
| G1 | Part form | STRING | Table 23 | EM |
| G2 | Material orientation code | STRING | | EM |
| G3 | Part specification | [Specification] | | RM |
| G4 | Part dimension parameter | STRING | | RM |
| G5 | Part dimension value | REAL | | RM |
| G6 | Part history | STRING | | EM |
| G7 | Part additional information | STRING | | RM |
| Part Auxiliary Test Subblock | | | | |
| G8 | Part resin content by weight | [Auxiliary test] | wt% | |
| G9 | Part fiber content, by volume | [Auxiliary test] | vol% | EM |

TABLE 1 *Continued*

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|-----|---------------------------------------|----------------------------------------|-----------------------------------|-------|
| G10 | Part fiber areal weight | [Auxiliary test] | g/m ² | |
| G11 | Part void content, by volume | [Auxiliary test] | vol% | EM |
| G12 | Part mass density | [Auxiliary test] | g/cm ³ | EM |
| G13 | Part glass transition temperature—dry | [Auxiliary test] | C(F) | EM |
| G14 | Part glass transition temperature—wet | [Auxiliary test] | C(F) | EM |
| G15 | Footnotes | STRING | | EM |

TABLE 2 Value Set for Reinforcement Class

| Fiber | Filler | Core |
|-------|--------|------|
| | | |

TABLE 3 Value Set for Reinforcement Subclass

| Fiber | Filler | Core |
|----------------------|-----------------|-----------------|
| Continuous | particulate | honeycomb |
| Discontinuous, long | platelet | close-cell foam |
| Discontinuous, short | hollow sphere | open-cell foam |
| Staple | hollow cylinder | |
| Milled | | |
| Whisker | | |
| Pulp | | |

TABLE 4 Category Set for Fiber Class

| |
|---------|
| Polymer |
| Metal |
| Carbon |
| Ceramic |

TABLE 5 Value Set for Fiber Chemical Class

| | |
|-----------------------------------------|--------|
| Alumina | AlO |
| Aluminum | Al |
| Aramid | Ar |
| Boron | B |
| Carbon | C |
| Glass | Gl |
| Graphite | Gr |
| Liquid crystal polymer | LCP |
| Lithium | Li |
| Metallic oxide | MO |
| Polybenzothiazole | PBT |
| Quartz/silica | Q |
| Silicon | Si |
| Silicon carbide | SiC |
| Titanium | Ti |
| Tungsten | W |
| Ultrahigh molecular weight polyethylene | UHMWPE |

TABLE 6 Value Set for Reinforcement Chemical Family

| Carbon | Glass | Quartz | Boron | Silicon Carbide |
|-----------------|----------------|---------|--------|-----------------|
| PAN precursor | E-glass | mineral | TBD | monofilament |
| Pitch precursor | S-glass | manmade | | multifilament |
| Rayon precursor | S2-glass | | | |
| | D-glass | | | |
| Aramid | Metallic Oxide | LCP | UHMWPE | Other |
| TBD | TBD | TBD | TBD | TBD |

TABLE 7 Value Set for Modulus Subfamily

| | |
|-------------|------------|
| <69 GPa | <10 Msi |
| 69-138 GPa | 10-20 Msi |
| 138-207 GPa | 20-30 Msi |
| 207-276 GPa | 30-40 Msi |
| 275-345 GPa | 40-50 Msi |
| 345-483 GPa | 50-70 Msi |
| 483-621 GPa | 70-90 Msi |
| 621-758 GPa | 90-110 Msi |
| >758 GPa | >110 Msi |

6. Database Design

6.1 This guide defines the principal elements of information, which are considered worth recording and storing perma-

nently in computerized data storage systems from which machine-readable databases will be developed. These are not

TABLE 8 Value Set for Fiber Cross-Section Type

| |
|------------------|
| Circular (round) |
| Annular |
| Rectangular |
| Square |
| Oval |
| Irregular |

TABLE 9 Value Set for Surface Treatment Type

| |
|----------------------|
| Chemical oxidation |
| Plasma etching |
| Adhesion promoting |
| Sizing |
| Anticorrosion |
| Finish free |
| Lubricant |
| Release treatment |
| No surface treatment |

TABLE 10 Category Set for Twist Direction

| | | | |
|---|---|----------|-------------|
| S | Z | N - none | U - unknown |
|---|---|----------|-------------|

TABLE 11 Category Set for Matrix Subclass

| | |
|-----------|---------------|
| Thermoset | Thermoplastic |
|-----------|---------------|

TABLE 12 Value Set for Matrix Chemical Family with Common Abbreviations^A

| | |
|--------------------------------------------|------|
| Bismaleimide | BMI |
| Epoxy | EP |
| Fluorocarbon | |
| Liquid crystal polymer | LCP |
| Phenolic (urea-formaldehyde) | PF |
| Polyamide-imide | PAI |
| Polyarylsulfone | PAS |
| Polybenzimidazole | |
| Polybutylene terephthalate | PBT |
| Polycyclohexylenedimethylene terephthalate | PCT |
| Polyester, thermoplastic (general) | TPES |
| Polyester, unsaturated | UP |
| Polyethylene terephthalate | PET |
| Polyetheretherketone | PEEK |
| Polyetherimide | PEI |
| Polyethersulfone | PES |
| Polyimide | PI |
| Polyimide, thermoplastic | TPPI |
| Polyphenylene sulfide | PPS |
| Polysulfone | PSU |
| Silicone | SI |

^A MIL-HDBK-17, Volume 2, Section 1.6.1, and Terminology D 1600

TABLE 13 Value Set for Matrix Subfamily (by Processing Temperature)

| Ambient Temperature, °C | Ambient Temperature, °F |
|-------------------------|-------------------------|
| <93 | <200 |
| 93-149 | 200-300 |
| 149-204 | 300-400 |
| 204-260 | 400-500 |
| 260-316 | 500-600 |
| 316-371 | 600-700 |
| 371-427 | 700-800 |
| >427 | >800 |

TABLE 14 Value Set for Preform Architecture

| |
|------------------|
| Filament winding |
| Braid |
| 2-D Fabric |
| 3-D Fabric |
| Stitched Fabric |

TABLE 15 Value Set for Preform Method of Manufacture

| |
|----------|
| Molded |
| Stitched |
| RFI |

TABLE 16 Value Set and Common Abbreviations for Fabric Weave Type

| | |
|------------------|------|
| Plain | PW |
| Crowfoot | CSW |
| 5-harness satin | 5HS |
| 8-harness satin | 8HS |
| 12-harness satin | 12HS |

TABLE 17 Value Set for Precursor Type

| |
|------------------------------|
| Prepreg |
| Prelam |
| Preimpregnated tow |
| BMC (bulk molding compound) |
| SMC (sheet molding compound) |
| XMC |

TABLE 18 Value Set for Dimension Parameters

| |
|------------------|
| Length |
| Outside diameter |
| Width |
| Thickness |
| Inside diameter |
| Fiber diameter |
| Wall thickness |

intended to be requirements of any specific database, but if available, are likely to be valuable to engineers or material specialists building databases for various applications.

6.2 It is recognized that many databases are prepared for specific applications, and individual database builders may elect to omit certain pieces of information considered to be of no value for that specific application. However, there are a certain minimum number of data elements considered essential to any database, without which the user will not have sufficient information to interpret the data reasonably. In the recommended standard format, these data elements are indicated by levels of requirement of ET or EM as defined in 8.2. Data

elements that are considered essential depending on the value of another data element are generally considered essential for database design.

6.3 The presentation of this format does not represent a requirement that all of the elements of information included in the recommendation must be included in every database. Rather, it is a guide as to those elements of information recommended for inclusion in all databases. This should not discourage database builders and users from proceeding as long as the minimum basic information is included (based on the level or requirement). Compared to the guide for identifying metals, there are many more data elements, and more data

TABLE 19 Value Set for Reinforcement Application

| | |
|-----------------------------------|---------------|
| Automated fiber placement—tape | preform—braid |
| Automated fiber placement—towpreg | preform—weave |
| Automated fiber placement—wet | spray |
| Automated lay-up—pregreg | wound—dry |
| Automated lay-up—wet | wound—wet |
| Hand lay-up—pregreg | wound—pregreg |
| Hand lay-up—wet | |

TABLE 20 Value Set for Process Mold Type

| | |
|----------------------------|------------------------------------------------|
| Autoclave | injection molding—vacuum assisted |
| Compression molding | oven |
| Diffusion bonding | pultrusion |
| Ebeam | resin transfer molding |
| Hydroclave | trapped rubber |
| Induction | vacuum infiltration |
| Injection molding | vapor deposition |
| Injection molding—liquid | VARTM (vacuum-assisted resin transfer molding) |
| Injection molding—reaction | |

TABLE 21 Value Set for Tackifier Form

| | |
|---------|--------|
| Aerosol | Liquid |
|---------|--------|

TABLE 22 Value Set for Process Stage Types

| | |
|---------------|-------------------|
| Age-harden | injection |
| Anneal | part insertion |
| Consolidate | part removal |
| Cool down | postcure |
| Cure—bleed | prebleed |
| Cure—no bleed | preform insertion |
| Debulk | preheat |
| Densify | isothermal dwell |

TABLE 23 Value Set for Part Forms

| |
|----------|
| Panel |
| Rod |
| Cylinder |
| Channel |
| Hoop |
| Shell |
| Ring |

elements are identified as essential. This relatively large number of data elements is due to the complexity of the materials. These data elements represent information that is needed to reproduce the material and may influence material property values. These requirements do not mean that each of these data elements must be included in each record for individual test specimens or material property values. A database specific to a project or to common practice within an organization may be structured so that values for data elements that are the same for the same material processing procedure, for a group of specimens, or for a group of material property values need only be entered once, as long as it is clearly indicated to which material they apply.

6.4 The order of the data elements or the block and subblock organization of these elements is not intended to establish a standard database schema. For a given database, it may be desirable to reorganize these data elements to suit the database application and the scope of data to be included in a database.

6.5 It is not uncommon for one or more elements of essential information to be unavailable, as noted in 5.3. It may be appropriate for databases to differentiate between zero values and null entries in data elements that are not used for a given test. Also it is recognized that in some individual cases, additional elements of information of value to users of a database may be available. In those cases, database builders are encouraged to include them as well as the elements in the recommended format.

6.6 The method of including information identifying the units for each data element is left to the database designer. Frequently used units, in both SI and inch-pound systems, are listed in the tables to clarify the format and examples. This should not be interpreted as requiring any particular implementation of data elements for units.

6.7 While data elements indicating the accuracy of each measurement are beyond the scope of this guide, it is recommended that entries in all data elements be given to the correct number of significant digits.

7. Data Element Sets

7.1 Sets of data elements that are used repetitively or are common to many documents have been identified. The following standard sets of data elements are used in this guide: Auxiliary Test, Date, Organization, Specification, and Test Method.

7.1.1 The format of the data elements sets is data_element_name : data type - definition.

7.1.2 The data type of an data element may be STRING, NUMBER (REAL or INTEGER), LOGICAL or DATE.

7.1.2.1 For database development, the closest available data type should be used. If a DATE type is not available, STRING should be used. The format for DATE is YYYY-MM-DD, where YYYY is a four-character string for the year, MM is a two-character string for the month as defined in ISO 8601 (5.2.1) for example, January is 01, February is 02, and so forth, and DD is a two-character string for the specified day of the month.

7.1.2.2 The hyphens in the date format shall be used for compatibility with ISO 8601. Dates are presented according to the Gregorian calendar.

7.2 Use of Standard Data Element Sets—The name of a standard data element set, indicated in this guide in brackets, represents all of the data elements in that set. The following example illustrates identical data elements, using a standard data element set. The descriptive name of the data element in the standard set is attached to the referring data element to help clarify the usage.

7.2.1 Example—Table 1, Data Element A12, Specification, indicates the standard data element set for Specification in square brackets in the third column. This is equivalent to listing the five data elements in the Specification standard data element set as individual data elements. Thus:

Data Element A12 Material specification [Specification]

is equivalent to:

Data Element A12a Material_specification_organization_name: string
- name of organization responsible for specification

Data Element A12b `Material_specification_id`: string - identification of specification
 Data Element A12c `Material_specification_date`: date - date of approval of most recent technical revision or initial release
 Data Element A12d `Material_specification_version`: string - identification of a specific version of a specification
 Data Element A12e `Material_specification_designation`: string - identification of a specific procedure or method when the Specification document contains more than one.

7.2.2 Note, as discussed in 4.9, that a database designer may combine these elements into a single field.

7.3 Auxiliary Test:

7.3.1 *Data Element Set Definition*—The auxiliary test is a record of information for a test method and results which are used as metadata or information used to define the material.

7.3.2 Data Elements:

`property` : string - objective of auxiliary test
`value` : real - result of auxiliary test
`units` : string - units for value
`test method` : [Test method] - test method used to generate value

7.3.3 *Example Usage*—The standard data element set Auxiliary test is used in Table 1 in the Part Auxiliary Test Subblock.

7.4 Organization:

7.4.1 *Data Element Set Definition*—An organization is an administrative structure.

7.4.2 Data Elements:

`id` : string - the means by which the organization's individuality may be deduced
`name` : string - the word, or group of words, by which an organization is referred to
`description` : string - text that relates the nature of an organization
`organization_role_name` : string - the word, or group of words, that indicate the function being performed

7.4.3 *Example Usage*—The standard data element set Organization is used in Table 1 in B11, Fiber manufacturer.

7.5 Specification:

7.5.1 *Data Element Set Definition*—A specification is a documented set of requirements for a material or process

7.5.2 Data Elements:

`organization_name` : string - name of organization responsible for specification, for example, AMS
`id` : string - identification of specification, for example, AMS3892
`date` : date - date of approval of most recent technical revision or initial release. For the example, October, 1997
`version` : string - identification of a specific version of a specification. For example, Revision A.
`designation` : string - identification of a specific procedure or set of requirements when the specification contains more than one. For this example /10.

7.5.3 *Example Usage*—The standard data element set Specification is used in Table 1 in A12 Material specification. The example used in 7.5.2 is AMS 3892/10, “Tow, Carbon Fiber For Structural Composites 550 (3792) Tensile Strength, 38 (262) Tensile Modulus,” Revision A, October 1997.

7.6 Test Method:

7.6.1 *Data Element Set Definition*—Identification of the documented test method used.

7.6.2 Data Elements:

`organization_name` : string - name of organization responsible for test method, for example, ASTM
`id` : string - identification of test method, for example, Test Method D 3410/D 3410M
`date` : date - date of approval of most recent technical revision or initial release

`version` : string - identification of a specific version of a test method. For example, ASTM uses lowercase letters to distinguish between revisions, to a document, in the same calendar year.
`designation` : string - identification of a specific procedure or method when the test method document contains more than one. For example, Test Method II, Procedure A in Test Methods D 790.

7.6.3 *Example Usage*—The standard data element set Test Method is used in Standard Data Element Set Auxiliary Test and in Table 1 in Data Element B15, Fiber Density Test Method.

8. Levels of Requirement

8.1 It is recognized that these data elements may be used by two different communities—testing laboratories, which do not necessarily have access to full material identification, and material suppliers and users, for whom material traceability is often important. To address the needs of both of these groups, data-reporting requirements in this guide have been separated into data elements for test validity and for material traceability.

8.2 The five levels of requirement are as follows:

- 8.2.1 ET—Essential for Test validation.
- 8.2.2 RT—Recommended for Test validity.
- 8.2.3 EM—Essential for Material traceability.
- 8.2.4 RM—Recommended for Material traceability.
- 8.2.5 O—Optional.

9. Recording of Material Identification

9.1 Table 1 lists the recommended data elements for the identification of fiber-reinforced composite materials. There are five columns of information:

9.1.1 *Data Element Number*—A reference number for ease of dealing with the individual data elements within this format guideline. It has no permanent value and does not become part of the database itself. Data element numbers are for reference only. They do not imply a necessity to include all these data elements in any specific database nor imply a requirement that data elements used be in this particular order.

9.1.2 *Data Element Descriptive Name*—The descriptive name of the data element, identifying of the element of information that would be included in this data element of the database.

9.1.3 *Data Type or Standard Data Element Set*—A data type is indicated for each individual data element. These are the same data types discussed in Section 8. Data types are presented in capital letters. Data element sets are indicated by the name of the standard data element set in brackets. This indicates that each element of the set is included, as demonstrated in 7.2.

9.1.4 *Category Set, Value Set, or Units*—A listing of the types of information which would be included in the data element or, in the case of properties or other numeric data elements, the units in which the numbers are expressed. Category sets list all possible values for a data element. Value sets are representative sets, listing sample (but not necessarily all acceptable) inputs to the data element. The units listed are SI, in accordance with IEEE/ASTM SI 10, followed by inch-pound units in parentheses. References to Tables 2-23 provide appropriate category sets or value sets as listed in Table 1. Also noted in this column are data elements where the recommended entry is calculated. Two examples of calculated

data elements are Composite Material Name (A3) and Material Subclass (A5). These elements are often useful for accessing and presenting data but are redundant with other data elements. As maintaining redundant data elements is not considered good database practice, the data elements are presented as calculated elements.

9.1.5 Level of Requirement—The fifth column indicates the level of requirement. The information for identifying materials is divided into nine blocks: Composite, Fiber, Matrix, Fabric, Preform, Winding, Prepreg, Process, and Part. Depending on the constituents of the material and how the fibers are manipulated or organized during fabrication, several of the blocks may be required to adequately identify a material while others are unnecessary. For example, a two-dimensional fabric that is laid up and cured into a laminate would require Material, Fiber, Matrix, Fabric, Prepreg, Processing, and Part blocks. A filament wound material that is resin transfer molded would require Material, Fiber, Matrix, Filament Winding, Processing, and Part blocks.

9.2 Dates—Several data elements require a date, for example, date of test. If process or procedure took more than one day, then the date of completion is reported.

9.3 Composite Material Identification Block—Data elements in this section should be considered as having the level of requirement shown for all materials. Data elements with particular concerns are discussed in the following sections.

9.3.1 Composite Material Name—This data element is calculated. Based on MIL-HDBK-17, one frequent calculation for this element is as follows:

$$[\text{Composite Material Name}] = [\text{Fiber Commercial Name}] + " " + [\text{Tow or Filament Count}] + " " + [\text{Matrix Commercial Name}] + " " + [\text{Fabric Weave Type}] + " " + [\text{Critical Processing Information}]$$

9.3.2 Material Class—The material class for all uses of this guide is “Composite.”

9.3.2.1 Material Subclass—This data element is calculated. Common usage is as follows:

$$[\text{Matrix Subclass}] = [\text{Fiber Class}] + ' ' + [\text{Matrix Class}]$$

9.3.3 Matrix Class—The matrix class for all uses of this guide is “Polymer.”

9.3.4 Reinforcement Class—The reinforcement class for most uses of this guide is “Fiber.” Guide E 1471 provides more information about reinforcement classes.

9.4 Fiber Identification Block—Data elements in this section should be considered as having the level of requirement shown for all materials. All essential data elements for fiber identification from Guide E 1471 have been included in this guide.

9.5 Matrix Identification Block—Data elements in this section should be considered as having the level of requirement shown for all materials.

9.6 Gel Time—Gel time is considered an auxiliary test, a property determined to help identify a particular material. In this case, gel time is measured on the matrix material prior to its incorporation into a composite material.

9.7 Preform Identification Block—For the purposes of this guide, preform encompasses all types of fiber assemblies that may or may not approach the final geometry of the part. These range from traditional two-dimensional fabrics to complex

three-dimensional woven materials. The block contains several header elements followed by subblocks - 2-D Fabric, 3-D Woven Materials, Stitching, Braiding Materials, and Winding. The appropriate subblock(s) is used based on the stages of assembly of fibers for the material product being identified. Note that there is some redundancy among the subblocks. The data elements are listed in the subblocks for which the data elements are appropriate to address the objective of data recording. It may be desirable in a database design to combine the subblocks and eliminate redundant data elements.

9.8 Prepreg Information Block—Elements in the block identify and describe the combination of matrix and fiber materials in a partially cured state. Prepreg batch identification and description is included as well as auxiliary tests that help identify the prepreg or that are performed on the prepreg to help identify the composite product. This block is used only for materials that are partially cured prior to final assembly. Based on the definition of prepreg (3.2.12), thermoset and thermoplastic materials may be covered.

9.9 Process Information Block—Data elements in this block are appropriate for all composite materials. Subblocks are included to identify specification information and to describe the process. Depending on the level of detail desired, the process description subblock may be repeated several times to identify one material.

9.10 Part Information Block—The final configuration of a material. Data elements in this block are appropriate for all composite materials.

9.10.1 Part History—Service history or similar information for the part (in contrast to a specimen in a controlled environment) is included in this data element.

9.10.2 Material Orientation Code—The lay-up code to describe stacking sequence in a laminar composite or a braiding orientation code for braided material forms. These material orientation codes are defined in Practice D 6507 based on the convention used in MIL-HDBK-17-2 and the DOD/NASA Advanced Composites Design Guide. Practice D 6507 includes the following modifications to the convention since many database programs do not accommodate subscripts and superscripts:

9.10.2.1 Information provided in a subscript is preceded by a colon (:) in the computerized notation. For example, [90/0:2/45]:s is the computerized notation for [90/0₂/45]_s.

9.10.2.2 The presence of a bar over a ply (designating a non-repeated ply in a symmetric laminate with an odd number of plies) is indicated by a backslash (\) after the ply in the computerized notation. For example, [90/45/0\]:s is the computerized notation for [90/45/ $\bar{0}$]_s.

9.10.2.3 The lay-up code should also indicate the location of core if the composite is a sandwich, for example, [(0/45/90)/core/(90/45/0)].

9.10.3 Footnotes—A brief statement of any significant information helpful in identifying the material. The method for including this information in a database should be determined by the database designer. Notes or comment fields may be appropriate for each block or subblock of data elements provided in Table 1 or for each database table in a database design.

10. Keywords

10.1 databases; data elements; fiber-reinforced polymer-matrix composite materials

ANNEX

(Mandatory Information)

A1. DATA ELEMENTS FOR PROPERTY-LEVEL COMPOSITE MATERIALS IDENTIFICATION

A1.1 This annex provides data elements for data that have been generally grouped, analyzed, and reviewed and are considered property-level data rather than test data. Data element numbers in this annex are coordinated with data element numbers in [Table 1](#). As [Table 1](#) is the first part of a

modular approach with [Guide E 1434](#), [Table 1](#), this annex is coordinated with [Guide E 1434](#), [Annex A1](#). All table numbers refer to [Guide E 1309](#).

TABLE A1.1 Data Elements for Property-Level Composite Materials Identification

NOTE 1—Requirement levels:

ET - Essential for Test validity

RT - Recommended for Test validity

EM - Essential for Material traceability

RM - Recommended for Material traceability

O - Optional

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|--------------------------------------------|------------------------------------|----------------------------------------|-----------------------------------|-------|
| A. Composite Material Identification Block | | | | |
| A1 | Material identifier | STRING | | ET |
| A2 | Data source identification | STRING | | ET |
| A3 | Composite material name | STRING | Calculated | O |
| A4 | Material class | STRING | “Composite” | O |
| A5 | Material subclass | STRING | Calculated | O |
| A6 | Material form | STRING | | EM |
| A7 | Matrix class | STRING | “Polymer” | EM |
| A8 | Reinforcement class | STRING | Table 2 | EM |
| A9 | Reinforcement subclass | STRING | Table 3 | EM |
| A10 | Material specification | [Specification] | | RM |
| A14 | Material MSDS and assigning org. | STRING | | O |
| A16 | Data restrictions | STRING | | O |
| B. Fiber Information Block | | | | |
| B1 | Fiber class | STRING | Table 4 | RM |
| B2 | Fiber chemical class | STRING | Table 5 | ET |
| B3 | Fiber chemical family | STRING | Table 6 | RM |
| B4 | Fiber moduli subfamily | STRING | Table 7 | O |
| B5 | Fiber commercial name | STRING | | EM |
| B6 | Fiber additional name information | STRING | | RM |
| B7 | Fiber manufacturer’s specification | [Specification] | | RM |
| B8 | Fiber user’s specification | [Specification] | | O |
| B10 | Fiber manufacturer | [Organization] | | RM |
| B12 | Fiber date of manufacture—minimum | DATE | | RM |
| B12 | Fiber date of manufacture—maximum | DATE | | RM |
| B14 | Fiber density—nominal | REAL | g/cm ³ | EM |
| B14 | Fiber density—minimum | REAL | g/cm ³ | EM |
| B14 | Fiber density—maximum | REAL | g/cm ³ | EM |
| B15 | Fiber density test method | [Test method] | | EM |
| B16 | Tow or yarn filament count | INTEGER | | EM |
| B24 | Surface treatment type | STRING | Table 9 | RM |
| B25 | Surface treatment detail | STRING | | RM |
| B26 | Tow or yarn sizing identification | STRING | | RM |
| B27 | Tow or yarn sizing amount | REAL | | RM |
| B28 | Tow or yarn twist amount | REAL | t/m | RM |
| C. Matrix Information Block | | | | |
| C1 | Matrix subclass | STRING | Table 11 | EM |
| C2 | Matrix chemical family | STRING | Table 12 | ET |
| C3 | Matrix subfamily | STRING | Table 13 | O |

TABLE A1.1 *Continued*

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|--------------------------------------------------------------|-----------------------------------------------|----------------------------------------|-----------------------------------|-------|
| C4 | Matrix commercial name | STRING | | EM |
| C5 | Matrix manufacturer | [Organization] | | EM |
| C7 | Matrix date of manufacture—minimum | DATE | | RM |
| C7 | Matrix date of manufacture—maximum | DATE | | RM |
| C10 | Matrix density—nominal | REAL | g/cm ³ | RM |
| C10 | Matrix density—minimum | REAL | g/cm ³ | RM |
| C10 | Matrix density—maximum | REAL | g/cm ³ | RM |
| C11 | Matrix density test method | [Test method] | | RM |
| C13 | Matrix manufacturer specification | [Specification] | | O |
| D. Preform Information Block | | | | |
| D1 | Preform architecture | STRING | Table 14 | EM |
| D2 | Preform identifier | STRING | | EM |
| D3 | Preform manufacturer | [Organization] | | EM |
| D4 | Preform method of manufacture | STRING | Table 15 | EM |
| D5 | Number of preform layers | INTEGER | | EM |
| 2-D Fabric Information Block | | | | |
| D6 | Fabric manufacturer | [Organization] | | EM |
| D7 | Fabric weave type | STRING | Table 16 | EM |
| D8 | Fabric style number | STRING | | EM |
| D10 | Fabric date of manufacture—minimum | DATE | | O |
| D10 | Fabric date of manufacture—maximum | DATE | | O |
| D12 | Fabric manufacturer specification | [Specification] | | O |
| D13 | Fabric user specification | [Specification] | | O |
| D14 | Fabric sizing identification | STRING | | EM |
| D15 | Fabric sizing content | REAL | | EM |
| D16 | Fabric end count (warp) | REAL | /m | EM |
| D17 | Fabric fill fiber (if different) | STRING | | EM |
| D18 | Fabric pick count (fill) | REAL | /m | EM |
| D19 | Fabric nominal fiber areal weight | REAL | g/mm ² | O |
| 3-D Woven Materials Subblock | | | | |
| D28 | Interlock description | STRING | | EM |
| D29 | Warp fiber filament count | INTEGER | | EM |
| D30 | Weft fiber filament count | INTEGER | | EM |
| D31 | Angle fiber filament count | INTEGER | | EM |
| D32 | Weaver yarn filament count | INTEGER | | EM |
| D33 | Percentage of warp yarn | REAL | % | EM |
| D34 | Percentage of weft yarn | REAL | % | EM |
| D35 | Angle of angle yarn (positive wrt axial yarn) | REAL | degrees | EM |
| D36 | Percentage of angle yarn | REAL | % | EM |
| D37 | Percentage of weaver yarn | REAL | % | EM |
| D38 | Percentage of through-thickness yarn | REAL | % | EM |
| D39 | Pitch length | REAL | in. | EM |
| D40 | Warp end count | REAL | tow/in. | EM |
| D41 | Weft end count | REAL | tow/in. | EM |
| Stitching Information Subblock | | | | |
| D45 | Stitch type | STRING | | EM |
| D46 | Stitch thread | STRING | | EM |
| D47 | Stitch axial pitch | REAL | degrees | EM |
| D48 | Stitch row spacing | REAL | in. | EM |
| D49 | Stitch denier | REAL | denier | RM |
| D50 | Stitch filament count | INTEGER | | EM |
| D51 | Bias yarn end count | INTEGER | | EM |
| D52 | Bias yarn angle | REAL | degrees | EM |
| Braiding Information Subblock | | | | |
| D53 | Braid description | STRING | | EM |
| D54 | Axial fiber type | STRING | | EM |
| D55 | Braid fiber type | STRING | | EM |
| D56 | Axial fiber filament count | INTEGER | | EM |
| D57 | Braid fiber filament count | INTEGER | | EM |
| D58 | Braid angle | REAL | degrees | EM |
| D59 | Percentage of axial yarn | REAL | % | EM |
| E60 | Percentage of braid yarn | REAL | % | EM |
| E61 | Axial yarn spacing in braids | REAL | in. | RM |
| Winding Information Subblock | | | | |
| D66 | Winding description | STRING | | EM |
| E. Prepreg Information Block Prepreg Identification Subblock | | | | |

TABLE A1.1 *Continued*

| No. | Data Element Descriptive Name | Data Type or Standard Data Element Set | Category Set, Value Set, or Units | Level |
|-------------------------------------------------------------|-----------------------------------------------|----------------------------------------|-----------------------------------|-------|
| E1 | Prepreg type | STRING | Table 17 | EM |
| E2 | Prepreg commercial name | STRING | | EM |
| E3 | Prepreg manufacturer | [Organization] | | EM |
| E9 | Scrim fiber chemical class | STRING | Table 5 | RM |
| E10 | Scrim fabric style | STRING | | RM |
| Prepreg Batch Information Subblock | | | | |
| E13 | Prepreg batch certification date - minimum | DATE | | O |
| E13 | Prepreg batch certification date - maximum | DATE | | O |
| Prepreg Auxiliary Test Subblock | | | | |
| E16 | Prepreg fiber areal weight—nominal | [Auxiliary test] | g/m ² | EM |
| E16 | Prepreg fiber areal weight—minimum | [Auxiliary test] | g/m ² | EM |
| E16 | Prepreg fiber areal weight—maximum | [Auxiliary test] | g/m ² | EM |
| E16 | Prepreg fiber areal weight—test method | [Auxiliary test] | g/m ² | EM |
| E17 | Prepreg volatile content, wt% | [Auxiliary test] | wt% | EM |
| E18 | Prepreg fiber content, vol% | [Auxiliary test] | vol% | RM |
| E19 | Prepreg matrix content, wt% | [Auxiliary test] | Wt% | RM |
| F. Process Information Block Process Specification Subblock | | | | |
| F1 | Process specification | [Specification] | | RM |
| F2 | Process reinforcement application | Table | Table 19 | EM |
| F3 | Process mold type | Table | Table 20 | EM |
| F4 | Tackifier common name | STRING | | RM |
| F5 | Tackifier chemical class | STRING | Table 12 | RM |
| F6 | Tackifier form | STRING | Table 21 | RM |
| F7 | Tackifier manufacturer | STRING | | RM |
| Process Description Subblock | | | | |
| F8 | Process stage type | STRING | Table 22 | RM |
| F9 | Process stage temperature—nominal | REAL | F | RM |
| F9 | Process stage temperature—minimum | REAL | F | RM |
| F9 | Process stage temperature—maximum | REAL | F | RM |
| F10 | Process stage pressure—nominal | REAL | psig | RM |
| F10 | Process stage pressure—minimum | REAL | psig | RM |
| F10 | Process stage pressure—maximum | REAL | psig | RM |
| F11 | Process stage vacuum | REAL | psig | RM |
| F12 | Process stage duration—nominal | REAL | min | RM |
| F12 | Process stage duration—minimum | REAL | min | RM |
| F12 | Process stage duration—maximum | REAL | min | RM |
| F13 | Process ramp rate | REAL | C/min (F/min) | RM |
| F14 | Process stage other parameter | STRING | | RM |
| F17 | Process end date—minimum | DATE | | RM |
| F17 | Process end date—maximum | DATE | | RM |
| G. Part Information Block Part Description Subblock | | | | |
| G1 | Part form | STRING | Table 23 | EM |
| G2 | Material orientation code | STRING | | EM |
| G3 | Part specification | [Specification] | | RM |
| G6 | Part history | STRING | | EM |
| G7 | Part additional information | STRING | | RM |
| Part Auxiliary Test Subblock | | | | |
| G4 | Part cured ply thickness—nominal | REAL | | RM |
| G4 | Part cured ply thickness—minimum | REAL | | RM |
| G4 | Part cured ply thickness—maximum | REAL | | RM |
| G9 | Part fiber areal weight | [Auxiliary test] | | RM |
| G11 | Part mass density—nominal | [Auxiliary test] | | EM |
| G11 | Part mass density—minimum | [Auxiliary test] | | EM |
| G11 | Part mass density—maximum | [Auxiliary test] | | EM |
| G11 | Part mass density—test method | [Auxiliary test] | | EM |
| G12 | Mean glass transition temperature—dry | [Auxiliary test] | | EM |
| G13 | Mean glass transition temperature—wet | [Auxiliary test] | | EM |
| G13 | Mean glass transition temperature—test method | [Auxiliary test] | | EM |

APPENDIX
(Nonmandatory Information)
X1. CONSIDERATIONS IN DIFFERENTIATING BETWEEN A REINFORCED PLASTIC AND A POLYMER MATRIX COMPOSITES
TABLE X1.1 Differences Between Reinforced Plastics and Polymer Matrix Composite

| Polymer, Reinforced | Polymer Matrix Composite |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <p>Reinforcement (enhances polymer properties)</p> <p>Short fibers (usually <math>< \frac{1}{2}</math> in.)</p> <p>Macerated fabric</p> <p>Particulate</p> <p>Flake (randomly mixed in molding compound or during flow to mold, or both, reinforcement simple and small relative to part size)</p> | <p>Reinforcement (usually controls properties)</p> <p>Long or continuous fiber/filament/tow</p> <p>Fabric and tape, woven or nonwoven</p> <p>Braided, stitched, knitted preforms</p> <p>High-modulus fiber (Emphasis on properties of reinforcement and its geometric placement; reinforcement dimensions approximate part dimensions)</p> |
| <p>Polymer</p> <p>Generally >50 mass% polymer content (compared to total, excluding from polymer mass percent any polymeric reinforcement added). The polymer has the structural role.</p> | <p>Polymer Matrix</p> <p>Generally <50 mass% polymer content (compared to total, excluding from polymer mass percent any polymeric reinforcement added). Role is often as a binder for the reinforcement.</p> |
| <p>Molding Material</p> <p>Pellets, powder, or granules (B-stage for thermosets)</p> <p>Dough or putty-like molding compounds (bulk molding compound, BMC)</p> <p>1- or 2-part (base and hardener) thermosets (Molding compound contains the reinforcement; carries it to the mold.)</p> | <p>Molding Material</p> <p>Prepreg</p> <p>Sheet molding compound</p> <p>Polymer system often kept separate from the reinforcement (united in the mold)</p> <p>Polymer carried to mold by reinforcement (filament winding and pultrusion.)</p> |
| <p>Processing</p> <p>Injection molding</p> <p>RRIM</p> <p>Screw extrusion</p> <p>Transfer molding</p> <p>Compression molding</p> <p>Rotational molding</p> <p>Thermoforming (Movement and orientation of reinforcement with resin flow in the mold)</p> | <p>Processing</p> <p>Lamination</p> <p>Lay-up</p> <p>Spray-up</p> <p>Resin transfer molding; mat molding</p> <p>Compression molding</p> <p>Pultrusion</p> <p>Filament winding</p> <p>RIM with preform</p> |

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).