



# Standard Practice for Conditioning and Testing Flexible Barrier Packaging<sup>1</sup>

This standard is issued under the fixed designation E171/E171M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification defines the standard temperature and humidity for conditioning and testing of flexible barrier packaging and flexible barrier packaging materials at nominally ambient conditions.

1.2 There are many other temperature and humidity conditions that may be appropriately used to test end use conditions (such as freezer, refrigerated, or abusive storage). These need to be individually established and are not in the scope of this practice.

1.3 Only those materials that fall under the general area of flexible barrier packaging materials are included in this practice.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D4332 Practice for Conditioning Containers, Packages, or Packaging Components for Testing](#)

[F17 Terminology Relating to Flexible Barrier Packaging](#)

[F2825 Practice for Climatic Stressing of Packaging Systems for Single Parcel Delivery](#)

## 3. Terminology

3.1 *conditioning*—the exposure of a material to the influence of a prescribed atmosphere for a stipulated period of time or until a stipulated relation is reached between material and atmosphere.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee F02 on Flexible Barrier Packaging and is the direct responsibility of Subcommittee F02.50 on Package Design and Development.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1960. Last previous edition approved in 2011 as E171/E171M-11. DOI:10.1520/E0171\_E0171M-11R15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 Terms and definitions used in this practice may be found in Terminology [F17](#).

## 4. Significance and Use

4.1 Conditioning is used to minimize the variation in test results that may result from fluctuations in temperature and humidity, or both. Many flexible packaging materials or components of flexible packaging materials, particularly materials that are hygroscopic, undergo changes in physical properties as the temperature and the relative humidity (RH) to which they are exposed are varied.

4.2 Many packaging materials do not exhibit a meaningful change in physical properties across the temperature and humidity range that is generally found in office and general laboratory settings. As a result, conditioning of samples is often not required in order to achieve useful test results and is often bypassed during routine testing.

4.3 Conditioning should be considered when (a) comparing between or among laboratory results (for example, supplier and customer), (b) temperature or humidity is anticipated to have an effect on the test outcomes, or (c) potential sources of variation in test results must be minimized.

4.4 Temperature and humidity alone are not sufficient to completely define a storage condition. Many other factors may be relevant (such as time, light, and atmospheric pressure) that are not defined in this specification.

## 5. Atmospheric Conditions

5.1 Condition and test materials as follows:

Temperature:	23 ± 2°C [73 ± 4°F]
Humidity:	50 ± 5 % RH
Conditioning Time :	24 h minimum

5.2 *Special Atmospheres*—If special atmospheres are required, see Practice [D4332](#) for guidance on temperature and relative humidity associated with specific environmental conditions. A conditioning time of 24 h minimum at the special atmosphere shall be used unless circumstances suggest another time may be more appropriate. The special atmospheres listed in Practice [D4332](#) are not intended to be performed in sequence. Practice [F2825](#) provides guidance on climatic stressing protocols.

## 6. Keywords

6.1 conditioning; conditions; flexible packaging; flexible barrier packaging; materials; package

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*