



Standard Test Method for Acidity in Acrylonitrile¹

This standard is issued under the fixed designation E1788; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of total acidity as acetic acid in concentrations below 500 $\mu\text{g/g}$ in acrylonitrile.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 8.

1.4 Review the current Safety Data Sheets (SDS) for detailed information concerning toxicity, first aid procedures, and safety precautions.

2. Referenced Documents

2.1 *ASTM Standards*:²

[D1193 Specification for Reagent Water](#)

[E200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis](#)

3. Summary of Test Method

3.1 The acrylonitrile sample is titrated with alcoholic sodium hydroxide solution to the visual end point.

4. Significance and Use

4.1 This test method is useful for determining low levels of acidity, below 500 $\mu\text{g/g}$ in acrylonitrile. The total acidity is calculated as acetic acid.

4.2 Acidity may be present as a result of contamination or decomposition during storage, distribution, or manufacture.

¹ This test method is under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee D16.16 on Industrial and Specialty Product Standards.

Current edition approved April 1, 2016. Published May 2016. Originally approved in 1996. Last previous edition approved in 2008 as E1788 – 08. DOI: 10.1520/E1788-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Apparatus

5.1 *Buret*, 10 mL, graduated in 0.05 mL subdivision.

6. Purity of Reagents

6.1 Use reagent grade chemicals in all tests. Unless otherwise indicated, all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 Unless otherwise indicated, references to water mean reagent water conforming to Type II or Type III of Specification [D1193](#).

7. Reagents

7.1 *Bromthymol Blue Indicator Solution* (1 g/L)—Weigh 100 mg into a 150 mL beaker, add 1.5 mL of 0.1 meq/mL NaOH to aid in dissolving, gradually add 100 mL of methanol. Neutralize to a deep green by dropwise addition of 0.02 meq/mL NaOH.

7.2 *Sodium Hydroxide Standard Solution* (0.02 meq/mL)—Dissolve 0.800 g NaOH in 500 mL of methanol and dilute to 1 L with methanol. Standardize in accordance with the appropriate sections of Practice [E200](#).

8. Hazards

8.1 Acrylonitrile is potentially hazardous to human health if not properly handled. Acrylonitrile is a suspected human carcinogen. Use acrylonitrile in a well ventilated hood.

8.2 Acrylonitrile can contribute to a toxic condition in systems of the human body from inhalation, swallowing, or contact with the eyes or skin. Direct contact with acrylonitrile can cause skin burns.

8.3 Acrylonitrile liquid and vapor are absorbed readily into shoe leather and clothing and will penetrate most rubbers,

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USP), Rockville, MD.

*A Summary of Changes section appears at the end of this standard

barrier fabrics, or creams. Contact lenses should not be worn in areas where eye contact with acrylonitrile could occur. Impermeable protective clothing must be used. Consult the current SDS for recommended materials.

9. Procedure

9.1 To a 250-mL Erlenmeyer flask, add 0.5 mL of bromthymol blue indicator solution.

9.2 Pipet 100 mL of the sample into the 250-mL Erlenmeyer flask. Titrate with the 0.02 meq/mL NaOH solution to the first perceptible blue color.

10. Calculation

10.1 Calculate the acidity of the sample as follows:

$$\text{Acidity as Acetic Acid, } \mu\text{g/g by wt.} = \frac{A \times N \times 60000}{B \times D} \quad (1)$$

where:

A = NaOH solution required for titration of sample, mL,

N = meq/mL of the NaOH solution,

B = volume of sample used, mL, and

D = Sp Gr of the sample at the test temperature.

11. Report

11.1 Report the total acidity as acetic acid to the nearest $\mu\text{g/g}$.

12. Precision and Bias⁴

12.1 *Precision*—The following criteria should be used for judging the acceptability of results (see **Note 1**):

12.1.1 *Repeatability (Single Analyst)*—The standard deviation for a single determination has been estimated to be the

⁴ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:E15-1049. Contact ASTM Customer Service at service@astm.org.

absolute value in **Table 1** at the indicated degrees of freedom. The 95 % limit for the difference between two such runs is given in **Table 1**.

12.1.2 *Laboratory Precision (Within-Laboratory, Between-Days Variability)*—The standard deviation of results (each the average of duplicates) obtained by the same analyst on different days has been estimated to be the absolute value in **Table 1**. The 95 % limit for the difference between two such averages is given in **Table 1**.

12.1.3 *Reproducibility (Multilaboratory)*—The standard deviation of results (each the average of duplicates) obtained by analysts in different laboratories has been estimated to be the absolute value in **Table 1** at the indicated degrees of freedom. The 95 % limit for the difference between two such averages is given in **Table 1**.

NOTE 1—The above precision estimates are based on an interlaboratory study of analyses performed in 1991 on two samples of acrylonitrile containing an average total acidity of 2 and 103 $\mu\text{g/g}$, respectively. One analyst in each of seven laboratories performed duplicate determinations and repeated one day later for a total of 56 determinations. Data from one laboratory, however, were excluded from the first sample and two laboratories were excluded from the second sample. Practice E180 was used in developing these precision estimates.

12.2 *Bias*—The bias of this test method has not been determined because of the lack of acceptable reference material.

13. Keywords

13.1 acidity; acrylonitrile; alcoholic sodium hydroxide; end point; indicator; titrated

TABLE 1 Precision for Total Acidity

Level, mg/kg	Repeatability			Laboratory Precision			Reproducibility		
	Standard Deviation	df	95 % Limit	Standard Deviation	df	95 % Limit	Standard Deviation	df	95 % Limit
2	0.0000	12	3 ^A	0.2887	6	0.8	0.5323	5	1
103	1.3229	10	4	0.7246	5	2	3.5532	4	10

^A Practical limit, based on reporting results to nearest 1 mg/kg.

SUMMARY OF CHANGES

Subcommittee E15.02 has identified the location of selected changes to this standard since the last issue (E1178-08 that may impact the use of this standard.

(1) Changed “Material Safety Data Sheets (MSDS)” to “Safety Data Sheets (SDS)” in **1.4**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>