



# Standard Practice for Determining Average Grain Size Using Electron Backscatter Diffraction (EBSD) in Fully Recrystallized Polycrystalline Materials<sup>1</sup>

This standard is issued under the fixed designation E2627; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice is used to determine grain size from measurements of grain areas from automated electron backscatter diffraction (EBSD) scans of polycrystalline materials.

1.2 The intent of this practice is to standardize operation of an automated EBSD instrument to measure ASTM *G* directly from crystal orientation. The guidelines and caveats of [E112](#) apply here, but the focus of this standard is on EBSD practice.

1.3 This practice is only applicable to fully recrystallized materials.

1.4 This practice is applicable to any crystalline material which produces EBSD patterns of sufficient quality that a high percentage of the patterns can be reliably indexed using automated indexing software.

1.5 The practice is applicable to any type of grain structure or grain size distribution.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[E7 Terminology Relating to Metallography](#)

[E112 Test Methods for Determining Average Grain Size](#)

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [E04](#) on Metallography and is the direct responsibility of Subcommittee [E04.11](#) on X-Ray and Electron Metallography.

Current edition approved Nov. 1, 2013. Published December 2013. Originally approved in 2010. Last previous edition approved in 2010 as E2627–10. DOI: 10.1520/E2627–13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

[E766 Practice for Calibrating the Magnification of a Scanning Electron Microscope](#)

[E1181 Test Methods for Characterizing Duplex Grain Sizes](#)

[E1382 Test Methods for Determining Average Grain Size Using Semiautomatic and Automatic Image Analysis](#)

## 3. Terminology

### 3.1 Definitions:

3.1.1 *cleanup*—Post processing applied to EBSD scan data to reassign extraneous points in the scan grid to neighboring points. The extraneous points are assumed to arise from non-indexed or misindexed EBSD patterns.

3.1.2 (*crystallographic*) *orientation*—The rotation required to bring the principle axes of a crystal into coincidence with the principle axes assigned to a specimen. For example, in a rolled material with cubic crystal symmetry, it is the set of rotations required to bring the [100], [010] and [001] axes of the crystal into coincidence with the rolling, transverse and normal directions of the specimen. Orientations may be described in terms of various sets of angles, a matrix of direction cosines or a rotation vector.

3.1.3 *electron backscatter diffraction (EBSD)*.—A crystalline specimen is placed in a scanning electron microscope (SEM) at a high tilt angle ( $\sim 70^\circ$ ). When a stationary electron beam is positioned on a grain, the electrons are scattered in a small volume (typically 30nm in the tilt direction, 10nm in the transverse direction and 20 nm in depth for a field emission gun SEM and approximately an order of magnitude larger in the lateral directions for a tungsten filament SEM). Electrons that satisfy Bragg's law are diffracted back out of the specimen. The diffracted electrons strike a phosphor screen (or alternatively a YAG crystal) placed in the chamber. The colliding electrons fluoresce the phosphor and produce a pattern. The pattern is composed of a set of intersecting bands (Kikuchi lines). These bands are indicative of the arrangement of crystal lattice planes in the diffracting crystal volume. Assuming the material is of

known crystal structure, the orientation of the crystal within the diffracting volume can be determined.

3.1.4 *EBSD pattern*—An EBSD pattern is composed of a set of intersecting bands. The geometrical arrangement of these bands is indicative of the crystallographic orientation of the crystal lattice within the diffraction volume.

3.1.5 *EBSD scan*—Under computer control, the beam of the SEM is moved to a point on the specimen, an EBSD pattern captured and indexed to determine the crystallographic orientation at the beam location. This process is repeated for a set of points lying on a regular grid.

3.1.6 *grain*—In EBSD, grains have a specific meaning. They are defined as a group of similarly oriented neighboring points on the scan grid. The group is surrounded by a perimeter where misorientation across that perimeter exceeds a specified tolerance value.

3.1.7 *indexing*—The process of identifying the crystallographic orientation of the crystal lattice associated with an EBSD pattern generated by the interaction of the electron beam with that lattice.

3.1.8 *misorientation* —The set of rotations (Euler angles) required to bring one crystal lattice into coincidence with a second crystal lattice.

3.1.9 *misorientation tolerance*—If the angular difference between two neighboring pixels is less than this tolerance value then they are assumed to belong to the same grain.

3.1.10 *orientation Map*—Each point in the scan grid is assigned a color according to its orientation. This forms an image showing the microstructure.

3.1.11 *step size* ( $\Delta$ ) —The distance between neighboring points on the scan grid.

## 4. Summary of Practice

4.1 An EBSD scan is performed on a specimen, post-processing routines are applied to the scan data, and the individual points of the scan are grouped into grains according to their orientation. Average grain size is determined from the field average of grain areas based on the number of points in the EBSD map and the step size.

## 5. Significance and Use

5.1 This practice provides a way to estimate the average grain size of polycrystalline materials. It is based on EBSD measurements of crystallographic orientation which are inherently quantitative in nature. This method has specific advantage over traditional optical grain size measurements in some materials, where it is difficult to find appropriate metallographic preparation procedures to adequately delineate grain boundaries.

## 6. Apparatus

6.1 An electron backscatter diffraction (EBSD) system mounted on a Scanning Electron Microscope (SEM) is used. The EBSD system is constituted by a low-light sensitive video camera (typically a charge-coupled device or CCD camera). The camera images a medium for detecting the diffracted

electrons such as a phosphor screen or YAG crystal. EBSD patterns formed on the detecting medium are imaged using the camera and transmitted to a computer.

6.2 Software capable of reliably indexing an EBSD pattern to determine the crystallographic orientation from the EBSD pattern is needed. The computer and resident software should be capable of rapid collection of orientation data from EBSD patterns.

6.3 Electronics and software to control the beam in the SEM (or the stage, or both) are required to collect orientation data at points on a regular scan grid.

## 7. Hazards

7.1 There are no hazards specific to this test method. However, SEM operators should be familiar with safe SEM operating procedures to prevent exposure to X rays and coming in contact with the high voltages inherent to SEMs. Care should also be exercised in preparing specimens for EBSD as is the case for specimen preparation for light and electron microscopy.

## 8. Sampling and Test Specimens

8.1 Specimens should be selected to represent average conditions within a heat lot, treatment lot, or product, or to assess variations anticipated across or along a product or component, depending on the nature of the material being tested and the purpose of the study. Sampling location and frequency can be based upon agreements between the manufacturers and the users.

8.2 Specimens should not be taken from areas affected by shearing, burning, or other processes that will alter the grain structure.

8.3 The surface to be polished should be large enough in area to permit measurement of at least five fields at the desired magnification.

## 9. Specimen Preparation

9.1 It is important to follow good metallographic preparation procedures for successful EBSD work. EBSD is a surface sensitive technique. The surface should be free from deformation and have minimal topography. Careful mechanical polishing or electropolishing, or both should be performed on specimen surfaces. However, as compared with preparing specimens for grain size measurements based on optical microscopy, the surface should not be etched or treated to produce relief to delineate grain boundaries. This would be disadvantageous for obtaining EBSD patterns that can be indexed. The grain boundaries are delineated by processing of the orientation measurement data.

## 10. Preparation of Apparatus

10.1 Good practices should be used in the operation of both the SEM and EBSD systems. Particular attention should be given to geometric alignment of the specimen surface with the assumed measurement plane (typically 70° from the horizontal). Misalignments can easily arise from sample preparation or mounting of the sample. It is critical to mitigate such

misalignment, as they affect both the accuracy of the orientation measurements as well as the accuracy of the beam position, particularly in the direction of tilt. Accurate measurements of orientation and position are critical for accurate characterization of grain size.

## 11. Calibration and Standardization

11.1 The EBSD instrumentation should be properly calibrated according to specific manufacturer instructions, including the EBSD imaging system magnification calibration per Practice E766 (SEM magnification calibration).

## 12. Procedure

12.1 The first step is to perform an EBSD scan. Some a-priori knowledge of the estimated grain size is helpful in selecting an appropriate scan area and step size. A map should be constructed from the scan data to insure that sensible results are obtained. In particular, the map should be inspected to see if any grains appear speckled. If the automated EBSD software is having difficulty indexing the EBSD patterns, the resulting orientation maps will appear “speckled”. Indexing problems arise when the patterns are too weak for the band detection algorithms to accurately detect the bands in the patterns, if the system is poorly calibrated, if the crystal structure data is incorrect, or if the configuration parameters for the indexing algorithms are not optimized. The “speckling” arises because incorrect orientations are obtained from individual patterns. Operators should following good practice as recommended by their EBSD vendors to mitigate such problems.

12.2 Once the scan data have been collected, a cleanup routine should be applied to the data to assimilate any non-indexed or misindexed points into the surrounding neighborhood grains. The number of points modified by the cleanup process should be monitored. No more than 10% of the points should be modified in the process.

12.3 Points of similar orientation should be grouped together to form grains. A misorientation tolerance value of  $5^\circ$  is recommended to define the orientation similarity, although other misorientation values could be specified in producer/purchaser agreements. After grain grouping, each point in the scan should be associated with a grain. Each grain group is identified as a grain. At least 50 whole grains should be observable in each scan area.

12.4 Set up an EBSD scan so that the average grain contains about 500 points. Count the number of scan points contained within each whole grain,  $P_i$ , within the scanned field, for a number of fields ( $n$ ), until at least 500 grains have been measured. Exclude grains with point counts less than 100. For each grain with  $P_i$  exceeding 100 calculate the corresponding area,  $A_i$ . For scan data measured on a regular square grid, the area of a grain,  $A_i$ , is equal to the number of points in the grain multiplied by the square of the step size:

$$A_i = P_i \Delta^2 \quad (1)$$

For data collected on a regular hexagonal grid, the area of a grain,  $A_i$ , is equal to the number of points in the grain multiplied by the square of the step size,  $\Delta^2$  multiplied by the square root of three divided by two:

$$A_i = \frac{\sqrt{3}}{2} P_i \Delta^2 \quad (2)$$

Store the areas of each grain in memory or record to a file. Calculate the mean area,  $\bar{A}$ , for  $N$  grains measured in true area units ( $\mu\text{m}^2$  or  $\text{mm}^2$ ):

12.5 A histogram of the frequency of the grain areas can be constructed to determine or illustrate the uniformity of the grain areas and to detect and analyze duplex grain size conditions. The analytical method is described in Test Methods E1181, Appendix X2.

$$\bar{A} = \frac{1}{N} \sum_{i=1}^N A_i \quad (3)$$

12.6 Calculate the standard deviation,  $s$ , of the measured grain areas,  $A_i$ :

$$s = \left[ \frac{1}{N-1} \sum_{i=1}^N (A_i - \bar{A})^2 \right]^{\frac{1}{2}} \quad (4)$$

## 13. Interpretation of Results

13.1 Follow the methodology set out in Section 14 of Test Methods E1382 for grain area measurements, namely: after the desired number of grains,  $N$ , have been measured, calculate the mean value of the measurement as described in 13.4 and its deviation as described 13.5. The ASTM grain size number,  $G$ , is then calculated according to the following:

$$G = (-3.3223 \cdot \log \bar{A}) - 2.995 \bar{A} \text{ in } \text{mm}^2 \quad (5)$$

$G = [-3.3223 \cdot \log (\bar{A} \cdot 10^6)] - 2.995 \bar{A} \text{ in } \mu\text{m}^2$   
Round off the value of  $G$  to the nearest tenth unit.

13.2 Determine the 95 % confidence intervals, 95%CI, of each measurement in accordance with:

$$95\% \text{ CI} = \pm \frac{t \cdot s}{\sqrt{N}} \quad (6)$$

Where:

$t = 1.960$  assuming  $N \geq 500$

13.3 Determine the percent relative accuracy, %RA, of the measurement by dividing the 95%CI value by the mean grain area and multiplying by 100:

$$\%RA = \frac{95\% \text{ CI}}{\bar{A}} \cdot 100 \quad (7)$$

13.4 For specimens with non-equiaxed grain structures measure the mean grain area using measurements on longitudinal ( $l$ ), transverse ( $t$ ) and planar ( $p$ ) oriented surfaces. The pooled mean grain area,  $\bar{A}_{pooled}$ , for the specimen can be obtained from the three mean area values for the three principle planes (longitudinal, transverse, and planar) according to:

$$\bar{A}_{pooled} = (\bar{A}_l \cdot \bar{A}_t \cdot \bar{A}_p)^{\frac{1}{3}} \quad (8)$$

Where  $l$ ,  $t$ , and  $p$  subscripts indicate the test plane. The grain size number can then be calculated based on Eq 3 using  $\bar{A}_{pooled}$ . Calculate the pooled standard deviation,  $s_{pooled}$ , according to Eq 9 (Test Methods E1382, equation A1.8).

$$s_{pooled} = \left( \frac{(N_l - 1)s_l^2 + (N_t - 1)s_t^2 + (N_p - 1)s_p^2}{(N_l - 1) + (N_t - 1) + (N_p - 1)} \right)^{\frac{1}{2}} \quad (9)$$

Determine the 95%CI and %RA based on the pooled standard deviation and the pooled mean grain area of the three

measurements according to equation Eq 6 and Eq 7.

13.5 For a duplex grain size distribution, the analysis is conducted as described in Appendix X2 of Test Methods E1181.

#### 14. Report

14.1 The report should document the identifying information regarding the specimen, its composition, specification designation or trade name, customer or data requester, date of analysis, heat treatment or processing history, specimen location and orientation, and any other information, as required to describe the specimen.

14.2 List the number of fields measured. For each field list the dimensions of the EBSD scan areas, the step size used and number of points modified during any applied clean up to the EBSD data.

14.3 List the total number of whole grain areas measured.

14.4 An orientation map to illustrate the typical appearance of the grain structure may be provided, if required or desired.

14.5 List the mean measurement value ( $\bar{A}$ ), its standard deviation ( $s$ ), 95 % confidence interval (95%CI) and percent relative accuracy(%RA).

14.6 List the computed ASTM grain size ( $G$ ).

14.7 A histogram to illustrate the distribution of grain areas may be provided, if required or desired.

14.8 For a specimen with non-equiaxed, elongated/flattened grains, report the specific test plane or planes measured, the specific measurements for each test plane, and the mean grain area and resulting mean grain size number for the specimen. Report the pooled standard deviation and the 95%CI and %RA.

#### 15. Precision and Bias

15.1 The precision of this test method is based on an interlaboratory study of Practice E2627, Standard Practice for Determining Average Grain Size Using Electron Backscatter Diffraction (EBSD) in Fully Recrystallized Polycrystalline Materials, conducted in 2012. Seventeen laboratories participated in the study, testing a single material. Every analyst reported triplicate test results. Triplicate test data from twelve of the seventeen laboratories conformed to Practice E2627.

Practice E691 was followed for the study design; the details are given in ASTM Research Report No. RR:E04-1008<sup>3</sup>

15.1.1 *Repeatability limit (r)*—Two test results obtained within one laboratory shall be judged not equivalent if they differ by more than the “ $r$ ” value for that material; “ $r$ ” is the interval representing the critical difference between two test results for the same paint, obtained by the same operator using the same equipment on the same day in the same laboratory.

15.1.1.1 Repeatability limits are listed in Table 1.

15.1.2 *Reproducibility limit (R)*—Two test results shall be judged not equivalent if they differ by more than the “ $R$ ” value for that material; “ $R$ ” is the interval representing the critical difference between two test results for the same paint, obtained by different operators using different equipment in different laboratories.

15.1.2.1 Reproducibility limits are listed in Table 1.

15.1.3 The above terms (repeatability limit and reproducibility limit) are used as specified in Practice E177.

15.1.4 Any judgment in accordance with statements 9.1.1 and 9.1.2 would have an approximate 95% probability of being correct.

15.2 *Bias*—There was a + 33% bias when compared to the supplier’s certification of the material’s grain size, 5.0, as determined by Test Methods E112. An explanation is included in the research report. The bias between the Test Methods E112 data and the Practice E2627 data is due to the fact that E2627 does not ignore twin boundaries in microstructures that contain them, while Test Methods E112 explicitly does. When  $\Sigma 3$  boundaries are excluded when following Practice E2627, the bias reduces to less than 1%. For consistency with Test Methods E112 it is therefore recommended to modify the Practice E2627 definition of a grain in 3.1.6 to ignore  $\Sigma 3$  boundaries when present in the microstructure, as defined by the  $60 \pm 5^\circ$ ,  $\langle 111 \rangle \pm 5^\circ$  criterion. Please see the research report for a full explanation.

15.3 The precision statement was determined through statistical examination of 36 results, from a total of seventeen laboratories, on a single alloy.

#### 16. Keywords

16.1 backscattered electrons; backscatter diffraction; EBSD; Grain size; Kikuchi pattern; orientation map; SEM; scanning electron microscope

<sup>3</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:E04-1008. Contact ASTM Customer Service at service@astm.org.

**TABLE 1 Average Grain Size (ASTM Grain Size Number, G)**

Material	Average	Repeatability Standard Deviation	Reproducibility Standard Deviation	Repeatability Limit	Reproducibility Limit
	$\bar{x}$	$s_r$	$s_R$	$r$	$R$
ASTM RR Alloy 690	6.65	0.11	0.38	0.30	1.10

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org/COPYRIGHT/](http://www.astm.org/COPYRIGHT/)).*