



# Standard Practice for Radiographic Examination of Flat Panel Composites and Sandwich Core Materials Used in Aerospace Applications<sup>1</sup>

This standard is issued under the fixed designation E2662; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This practice is intended to be used as a supplement to Practices [E1742](#), [E1255](#), [E2033](#), and [E2698](#).

1.2 This practice describes procedures for radiographic examination of flat panel composites and sandwich core materials made entirely or in part from fiber-reinforced polymer matrix composites. Radiographic examination is: *a*) Film Radiography (RT), *b*) Computed Radiography (CR) with Imaging Plate, *c*) Digital Radiography (DR) with Digital Detector Array's (DDA), and *d*) Radioscopic (RTR) Real Time Radiography with a detection system such as an Image Intensifier. The composite materials under consideration typically contain continuous high modulus fibers (> 20 GPa), such as those listed in [1.4](#).

1.3 This practice describes established radiographic examination methods that are currently used by industry that have demonstrated utility in quality assurance of flat panel composites and sandwich core materials during product process design and optimization, process control, after manufacture inspection, in service examination, and health monitoring. Additional guidance can be found in [E2533](#), Guide for Non-destructive Testing of Polymer Matrix Composites Used in Aerospace.

1.4 This practice has utility for examination of flat panel composites and sandwich constructions containing, but not limited to, bismaleimide, epoxy, phenolic, poly(amide imide), polybenzimidazole, polyester (thermosetting and thermoplastic), poly(ether ether ketone), poly(ether imide), polyimide (thermosetting and thermoplastic), poly(phenylene sulfide), or polysulfone matrices; and alumina, aramid, boron, carbon, glass, quartz, or silicon carbide fibers. Typical as-fabricated geometries include uniaxial, cross ply and angle ply laminates; as well as honeycomb core sandwich constructions.

1.5 This practice does not specify accept-reject criteria and is not intended to be used as a means for approving flat panel composites or sandwich core materials for service.

1.6 To ensure proper use of the referenced standards, there are recognized nondestructive testing (NDT) specialists that are certified according to industry and company NDT specifications. It is recommended that a NDT specialist be a part of any composite component design, quality assurance, in service maintenance or damage examination.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- [C274 Terminology of Structural Sandwich Constructions](#)
- [D1434 Test Method for Determining Gas Permeability Characteristics of Plastic Film and Sheet](#)
- [D3878 Terminology for Composite Materials](#)
- [E94 Guide for Radiographic Examination](#)
- [E543 Specification for Agencies Performing Nondestructive Testing](#)
- [E747 Practice for Design, Manufacture and Material Grouping Classification of Wire Image Quality Indicators \(IQI\) Used for Radiology](#)
- [E1000 Guide for Radioscopy](#)
- [E1025 Practice for Design, Manufacture, and Material Grouping Classification of Hole-Type Image Quality Indicators \(IQI\) Used for Radiology](#)
- [E1165 Test Method for Measurement of Focal Spots of Industrial X-Ray Tubes by Pinhole Imaging](#)
- [E1255 Practice for Radioscopy](#)
- [E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases](#)

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [E07](#) on Nondestructive Testing and is the direct responsibility of Subcommittee [E07.01](#) on Radiology (X and Gamma) Method.

Current edition approved June 1, 2015. Published July 2015. Originally approved in 2009. Last previous edition approved as E2662–15. DOI: 10.1520/E2662-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

- E1316 Terminology for Nondestructive Examinations
- E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases
- E1742 Practice for Radiographic Examination
- E1815 Test Method for Classification of Film Systems for Industrial Radiography
- E1817 Practice for Controlling Quality of Radiological Examination by Using Representative Quality Indicators (RQIs)
- E2007 Guide for Computed Radiography
- E2033 Practice for Computed Radiology (Photostimulable Luminescence Method)
- E2445 Practice for Performance Evaluation and Long-Term Stability of Computed Radiography Systems
- E2446 Practice for Classification of Computed Radiology Systems
- E2533 Guide for Nondestructive Testing of Polymer Matrix Composites Used in Aerospace Applications
- E2597 Practice for Manufacturing Characterization of Digital Detector Arrays
- E2698 Practice for Radiological Examination Using Digital Detector Arrays
- E2736 Guide for Digital Detector Array Radiology
- E2737 Practice for Digital Detector Array Performance Evaluation and Long-Term Stability

2.2 *National Council on Radiation Protection and Measurement (NCRP) Documents:*<sup>3</sup>

- NCRP 49 Structural Shielding Design and Evaluation for Medical Use of X-Rays and Gamma Rays of Energies up to 10 MeV
- NCRP 116 Limitation of Exposure to Ionizing Radiation
- NCRP 144 Radiation Protection for Particle Accelerator Facilities

2.3 *Federal Standards:*<sup>4</sup>

- 10 CFR 20 Standards for Protection Against Radiation
- 21 CFR 1020.40 Safety Requirements of Cabinet X-ray Systems
- 29 CFR 1910.1096 Ionizing Radiation (X-rays, RF, etc.)

2.4 *Aerospace Industries Association Document:*<sup>5</sup>

- NAS 410 Certification and Qualification of Nondestructive Test Personnel

2.5 *Department of Defense (DoD) Documents:*<sup>4</sup>

- MIL-I-24768/10 Insulation, Plastics, Laminated, Thermosetting, Paper-Base, Phenolic-Resin (PBE)
- MIL-I-24768/11 Insulation, Plastics, Laminated, Thermosetting, Paper-Base, Phenolic-Resin (PBG)

2.6 *ISO Documents:*<sup>6</sup>

- ISO 19232-1 Non-destructive Testing—Image Quality of Radiographs—Part 1: Determination of the Image Quality

Value using Wire-type Image Quality Indicators

2.7 *EN Documents:*<sup>7</sup>

- EN 4179 Qualification and Approval of Personnel for Non-destructive Testing

### 3. Terminology

3.1 *Definitions*—Terminology in accordance with Terminologies C274, D3878, and E1316 shall be used where applicable.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *CEO—Cognizant Engineering Organization, n*—the company, government agency, or other authority responsible for the design, or end use, of the device(s) for which radiographical examination is required. This, in addition to design personnel, may include personnel from engineering, material and process engineering, nondestructive testing (usually the cognizant Radiographic Level 3), or quality groups, as appropriate.

3.2.2 *flat panel composite, n*—any fiber reinforced composite lay-up consisting laminae (plies) with one or more orientations with respect to some reference direction that are consolidated by press or autoclave to yield a two-dimensionally flat article of finite thickness.

3.2.3 *sandwich core material, n*—a structural panel made up of two relatively thin outer skins of composite laminate or other material, such as metal or wood, separated by and bonded to a relatively thick lightweight inner core such as honeycomb, open and close cell foam, wave formed material, bonded composite tubes, or naturally occurring material such as balsa wood. See also *sandwich core construction* in Terminology C274.

### 4. Summary of Practice

4.1 *Agency Evaluation*—When specified in the contractual agreement, NDT agencies shall be evaluated and qualified in accordance with Practice E543.

4.2 RT shall be conducted in accordance with Practice E1742, Guide E94, and the additional requirements of this practice.

4.3 RTR shall be conducted in accordance with Practice E1255, Guide E1000, and the additional requirements of this practice.

4.4 CR shall be conducted in accordance with Practice E2033, Guide E2007, and the additional requirements of this practice.

4.5 DR shall be conducted in accordance with Practice E2698, Guide E2736, and the additional requirements of this practice.

### 5. Significance and Use

5.1 Radiographic examination may be used during product and process design optimization, on line process control, after manufacture inspection, and in service inspection. In addition

<sup>3</sup> Available from NCRP Publications, 7010 Woodmont Ave., Suite 1016, Bethesda, MD 20814.

<sup>4</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

<sup>5</sup> Available from Aerospace Industries Association of America, Inc. (AIA), 1000 Wilson Blvd., Suite 1700, Arlington, VA 22209-3928, <http://www.aia-aerospace.org>.

<sup>6</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, CP 56, CH-1211 Geneva 20, Switzerland, <http://www.iso.org>.

<sup>7</sup> Available from European Committee for Standardization (CEN), Avenue Marnix 17, B-1000, Brussels, Belgium, <http://www.cen.eu>.

to verifying structural placement, radiographic examination can be used in the case of honeycomb core materials to detect node bonds, core-to-core splices, and core-to-structure splices. Radiographic examination is especially well suited for detecting sub-surface flaws. The general types of defects detected by radiographic examination include blown core, core corrosion, damaged filaments, density variation, entrapped fluid, fiber debonding, fiber misalignment, foreign material, fractures, inclusions, micro-cracks, node bond failure, porosity/voids, and thickness variation.

5.2 Factors that influence image formation and X-ray attenuation in radiographic examination, and which are relevant to interpreting the images for the conditions of interest, should be included in the examination request. Examples include, but not limited to, the following: laminate (matrix and fiber) material, lay-up geometry, fiber volume fraction (flat panels); facing material, core material, facing stack sequence, core geometry (cell size); core density, facing void content, adhesive void content, and facing volume percent reinforcement (sandwich core materials); overall thickness, specimen alignment, and specimen geometry relative to the beam (flat panels and sandwich core materials).

5.3 Information regarding discontinuities that are detectable using radiographic examination methods can be found in Guide E2533.

**6. Qualification**

6.1 *Personnel Qualification*—Personnel performing examinations to this practice shall be qualified in accordance with NAS410 or EN 4179 and certified by the employer. Other equivalent qualification documents may be used when specified on the contract or purchase order. The applicable revision shall be the latest unless otherwise specified in the contractual agreement between parties.

6.2 *Qualification of Nondestructive Testing (NDT) Agencies*—When specified in the contractual agreement, non-destructive testing agencies shall be qualified and evaluated as described in Practice E543.

6.2.1 *Safety*—The NDT facility shall present no hazards to the safety of personnel and property. NCRP 144 and NCRP 116 may be used as guides to ensure that radiographic procedures are performed so that personnel shall not receive a radiation dose exceeding the maximum safe limits as permitted by city, state, or national codes.

**7. Equipment and Materials**

7.1 *Equipment:*

7.1.1 *X-Radiation Sources*—Selection of suitable X-ray machines will depend upon variables regarding the specimen being examined and the size and type of defects being sought. The suitability of an X-ray machine shall be demonstrated by attainment of the required radiographic quality level, radiographic contrast, and compliance with all other requirements stipulated in this practice.

7.1.1.1 Geometric magnification may be used with the following caveats and considerations:

(a) The higher the magnification factor used, the smaller the area of inspection becomes within the part that is normal to

the radiation beam. This makes detection of certain discontinuities, such as cracks that occupy a significant portion of the part thickness more challenging to detect.

(b) System spatial resolution increases with magnification, which can increase overall system sharpness. However, the maximum magnification allowed shall be based on the unsharpness requirements of Table 1.

(c) Contrast to Noise increases with greater object-to-detector distance because less scatter radiation reaches the detector.

7.1.1.2 When using magnification, the focal spot size should be small enough to avoid unsharpness due to the size of the focal spot in accordance with section 8.5 herein.

7.1.2 *Gamma Radiation Sources*—Gamma radiation sources are generally not suitable for the high contrast, high sensitivity requirements needed to meet the requirements of this practice. The use of gamma ray sources will only be allowed when approved by the CEO, or the cognizant Level 3 Radiographer, or both. The suitability of a specific gamma ray source shall be demonstrated by attainment of the required radiographic quality level, radiographic contrast, and compliance with all other requirements stipulated in this practice.

7.1.3 *Film Processing Equipment*—The following are the descriptions of automatic processors and manual processing in regards to film processing equipment.

7.1.3.1 *Automatic Film Processors*—Automatic film processors shall conform to the film manufacturer’s requirements (that is, time, temperature, and replenishment rates) for film processing, and be maintained in accordance with the manufacturer’s recommendations in such a manner as to consistently produce blemish-free and archival quality radiographs. Automatic processor replenisher tanks, including auto mixers shall be set up and maintained in accordance with the film manufacturer’s recommendations, that is, floating lid in developer tank, filters on replenishment lines, or cleaned periodically.

7.1.3.2 *Manual Film Processing*—Manual processing tanks and film dryers shall conform to the film manufacturer’s requirements (that is, stainless steel or other non-reactive material, proper covers) and shall be large enough to consistently produce blemish-free and archival quality radiographs. Manual tanks shall be cleaned and supplied with fresh chemistry using the following guidelines:

(1) *Developer Tank*—Drain and clean it when replenisher has been added to an amount equal to five times the volume of the tank. The amount of replenisher added shall be recorded for reference.

(2) *Fixer Tank*—Drain and clean it when the clearing time is twice as long as it was when fresh (fresh fixer will usually clear a film in approximately 60 seconds). The initial clearing time shall be recorded for reference.

**TABLE 1 Image Unsharpness (U<sub>i</sub>) (Maximum)**

Material Thickness (t), in. (mm)	U <sub>i</sub> , in. (mm)
t ≤ 0.5 (t ≤ 12.7)	0.008 (0.203)
0.5 < t ≤ 1.0 (12.7 < t ≤ 25.4)	0.010 (0.254)
1.0 < t ≤ 2.0 (25.4 < t ≤ 50.8)	0.020 (0.508)
2.0 < t ≤ 4.0 (50.8 < t ≤ 101.6)	0.030 (0.762)
4.0 < t (101.6 < t)	0.040 (1.016)



(3) *Wash and Stop Bath Tanks*—The wash tank and stop bath tanks shall be cleaned whenever the fixer or developer tanks are cleaned.

7.1.4 *Digital Detector Array, or CR, or Both*—The DDA, or CR, or both, must have an appropriate signal-to-noise ratio, contrast sensitivity, spatial resolution capability, image lag for DDA effective erasure capability for CR, and dynamic range to show the required radiographic quality level as agreed upon between user and the CEO. Practices [E2033](#), [E2445](#), [E2597](#), [E2698](#), and [E2737](#) should be consulted as applicable for aid in determining relevant variables and values to consider.

7.1.4.1 Users shall comply with the manufacturers' recommendations of temperatures for both operation and shipping, and tolerances in the temperature thereof.

7.1.5 Upon installation of the DDA, or CR, or both, an initial series of user tests shall be accomplished to establish baseline system performance in accordance with Practices [E2445](#) and [E2737](#) as applicable.

7.1.6 *Image Quality Indicators (IQI) and Shims*:

7.1.6.1 Hole Type IQIs shall comply with Practice [E1025](#) group 001 for non-metals and shall be radiographically similar to the material under examination.

*Discussion*—The non-metal group was established experimentally at a range of 15 to 60 kV on 0.100-in to 0.250-in (2.54-mm to 6.35-mm) thick specimens using thermosetting plastic laminated insulation materials specified as MIL-I-24768/10 type PBE and MIL-I-24768/11 type PBG. This material is known by the trade name Garolite. There are many variations and the uniformity of the material can vary from different manufacturers and batches; it is therefore recommended that the material first be radiographically examined to determine its suitability for IQI, shims, step wedges etc., prior to manufacturing those items. The alternative to MIL-I-24768 material, as stipulated in [E1025](#), is to make IQIs, shims, etc., from the same material as the parts to be examined.

7.1.6.2 Wire Type IQIs shall comply with Practice [E747](#) or ISO 19232-1 and shall be radiographically similar to the material under examination.

*Discussion*—Currently there is not a non-metals material group listed in either Practice [E747](#) or ISO 19232-1. In order to use wire IQIs for composite material examinations, IQIs shall be fabricated with radiographically similar material as defined in Practice [E1025](#).

7.1.7 *Representative Quality Indicators (RQI)*—RQIs may be used in lieu of IQIs when approved by the CEO or the cognizant Level 3 Radiographer, or both. RQIs shall be used in accordance with Practice [E1817](#).

7.1.8 *Software*—The DDA, or CR, or both, cannot be operated without computing hardware and software for image acquisition and image display. The software should be capable of acquiring the images frame by frame from a DDA and performing an image calibration to correct the fixed pattern noise of the DDA and to substitute bad DDA pixels. The software shall be able to scale images in size (zoom) and pixel values by converting images for optimal monitor display.

7.1.9 *Film, or Imaging Plate Cassettes, or Both*—In addition to the requirements in Practice [E1742](#), exposure cassettes

used for film and computed radiography imaging plates shall not interfere with the clarity of the radiographic image.

7.2 *Materials*:

7.2.1 *Film*—Only film systems meeting the Class I (or better) requirements of Test Method [E1815](#) shall be used. Class II films may be used in multi-load applications to image varying thickness ranges when approved by the CEO, or the cognizant Level 3 Radiographer, or both.

## 8. Procedure

8.1 *Special Handling Requirements*—Identify special handling requirements from purchase orders, engineering drawings, work orders, work instructions, or other authorizing documents that may be applicable. Special handling requirements shall be noted on the Radiographic Technique, or Scan Plan, or both.

8.2 *Written Procedure (Radiographic Technique, or Scan Plan, or Both)*—A radiographic examination procedure shall be established and documented for each part radiographed. The procedure shall be established with the acceptance criteria for defect type and size in mind, and shall be capable of consistently producing the requirements for the required radiographic quality level and when applicable, radiographic film density and contrast.

8.3 *IQI Selection*—As stated in Section 7, IQIs shall be fabricated from radiologically similar material as described in Practice [E1025](#).

8.4 *Non Requirement of IQIs*—IQIs are not required when:

8.4.1 Examining assemblies for debris,

8.4.2 Conducting radiography for defect removal provided final examination of the area includes an IQI,

8.4.3 Examining to show material details or contrast between two or more dissimilar materials, for example, such as examining honeycomb structures to determine location, presence, or absence of inserts or core splices,

8.4.4 Non-use of IQI for other reasons not listed here requires approval by the CEO, or the cognizant Level 3 Radiographer, or both.

8.5 *Image Unsharpness*—The total image unsharpness shall comply with [Table 1](#) and shall be calculated in accordance with equations established in [E1000](#), [E1742](#), [E2033](#), and [E2698](#), as applicable.

8.6 *Radioscopy*—When RTR is used, a permanent record shall be produced in the form of electronic images. RTR systems that do not provide permanent records may only be used when approved by the CEO, or the Radiographic Level 3, or both.

8.7 *Image Interpretation and Evaluation*—All images, whether film or electronic shall be qualified by the certified radiographic interpreter. Verification of film density or pixel value, contrast, radiographic quality level/correct IQI, image identification, complete coverage, etc., is required for image qualification prior to evaluation of images to accept/reject criteria.

## 9. Safety and Hazards

9.1 The safety procedures for the handling and use of ionizing radiation sources must be followed. Mandatory rules and regulations are published by governmental licensing agencies. Careful radiation surveys should be made in accordance with regulations and codes and should be conducted in the examination area as well as in adjacent areas under all possible operating conditions.

9.2 Issues associated with personnel protection against X-rays and gamma rays are not covered by this document. For information on personnel protection, refer to documents issued by the National Committee on Radiation Protection and Measurement, Federal Register, U.S. Energy Research and Development Administration, and to state and local regulations, if such exist. For specific radiation safety information, refer to 10 CFR 20, 21 CFR 1020.40, and 29 CFR 1910.1096 or state regulations for agreement states.

9.3 Radiographic examination procedures shall be conducted under protective conditions so that personnel will not receive radiation dose levels exceeding that permitted by company, city, state, or national regulations. The recommendations of the National Committee on Radiation Protection (NCRP) should be a guide to radiation safety. NCRP 49, NCRP 144, and NCRP 116 may be used as guides to ensure the radiographic or radioscopy procedures are performed so that personnel shall not receive a radiation dose exceeding the maximum permitted by city, state, or national codes.

9.4 Radiographic systems wherein the radiation source and detection system are manipulated instead of, or in addition to, the test article necessitate the use of more stringent shielding requirements.

9.5 *Electrical Safety*—The radiographer must comply with safe electrical practices when working with X-ray equipment. Modern X-ray equipment uses high voltage circuits. Permanently installed X-ray facilities are designed so that personnel will encounter few electrical hazards; however, use of portable X-ray equipment requires that added precaution be taken such

as ensuring that units are grounded appropriately, power cables are free from wear, and condensers are discharged prior to checking of circuits.

## 10. Report

10.1 To ensure material traceability, essential information about the composite material, reinforcement, matrix, preform, prepreg, process method, and part information shall be recorded as described in Guide E1309. Additional information may be necessary when individual constituents that make up the composite material being tested are considered independently. For example, for identification of reinforcements in terms of class, subclass, chemical family, form, dimensional parameters, and dimensional distribution, Guide E1471 should be consulted.

10.2 To ensure test validity, including reproducibility and repeatability, essential information about test method, specimen preparation, specimen geometry, specimen conditioning, test equipment, test environment, loading (if applicable), raw and normalized data, and statistical analysis (if applicable) shall be recorded as described in Guide D1434.

10.3 The inspection report shall reference the acceptance criteria, provide traceability to the specific part or the lot of parts examined, the disposition of the part (accept or reject), the reason for rejection of any items, and shall include the name or signature, or both, of the radiographic interpreter(s), or their acceptance stamp as applicable.

## 11. Keywords

11.1 aerospace composites; computed radiology (CR); digital detector array (DDA); digital radiography (DR); fiber-reinforced polymer matrix composites; flat panels; high modulus fibers; high performance composites; honeycomb core; laminates; nondestructive evaluation (NDE); nondestructive inspection (NDI); nondestructive testing (NDT); polymeric matrix composites (PMC); radiography (RT); radioscopy (RTR); sandwich core materials; sandwich constructions; structural sandwich constructions

## SUMMARY OF CHANGES

Committee E07 has identified the location of selected changes to this standard since the last issue (E2662-09) that may impact the use of this standard. (Approved June 1, 2015.)

- (1) Added references to Section 2.
- (2) Changed “radiology” to “radiography” where appropriate.
- (3) Relocated IQI and RQI information to subsections 7.1.6 and 7.1.7.

- (4) Revised Sections 7 and 8.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*