



Standard Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition¹

This standard is issued under the fixed designation E55; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This practice covers the sampling, for the determination of chemical composition (**Note 1**), of nonferrous metals and alloys that have been reduced to their final form by mechanical working; that is, by such means as rolling, drawing, and extruding.

1.1.1 Refer to Practice **E255** for copper and copper alloys.

NOTE 1—The selection of correct portions of material and the preparation of a representative sample from such portions are necessary prerequisites to every analysis, the analysis being of no value unless the sample actually represents the average composition of the material from which it was selected.

1.2 In special cases, when agreed upon by the purchaser and the manufacturer, the heat analysis may be accepted as representative of the composition of the finished product. In such cases, the identity of each heat of metal should be maintained through each stage of the manufacturing process to the final form. This method of sampling is not intended to apply under these conditions.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

¹ This practice is under the jurisdiction of ASTM Committee **E01** on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee **E01.05** on Cu, Pb, Zn, Cd, Sn, Be, their Alloys, and Related Metals.

Current edition approved Feb. 1, 2011. Published February 2011. Originally approved in 1946. Last previous edition approved in 2005 as E55 – 91 (2005). DOI: 10.1520/E0055-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

3. Terminology

3.1 For definitions of terms used in this practice, see Terminology **E135**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *portion, n*—the term “portion” is used in this practice to designate the selected pieces of material from which the sample is prepared.

3.2.2 *sample, n*—the term “sample” is used in this practice to designate the final form of the material submitted for analysis (drillings, millings, etc.). A representative sample is defined as a small part containing the same ingredients in the same proportions as they occur in the original lot or lots of material.

4. Selection of Portion

4.1 A portion representative of the total shipment or order shall be selected at random for the final sample. These portions shall be so taken that minimum wastage of material is incurred, consistent with the required accuracy in sampling.

4.2 Quantities of material withdrawn for sampling shall comply with the requirements of the ASTM standard covering that particular material.

4.3 When portions are to be withdrawn from finished material, it is recommended that arrangements be made for excess length or amount of material to provide the necessary samples for inspection purposes.

4.4 Broken tension test specimens may be used conveniently in place of specially selected portions when such practice is agreeable to the purchaser.

5. Preparation of Sample

5.1 Samples of material too thin to be handled conveniently for machining (drilling, milling, etc.) may be prepared by clipping. Usually clippings would be limited to material

thinner than 1.02 mm (0.040 in.). Drillings, sawings, or millings shall be taken from material of heavier gage.

5.2 Rods, bars, plates, shapes, tubes, and pipes shall be sampled by milling the entire cross-section or by drilling entirely through the material at several points along their length. Sheets and strips may be folded once or more, by bringing the ends together and closing the bend; the portion may then be milled on the inside sheared edges or drilled entirely through the flat surface. For the lighter gages, several portions may be taken and stacked together before folding.

5.3 Equal weights of drillings, millings, sawings, or clippings shall be taken from each piece representing the lot of material, and these shall be combined into one sample and thoroughly mixed.

5.4 In some cases a complete section of the selected portions may be required for spectrometric examination. Sections may therefore be taken and properly marked before using the remainder of the portions for sampling operations; such sections may be supplied, together with the milled, drilled, or sawed sample, at the request of the purchaser.

6. Details of Sampling

6.1 The portions selected for the preparation of samples for chemical analysis, when testing for conformance with specifications, shall be clean and free from scale, dirt, oil, grease, etc. If necessary, the portions may be cleaned in ethyl ether or acetone, rinsed in ethanol, and dried before sampling. Scale and dirt may be removed by suitable mechanical or chemical treatment of the metal; if chemical methods of cleaning are used, however, such operations should not alter the metal surface in any way. When testing for pounds of metal contained, as in the sale of scrap, these provisions do not apply as a general rule.

6.2 The saw, drill, cutter or other tools used for sampling shall be thoroughly cleaned prior to use. Depth of cut, speed of cutting, etc., shall be so regulated that excessive heating and consequent oxidation of the sample shall be avoided.

6.3 The chips obtained by milling, drilling, etc., should be uniformly small in size, particularly when such samples are to be used for spectrometric analyses or for special chemical determinations requiring a relatively finely divided sample. Very fine dust-like material should be avoided. To facilitate the preparations of chips of satisfactory size, V-shape chip-breaking grooves may be formed in the cutting edge of the tool by grinding or other convenient means at approximately right angles to the cutting edge. The spacing of the grooves may vary depending upon the tool and would have to be determined for each application. The grooves in adjacent cutting edges should be staggered.

6.4 Lubricants are not required in the sampling of the majority of wrought metals and alloys. With certain refractory alloys, lubrication may be necessary either to avoid excessive oxidation of the sample, to reduce power requirements, or to save labor and time. In such cases, the use and choice of a satisfactory lubricant should be by mutual agreement between the manufacturer and the purchaser. Lubricants should be selected that do not alter or change the composition of the sample during contact. Lubricants should be completely removed as soon as possible after the sampling operation by the use of suitable solvents, such as ethyl ether or acetone, followed by a final rinse in ethanol and drying.

6.5 Drillings, millings, sawings, or clippings of nonmagnetic, nonferrous alloys shall be carefully treated with a strong magnet to remove any particles of iron introduced in taking the sample. Contamination of this kind should be avoided as much as possible by the use of suitable cutting tools, such as those made of carbide. In the case of some metals, an acid dip may be required if low iron is critical.

6.6 Drillings, millings, sawings, or clippings shall be carefully examined, and any foreign material accidentally introduced in taking the sample shall be removed.

7. Size of Sample and Storage

7.1 The prepared sample shall weigh three times the amount required for the analysis and shall be divided into three equal parts, each of which shall be placed in a package and sealed, one for the seller, one for the purchaser, and one for an umpire, if necessary.

7.2 Samples that are to be stored over long periods, or that are oxidized readily or otherwise altered in composition under varying atmospheric conditions, or that may become seriously contaminated in contact with paper or cardboard, should be kept in wide-mouth glass bottles of approximately 56-g (2-oz) capacity, having tight-fitting screw caps of metal or, preferably, plastic composition. In other cases tight, leak-proof, paper sample envelopes or cardboard cartons may be used to hold the sample.

8. Resampling

8.1 In the case of dissatisfaction, either party may require that the material be resampled in the presence of representatives of the seller and the purchaser. The thoroughly mixed sample shall be divided into three equal parts, each of which shall be placed in a package and sealed, one for the seller, one for the purchaser, and one for an umpire, if necessary.

9. Keywords

9.1 alloys; sampling; wrought nonferrous metals

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).