

Designation: E 560 - 01

Standard Practice for Extrapolating Reactor Vessel Surveillance Dosimetry Results, E 706(IC)¹

This standard is issued under the fixed designation E 560; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

LWR power plant safety analysis report and subsequent neutron exposure parameter calculations for the PV wall and critical welds need to be verified using modern codes and information from surveillance dosimetry. That is, the location of critical welds relative to the axial and azimuthal flux map should be taken into account, as well as changes in fuel loading during periods when surveillance capsules are exposed.

This practice is intended to be used together with other E 706 LWR Matrix Standards to provide estimates of the neutron exposure and exposure rate (together with uncertainties) at positions at the inner diameter and within the pressure vessel wall of a light water reactor. Also provided will be estimates of gamma-ray exposure and exposure rates to interpret dosimetry sensor photo-reaction and other gamma-ray induced effects. Information used to make these estimates is obtained from neutron-gamma transport calculations and from neutron and other sensor monitors located in surveillance positions on the core side of the vessel and in the cavity outside the vessel wall (1)². Benchmark field irradiations of similar monitors also provide valuable information used in the verification of the accuracy of the calculations (a type of cross section covariance and dosimetry monitor counting calibration) (1).

Knowledge of the time-dependent relationship between exposure parameters at surveillance locations and selected (r, θ, z) locations within the pressure vessel wall is required to allow determination of the time dependent radiation damage to the pressure vessel. The time dependency must be known to allow proper accounting for complications due to burn-up, as well as, changes in core loading configurations (2-5). An estimate of the uncertainty in the neutron exposure parameter values at selected (r, θ, z) points in the vessel wall (1) is also needed to place an upper bound on the allowable operating lifetime of the reactor vessel without remedial action (6-9). (See Guide E 509).

1. Scope

1.1 This practice covers analytical and analytical-experimental approaches that can be used to determine the variation in neutron exposure (fluence E > 1.0 MeV, dpa, etc.) and exposure rate and energy spectrum between surveillance locations and points in the pressure vessel wall. Procedures for reporting² the results of these analyses with assigned uncertainties are also suggested. This practice deals with the physics-dosimetry aspects of surveillance programs and must

be used in conjunction with other Matrix E 706 standards to provide extrapolations based on metallurgical damage correlations.

- 1.2 The physics-dosimetry relationships determined from this practice may be used to estimate pressure vessel damage through application of Practice E 693 and Guide E 900 standards, using fluence (E > 1.0 MeV), dpa, or damage function derived exposure parameters as independent exposure variables. Supporting the application of these standards is E 944, E 1018, E 1005, and E 854 standards, identified in 2.1.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

¹ This practice is under the jurisdiction of ASTM Committee E10 on Nuclear Technology and Applications and is the direct responsibility of Subcommittee E10.05 on Nuclear Radiation Metrology.

Current edition approved June 10, 2001. Published September 2001. Originally published as $E\,560-77$. Last previous edition $E\,560-84$ (1996).

² The boldface numbers in parentheses refer to the list of references appended to this practice.

2. Referenced Documents

- 2.1 ASTM Standards:
- C 859 Terminology Relating to Nuclear Materials³
- E 170 Terminology Relating to Radiation Measurements and Dosimetry⁴
- E 184 Practice for Effects of High-Energy Neutron Radiation on the Mechanical Properties of Metallic Materials, E706 (IB)^{4,5}
- E 185 Practice for Conducting Surveillance Tests for Light Water-Cooled Nuclear Power Reactor Vessels, E706 (IF)^{4,6}
- E 482 Guide for Application of Neutron Transport Methods for Reactor Vessel Surveillance, E706 (IID)^{4,6}
- E 509 Guide for In-Service Annealing of Light-Water Cooled Nuclear Reactor Vessels⁴
- E 636 Practice for Conducting Supplemental Surveillance Tests for Nuclear Power Reactor Vessels, E706 (IH)^{4,6}
- E 693 Practice for Characterizing Neutron Exposures in Iron and Low Alloy Steels in Terms of Displacements Per Atom (DPA), E706 (ID)^{4,6}
- E 706 Master Matrix for Light-Water Reactor Pressure Vessel Surveillance Standards, E706 (0)⁴
- E 844 Guide for Sensor Set Design and Irradiation for Reactor Surveillance, E706 (IIC)^{4,6}
- E 853 Practice for Analysis and Interpretation of Light-Water Reactor Surveillance Results, E706 (IA)^{4.6}
- E 854 Test Method for Application and Analysis of Solid State Track Recorder (SSTR) Monitors for Reactor Surveillance, E706 (IIIB)^{4,6}
- E 900 Guide for Predicting Neutron Radiation Damage to Reactor Vessel Materials, E706 (IIF)^{4.6}
- E 910 Test Method for Application and Analysis of Helium Accumulation Fluence Monitors for Reactor Vessel Surveillance, E706 (IIIC)^{4,6}
- E 944 Guide for Application of Spectrum Adjustment Methods in Reactor Surveillance E706 (IIA)⁴
- E 1005 Test Method for Application and Analysis of Radiometric Monitors for Reactor Vessel Surveillance, E706 (IIIA)⁴
- E 1006 Practice for Analysis and Interpretation of Physics Dosimetry Results for Test Reactors, E706 (II)⁴
- E 1018 Guide for Application of the ASTM-evaluated Cross Section Data Files, E706 (IIB)⁴
- E 1035 Practice for Determining Radiation Exposure for Nuclear Reactor Vessel Support Structures, E706 (IG)⁴
- E 2005 Guide for the Benchmark Testing of Reactor Dosimetry in Standard and Reference Neutron Fields, E706 (IIE-1)^{2.3}
- E 2006 Guide for the Benchmark Testing of LWR Calculations, E706 (IIE-2)^{2,3}
- 2.2 American Society of Mechanical Engineers Standard: Boiler and Pressure Vessel Code, Sections III and XI⁷
- 2.3 Nuclear Regulatory Document:

³ Annual Book of ASTM Standards, Vol 12.01.

- ⁴ Annual Book of ASTM Standards, Vol 12.02.
- ⁵ For standards that are in the draft stage and have not received an ASTM designation, see Section 5 as well as Figs. 1 and 2 of Matrix E706.
- ⁶ The reference in parentheses refers to Section 5 as well as Figs. 1 and 2 of Matrix E706.

Code of Federal Regulations, Chapter 10, Part 50, Appendixes G and H⁸

3. Significance and Use

- 3.1 Regulatory Requirements—The Code of Federal Regulations (10CRF Part 50, Appendix H) requires the implementation of a reactor vessel materials surveillance program for all operating LWR's (10). The purpose of the program is to (1) monitor changes in the fracture toughness properties of ferritic materials in the reactor vessel beltline region resulting from exposure to neutron irradiation and the thermal environment, and (2) make use of the data obtained from the surveillance program to determine the conditions under which the vessel can be operated with adequate margins of safety throughout its service life. Practice E 185, derived mechanical property data, and (r, θ, z) physics-dosimetry data (derived from the calculations and cavity and surveillance capsule measurements (1) using Matrix E 706 physics-dosimetry standards) can be used together with information in Guide E 900 and Refs. 4, 11-18 to provide a relation between property degradation and neutron exposure, commonly called a "trend curve." To obtain this trend curve at all points in the pressure vessel wall requires that the selected trend curve be used together with the appropriate $(r \theta, z)$ neutron field information derived by use of this practice to accomplish the necessary interpolations and extrapolations in space and time.
- 3.2 Neutron Field Characterization—The tasks required to satisfy the second part of the objective of 3.1 are complex and are summarized in Practice E 853. In doing this, it is necessary to describe the neutron field at selected (r, θ, z) points within the pressure vessel wall. The description can be either time dependent or time averaged over the reactor service period of interest. This description can only be obtained by combining neutron transport calculations with cavity and surveillance capsule measurements, benchmark irradiations of dosimeter sensor materials, and a knowledge of the core power distribution, including either the time dependence, or time averaged. Because core power distribution may change with time, the cavity or surveillance capsule measurement obtained early in plant life may not be representative of long-term reactor operation. Therefore, a simple normalization of neutron transport calculations to dosimetry data from a given capsule is unlikely to give a satisfactory solution to the problem over the full reactor lifetime. Guide E 482 and Guide E 944 standards provide detailed information related to the characterization of the neutron field for BWR and PWR power plants.
- 3.3 Fracture Mechanics Analysis—Currently, operating limitations for normal heat up and cool down transient imposed on the reactor pressure vessel are based on the fracture mechanics techniques outlined in the ASME Boiler and Pressure Vessel Code. This code requires the assumption of the presence of a surface flaw of depth equal to one fourth of the pressure vessel thickness. In addition, the fracture mechanics analysis of accident-induced transients (Pressurized Thermal Shock, (PTS)) may involve evaluating the effect of flaws of varying depth within the vessel wall (4). Thus, information is required regarding the distribution of neutron exposure and the corresponding radiation damage within the pressure vessel, both in space and time (4). In this regard, Practice E 185

standard provides guidelines for designing a minimum surveillance program, selecting materials, and evaluating metallurgical specimen test results for BWR and PWR power plants.

3.4 Neutron Spectral Effects and DPA—Analysis of the neutron fields of operating power reactors has shown that the neutron spectral shape changes with radial depth into the pressure vessel wall (2, 3). The ratio of dpa/ ϕt (E > 1.0 MeV) changes by factors of the order of 2.0/1.0 in traversing from the inner to the outer radius. Although dpa, since it includes a more detailed modeling of the displacement phenomenon, should theoretically provide a better correlation with property degradation than fluence (E > 1.0 MeV) (1, 19), this topic is still controversial and the available experimental data does not provide clear guidence (19, 42). Thus it is recommended to calculate and report both quantities; see Practice E 853 and Practice E 693.

3.5 In-Vessel Surveillance Program:

3.5.1 The neutron dosimetry monitors used in reactor vessel surveillance capsules provide measurements of the neutron fluence and fluence rate at single points within the reactor and near the vessel wall; that is, at the surveillance capsule locations (1). In actual practice, the surveillance capsules may be located within the reactor at an azimuthal position that differs from that associated with the maximum neutron exposure (or that differs from the azimuthal and axial location of the assumed flaw); and at a radial position a few centimetres or more from the flaw and pressure vessel wall (4, 5). Although the surveillance capsule dosimetry does provide points for normalization of the neutron physics transport calculations, it is still necesary to use analytical methods that provide an accurate representation of the spatial variation of the neutron fluence, see Guide E 482.

3.5.2 The neutron fluence calculation on the PV inner surface can be further verified by means of the "scratch sampling" neutron fluence measurement method. During the reactor shut down periods, small samples (50–100 mg) can be taken from the PV inner steel plating. From the measured ⁵⁴Mn, ⁵⁸Co, and eventually ^{93m}Nb activities, the fast neutron fluence distribution and its maximum on the PV inner surface can be determined. By comparison of these data to the dosimetry data of the surveillance capsules, the lead factor can also be obtained.

3.6 Ex-Vessel Surveillance Program—Calculations of neutron fields in commercial reactors show that the neutron exposure (dpa) at the inner diameter of the pressure vessel varies by factors of the order of 3.0/1.0 for various azimuthal positions (2, 3). Dosimetry monitors in the cavity outside the pressure vessel are a useful tool, therefore, in determining the accuracy of the neutron field calculations at points inside the pressure vessel wall. Practice E 853 standard recommends the use of ex-vessel cavity dosimetry measurements for verification of the physics transport calculations. The status of benchmark field and power reactor applications as well as studies of this approach are discussed in Refs 1, 18-36.

4. Analytical Procedures

4.1 *Basic Approach*—Several auxiliary ASTM practices cover various aspects of the extrapolation problem (see 2.1). The basic approach is that a benchmarked Guide E 482,

transport calculation is to be used to supply the neutron field information at the (r, θ, z) points in the pressure vessel wall where property deterioration information will be calculated using Guide E 900, or other trend curves (4, 11-18). 4The dosimetry information obtained from cavity and surveillance capsule measurements is to be used to adjust the transport results and ensure that the transport calculation is valid. The adjustments are to be accomplished using the guidelines presented in Guide E 944. Dosimetry from monitors in the cavity and surveillance capsules will be used in establishing uncertainties for the calculated neutron field at selected (r, θ, z) positions in the pressure vessel wall. Time dependence of the core power distribution (due to burnup within a given cycle, or due to variations in cycle to cycle loading), surveillance capsule perturbation effects, and dosimetry monitor experimental effects must be recognized as complications, and these effects must be accounted for in the calculation and adjustment methods chosen (1-6, 11).

4.2 Spatial Extrapolations:

4.2.1 Transport Codes—In general, a two dimensional [(r, θ), (x, y)] transport code is needed for the calculation of the neutron and gamma fields in the region from the core to the interior of the biological shield beyond the pressure vessel. Guide E 482 should be followed for the calculations and Guide E 944 for measured dosimetry adjustments. The mesh should be fine enough in all regions of importance so that diamond difference breakdown difficulties are avoided in a discrete ordinate method. Methods of ensuring that the mesh is sufficiently fine are the province of Guide E 482. If cavity dosimeter measurement results are used, the modeling in the cavity and external shield should be adequate to provide usable calculations for the neutron field in the cavity region. This requires an attention to mesh size in the ex-vessel region and an accurate representation of the chemical makeup of the external shield. Adequacy of methods of calculation and adjustments for the cavity region are also the province of Guide E 482 and Guide E 944.

4.2.1.1 *Benchmarking*—It is not the purpose of this practice to dictate the type of transport calculation to be used in the region between the core and the outer radius of the pressure vessel or the adjustment procedures, but any such calculations or adjustment procedures should be adequately benchmarked by a test calculation of well defined problems (for example, PCA Blind Test (21), VENUS (32), NESDIP (33), BWR (25, 26), and PWR (1, 20, 27-30)). For further details see Guide E 2006 and Guide E 944.

4.2.1.2 *Calculation Steps*—With reference to Practice E 853, the steps to be taken in the overall calculations are as follow:

4.2.1.3 *Power Distribution*—As discussed in Practice E 853, obtain a valid time averaged core power distribution using a diffusion calculation, or a transport calculation, but in either case obtain experimental verification of the accuracy of the results (20, 21, 32). A time dependent approach is also acceptable, with appropriate documented procedures for the remaining parts of the extrapolation.

4.2.1.4 Ex-Core Regions—Perform a transport calculation for the neutron field in all ex-core regions, using adequate

modeling of the surveillance capsules, and adequate modeling of the ex-vessel region (adequacy depending on whether or not ex-vessel dosimetry has been used in the verification of the extrapolation). The neutron balance should be checked in all regions to make sure the calculation has converged. Further, the transport calculation should be benchmarked following requirements of Guide E 482.

4.2.2 Dosimetry Sensor Analysis—For analysis of any given set of cavity or surveillance capsule dosimetry sensors, the integral reactions or reaction rates of the individual sensors, or both, should be calculated, using the results of the transport calculation. The measurement and analysis procedures for individual Radiometric Monitors (RM), Solid State Track Recorders (SSTR), Helium Accumulation Fluence Monitors (HAFM), and Damage Monitors (DM) should be benchmarked for each sensor type, using reference neutron fields (for example, NIST or MOL U-235 fission spectrum cavities), see Guide E 844, E 1018, Test Method E 1005, E 854, and E 910 (See 2.1). If the calculated and experimental integral results (C/E ratios) agree to within the required accuracy (± 5 to 15 %, 1σ being the best attainable, see Ref 21) expected from the benchmark calibration of the transport code, the transport calculation may be used directly to calculate the neutron field at all (r, θ, z) points in the pressure vessel wall. If the C/E ratios do not agree within acceptable accuracy limits, a physicsdosimetry adjustment code analysis should be performed as outlined in 4.2.3.

4.2.3 Physics-Dosimetry Adjustment Code Analysis—Guide E 944 should be used to combine the transport calculation with the dosimeter results. Guide E 944 adjustment procedure should be used to indicate whether the dosimeter measurements and associated uncertainties are consistent with the transport calculation and with uncertainties implied from benchmark tests of the transport code (PCA, VENUS, NESDIP, and an appropriate Commercial BWR or PWR; see Refs 1, 20, 21, 25-30). Having established the required consistency, the adjusted transport code results may be used to calculate the neutron field at all points in the pressure vessel wall with the uncertainty estimates derived from the application of the adjustment codes. Direct use of the transport code results with appropriate bias factors and uncertainties is another acceptable approach.

- 4.2.3.1 Surveillance Capsule Results—If the calculated neutron field at the surveillance capsule is inconsistent with the experimental dosimetry results, an attempt should be made to uncover and correct errors in order to obtain consistency. Particular attention will be required to sensor monitor correction factors for perturbation, photo-reaction, impurity, burn-in, and other effects.
- 4.2.3.2 If the transport result indicates a higher flux than that indicated by the dosimetry, the transport result can be used for extrapolation purposes, but with an appropriate increase in the stated uncertainty for the results.
- 4.2.3.3 If the transport calculation indicates a lower flux than that which would be consistent with the dosimetry (taking account of the uncertainties in both the dosimetry and transport results) and if the discrepancy cannot be resolved, then the transport results should be scaled up proportionally to obtain

agreement, following which the transport results are to be used for extrapolation purposes. In this case, appropriate increases should be made in the stated uncertainties of the final result, and documented logic should be provided to defend the assigned uncertainties.

4.2.4 Ex-Vessel Surveillance Results—Ex-vessel cavity dosimetry is to be treated in the same manner as surveillance capsule dosimetry, but care must be exercised to ensure that the physics calculation modeling is adequate and includes the proper modeling of the cavity surveillance capsule and any covers, as well as any nearby vessel support members.

4.2.4.1 The biological shield is accurately modeled.

4.2.4.2 In the final calculation of the neutron and gamma field at any point in the vessel wall, proper statistical weight should be given to ex-vessel dosimetry, taking account of modeling problems as well as the possibility that a larger logarithmic extrapolation or interpolation in absolute flux value exists from ex-vessel positions to a ½ T location when compared to the extrapolation or interpolation from an internal surveillance capsule position to a ½ T location.

4.2.5 Power Plant Dimensions—In all calculations, as-built dimensions should be used. If they are unavailable, documented logic should be presented to defend the dimensions used, and the uncertainty in the final results should reflect the added uncertainty. It should be noted that dpa declines $\sim 10~\%/$ cm of radial travel, in water, and deviations of $\sim 3~$ cm between design dimensions and as-built dimensions have been observed in commercial reactors.

4.3 *Time Extrapolations*—In the case where a time averaged core loading has been used to define the neutron source term, the fluence or dpa in future years is estimated by multiplying by the expected integrated time at full power. Existing problems associated with time extrapolations (for example, saturation effects and differences in the slope of trend curves for different ferritic steels) are addressed elsewhere. The reader is referred to Refs 1, 6, 11-18, 23, and Guide E 900 for more information on these subjects.

5. Report and Bias of Results

- 5.1 As a minimum, the documentation of results should include the following information:
- 5.1.1 A description of the analytical technique used, including a listing of pertinent input parameters that may affect the bias of the calculation. For example, if the discrete ordinates approach is used, specify or reference the cross-section preparation procedures, energy group structure, spatial mesh, $S_{\rm n}$ order, and $P_{\rm 1}$ order.
- 5.1.2 Information indicating the bias of the analytical approach in steel-water systems, including the details of benchmark calculations used to validate the procedures, and data and the bias attained in the benchmark tests.
- 5.1.3 The calculated total, thermal, epi-thermal (also known as epi-cadmium flux) E>0.1 MeV, E>1.0 MeV neutron flux-fluence values, and energy spectrum at the surveillance capsule, and any ex-vessel dosimetry locations. Also calculated values of dpa/s and dpa at the same locations.
- 5.1.3.1 The location of peak flux-fluence points on the surface and in the interior of the vessel wall are calculated values that are required for all the above exposure and



exposure rate parameters, except for the thermal and epithermal fluxes, which generally can be best determined by dosimetry measurements. For some damage analysis studies, all of the above information is needed (36-41).

- 5.1.3.2 At dosimetry measurement locations, gamma ray flux-fluence should be estimated to the bias required to make necessary photo reaction corrections. Similarly, gamma field parameters should be estimated to whatever bias is needed to allow temperature corrections for radiation damage in PV steels and in surveillance capsule mechanical property specimens.
- 5.1.4 Methods and pertinent parameters used in the physics-dosimetry analysis must be documented or referenced, includ-

ing appropriate tabulations of all measured individual sensor results and uncertainties. Methods of extrapolation and interpolation must specifically be delineated.

5.1.5 Details must be given relative to the methods used to assign uncertainties for calculated values of neutron flux, fluence, dpa/s, and dpa. Uncertainties for calculated values for total, thermal, E>0.1 MeV, and E>1.0 MeV neutron fluxes and fluences should be provided.

6. Keywords

6.1 damage correlations; dosimetry; dpa; exposure parameters; pressure vessel; surveillance

REFERENCES

- (1) McElroy, W. N., et al, "LWR Pressure Vessel Surveillance Dosimetry Improvement Program: 1982 Annual Report," NUREG/CR-2345, Vol 3 and HEDL-TME 82-20, Hanford Engineering Development Laboratory, Richland, WA, January 1983.
- (2) Guthrie, G. L., McElroy, W. N., and Anderson, S. L., "Investigation of Effects of Reactor Core Loadings on PV Neutron Exposure," LWR-PV-SDIP Quarterly Progress Report, October–December 1981, NUREG/CR-2345, Vol 4 and HEDL-TME 81-36, NRC, Washington, DC, September 1982.
- (3) Guthrie, G. L., McElroy, W. N., and Anderson, S. L., "A Preliminary Study of the Use of Fuel Management Techniques for Slowing Pressure Vessel Embrittlement," *Proceedings of the 4th ASTM Eura*tom Symposium on Reactor Dosimetry, NUREG/CP-0029, NRC, Washington, DC, July 1982, p. 111.
- (4) Dircks, W. J., et al, "Pressurized Thermal Shock (PTS): Policy Issue," SECY-82-465, Nuclear Regulatory Commission, Nov. 23, 1982.
- (5) Aronson, A. L., et al, "Evaluation of Methods for Reducing Pressure Vessel Fluence," BNL-NUREG-32876, Brookhaven National Laboratory, March 1983.
- (6) Tagart, S. W., et al, "Structural Mechanics Program: Progress in 1981," Special Report, NP-2705-SR, Electric Power Research Institute, Palo Alto, CA, October 1982.
- (7) Marston, T. U., and Mager, T. R., "ERPI Thermal Anneal Program RP1021-1," *Report to ASME Section XI Subcommittee on Repairs and Replacements and to NRC*, February 1982.
- (8) Mager, T. R., et al, "Feasability of and Methodology for Thermal Annealing of Embrittled Reactor Vessel: Detailed Technical Description of the Work," *Final Report*, EPRI NP 2712, Vol 1, Project 1021-1, Electric Power Research Institute, Palo Alto, CA, January 1983.
- (9) Mager, T. R., et al, "Feasability of and Methodology for Thermal Annealing of Embrittled Reactor Vessel: Detailed Technical Description of the Work," *Final Report*, EPRI NP 2712, Vol 2, Project 1021-1, Electric Power Research Institute, Palo Alto, CA, November 1982.
- (10) "Domestic Licensing of Production & Utilization Facilities," Code of Federal Regulations, 10CFR50; "General Design Criteria for Nuclear Power Plants," Application A; "Fracture Toughness Requirements," Application G; "Reactor Vessel Material Surveillance Program Requirements," Application H; GPO, Washington, DC, Current Edition.
- (11) Schneider, W., editor, "CAPRICE 79: Correlation Accuracy in Pressure Vessel Steel as Reactor Component Investigation of Change of Material Properties with Exposure Data," Proceedings of the IAEA Technical Committee Meeting, J;auulich, Federal Republic of Germany, Jul-CONF-37, IAEA, Vienna, Austria, 1980.
- (12) Randall, P. N., "The Status of Trend Curves and Surveillance Results in USNRC Regulatory Activities," *Proceedings of IAEA Specialists' Meeting*, Vienna, Austria, Oct. 20, 1981.
- (13) Randall, P. N., "Status of Regulatory Demands in the US on the

- Application of Pressure Vessel Dosimetry," *Proceedings of 4th ASTM-Euratom Symposium on Reactor Dosimetry*, NUREG/CP-0029, NRC, Washington, DC, July 1982, p. 1011.
- (14) Regulatory Guide 1.99, "Effects of Residual Elements on Predicted Radiation Damage to Reactor Vessel Materials," Rev. 1, NRC, Washington, DC, April 1977.
- (15) McConnel, P., et al, *Irradiated Nuclear Pressure Vessel Steel Data Base*, NP-2428, EPRI, Palo Alto, CA, June 1982.
- (16) Varsiks, J. D., "Evaluation of Irradiation Response of Reactor Pressure Vessel Materials," *Final Report*, EPRI NP 2720, Project 1553-1, Electric Power Research Institute, Palo Alto, CA, November 1982.
- (17) Guthrie, G. L., "Development of Trend Curve Formulas Using Surveillance Data," LWR-PV-SDIP Quarterly Progress Report, January—March 1982, NUREG/CR-2805, Vol 1, HEDL-TME 82-18, HEDL-3, HEDL, Richland, WA, December 1982.
- (18) Guthrie, G. L., "Development of Trend Curve Formulas Using Surveillance Data," LWR-PV-SDIP Quarterly Progress Report, April–June 1982, NUREG/CR-2805, Vol 2, HEDL-TME 82-19, HEDL-3, HEDL, Richland, WA, December 1982.
- (19) Odette, G. R., "Neutron Exposure Dependence of the Embrittlement of Reactor Pressure Vessel Steels: Correlation Models and Parameters," *Conference Report*, Schneider, W., editor, CAPRICE 79, September 1979, Jülich, Germany, July 1979, CONF-37, ISSN0344-5798, May 1980, p. 310.
- (20) Fabry, A., et al, "Improvement of LWR Pressure Vessel Steel Embrittlement Surveillance: Progress Report on Belgian Activities in Cooperation with the USNRC and other R and D Programs," Proceedings of 4th ASTM-Euratom Symposium on Reactor Dosimetry, NUREG/CP-0029, NRC, Washington, DC, July 1982, p. 45.
- (21) McElroy, W. N., editor, LWR-PV-SDIP: PCA Experiments and Blind Test, NUREG/CR-1861, HEDL-TME 80-87, HEDL, Richland, WA, July 1981.
- (22) Fabry, A., et al, "The Mol Cavity Fission Spectrum Standard Neutron Field and Its Applications," *LWR-PV-SDIP: PCA Experiments and Blind Test*, Ref 21, p. 655.
- (23) Austin, M., "Sense of Direction: An Observation of Trends in Materials Dosimetry in the United Kindgom," LWR-PV-SDIP: PCA Experiments and Blind Test, p. 461.
- (24) Grundl, J. A., et al, "NRC-EPRI Studies of Pressure-Vessel-Cavity Neutron Fields," *Presented at NRC 9th WRSR Information Meeting*, Oct. 26–30, 1981, NBS, Washington, DC, 1981.
- (25) Shaw, R. A., "Brown's Ferry and Arkansas Nuclear One Pressure Vessel Neutron Fluence Benchmarks," *Proceedings of 4th ASTM-Euratom Symposium on Reactor Dosimetry*, NUREG/CP-0029, NRC, Washington, DC, July 1982, p. 513.
- (26) Martin, G. C., "Brown's Ferry Unit-3 Cavity Neutron Spectral

- Analysis," *Proceedings of the 4th ASTM-Euratom Symposium on Reactor Dosimetry*, p. 555, and EPRI NP-1997, EPRI, Palo Alto, CA, August 1981.
- (27) Brandon, W. E., et al, "Neutron Dosimetry in the Pressure Vessel Cavity of Two Pressurized Water Reactors," *Proceedings of the 4th ASTM-Euratom Symposium on Reactor Dosimetry*, p. 533.
- (28) Tsoulfanidis, N., et al, "Calculation of Neutron Spectra at the Pressure Vessel and Cavity of a PWR," *Proceedings of the 4th ASTM-Euratom Symposium on Reactor Dosimetry*, July 1982, p. 519.
- (29) Petilli, M., "A New Analysis of the Experiment for Measurement of φ ≥ 1 MeV in Pressure Vessel Cavity of US Light Water Power Reactor Arkansas," Proceedings of the 4th ASTM-Euratom Symposium on Reactor Dosimetry, p. 545.
- (30) Selph, W. E., and MacKenzie, J., Passive Neutron Dosimetry for Measurements at the McGuire Reactor, EPRI NP-2570, EPRI, Palo Alto, CA, September 1982.
- (31) Maerker, R. E., Wagshal, J. J., and Broadhead, B. L., Development and Demonstration of an Advanced Methodology for LWR Dosimetry Applications, EPRI-NP 2188, Interim Report, EPRI, Palo Alto, CA, 1981.
- (32) Fabry, A., et al, "VENUS Dosimetry Program," Proceedings of NRC 10th WRSR Information Meeting, NBS, Washington, DC, Oct. 12–15, 1982.
- (33) Austin, M., "Description and Status of the NESTOR Dosimetry Improvement Programme (NESDIP)," *Proceedings of NRC 10th WRSR Information Meeting*, NBS, Washington, DC, Oct. 12–15, 1982.
- (34) Martin, G. C., *BR3 Benchmark Neutron Field Reaction Rate Measurements*, NEDO-22168, 82NEDO72, Class 1, General Electric Co., San Jose, CA, June 1982.

- (35) Hopkins, W. C., "Suggested Approach for Fracture-Safe RPV Support Structure Design in Neutron Environments," *ANS Transactions Vol 30*, November 1978, p. 187.
- (36) Simons, R. L., "Re-evaluation of Ferritic Steel DBTT Data Used in Damage Function Analysis," NUREG/CR-0720, HEDL-TME 79-18, HEDL-15, July 1980. Condensed version published in *Proceedings of* the Third International ASTM-Euratom Symposium on Reactor Dosimetry, Ispra, Italy, EUR6813, Vol 1, Oct. 1–5, 1979, p. 178, European Atomic Energy Committee, 1980.
- (37) McElroy, W. N., Dahl Jr., R. E., and Serpan Jr., C. Z., "Damage Functions and Data Correlation," *Nuclear Applications and Technol*ogy 7, December 1969.
- (38) Serpan Jr., C. Z., and McElroy, W. N., "Elevated-Temperature Damage Functions for Neutron Embrittlement in Pressure Vessel Steels," Nuclear Technology 13, February 1972.
- (39) Serpan Jr., C. Z., "Damage Function Analysis of Neutron-Induced Embrittlement in A302B Steel at 550°F (288°C)," Effects of Radiation on Substructure and Mechanical Properties of Metals and Alloys, ASTM STP 529, 1973, pp. 92–106.
- (40) Serpan Jr., C. Z., "Engineering Damage Cross Sections for Neutron Embrittlement of A302B Pressure Vessel Steel," *Nuclear Engineer Design* 33, 1975, pp. 19–29.
- (41) Serpan Jr., C. Z., and McElroy, W. N., "Damage Function Analysis of Neutron Energy and Spectrum Effects Upon the Radiation Embrittlement of Steels," NRL Report 6925, July 1969.
- (42) Alberman, A., Carcreff, H., Ermont, G., Soulat, P., Beretz, D., Pichon, C., and Brillaud, C., "Neutron Spectrum Effect and Damage Analysis of Pressure Vessel Steels Irradiations," *Proceedings of the 9th International Symposium on Reactor Dosimetry*, H. A. Abderrahim, P. D'hondt, B. Osmera, Eds., World Scientific, Singapore, 1998.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).