



Standard Test Method for Effect of Impact on Bonding of Sprayed Fire-Resistive Material Applied to Structural Members¹

This standard is issued under the fixed designation E760/E760M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^{ε1} NOTE—Designation was changed to dual and units information was corrected editorially in August 2015.

1. Scope

1.1 This test method covers a procedure for determining the effect of impact loading on the bonding of sprayed fire-resistive material (SFRM) applied to the underside of steel floor deck. These materials include sprayed fibrous and cementitious materials applied directly in contact with the structural members. The test method is applicable only to laboratory procedures.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[E84 Test Method for Surface Burning Characteristics of Building Materials](#)

[E119 Test Methods for Fire Tests of Building Construction and Materials](#)

[E605/E605M Test Methods for Thickness and Density of Sprayed Fire-Resistive Material \(SFRM\) Applied to Structural Members](#)

¹ This test method is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.21 on Serviceability.

Current edition approved Aug. 1, 2015. Published August 2015. Originally approved in 1980. Last previous edition approved in 2011 as E760 – 92 (2011). DOI: 10.1520/E0760_E0760M-92R15E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E695 Test Method of Measuring Relative Resistance of Wall, Floor, and Roof Construction to Impact Loading](#)

3. Summary of Test Method

3.1 In this test method, a cellular steel deck with a concrete topping sprayed with fire-resistive material is subjected to a leather bag drop impact while supported horizontally at its ends.

4. Significance and Use

4.1 The intent of this test method is to determine a property of SFRM that may be used to provide an indication of its in-place serviceability. Satisfactory performance of SFRM applied to structural members and assemblies depends upon its ability to withstand the various influences that may occur during construction and during the life of the structure, as well as upon its satisfactory performance under fire conditions.

4.2 The test method measures the behavior of SFRM when the floor construction to which it is applied is subjected to shock loading and evaluates adhesion and resistance to spalling, cracking, and delamination. It is an indication of the ability of SFRM to remain in place and resist removal during anticipated service conditions.

5. Apparatus

5.1 *Supports*—Rigid base to provide at least 50 mm [2 in.] bearing and a clear span between supports of at least 3 m [10 ft].

5.2 *Impact Instrument*—A lead shot- or steel shot-filled leather bag weighing 27.2 kg [60 lb] and equipped with a leather hoisting strap, both as described in Test Method [E695](#).

5.3 *Rule*—To measure the height of drop (1.2 m [4 ft]) with an accuracy of 12.8 mm [$\frac{1}{2}$ in.].

6. Materials

6.1 The test specimen shall be a deck assembly consisting of cellular steel deck and a concrete topping. The cellular steel deck shall be of the noncomposite type, nominal 40 mm [$\frac{1}{2}$

in.] deep, 600 mm [24 in.] wide, by 3600 mm [2 ft] long, consisting of a 1.5-mm [0.060-in.] thick galvanized or painted steel fluted top section and 1.2-mm [0.048-in.] galvanized steel flat bottom section welded together to form four cells 150 mm [6 in.] on center.

6.2 The concrete shall be nominal 20 MPa [3000 psi], and 64 mm [2½ in.] deep as measured from the top plane to the steel decking.

6.3 This test method requires the application of SFRM in accordance with manufacturers' published instructions. The apparatus, materials, and procedures used to apply the SFRM for this test shall be representative of application in the field.

6.4 The density of the prepared sample shall be similar to the density tested and reported during the Test Methods **E119** and Test Method **E84** fire exposure tests or as required by the sponsor of the test.

6.5 Determine the density and thickness of each of the laboratory-prepared specimens. Report in accordance with Test Methods **E605/E605M**.

7. Test Specimen

7.1 Laboratory Tests:

7.1.1 Apply the SFRM to the underside of the steel deck no sooner than seven days after the concrete has been placed. Do not apply the SFRM to the area 330 mm [13 in.] in from each end of the specimen, in order to permit the steel deck to bear directly on the supports.

7.1.2 Condition the prepared specimen for a period of not less than one week at ambient temperature and humidity conditions (not less than 4.4°C [40°F]).

7.1.3 Condition the specimen for a period sufficient to be considered dry in accordance with the manufacturers' recommendation.

8. Procedure

8.1 Place the specimen on the test supports with the SFRM as the lower surface and the concrete as the upper surface.

8.2 Hoist the bag to a height of 1.2 m [4 ft] as measured from the upper face of the specimen to the bottom of the bag.

8.3 Apply an impact load once to the middle of the upper face of the specimen by dropping the leather bag.

9. Report

9.1 Report the following information:

9.1.1 A complete description of the overall specimen, including the final physical condition and appearance of the SFRM after impact,

9.1.2 Any spalling, delamination, cracking, and

9.1.3 Thickness in millimetres [or inches] and the density of the SFRM in kilograms per cubic metre [or pounds per cubic foot].

10. Precision and Bias

10.1 No statement is made about either precision or bias of this test method since the results merely describe qualitatively the physical condition of the test specimen after exposure to the specified procedure.

11. Keywords

11.1 impact loading; sprayed fire-resistive material; steel floor deck

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/