



Standard Specification for Structural Film Adhesives for Honeycomb Sandwich Panels¹

This standard is issued under the fixed designation E865; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers film adhesives for bonding of honeycomb sandwich panels. The adhesives are used for new production or depot repair. The adhesives shall be suitable for forming bonds that can withstand long exposures to temperatures from -55 to 93°C (-67 to 200°F) and also withstand the combinations of stress, temperature, and relative humidity expected to be encountered in service. The adhesives shall be used for bonding aluminum alloy facing to nonmetallic core, edge attachments, and other components of a sandwich panel.

1.2 The values stated in SI units are to be regarded as the standard where only SI units are given or where SI units are given first followed by inch-pound units; where inch-pound units are given first followed by SI units, the inch-pound units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- [B117 Practice for Operating Salt Spray \(Fog\) Apparatus](#)
- [B209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate](#)
- [C297/C297M Test Method for Flatwise Tensile Strength of Sandwich Constructions](#)
- [D1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading \(Metal-to-Metal\)](#)
- [D1781 Test Method for Climbing Drum Peel for Adhesives](#)

¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved Nov. 1, 2012. Published December 2012. Originally approved in 1982. Last previous edition approved in 2008 as E865 – 08. DOI: 10.1520/E0865-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [D2919 Test Method for Determining Durability of Adhesive Joints Stressed in Shear by Tension Loading](#)
 - [D3167 Test Method for Floating Roller Peel Resistance of Adhesives](#)
 - [E631 Terminology of Building Constructions](#)
 - [E864 Practice for Surface Preparation of Aluminum Alloys to Be Adhesively Bonded in Honeycomb Shelter Panels](#)
 - [E866 Specification for Corrosion-Inhibiting Adhesive Primer for Aluminum Alloys to Be Adhesively Bonded in Honeycomb Shelter Panels](#)
 - [E874 Practice for Adhesive Bonding of Aluminum Facings to Nonmetallic Honeycomb Core for Shelter Panels](#)
 - [E1091 Specification for Nonmetallic Honeycomb Core for Use in Shelter Panels](#)
 - [E1749 Terminology Relating to Rigid Wall Relocatable Shelters](#)
 - [E1826 Specification for Low Volatile Organic Compound \(VOC\) Corrosion-Inhibiting Adhesive Primer for Aluminum Alloys to Be Adhesively Bonded](#)
- 2.2 *Federal Specifications:*³
- [QQ-A-250/8d Aluminum Alloy 5052H34, Plate and Sheet](#)
 - [QQ-A-250/11d Aluminum Alloy 6061T6, Plate and Sheet](#)

NOTE 1—Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific purchases shall be obtained from the purchaser or as directed by his contracting officer.

3. Terminology

3.1 *Definitions*—See Terminologies E631 and E1749 for definitions of general terms used in this practice.

4. Ordering Information

4.1 *Procurement Documents*—Purchasers shall select any of the desired options offered herein and the procurement documents shall specify the following:

- 4.1.1 Title, number, and date of this specification;
- 4.1.2 Adhesive type and code number;
- 4.1.3 Amounts and unit quantities of adhesives required;
- 4.1.4 Length, width, and film weight of adhesive;
- 4.1.5 Curing conditions;

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

- 4.1.6 Level of packaging and packing required; and
 4.1.7 Whether or not qualification (see 4.2) is necessary.

4.2 *Qualification*—In the case of adhesives for which the purchaser requires qualification, comprehensive testing in accordance with Section 6 shall be performed and documented in a test report.

5. Requirements

5.1 *Material*—The adhesive shall be thermosetting and, when tested using the tests described in Section 6, shall meet the strength and durability requirements of this specification. The adhesive shall not have a deleterious effect on the metal surfaces being bonded over the range of temperatures at which the adhesives will be used.

5.2 *Form and Film Weight*—The adhesive shall be film form and shall consist either entirely of adhesive or of a carrier impregnated with adhesive. The film weight shall be within the range specified in Table 1.

5.3 *Appearance*—The adhesive film shall be uniform in appearance. It shall be of a uniform coating that is free of streaks and color variations.

5.4 *Qualification*—At the option of the purchaser, the adhesive may be required to be a product (see 7.3) for listing on the applicable qualified products list at the time set for opening of bids. The qualification shall only apply to the formulation on which qualification tests have been made. Any changes by the manufacturer, such as the adding of fillers, changing the carrier, changing the method of manufacture, or changing the mass per unit area, shall be cause for designating the adhesive as a new product. The new product shall be given a new code number and shall not be approved until it has been shown to meet the requirements of the specification.

5.5 Working Characteristics:

5.5.1 *Application*—The adhesive shall be suitable for application to metal facings and core materials in accordance with the manufacturer’s instructions at temperatures between 18 and 30°C (65 and 85°F) and at relative humidities of up to 50 %.

5.5.2 *Curing*—The time, temperature, and pressure used to cure the adhesive shall be within the range specified herein.

5.5.2.1 *Curing Time and Temperature*—The adhesive shall meet the requirements of this specification when cured for not longer than 1 h at a bond line temperature not exceeding 145°C (293°F).

5.5.2.2 *Curing Pressure*—In the preparation of specimens fabricated for qualification, the pressure required for curing the adhesive shall not be less than 140 kPa (20 psi) nor more than 350 kPa (50 psi).

5.6 *Storage Life*—The adhesive manufacturer shall determine the maximum temperature and the storage period at this temperature (from date of manufacture) for which the adhesive, when stored in airtight containers or wrapped in suitable vapor barriers, will retain its ability to meet the strength requirements specified in Table 1. These storage conditions shall be stated in the instruction sheet (see 7.3.1.1).

5.7 *Mechanical Properties*—The average mechanical properties of the adhesive shall meet the requirements of Table 1.

6. Test Methods

6.1 *Qualification Tests*—For qualification, the adhesive shall be tested using the tests described in this section. Shear tests shall be performed in accordance with Test Method D1002.

6.2 *Preparation of Test Specimens*—Prepare at least ten specimens for each separate test except as otherwise specified in the individual test methods. The metal bonded shall be 6061T6 or 5052H34 aluminum alloy (Federal Specification QQ-A-250/11d or QQ-A-250/8d, respectively, or Specification B209) cleaned as described in Practice E864 and at the purchaser’s option, primed in accordance with Specification E866 or Specification E1826. Time and temperature of curing of the adhesive shall be in accordance with the adhesive manufacturer’s most recent recommendation. Test panels or specimens, or both, other than the breakaway type shall be cut in such a manner that minimum vibration or heat is generated during the cutting operation.

6.3 *Normal-Temperature Lap Shear*—Subject specimens to a lap shear test at normal temperature $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$).

6.4 *High-Temperature Lap Shear*—Test specimens at $60 \pm 3^\circ\text{C}$ ($140 \pm 5^\circ\text{F}$) and $93 \pm 3^\circ\text{C}$ ($200 \pm 5^\circ\text{F}$). Bring the specimen to temperature as indicated by a thermocouple at the bond area and stabilize for 10 min just prior to test. Stabilize the chamber used to test the specimens at the test temperature for 45 min prior to testing.

6.5 *Low-Temperature Lap Shear*—Test specimens at $-55 \pm 3^\circ\text{C}$ ($-67 \pm 5^\circ\text{F}$). Bring the specimen to temperature as indicated by a thermocouple at the bond area and stabilize for 10 min just prior to test. Stabilize the chamber used to test the specimens at the test temperature for 45 min prior to testing.

6.6 *Humidity Exposure Lap Shear*—Test lap shear specimens at $93 \pm 3^\circ\text{C}$ ($200 \pm 5^\circ\text{F}$) after 2 weeks’ exposure to 95

TABLE 1 Physical Requirements for the Film Adhesive

Test	Requirement ^A
Film weight, kg/m ² (lb/ft ²)	0.405 to 0.480 (0.083 to 0.100)
Normal-temperature lap shear, MPa (psi)	20 (2903)
High-temperature lap shear, MPa (psi)	
60°C (140°F)	20 (2903)
93°C (199°F)	13 (1888)
Low-temperature lap shear, MPa (psi)	20 (2903)
Humidity exposure lap shear, MPa (psi)	5 (723)
Salt spray exposure lap shear, MPa (psi)	16 (2322)
Normal-temperature floating roller peel, N/m (lbf/in.)	4400 (25.1)
Low-temperature floating roller peel, N/m (lbf/in.)	2625 (15.0)
Dead load stress durability, h:	
40 % of 60°C (140°F) failure stress	40
30 % of 60°C (140°F) failure stress	540
20 % of 60°C (140°F) failure stress	1500
Normal-temperature climbing drum peel, N-m/m (lbf-in./in.)	36 (8)
High-temperature climbing drum peel, N-m/m (lbf-in./in.)	18 (4)
Flatwise tensile strength, MPa (psi)	2.1 (306)
Storage life test	^B

^A Except for film weight, values stated are the minimal to be met by the averages of the results for the specimens tested.

^B The storage life at the maximum recommended temperature and under the recommended storage conditions shall be stated in the instructions.

$\pm 5\%$ relative humidity and $93 \pm 3^\circ\text{C}$ ($200 \pm 5^\circ\text{F}$). Bring the specimen to temperature as indicated by a thermocouple at the bond area and test within 2 min. The test chamber used to test the specimens shall be stabilized at the test temperature for at least 45 min prior to testing. Start the test of each humidity exposure lap shear test specimen no later than 30 min after removing it from the humidity chamber.

6.7 Salt Spray Exposure Lap Shear—Test specimens in accordance with the salt spray test of Practice **B117** for 2 weeks' exposure to salt spray using 5 % NaCl solution at $35 \pm 3^\circ\text{C}$ ($95 \pm 5^\circ\text{F}$).

6.8 Normal-Temperature Floating Roller Peel—Test specimens at normal temperature $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$) in accordance with Test Method **D3167**.

6.9 Low-Temperature Floating Roller Peel—Test each specimen at $-55 \pm 3^\circ\text{C}$ ($-67 \pm 5^\circ\text{F}$). Bring the specimen to temperature as indicated by a thermocouple at the bond area and stabilize for 10 min just prior to testing. Stabilize the chamber used to test the specimen at the test temperature for 45 min prior to testing.

6.10 Dead Load Stress Durability—Test the specimens in accordance with Test Method **D2919**. Maintain the conditions of the test chamber at $60 \pm 3^\circ\text{C}$ ($140 \pm 5^\circ\text{F}$) and $95 \pm 5\%$ relative humidity.

6.11 Normal-Temperature Climbing Drum Peel—Test five specimens (constructed using a 50-mm (2-in.) deep core, Type IV of Specification **E1091**, and 0.5-mm (0.02-in.) skins) in the “L” direction for peel strength in accordance with Test Method **D1781** using the load correction described in **8.1.2** of that method. Make an autographic recording of force versus head movement. Test the specimen at normal temperature $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$) and at a relative humidity of $50 \pm 10\%$.

6.12 High-Temperature Climbing Drum Peel—Test five specimens (constructed using a 50-mm (2-in.) deep core, Type IV of Specification **E1091**, and 0.5-mm (0.02-in.) skins) in accordance with **6.11**, except stabilize the test temperature at $93 \pm 3^\circ\text{C}$ ($200 \pm 5^\circ\text{F}$) for 10 min as determined by a thermocouple adjacent to the specimen skin. The test chamber used to test the specimens shall be stabilized at the test temperature for at least 45 min prior to testing.

6.13 Flatwise Tensile Strength—Test five specimens (constructed using 50-mm (2-in.) deep core, Type IV of Specification **E1091**, and 0.50-mm (0.02-in.) thick skins) in accordance with Test Method **C297/C297M**, except that 76.2 by 76.2-mm (3 by 3-in.) test specimens shall be used with corresponding 76.2 by 76.2-mm (3 by 3-in.) tension blocks. Test the specimens at normal temperature $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$) and at a relative humidity of $50 \pm 10\%$.

NOTE 2—Core may be dried prior to preparation of test specimen.

7. Inspection

7.1 Responsibility for Inspection—Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities

suitable for the performance of inspection requirements specified herein unless disapproved by the purchaser. The purchaser has the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure compliance with the requirements.

7.2 Classification of Inspections—The inspection requirements specified herein are classified as follows:

7.2.1 Qualification inspection (see **7.3**), and

7.2.2 Quality conformance inspection (see **7.4**).

7.3 Qualification Inspection:

7.3.1 Qualification Test—Unless otherwise specified by the purchaser (see **4.2**), adhesives that have not passed the qualification tests, or that have previously passed the tests but have subsequently been modified in any manner, must be tested against this specification and shown to meet its requirements.

7.3.1.1 Instruction Sheet—A dated, coded, and titled instruction sheet that outlines instructions for use of the adhesive in bonding metal facings to paper cores and metal components shall be supplied by the manufacturer. These instructions shall be forwarded with the test report (see **7.3.3**) when requesting qualification. In addition, a copy of the instruction sheet shall accompany each shipment of the adhesive. At the option of the purchaser, qualification tests may be repeated at any time on material previously found satisfactory.

7.3.2 Periodic Reevaluation—A reevaluation of an adhesive shall be made at 5-year intervals after the date of notification of the product's acceptability for qualification.

7.3.2.1 Reevaluation Procedure—It shall be the responsibility of the supplier of the qualified adhesive to furnish to the purchaser, at 5-year intervals, the data necessary to confirm the continued conformity of the product to the qualification requirements. These data shall be complete test results for a sample representative of current production, tested against all the requirements of the specification. In the event the date for requalification has passed and no current production materials or data are available for reevaluation, the supplier shall still be eligible for contract award; however, final acceptance of material from such a supplier is contingent upon meeting all the requirements of this specification.

7.3.3 Test Report—In addition to the qualification test samples, the manufacturer shall furnish a dated and numbered report, certified by notarized affidavit, giving the results of all tests listed in Section **6**. The individual and average values for the tests shall be reported. The test report shall cover all the requirements of Section **5**. The type of core, surface preparation (including cleaning and primer, if required), assembly condition, pressure, and time of curing used in the preparation of the test panels shall be reported. The report shall certify that the preparation of the adhesive and test specimens conformed to the description given in the instruction sheet.

7.3.4 Instruction Sheet—The manufacturer shall submit with the test report (see **7.3.3**) two copies of an instruction sheet that contains the information specified in **7.3.1.1**.

7.4 Quality Conformance Inspection:

7.4.1 Tests—Samples of each lot of adhesive delivered on contract or order shall be subjected to the following quality conformance tests. Test reports, in duplicate, shall be furnished

for all quality conformance tests specified in this specification, and shall be signed by an authorized representative of the laboratory making the tests. Acceptance or approval of material during the course of manufacture shall not be construed as a guarantee of the acceptance of the finished products.

7.4.2 *Normal-Temperature Lap Shear Strength (acceptance)*—The normal-temperature shear strength test shall be conducted in accordance with 6.3.

7.4.3 *High-Temperature Lap Shear (acceptance)*—The high-temperature shear test shall be conducted in accordance with 6.4.

7.4.4 *Normal-Temperature Climbing Drum Peel (acceptance)*—The normal-temperature climbing drum peel test shall be conducted in accordance with 6.11.

8. Packaging

8.1 *Packaging*—Packaging shall be in accordance with the supplier’s standard practices and applicable regulations. The product shall be clearly and legibly labeled with the following information:

8.1.1 Specification number,

- 8.1.2 Date of manufacture (month and year),
- 8.1.3 Manufacturer’s name and address,
- 8.1.4 Manufacturer’s product trade name,
- 8.1.5 Manufacturer’s product type designation,
- 8.1.6 Manufacturer’s batch/lot designation,
- 8.1.7 Contract number,
- 8.1.8 Date of shipment,
- 8.1.9 Expiration date,
- 8.1.10 Manufacturer’s recommended storage temperature range,
- 8.1.11 Quantity contained,
- 8.1.12 Film mass, and
- 8.1.13 Manufacturer’s certification that the batch, lot, and unit meet the requirements of this specification. (See Glossary of Terms for Rigidwall Relocatable Shelters, Practice E874, Appendix X1, for definitions.)

9. Keywords

9.1 adhesive bond; aluminum; bonding process; film adhesive; honeycomb sandwich panels; relocatable shelters

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).