



# Standard Specification for Stainless Steel Suture Needle Holders-General Workmanship Requirements and Corresponding Test Methods<sup>1</sup>

This standard is issued under the fixed designation F1325; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers general workmanship aspects of stainless steel suture needle holders intended for reuse in surgery.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E18 Test Methods for Rockwell Hardness of Metallic Materials

E92 Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials

E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

F899 Specification for Wrought Stainless Steels for Surgical Instruments

F921 Terminology Relating to Hemostatic Forceps

F1089 Test Method for Corrosion of Surgical Instruments

## 3. Terminology

3.1 *Definitions:*

3.1.1 *modified working end*—working surfaces possessing superior hardness characteristics which are either the result of depositing various materials on the base metal or the result of permanently securing an insert (such as by brazing) to the base metal.

3.1.2 *Discussion*—The typical method of modifying the working end of the suture needle holder is to use jaw inserts or to plasma deposit (flame plate) materials with improved wear characteristics such as tungsten carbide or stellite (trade-

marked). For the jaw insert method, the insert is brazed to the jaw face with a uniform deposit of silver solder which is free of crevices at all interfaces. For the flame plating method, a uniform layer of material is deposited which is  $0.004 \pm 0.001$  in. thick.

3.2 Definitions applicable to stainless steel suture needle holders and the terms specified herein, shall be in accordance with Terminology F921.

## 4. Materials

4.1 All component parts of the instrument other than the modified working end shall be fabricated from martensitic stainless steel type 410, 410X, 416, 420A, 420B, 420C, 420F, 420F Mod, and 440B per Specification F899 (see Note 1). The modified working end may be made of stellite (trademarked), tungsten carbide, or other suitable material.

NOTE 1—Free-machining grades of stainless steel are inappropriate for use due to their lower corrosion resistance and toughness.

## 5. Requirements

5.1 Heat treatment and hardness for component parts.

5.1.1 Stainless steel component parts of the instrument shall be heat treated under conditions recommended for the material used.

5.1.2 The Rockwell hardness of an instrument with the working end not modified shall be 42 HRC to 52 HRC. Instruments where the working end has been modified shall have a modified working surface whose Rockwell hardness is A77 minimum.

5.2 *Corrosion Resistance*—Holders with working ends not modified shall be subjected to corrosion tests as specified in Test Method F1089. Holders with modified working ends shall be subject to corrosion tests as specified in Test Method F1089 except for the modifying material.

## 6. Performance Requirements

6.1 *Needle retention test*—From Table 1, select a needle, sized for use with the holder being tested. The suture needle, with its axis held perpendicularly to the axis of the jaw shall, upon engagement of the second ratchet of the suture needle

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.33 on Medical/Surgical Instruments.

Current edition approved Oct. 1, 2016. Published October 2016. Originally approved in 1991. Last previous edition approved in 2008 as F1325 – 91 (2008) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/F1325-91R16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Suture/Needle/Holder Relationship**

Suture Needle Holder	Most Common Use	Recommended Teeth Per Square Inch	Compatible Suture Size Per USP <sup>A</sup>	Corresponding Wire Size (Diameter) of Needle	
Debakey 7 thru 12 in.	vascular and valve replacement	2500	0 2-0	0.16 in. 0.14	0.035 in. 0.24
Hufnagel 8 thru 10 in.		2500	3-0 4-0	0.010 0.008	0.024 0.015
Webster Hegar-Mayo Brown	coronary bypass	3500 or smooth	5-0 6-0 7-0	0.006 0.004 0.003	0.015 0.009 0.009
Castrovieijo	microsurgery	smooth	8-0 9-0	0.002 0.0015	0.006 0.006
Kalt		smooth	10-0	0.0008	0.006

<sup>A</sup> Mean average of USP absorbable and non-absorbable and Suture size averages.

holder, show no lateral, rotational, or longitudinal motion when subjected to a one-half pound pull and a one-inch-pound torsion.

## 7. Workmanship, Finish, and Appearance

### 7.1 Finish:

7.1.1 *Surfaces*—Surfaces of the instrument shall be uniformly finished and free from burrs, sharp edges, cracks, coarse marks, and processing materials.

7.1.2 *Type*—The finish shall be one of the types specified in Terminology **F921** or as specified by the purchaser.

### 7.2 Workmanship:

7.2.1 Finger rings—inside surfaces of the finger rings shall be well rounded and conform to the requirements of Section **7.1.1**.

7.2.2 The pivot screw or pin shall be permanently set peened, and flush.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*