



Standard Specification for Pure Aluminum (Unalloyed) Source Material for Vacuum Coating Applications¹

This standard is issued under the fixed designation F1594; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers pure aluminum metal (unalloyed) for use as raw material for making evaporation sources, sputtering targets, and superconducting wires.

1.2 This specification sets purity grade levels, physical attributes, analytical methods, and packaging requirements.

2. Referenced Documents

2.1 *ASTM Standards*:²

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E112 Test Methods for Determining Average Grain Size](#)

3. Terminology

3.1 *Definitions*:

3.1.1 *raw material lot*—a quantity of material that is melted, consolidated, or purified, or both, in one equipment run as a nominally uniform batch of metal.

4. Classification

4.1 Grades of aluminum are defined in [Table 1](#).

4.2 Purity and total metallic impurity levels are based upon elements listed in [Table 2](#).

5. Ordering Information

5.1 Orders for these products shall include the following:

5.1.1 Grade (see [4.1](#)).

5.1.2 Configuration (see [8.1](#)).

5.1.3 Whether or not certification is required (see [12.1](#)).

5.1.4 Whether or not a sample representative of the finished product is required to be provided by the supplier to the purchaser.

¹ This specification is under the jurisdiction of ASTM Committee F01 on Electronics and is under the direct responsibility of Subcommittee F01.17 on Sputter Metallization.

Current edition approved June 1, 2011. Published June 2011. Originally approved in 1995. Last previous edition approved in 2003 as F1594–95 (2003). DOI: 10.1520/F1594-95R11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

6. Impurities

6.1 The suite of metallic elements to be assayed for is defined in [Table 2](#). Acceptable analysis methods are specified in Section [12](#). Elements not detected will be counted and reported as present at the detection limit. Additional elements may be analyzed and reported, as agreed upon between supplier and purchaser, but these shall not be counted in defining the grade designation.

6.2 Acceptable concentration limits for individual elements and analytical techniques shall be agreed upon between the supplier and the purchaser.

7. Physical Properties

7.1 Grain size and measurement method for grain size shall be agreed upon between the supplier and the purchaser. When the grain morphology is equiaxed, refer to Practice [E112](#).

8. Dimensions

8.1 Each product shall conform to an appropriate engineering drawing.

8.2 Nominal dimensions, tolerances, and other attributes shall be agreed upon between the supplier and the purchaser.

9. Workmanship, Finish, and Appearance

9.1 Workmanship, finish, and appearance shall be agreed upon between the supplier and the purchaser.

9.2 Surface must be free of any contaminants such as mold release, dirt, or oils that could adversely affect the purity of the material when remelted, unless otherwise agreed upon between supplier and purchaser.

10. Sampling

10.1 Analyses for impurities shall be performed on a sample that is representative of the finished material lot provided by the supplier.

11. Analytical Methods

11.1 Analysis for impurities in [Table 2](#) and [6.2](#) shall be performed using optical emission spectroscopy, atomic absorption, or any other technique that meets the purchaser-required detection limits.

TABLE 2 Minimum Metallic Elements to be Assayed

boron	beryllium	bismuth	calcium	cadmium	cobalt	chromium	copper	iron	gallium	vanadium
lithium	magnesium	manganese	sodium	nickel	lead	silicon	tin	strontium	titanium	zinc
zirconium										

TABLE 1 Aluminum Grades

Grade	Purity, %	Maximum Total Metallic Impurity Level (by weight), ppm
4N5	99.995	50
4N	99.99	100
3N8	99.98	200
3N5	99.95	500

11.2 Impurity levels shall be reported using Practice E29.

12. Certification

12.1 When required by the purchaser, a certificate of analysis/compliance that represents the finished material lot shall be provided for each lot by the supplier.

12.2 The certificate of analysis/compliance shall state the manufacturer's or supplier's name, the supplier's lot number,

impurity levels, method of analysis, and any other information agreed upon between the supplier and the purchaser.

12.3 Impurity levels may be reported in the certificate of analysis/compliance using actual analytical results for the material lot, or by a certificate of analysis/compliance using typical analytical results based upon historical statistical data for the same process. Certification and the manner of reporting impurity levels shall be agreed upon between the supplier and the purchaser.

13. Packaging

13.1 Each piece shall be enclosed in a shipping carton that ensures product integrity during shipment.

14. Keywords

14.1 aluminum source; evaporation; thin films; vacuum coating

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).