



Standard Specification for Metallic Mechanical Fittings for Use on Outside Diameter Controlled Thermoplastic Gas Distribution Pipe and Tubing¹

This standard is issued under the fixed designation F1948; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers requirements and test methods for the qualification of metallic mechanical fittings for use with outside diameter controlled thermoplastic gas distribution pipe and tubing as specified in Specification [D2513](#).

1.2 The test methods described are not intended to be routine quality control tests.

1.3 This specification covers the types of mechanical fittings described in [3.3](#).

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The following safety hazards caveat pertains only to the test method portion, Section [7](#), of this specification. *This standard may involve hazardous material, operations and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures), shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:²

- [D638](#) Test Method for Tensile Properties of Plastics
- [D1598](#) Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
- [D1600](#) Terminology for Abbreviated Terms Relating to Plastics

¹ This specification is under the jurisdiction of ASTM Committee [F17](#) on Plastic Piping Systems, and is the direct responsibility of Subcommittee [F17.60](#) on Gas.

Current edition approved Dec. 1, 2015. Published February 2016. Originally published in 1999. Last previous edition approved in 2012 as F1948–12. DOI: 10.1520/F1948-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D2513](#) Specification for Thermoplastic Gas Pressure Pipe, Tubing, and Fittings

[E515](#) Practice for Leaks Using Bubble Emission Techniques

[F412](#) Terminology Relating to Plastic Piping Systems

[F1588](#) Test Method for Constant Tensile Load Joint Test (CTLJT)

[F2785](#) Specification for Polyamide 12 Gas Pressure Pipe, Tubing, and Fittings

[F2897](#) Specification for Tracking and Traceability Encoding System of Natural Gas Distribution Components (Pipe, Tubing, Fittings, Valves, and Appurtenances)

[F2945](#) Specification for Polyamide 11 Gas Pressure Pipe, Tubing, and Fittings

2.2 ASME Standard:

[ASME B 31.8](#) Gas Transmission and Distribution Piping Systems³

2.3 Federal Specification:

[OPS Part 192 Title 49](#), Code of Federal Regulations⁴

2.4 Other Document:

[PPI TR-4](#) Recommended Hydrostatic Strengths and Design Stresses for Thermoplastic Pipe and Fitting Compounds⁵

3. Terminology

3.1 Definitions are in accordance with Definitions [F412](#) unless otherwise specified. Abbreviations are in accordance with Abbreviations [D1600](#) unless otherwise specified.

3.1.1 The gas industry terminology used in this specification is in accordance with ASME/ANSI B31.8 or United States CFR 49 Part 192 unless otherwise indicated.

3.1.2 The term “pipe” used herein refers to both pipe and tubing unless specifically stated otherwise. The term “fitting” refers to a mechanical connecting device as described in [3.2.5](#) and [3.2.7](#).

3.2 Definitions:

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from the Office of Pipeline Safety, Research and Special Programs Administration, U.S. Department of Transportation, 400 Seventh Street, S.W., Washington, DC, 20006-1301.

⁵ Available from Plastics Pipe Institute (PPI), 105 Decker Court, Suite 825, Irving, TX 75062, <http://www.plasticpipe.org>.

*A Summary of Changes section appears at the end of this standard

3.2.1 *Category 1 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) to provide for pressure integrity, leak tightness, and resistance to end loads sufficient to cause no less than 25 % elongation of the piping, as described in this standard.

3.2.2 *Category 2 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) to provide for pressure integrity and leak tightness; Category 2 fittings do not provide for resistance to end loads.

3.2.3 *Category 3 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) for pressure integrity, leak tightness, and resistance to end loads; the nominal size of the fitting shall be 4 and larger in diameter.

3.2.3.1 *Discussion*—Resistance to end loads shall be equal to or greater than the maximum thermal stress that would be produced by a temperature change of 100°F (55°C) (for formula, see [Annex A1](#)).

3.2.4 *joint, n*—the location at which two or more pieces of pipe, or a pipe and a fitting, are connected (an installed coupling has two joints).

3.2.5 *joint, mechanical, n*—a connection between piping components employing physical force to develop a seal or produce alignment.

3.2.6 *maximum allowable operating pressure, MAOP, n*—of the fuel gas piping system, in psig, as determined in accordance with US DOT CFR, Title 49, Part 192.121, and as represented in the following:

$$MAOP = P = 2 \times S / (R - 1) \times f \quad (1)$$

where:

- S = the pipe material's HDB as published in PPI TR 4,
- R = the pipe's dimension ratio determined by dividing the pipe's specified nominal outside diameter by the pipe's specified nominal wall thickness, and
- f = design (derating) factor for thermoplastic fuel gas piping as set by the authority having jurisdiction. In the United States, the design factor is cited in CFR, Title 49, Part 192.121.

3.2.7 *mechanical fitting, n*—fitting for making a mechanical joint to provide for pressure integrity, leak tightness, and, depending on category, as defined in this standard, resistance to end loads.

3.3 Types of Mechanical Fittings:

3.3.1 *clamped insert fitting, n*—mechanical fitting used to make a mechanical joint that utilizes external clamps, or other mechanical devices, to form a pressure seal between the reinforcing tubular stiffener and the surface of the pipe.

3.3.2 *compression fitting, n*—mechanical fitting used to make a mechanical joint by compressing either externally, internally, or radially to form a pressure seal between the fitting and the surface of the pipe.

3.3.3 *compression gasket fitting, n*—mechanical fitting used to make a mechanical joint that utilizes a compression nut, tightening ring, bolts, or any other device to compress gasketing onto the surface of the pipe to form a pressure seal.

3.3.4 *stab-type fitting, n*—mechanical fitting used to make a mechanical joint in which a seal is achieved by radial compression of a gasket between; the outside diameter (OD) of the pipe and the inside diameter (ID) of the fitting; the inside diameter (ID) of the pipe with the insert stiffener; or both.

4. Material

4.1 The physical properties of each material used to produce the fitting shall be available from the fitting manufacturer upon request.

4.2 Specifications outlining the physical and chemical properties of all fitting materials shall be available from the fitting manufacturer upon request.

NOTE 1—Materials in long-term contact with natural gas of line quality and LP gas vapor should be demonstrated to not adversely effect the performance of the fitting.

NOTE 2—Materials should have a demonstrated resistance to environmental stress cracking when exposed, under stress, to chemical compounds encountered in or external to gas piping systems, and a demonstrated resistance to bacteriological decomposition. Such compounds include, but are not limited to, ice thawing chemicals, fertilizers, insecticides, herbicides, leak detection fluids, acids, bases and antifreeze solutions used to thaw frozen lines.

5. Dimensions

5.1 The dimensions and tolerances shall be determined by the manufacturer.

6. Qualification Requirements

6.1 *General*—Unless otherwise specified, each nominal size of fitting shall be tested. Testing the fitting with the thickest wall pipe for which the fitting is designed qualifies that type of fitting for use with pipe of lesser wall thickness.

6.1.1 Mechanical joint qualification shall be performed on assembled joints using the fitting manufacturer's joining procedure. All mechanical fittings offered by the manufacturer shall be capable of meeting the requirements of this standard when:

6.1.1.1 Connecting thermoplastic gas piping complying with applicable ASTM thermoplastic gas piping standards, as listed in Section 2, Referenced Documents, either same to same (for example, PE to PE) or transitioning (for example, PE to PA).

6.1.1.2 Transitioning between thermoplastic gas piping complying with applicable ASTM thermoplastic gas piping standards, in Section 2, Referenced Documents, and metal piping. It is not the intent of this standard to require the testing of all fitting configurations (that is, tee, ells, etc.) but each fitting joint design in each size.

6.1.2 All mechanical fittings described in 3.3 shall have an internal pipe reinforcing tubular stiffener that extends at least under the seal and gripping device (where used). Exception: When the fitting is used to transition from plastic to metal, only the plastic end of the fitting is required to have a stiffener employed.

6.1.3 In the case of fittings designed to transition between different thermoplastic materials, between different wall thicknesses (SDRs), or different diameters of the same thermoplastic material, the pipe requiring the lowest force to elongate to

yield shall fail before any joint fails. For example, when transitioning between PE and PA of the same wall thickness (same DR) and diameter, failure of the PE before the joint fails, qualifies the fitting in this transition scenario. Another example is a fitting used to transition between 1CTS PE and ½ CTS PE piping, of the same DR, qualifies if the ½ CTS tubing fails before the joint fails.

6.1.4 In the case of fittings designed to transition between metallic piping and thermoplastic piping, the fitting shall be qualified as Category 1 under this standard only if the joint between the fitting and the metallic piping has been tested to provide axial tensile restraint strength of 1.5 times the tensile strength at yield of the thermoplastic piping joined to the opposite end.

6.1.4.1 The metallic piping shall not pull out of the fitting when tested to the following pull-out forces and tested in accordance with 7.2.

- (1) For PE 3770 psi
- (2) For PA11 8700 psi
- (3) For PA12 7614 psi

6.2 Performance Requirements:

6.2.1 Tensile Strength—The fitting shall provide a thermoplastic pipe joint design capable of accommodating the following tensile loads, when tested in accordance with 7.2.

6.2.1.1 Category 1—A fitting that, when properly installed and meeting the qualification requirements of 6.1.1, 6.1.2 and 6.1.3, shall provide for joints in thermoplastic piping that resist pull-out to a force on the thermoplastic pipe equal to or greater than that which will cause no less than 25% elongation of the plastic pipe, or which causes the plastic pipe to fail outside the joint area when tested in accordance with 7.2. Furthermore, a fitting designed to transition between metallic piping and thermoplastic piping that, when properly installed, shall meet the qualification requirements of 6.1.4 when tested in accordance with 7.2.

6.2.1.2 Category 2—Fitting that, when properly installed, creates a joint that provides only a seal. A mechanical joint designed for this category excludes any provisions in the design of the joint to resist axial pullout forces; therefore, tensile tests are not required.

6.2.1.3 Category 3—Fittings of nominal pipe size 4 and larger in diameter that, when properly installed provides a pull-out resistance to a force on the thermoplastic pipe joint equal to or greater than the maximum thermalstress that would be produced by a temperature change of 100°F (55°C)(for formula, see Annex A1).

NOTE 3—Category 3 has a manufacturer’s rated pipe end restraint less than the value required to yield the pipe as outlined in 6.2.1.1 (Category 1).

6.2.1.4 Fitting restraint capabilities less than as defined in 6.2.1.1 and 6.2.1.3 shall constitute failure of the test.

6.2.2 Temperature Cycling Test—The mechanical joint shall provide a pressure seal after 10 cycles of the temperature cycling test when tested in accordance with 7.3.

6.2.3 Constant Tensile Load Test (CTLIT)—Pull out of the pipe or leakage before, during or after testing in accordance with 7.4, shall constitute failure of the test.

6.3 Elevated Temperature Sustained Pressure—The fitting, joint or pipe in the area affected by the fitting shall not fail as defined in Test Method D1598, when tested in accordance with 7.5. The fitting or joint meets this requirement when tested in accordance with any one of the three conditions (A, B, or C) for PE (polyethylene) piping, or any of the two conditions (D or E) for PA (polyamide) piping, as listed in Table 1 Elevated Temperature Sustained Pressure Test Conditions. To qualify fittings designed and used for transitioning between different thermoplastic piping materials, the hoop stress condition of the material with the lowest HDB shall be used.

7. Test Methods

7.1 General—The test methods in this specification cover mechanical joint designs. Test methods that are applicable from other specifications are referenced in the paragraph pertaining to that particular test.

7.1.1 Conditioning—Unless otherwise specified, condition the specimens (pipe and fittings) prior to joining at 73.4 ± 3.6°F (23 ± 2°C) for not less than 16 h.

7.1.2 Test Conditions—Conduct the testing at the standard laboratory temperature of 73.4 ± 3.6°F (23 ± 2°C) unless otherwise specified.

7.1.3 Test Specimens—Test joints shall be prepared with the appropriate size thermoplastic pipe, complying with the dimensional requirements of Specification D2513, in accordance with the manufacturer’s joining procedures.

7.1.4 Precautions and Safety Considerations—It is strongly recommended that liquid be used as the pressurizing fluid when testing systems that may fail in a brittle manner (specifically PVC systems). If that is not possible, the test specimens must be placed in a strong chamber at all times when pressurized. Also, fittings as specified in 6.2.1.2 should be restrained to prevent pull-out during testing.

7.2 Tensile Strength Test:

7.2.1 The test pipes, for sizes below NPS 4, shall be prepared so that the minimum length of unreinforced pipe from a joint being tested is equal to five times the nominal outside diameter of the pipe being tested. The test pipes, for sizes NPS 4 and above, shall be prepared so that the minimum length of unreinforced pipe from a joint being tested is equal to three times the nominal outside diameter of the pipe being tested, but in no case less than 12 in. (304 mm). It is permissible to test multiple joints together, provided that the minimum length of unreinforced pipe (as stated above) exists on at least one joint.

TABLE 1 Elevated Temperature Sustained Pressure Test Conditions

	Test Temperature	HRS, minimum	PE, Hoop Stress	PA, Hoop Stress
A	140±3.6°F (60±2°C)	3000	1000 psi, (6.8 Mpa)	NA
B	176±3.6°F (80±2°C)	1000	580 psi, (4.0 Mpa)	NA
C	176±3.6°F (80±2°C)	170	670 psi, (4.6 MPA)	NA
D	73±3.6°F (23±2°C)	1000	NA	3200 psi (22Mpa)
E	176±3.6°F (80±2°C)	100	NA	1850 psi (12.7 Mpa)

7.2.2 The apparatus and report shall be as specified in Test Method **D638**. Test six joints.

7.2.3 The test shall be conducted at 73.4°F ± 3.6°F (23°C ± 2°C).

7.2.4 The speed of the testing shall be 0.2 in. (5 mm)/min. ± 25 %.

7.2.5 Failure of any sample shall constitute failure of the test.

7.3 Temperature Cycling Test:

7.3.1 The test shall be conducted on six of the smallest and six of the largest nominal pipe sizes of each mechanical joint design and assembled as outlined in **6.1.1**.

7.3.2 Leak test specimens at ambient temperature at 7 ± 3 psig (48.3 ± 20.7 kPa) and a minimum of 1.5 X MAOP.

7.3.3 Cool specimens to a temperature of -20°F ± 3.6°F (-29°C ± 2°C) and maintain for a minimum of 2.5 h.

7.3.4 Condition specimens to a temperature of 140°F ± 3.6°F (60°C ± 2°C) and maintain for a minimum of 2.5 h.

7.3.5 Repeat **7.3.3** and **7.3.4** for a total of 10 cycles.

7.3.6 Pressurize 50 % of the specimens of each size at 7 ± 3 psig (48.3 ± 20.7 kPa) and the remaining 50 % of each size at 1.5 × MAOP of the piping material and SDR for which the fittings are designed to be used. Leak test first at 140 ± 3.6°F (60 ± 2°C) and then at -20 ± 3.6°F (-29 ± 2°C).

NOTE 4—If immersion is used for leak testing, and the design of the joint is such that air can be trapped within the joint assembly, allow adequate time for all air trapped within the joint to escape prior to observing for leaks.

7.4 Constant Tensile Load Joint Test:

7.4.1 The testing shall be carried out in accordance with Test Method **F1588** and as follows:

7.4.1.1 Prepare fitting/piping assemblies in accordance with manufacturer installation instructions making one sample of each piping/combination of piping joints to be categorized.

7.4.1.2 Pressurize specimen at a pressure between 4 psig (27.6 kPa) and the lowest design pressure of the pipe combination being tested. Record and monitor pressure. When qualifying fittings designed and used to transition between different materials (for example, metal, PA or PE), fiber stress of the lowest tensile strength material shall be used.

7.4.2 The fiber stress shall be as follows:

7.4.2.1 1320 psi for PE piping.

7.4.2.2 2060 psi for polyamide 11 (PA11) 32312 piping.

7.4.2.3 2600 psi for polyamide 11 (PA11) 32312 and 32316 and polyamide 12 (PA12) 42316 piping.

7.4.3 The duration of the test shall be 1000 h.

7.4.4 The samples shall be leak tested at 7 ± 3 psig and a minimum of 1.5 × the lowest design pressure of the pipe combinations being tested, prior to and at the end of the 1000h test (while still under tensile load and immediately following the CTLJT). No leakage shall be permitted prior, during or after the CTLJT testing when tested in accordance with the Liquid Application Technique in **7.6**.

7.4.5 Failure of the specimen shall constitute failure of the test.

7.5 Elevated Temperature Sustained Pressure Test:

7.5.1 The test shall be conducted on six of the smallest and six of the largest nominal pipe sizes of each mechanical joint design and assembled as outlined in **6.1.1**.

7.5.2 The apparatus and report shall be as specified in Test Method **D1598**.

7.5.3 The assembled joints shall be tested in accordance with Test Method **D1598** with the exception that it is not required that 12 in. or five times the nominal outside diameter of the pipe used in conducting the test be placed on each side of the fitting tested. The test shall be conducted at one of the time/temperature/hoop stress combinations shown in **Table 1** with the test pressure calculated using the following equation:

$$P = \frac{2S}{DR - 1} \quad (2)$$

where:

P = test pressure, psig,

S = hoop stress, and

DR = dimension ratio (OD/wall).

If ductile failure occurs in the pipe at 176°F (80°C)/670 psi (4620 kPa) hoop stress, retest at 176°F (80°C)/580 psi (3999 kPa) hoop stress.

7.5.4 Failure of any two of the six specimens tested shall constitute failure of the test. Failure of one of the six specimens tested is cause for re-test of six additional specimens. Failure of one of the six specimens in re-test shall constitute failure of the test. Evidence of failure of the pipe shall be defined in Test Method **D1598**.

7.6 Leak Testing:

7.6.1 Pressurize the sample using air or other inert gas.

NOTE 5—SAFETY – In large diameter samples it is prudent to first fill the specimen with a coarse granular solid to reduce the pressurized volume of the sample. Plastic granules are frequently used for this purpose.

7.6.2 Ensure that all end caps and test fittings are bubble tight.

7.6.3 Detect leakage of the transition joint in accordance with Test Method **E515** 9.1, 9.2, and 9.3 Liquid Application Technique. Conduct leak testing for 2 min.

8. Product Instructions

8.1 Qualified installation instructions shall be available from the manufacturer and supplied with the fitting.

8.2 The installation instructions shall state what piping material(s)/combinations for which the mechanical fitting has been qualified.

9. Product Marking

9.1 Fittings shall be marked with the following:

9.1.1 ASTM designation F1948,

9.1.2 Date or lot code identification,

9.1.3 Manufacturer's name or trademark,

9.1.4 Size, followed by "IPS" or "CTS" designation, SDR or wall thickness range,

9.1.5 The word "gas" or, if space does not permit, the letter "G", and

9.1.6 "Category 1," Category 2," or "Category 3"; abbreviation is permitted as CAT1, CAT2 or CAT3.

9.2 All required markings shall be legible and so applied as to remain legible under normal handling and installation practices. If indentation is used, it shall be demonstrated that these marks have no affect on the long term strength of the fitting.

9.3 Fittings intended for transport of natural gas and meeting the requirements of this specification shall be marked with the 16-character gas distribution component tracking and traceability identifier in accordance with Specification **F2897**. The 16-character code shall be expressed in alpha-numeric format and Code 128 bar code format with a minimum bar thickness value of 0.005 in. or an alternative **1D** or **2D** bar code symbology as agreed upon between manufacturer and end user. All fittings shall have the 16-character codes marked or affixed

to the product, product packaging, or any manner agreed upon between manufacturer and end user.

10. Quality Assurance

10.1 When the product is marked with this designation, F1948, the manufacturer affirms that the product was manufactured, inspected, sampled and tested in accordance with this specification and has been found to meet the requirements of this specification.

11. Keywords

11.1 gas; manufacturer's joining procedure; metallic mechanical fittings; reinforcing tubular stiffener; temperature cycling test

ANNEX

(Mandatory Information)

A1. THERMAL STRESS

A1.1 Calculate the longitudinal stress (theoretical) induced in a pipe member between fixed points as follows:

$$S = E \times C \times \Delta t \quad (A1.1)$$

where:

- S = stress, psi (MPa),
- E = modulus of elasticity, psi (MPa), instantaneous, at 73°F (23°C),
- C = coefficient of expansion, in./in./°F (mm/mm/°C), and
- Δt = maximum temperature minus minimum temperature, °F (°C).

A1.1.1 The measured stress has been determined to be less than that calculated. This difference is caused by the stress relaxation in viscoelastic materials.

A1.2 Calculate the theoretical force sustained at the fixed points (typically joints) in a pipe member as follows:

$$F = S \times A \quad (A1.2)$$

where

- F = force, lbf (N),
- S = stress, psi (MPa), and
- A = cross-section pipe wall area, in.² (mm²).

A1.3 Calculate pipe contraction in unrestrained pipe caused by a reduction in temperature as follows:

$$\Delta L = k \times L \times C \times \Delta t \quad (A1.3)$$

where:

- ΔL = change in length,
- k = 1000 for ΔL (mm), L (m), C (°C⁻¹), Δt (°C), or 12 for ΔL (in.), L (ft.), C (°F⁻¹), Δt (°F),
- L = coefficient of linear expansion, and
- Δt = temperature change.

APPENDIX

(Nonmandatory Information)

X1. CORROSION

X1.1 In considering metallic mechanical fittings in designed joints on thermoplastic piping systems, the corrosion aspect of the fitting material must be addressed. Care should be taken to adequately protect the fitting from the effects of galvanic

corrosion in a buried application. These concerns may be alleviated by cathodic protection as specified in Code of Federal Regulations Title 49 Part 192, Paragraph 192.455.

SUMMARY OF CHANGES

Committee F17 has identified the location of selected changes to this standard since the last issue (F1948–12) that may impact the use of this standard.

- (1) Added Specifications **F2785** and **F2897** to Section 2, Reference Documents. (3) Appendix X2 Transition was eliminated and requirements for metal mechanical fitting joints were added to the body of the standard.
- (2) Added transition fitting requirements to body of standard.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>