



Standard Specification for Sheet Linoleum Floor Covering¹

This standard is issued under the fixed designation F2034; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers sheet linoleum floor covering.

1.2 Three types of linoleum floor covering are covered (see Section 4). These floor coverings are intended for use in commercial, light commercial, and residential buildings based on serviceability characteristics. General information and performance characteristics, which determine serviceability and recommended use, are included in this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 11, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

F137 Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus

F141 Terminology Relating to Resilient Floor Coverings

F150 Test Method for Electrical Resistance of Conductive and Static Dissipative Resilient Flooring

F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces

F410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

F710 Practice for Preparing Concrete Floors to Receive Resilient Flooring

¹ This specification is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of F06.80 on Specifications.

Current edition approved Nov. 1, 2013. Published December 2013. Originally approved in 2000. Last previous edition approved in 2008 as F2034-08. DOI: 10.1520/F2034-08R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

F925 Test Method for Resistance to Chemicals of Resilient Flooring

F970 Test Method for Static Load Limit

F1482 Practice for Installation and Preparation of Panel Type Underlayments to Receive Resilient Flooring

F1514 Test Method for Measuring Heat Stability of Resilient Flooring by Color Change

F1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change

F1516 Practice for Sealing Seams of Resilient Flooring Products by the Heat Weld Method (when Recommended)

2.2 *European Norms:*

EN 670 Identification and Composition of Linoleum—Determination of Cement and Ash Residue³

2.3 *American National Standard:*

ANSI/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes⁴

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions, refer to Terminology F141.

4. Classification

4.1 The floor coverings shall be of the following types:

Type I — Linoleum sheet with backing

Type II — Static dissipative linoleum sheet with backing

Type III — Linoleum sheet with special backing

5. Ordering Information

5.1 Linoleum sheet shall be ordered by type, class, thickness, and other characteristics important to the purchaser for the intended use.

5.1.1 Title, number, and date of this specification.

5.1.2 Type, class, and pattern number.

5.1.3 Quantity in square yards (square metres).

5.1.4 Thickness required (see Section 8).

5.1.5 Sampling if other than as specified in ANSI/ASQC Z1.4, level S-1, as noted in Table 1.

³ Available from CEN European Committee for Standardization—Central Secretariat: rue de Stassart, 36 B-1050, Brussels.

⁴ Available from American National Standards Institute, 11 West 42nd St., 13th Floor, New York, NY 10036.

TABLE 1 Performance Requirements

Property	Requirement	Test Method	Reference
Thickness	Average overall thickness shall be the nominal thickness with a tolerance of ± 0.006 in. (0.15 mm)	ASTM F386	11.1
Static load	Residual indentation shall not exceed 0.005 in. (0.12 mm), tested with a load of 150 lb (67.5 kg)	ASTM F970	11.2
Resistance to chemicals	No more than a slight change in surface dulling, surface attack, or staining	ASTM F925	11.3
Resistance to heat	ΔE not more than 8.0	ASTM F1514	11.4
Resistance to light	ΔE not more than 8.0	ASTM F1515	11.5
Flexibility	The wear surface will not crack or break when bent face out (see Table 2)	ASTM F137	11.6
Static dissipation (Type II)	Surface to ground resistance in the range of 1.0×10^6 to 1.0×10^9 Ω tested at 100 or 500 V	ASTM F150	11.7
Wear surface	Wear surface shall be a minimum thickness of 0.04 in. (1 mm)	ASTM F410	11.8

5.1.6 Packing requirement if other than specified (see Section 14).

5.1.7 Marking required if other than specified (see Section 14).

5.1.8 For specific chemical resistance (see 11.3).

5.1.9 Other requirements.

6. Material

6.1 *Wear Surface*—The wear surface is the portion above the fibrous or suitable backing/bedding layer or base coat. The wear surface should have a minimum thickness of 0.04 in. (1 mm).

6.1.1 *Type I/Type II/Type III*—For all types, the wear surface of the linoleum shall consist of a homogeneous mixture of linseed oil or vegetable drying oils, or both; rosin, wood flour, or cork flour, or a combination thereof; color pigments; and inorganic filler. For Type II, the linoleum shall have incorporated into the wearing surface additives, which will give the linoleum electrostatic discharge controlling properties.

6.2 Backings:

6.2.1 *Jute*—The jute backing shall be firmly bonded to and partially embedded in the linoleum mix.

6.2.2 *Special Backing*—In some cases a special backing is added such as cork, polyolefin, or other suitable backing.

6.3 *Composition*—The minimum amount of linoleum cement shall be 30 % when tested in accordance with European Norm 670.

7. Performance Requirements

7.1 Linoleum sheet floor covering shall meet the requirements in Table 1.

8. Dimensions

8.1 Linoleum sheet flooring is available in standard widths of 79 in. (2 m) and typical lengths of 65 ft (20 m) to 105 ft (32 m). Other widths and lengths may be available.

8.2 Linoleum sheet is available in standard thicknesses of 0.080 in. (2.0 mm), 0.100 in. (2.5 mm), 0.125 in. (3.2 mm), and 0.160 in. (4.0 mm). Other gages may be available.

9. Workmanship, Finish, and Appearance

9.1 Materials furnished under this specification shall be an acceptable match to an approved sample(s) in pattern, color, and surface appearance. The product shall be free of defects that would adversely affect performance or appearance.

9.2 Drying room yellowing will disappear when the linoleum is exposed to either natural or artificial light to give a stable color in service; it may reappear or not disappear in areas not exposed to light.

10. Sampling

10.1 Sampling for testing physical characteristics listed in Table 2 shall be done in accordance with the provisions set forth in ANSI/ASQC Z1.4. The inspection level shall be special inspection level S-1 as noted in Table I, and the acceptance quality level (AQL) shall be 6.5 defects per hundred units as noted in Table II-A, or as specified in 10.2.

10.2 Sampling for testing physical characteristics listed shall be done in accordance with provisions set forth in ANSI/ASQC Z1.4. The inspection level shall be special inspection level S-1 as noted in Table I, and the acceptance quality level (AQL) shall be 6.5 defects per hundred units as noted in Table II, or as specified in 10.1.

11. Test Methods

11.1 *Overall Thickness*—The overall thickness when measured shall be determined in accordance with Test Method F386 except that the presser foot shall exert a total force of 1 ± 0.1 oz (28.3 ± 2.8 g) on the specimen. The thickness of the sample should be the average of the measurements on the three specimens taken 12 in. (305 mm) in from each edge and the center of the sample.

11.2 *Static Load*—Residual indentation shall be determined in accordance with Test Method F970, except a load of 150 lb (67.5 kg) shall be applied.

11.3 *Resistance to Chemicals*—The chemical resistance of linoleum sheet flooring shall be determined in accordance with Test Method F925 when exposed to the following chemicals:

TABLE 2 Physical Characteristics

Material thickness	Mandrel Diameter
0.080 in. (2.0 mm)	1.2 in. (30 mm)
0.100 in. (2.5 mm)	1.6 in. (40 mm)
0.125 in. (3.2 mm)	2.0 in. (50 mm)
0.160 in. (4.0 mm)	2.4 in. (60 mm)

White vinegar (5 % acetic acid)
 Rubbing alcohol (70 % isopropyl alcohol)
 White mineral oil (medicinal grade)
 Hydrochloric acid (5 % HCl)
 Sulfuric acid (5 % H₂SO₄)
 Household ammonia solution (5 % NH₄OH)
 Household bleach (5.25 % NaOCl)
 Disinfectant – phenol type (5 % active phenol)
 Kerosene (K1)
 Olive oil (light)
 Unleaded gasoline (regular grade)

NOTE 1—These chemicals are representative of those likely to be found in domestic, commercial, and institutional use. Many proprietary compounds contain one or more of these chemicals. Should the flooring for an unusual application need to be resistant to a specific chemical, this additional requirement should become part of the procurement document.

11.4 *Resistance to Heat*—The resistance of the linoleum sheet flooring to color change from exposure to an elevated temperature of 158°F (70°C), over a specified time of 7 days, shall be determined in accordance with Test Method F1514. Remove drying room film (stove yellowing) by exposing the sample to a Xenon-Arc light source for a minimum of 24 h before measuring initial color.

11.5 *Resistance to Light*—The resistance of the linoleum sheet flooring to color change from exposure to light, simulated by a properly fitted Xenon-Arc radiant energy source, over a specified time of 200 h, shall be determined in accordance with Test Method F1515. Remove drying room film (stove yellowing) by exposing the sample to a Xenon-Arc light source for a minimum of 24 h before measuring initial color.

11.6 *Flexibility*—The flexibility shall be such that the wear surface will not crack or break when bent face out over the specified diameter mandrel.

11.7 *Static Dissipation*—The static dissipative properties of Type II linoleum sheet flooring shall be determined in accordance with Test Method F150 when tested at 100 or 500 V, surface to ground.

11.8 *Wear Surface*—The thickness of the wear surface shall be determined in accordance with Test Method F410. The minimum thickness of the wear surface/topcoat shall be 0.04 in. (1 mm).

12. Inspection

12.1 Sampling for inspection of the sheet linoleum floor covering for defects that would adversely affect performance (9.1) shall be done in accordance with the provisions set forth in ANSI/ASQC Z1.4. The inspection level shall be Level 1 as noted in Table I and the acceptance quality level (AQL) shall be 6.5 defects per hundred units as noted in Table II-A or shall be specified in 12.2.

12.2 Inspection of the linoleum floor covering for defects that would adversely affect performance (Section 7) shall be agreed upon by the purchaser and the manufacturer as part of the procurement documents or shall be as specified in 5.1.

13. Certification

13.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, inspected and packaged in accordance with this specification and has been found to meet the requirements.

14. Packaging, Packing and Marking

14.1 The linoleum floor covering shall be packaged and marked in accordance with normal commercial practice and packed to ensure acceptance by common carrier and to provide product protection against damage during normal shipping, handling, and storage.

14.2 When product sample sets, sample set cover cards, and marketing and technical literature reference this specification, the complete product classification information relative to this specification shall be included.

15. Keywords

15.1 drying room film; jute; linoleum; linoleum cement; rosin; sheet flooring; static dissipative

APPENDIX

(Nonmandatory Information)

X1. ADDITIONAL INFORMATION

X1.1 The following sources can be consulted for additional information:

<i>ASTM Standards:</i>	Practice F710, Guide F1482, and Practice F1516 (when recommended)
<i>Other Sources:</i>	EN 548 Linoleum Floor Coverings

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).