



# Standard Specification for Mechanical Couplings Used on Polyethylene Conduit, Duct and Innerduct<sup>1</sup>

This standard is issued under the fixed designation F2176; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification establishes requirements for material, performance, workmanship and test methods for the qualification of 2 in. and smaller mechanical couplings that connect to DR 15.5 and lower polyethylene conduit, duct and innerduct covered by Specification F2160. Throughout this standard, “conduit” refers to “conduit, duct or innerduct” manufactured in accordance with Specification F2160.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The couplings covered by this specification are typically designed to join between conduit ends (in-line coupling). The same coupling-to-conduit joint design may be used as a part of other coupling joint designs that telescope, or connect to bulkheads, or other adapter fitting designs. The requirements of this standard apply only to the coupling-to-conduit joint design. The performance requirements of other coupling joint designs are not a part of this standard.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 9 of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D638 Test Method for Tensile Properties of Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.10 on Fittings.

Current edition approved March 1, 2009. Published March 2009. Originally approved 2002. Last previous edition approved in 2002 as F2176-02. DOI: 10.1520/F2176-02R09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)

F412 Terminology Relating to Plastic Piping Systems

F2160 Specification for Solid Wall High Density Polyethylene (HDPE) Conduit Based on Controlled Outside Diameter (OD)

## 3. Terminology

3.1 Definitions are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise specified.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *coupling joint, n*—the connection between the coupling and a conduit end.

3.2.2 *duct, n*—a conduit (see Terminology F412, *conduit*).

3.2.3 *inline mechanical couplings, n*—a device used to join two conduit ends.

3.2.4 *innerduct, n*—a conduit installed inside a conduit.

## 4. Materials and Manufacture

4.1 The physical properties of each material used to produce mechanical couplings shall be available from the coupling manufacturer upon request.

4.2 Specifications outlining all the physical properties and effects of environmental conditions for materials of manufacture shall be available from the coupling manufacturer upon request.

NOTE 1—Materials should have a demonstrated resistance to environmental stress cracking when exposed, under stress, to chemical compounds encountered in or external to conduit systems and a demonstrated resistance to bacteriological decomposition. Such compounds include, but are not limited to, alkalines, fertilizers, ice thawing chemicals, insecticides, herbicides, and acids.

## 5. Performance Requirements

5.1 The following requirements shall be met on each coupling design and nominal size. Any revisions by the manufacturer to the original coupling design after the initial qualification testing requires retesting to ensure conformance with these requirements.

NOTE 2—It is permissible when accomplishing these tests to do so on

only the thickest and thinnest (lowest and highest DR) conduit wall sections in Specification F2160 that the coupling is to be used on. If in those tests all performance requirements are met, all wall thicknesses between those tested may be considered as having met the requirements.

## 5.2 Pressure Requirements:

5.2.1 *Sustained Internal Pressure*—The coupling/conduit joint shall not fail by leakage as described by and tested in accordance with 9.1.

5.2.2 *Sustained External Pressure*—The coupling/conduit joint shall not fail by leakage as described by and tested in accordance with 9.2.

## 5.3 Tensile Strength Requirements :

5.3.1 *Pullout Resistance*—The coupling/conduit joint assemblies tested shall be able to comply with tensile loading requirements in Table 1 when tested in accordance with 9.3.

NOTE 3—Minimum pullout resistance's in Table 1 were derived by the following formula. Double the requirements for constant tensile load in Table 2.

5.4 *Constant Tensile Load*—The joint or coupling shall not fail by pullout when loaded to axial tensile load requirements in Table 2 and tested in accordance with 9.4.

NOTE 4—The constant tensile load test is intended to demonstrate that a joint in the conduit system is resistant to the effects of long term creep that may result from temperature changes and other forces after installation. Load values in Table 2 were derived by the following methodology. Nominal modulus of elasticity of high density polyethylene (113 000 psi) × coefficient of thermal expansion (0.00011 in./in./F°) × 50°F (10°C) temperature change × average area of DR11 conduit wall.

5.5 *Impact Resistance*—The coupling shall not fail as defined by and tested in accordance with 9.5.

## 6. Dimensions

6.1 The manufacturer, upon request of the user shall furnish critical dimensions and tolerances of his couplings.

NOTE 5—Because of the varied fitting designs of couplings available for use on PE conduit a table of dimensions would be meaningless and without value and is therefore omitted from this standard.

## 7. Workmanship, Finish, and Appearance

7.1 The manufacture of these couplings shall be in accordance with good commercial practice, uniform in color and free of visual defects such as burrs, cracks, holes, foreign materials or voids so as to produce fittings meeting the requirements of this standard.

## 8. Specimen Preparation

### 8.1 Conditioning:

8.1.1 Unless otherwise specified, condition the specimens (coupling and conduit) at the standard laboratory temperature of 73.4 ± 3.6°F (23 ± 2°C) for not less than 16 h before assembly.

**TABLE 1 Mechanical Joint Pullout Resistance**

Nominal Conduit Size	Minimum Pullout Resistance
¾ IPS	380 lbs (172 kg)
1 IPS	760 lbs (345 kg)
1¼ IPS	940 lbs (426 kg)
1½ IPS	1220 lbs (553 kg)
2 IPS	1920 lbs (871 kg)

**TABLE 2 Mechanical Joint Constant Load Resistance**

Nominal Conduit Size	Minimum Pullout Resistance
¾ IPS	190 lbs (86.2 kg)
1 IPS	380 lbs (172.4 kg)
1¼ IPS	470 lbs (213.2 kg)
1½ IPS	610 lbs (276.7 kg)
2 IPS	960 lbs (435.5 kg)

## 8.2 Preparation of Specimens for Testing:

8.2.1 Prepare test specimens so that the minimum free length of conduit from a joint being tested is not less than five times the conduit diameter. It is permissible to test multiple couplings together provided they are separated by a minimum distance equal to five times the conduit diameter.

8.2.2 Test joints shall be assembled on the appropriate size conduit in accordance with the fitting manufacturer's joining procedure. For referee testing, conduit shall be straight with no scratches or gouges.

8.2.3 Condition assembled test specimens a minimum of 2 h at the test temperature to be used after being assembled before initiating test procedure.

NOTE 6—The additional conditioning time following assembly of typical fitting designs used for conduit joining provides more consistent test results.

8.3 *Test Conditions*—Testing shall be conducted at the standard laboratory temperature of 73.4 ± 3.6°F (23 ± 2°C) unless otherwise specified.

## 9. Test Methods

### 9.1 Sustained Internal Pressure Test:

9.1.1 Test six joints assembled in accordance with 8.2. Pressurize specimens with air to 150 ± 2 psig (1030 ± 10 kPa) and hold at pressure while top of fitting is submerged in water at a depth of 6.00 ± 0.50 in. (152.4 ± 12.7 mm) for one hour. Then, visually monitor the specimens. The coupling shall not fail by leaking as defined by visual bubbles coming from the coupling/conduit interface at a rate greater than one bubble per second.

NOTE 7—**Warning:** Pressure testing with air at the pressures in 9.1.1 can be hazardous in the event of a catastrophic failure of the test specimen. Specimens under pressure should be observed through a transparent shield or other means to assure the safety of the observers.

9.1.2 Failure of two of the six specimens shall constitute failure of the test. Failure of one of the six specimens tested is cause for retest of six additional specimens. Failure of one of the six specimens in the re-test shall constitute failure of the test.

### 9.2 Sustained External Pressure Test:

9.2.1 Test six joints assembled in accordance with 8.2. Externally pressurize the specimen utilizing a suitable pressure vessel. Pressurize the vessel with water to 10 psi (69 kPa) and monitor for leakage for 1000 h. Leakage of water into the conduit constitutes failure of the joint.

NOTE 8—It is permissible rather than the external test as described in 9.2.1 to draw a vacuum on the test specimens while submerged in water at a depth of not more than 6 in. (152.4 mm).

9.2.2 Failure of two of the six specimens tested shall constitute failure of the test. Failure of one of the six specimens tested is cause for re-test of six additional specimens. Failure of one of the six specimens in re-test shall constitute failure of the test.

### 9.3 Tensile Strength Test:

9.3.1 In-line couplings shall be tested with the apparatus specified in Test Method **D638**.

9.3.2 Test six joint specimens assembled in accordance with **8.2**. The speed of the testing shall be 0.2 in./min (5.0 mm/min)  $\pm 25\%$ . The joint design fails if the minimum load requirements specified in **Table 1** are not reached.

9.3.3 Failure of two of the six specimens tested shall constitute failure of the test. Failure of one of the six specimens tested to achieve the minimum load specified in **Table 1** is cause for re-test of six additional specimens. Failure of one of the six additional specimens to achieve the minimum load in the re-test shall constitute failure of the test.

### 9.4 Constant Tensile Load Test :

9.4.1 One specimen of each nominal pipe size coupling shall be tested by application of axial in line loading to the values stated in **Table 2** for a minimum time period of 1000 h.

NOTE 9—Any loading method that maintains the correct, in-line tensile load on the joint for the required duration is acceptable. Dead weight (a pile of scrap iron or steel) has worked well for loads up to 2000 lbs (907 kg).

9.4.2 Conduit pull out of the coupling specimen before the test time is completed constitutes failure of the test.

### 9.5 Impact Test:

9.5.1 Select six specimens at random and condition in freezer at  $10 \pm 5^\circ\text{F}$  ( $-12.2 \pm 2^\circ\text{C}$ ) for not less than 16 h.

9.5.2 Remove the specimens from the freezer one at a time and impact with a force of 20 ft-lbf using Tup “B” as described in Test Method **D2444**.

9.5.3 Visually inspect each specimen after impact test for failure. Failure is defined as shattering or any crack or split created by the impact that can be seen with the naked eye.

9.5.4 Failure of two of the six specimens tested shall constitute failure of the test. Failure of one of the six specimens tested is cause for retest of six additional specimens. Failure of one of the six additional specimens in retest shall constitute failure of the test.

## 10. Product Marking

10.1 The coupling shall be marked with the following information. Required markings shall remain legible under normal handling up to the time of installation.

10.1.1 Manufacturer’s name or trademark.

10.1.2 Size of the conduit suitable for joining by the coupling.

10.1.3 This designation, Specification F2176.

## 11. Installation Instructions

11.1 Manufacturer’s installation instructions shall be supplied with the coupling packaging.

## 12. Quality Assurance

12.1 When the product is marked with this designation, Specification F2176, the manufacturer affirms that the product was manufactured, inspected, sampled and tested in accordance with this specification and has been found to meet the requirements of this specification.

## 13. Keywords

13.1 conduit; duct; innerduct; mechanical fitting

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*