



# Standard Specification for Additive Manufacturing Nickel Alloy (UNS N06625) with Powder Bed Fusion<sup>1</sup>

This standard is issued under the fixed designation F3056; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

---

<sup>ε1</sup> NOTE—In Tables 1 and 2, Columbium was changed to Niobium editorially in November 2014.

---

## 1. Scope

1.1 This specification covers additively manufactured UNS N06625 components using full-melt powder bed fusion such as electron beam melting and laser melting. The components produced by these processes are used typically in applications that require mechanical properties similar to machined forgings and wrought products. Components manufactured to this specification are often, but not necessarily, post processed via machining, grinding, electrical discharge machining (EDM), polishing, and so forth to achieve desired surface finish and critical dimensions.

1.2 This specification is intended for the use of purchasers or producers, or both, of additively manufactured UNS N06625 components for defining the requirements and ensuring component properties.

1.3 Users are advised to use this specification as a basis for obtaining components that will meet the minimum acceptance requirements established and revised by consensus of the members of the committee.

1.4 User requirements considered more stringent may be met by the addition to the purchase order of one or more supplementary requirements, which may include, but are not limited to, those listed in Supplementary Requirements S1–S16.

1.5 *Units*—The values stated in SI units are to be regarded as the standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 *ASTM Standards*:<sup>2</sup>

- B213 Test Methods for Flow Rate of Metal Powders Using the Hall Flowmeter Funnel
- B214 Test Method for Sieve Analysis of Metal Powders
- B243 Terminology of Powder Metallurgy
- B311 Test Method for Density of Powder Metallurgy (PM) Materials Containing Less Than Two Percent Porosity
- B769 Test Method for Shear Testing of Aluminum Alloys
- B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys
- B964 Test Methods for Flow Rate of Metal Powders Using the Carney Funnel
- D3951 Practice for Commercial Packaging
- E3 Guide for Preparation of Metallographic Specimens
- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E9 Test Methods of Compression Testing of Metallic Materials at Room Temperature
- E10 Test Method for Brinell Hardness of Metallic Materials
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E21 Test Methods for Elevated Temperature Tension Tests of Metallic Materials
- E23 Test Methods for Notched Bar Impact Testing of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E238 Test Method for Pin-Type Bearing Test of Metallic Materials
- E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

---

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F42 on Additive Manufacturing Technologies and is the direct responsibility of Subcommittee F42.05 on Materials and Processes.

Current edition approved Feb. 1, 2014. Published March 2014. DOI: 10.1520/F3056-14E01.

---

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**E384** Test Method for Knoop and Vickers Hardness of Materials

**E399** Test Method for Linear-Elastic Plane-Strain Fracture Toughness  $K_{Ic}$  of Metallic Materials

**E407** Practice for Microetching Metals and Alloys

**E466** Practice for Conducting Force Controlled Constant Amplitude Axial Fatigue Tests of Metallic Materials

**E606** Test Method for Strain-Controlled Fatigue Testing

**E647** Test Method for Measurement of Fatigue Crack Growth Rates

**E1019** Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

**E1417** Practice for Liquid Penetrant Testing

**E1450** Test Method for Tension Testing of Structural Alloys in Liquid Helium

**E1473** Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

**E1820** Test Method for Measurement of Fracture Toughness

**E1941** Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis

**E2368** Practice for Strain Controlled Thermomechanical Fatigue Testing

**F629** Practice for Radiography of Cast Metallic Surgical Implants

**F2792** Terminology for Additive Manufacturing Technologies<sup>3</sup>

**F2924** Specification for Additive Manufacturing Titanium-6 Aluminum-4 Vanadium with Powder Bed Fusion

2.2 *ISO/ASTM Standards:*<sup>2</sup>

**52915** Specification for Additive Manufacturing File Format (AMF) Version 1.1

**52921** Terminology for Additive Manufacturing—Coordinate Systems and Test Methodologies

2.3 *ASQ Standard:*<sup>3</sup>

**ASQ C1** Specification of General Requirements for a Quality Program

2.4 *ISO Standards:*<sup>4</sup>

**ISO 148-1** Metallic materials—Charpy pendulum impact test—Part 1: Test method

**ISO 1099** Metallic materials—Fatigue testing—Axial force-controlled method

**ISO 4545** Metallic materials—Knoop hardness test—Part 2: Verification and calibration of testing machines

**ISO 6506-1** Metallic materials—Brinell hardness test—Part 1: Test method

**ISO 6507-1** Metallic materials—Vickers hardness test—Part 1: Test method

**ISO 6508** Metallic materials—Rockwell hardness test—Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)

**ISO 6892-1** Metallic materials—Tensile testing at ambient temperature

**ISO 6892-2** Metallic materials—Tensile testing—Part 2: Method of test at elevated temperature

**ISO 9001** Quality management system—Requirements

**ISO 9044** Industrial woven wire cloth—Technical requirements and testing

**ISO 12108** Metallic materials—Fatigue testing—Fatigue crack growth method

**ISO 12111** Metallic materials—Fatigue testing—Strain-controlled thermomechanical fatigue testing method

**ISO 12135** Metallic materials—Unified method of test for the determination of quasistatic fracture toughness

**ISO 12737** Metallic materials—Determination of plane-strain fracture toughness (withdrawn)

**ISO 13485** Medical devices—Quality management systems—Requirements for regulatory purposes

**ISO 19819** Metallic materials—Tensile testing in liquid helium

2.5 *Military Standard:*<sup>5</sup>

**MIL-C-24615A** Military Specification, Castings, Nickel-Chromium-Molybdenum, Columbium Alloy

2.6 *SAE Standards:*<sup>6</sup>

**AMS 2269** Chemical Check Analysis Limits Nickel, Nickel Alloys, and Cobalt Alloys

**AMS 5599** Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip, and Plate 62Ni-21.5Cr-9.0Mo-3.7Cb (Nb) Solution Heat Treated

**AMS 2774** Heat Treatment Wrought Nickel Alloy and Cobalt Alloy Parts

**AS 9100** Quality Systems—Aerospace—Model for Quality Assurance in Design, Development, Production, Installation and Servicing

2.7 *ASME Standard:*<sup>7</sup>

**ASME B46.1** Surface Texture

2.8 *NIST Standard:*<sup>8</sup>

**IR 7847** (March 2012) CODEN:NTNOEF

### 3. Terminology

#### 3.1 Definitions:

- 3.1.1 Terminology relating to powder bed fusion in Specification **F2924** shall apply.
- 3.1.2 Terminology relating to additive manufacturing in Terminology **F2792** shall apply.
- 3.1.3 Terminology relating to coordinate systems in Terminology **52921** shall apply.
- 3.1.4 Terminology relating to powder metallurgy in Terminology **B243** shall apply.

### 4. Classification

4.1 Unless otherwise specified herein, all classifications shall meet the requirements in each section of this standard.

<sup>5</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

<sup>6</sup> Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

<sup>7</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

<sup>8</sup> Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

<sup>3</sup> Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

- 4.1.1 Class A components shall be stress relieved or annealed per Section 12.
- 4.1.2 Class B components shall be annealed per Section 12.
- 4.1.3 Class C components shall be hot isostatically pressed per Section 13.
- 4.1.4 Class D—Not Used.
- 4.1.5 For Class E components, all thermal post processing shall be optional.
- 4.1.6 Class F—Not Used.

## 5. Ordering Information

5.1 Orders for components compliant with this specification shall include the following to describe the requirements adequately:

- 5.1.1 This specification designation,
- 5.1.2 Description or part number of product desired,
- 5.1.3 Quantity of product desired,
- 5.1.4 Classification,
- 5.1.5 SI or SAE units,
  - 5.1.5.1 *Discussion*—The STL file format used by many powder bed fusion machines does not contain units of measurement as metadata. When only STL files are provided by the purchaser, ordering information should specify the units of the component along with the electronic data file. More information about data files can be found in ISO/ASTM 52915.
- 5.1.6 Dimensions and tolerances (Section 14),
- 5.1.7 Mechanical properties (Section 11),
- 5.1.8 Methods for chemical analysis (Section 9),
- 5.1.9 Sampling methods (Section S16),
- 5.1.10 Post-processing sequence of operations,
- 5.1.11 Thermal processing,
- 5.1.12 Allowable porosity (Section S8),
- 5.1.13 Component marking such as labeling the serial or lot number in the CAD file prior to the build cycle, or product tagging,
- 5.1.14 Packaging,
- 5.1.15 Certification,
- 5.1.16 Disposition of rejected material (Section 15), and
- 5.1.17 Other supplementary requirements.

## 6. Manufacturing Plan

6.1 Class A, B, C, and E components manufactured to this specification shall have a manufacturing plan that includes, but is not limited to, the following:

6.1.1 A machine, manufacturing control system, and qualification procedure as agreed between component supplier and purchaser;

*NOTE 1*—Qualification procedures typically require qualification build cycles in which mechanical property test specimens are prepared and measured in accordance with Section 11 or other applicable standards. Location, orientation on the build platform, number of test specimens for each machine qualification build cycle, and relationship between specimen test results and component quality shall be agreed upon between component supplier and purchaser.

- 6.1.2 Feedstock that meets the requirements of Section 7;
- 6.1.3 The machine identification, including machine software version, manufacturing control system version (if

automated), build chamber environment, machine conditioning, and calibration information of the qualified machine;

- 6.1.4 Predetermined process as substantiated by the qualification procedure;
- 6.1.5 Safeguards to ensure traceability of the digital files, including design history of the components;
- 6.1.6 All the steps necessary to start the build process, including build platform selection, machine cleaning, and powder handling;
- 6.1.7 The requirements for approving machine operators;
- 6.1.8 Logging of machine build data files, upper and lower limits of the parameters affecting component quality and other process validation controls;
- 6.1.9 The number of components per build cycle, their orientation and location on the build platform, and support structures, if required;
- 6.1.10 Process steps including, but not limited to, Section 8;
- 6.1.11 Post-processing procedure, including sequence of the post-processing steps and the specifications for each step;
- 6.1.12 Thermal processing including stress relieve, furnace anneal, hot isostatic pressing, and heat treat; and
- 6.1.13 Inspection requirements as agreed between the purchaser and component supplier, including any supplementary requirements.

## 7. Feedstock

7.1 The feedstock for this specification shall be metal powder, as defined in ASTM B243, that has the powder type, size distribution, shape, tap density, and flow rate acceptable for the process as determined by the component supplier.

7.2 The metal powder shall be free from detrimental amounts of inclusions and impurities and its chemical composition shall be adequate to yield, after processing, the final material chemistry listed in Table 1.

7.3 Powder blends are allowed unless otherwise specified between the component supplier and component purchaser, as long as all powder used to create the powder blend meets the requirements in Table 1 and lot numbers are documented and maintained.

7.4 Used powder is allowed. The proportion of virgin powder to used powder shall be recorded and reported for each production run. The maximum number of times used powder

**TABLE 1 Composition (wt %)**

Element	min	max
Carbon	–	0.10
Manganese	–	0.50
Silicon	–	0.50
Phosphorus	–	0.015
Sulfur	–	0.015
Chromium	20.00	23.00
Cobalt	–	1.00
Molybdenum	8.00	10.00
Niobium	3.15	4.15
Titanium	–	0.40
Aluminum	–	0.40
Iron	–	5.00
Nickel		remainder

can be used as well as the number of times any portion of a powder lot can be processed in the build chamber should be agreed upon between component supplier and purchaser for Class A, B, and C. There are no limits on the number of build cycles for used powder for Class E components. After a build cycle, any remaining used powder may be blended with virgin powder to maintain a powder quantity large enough for next build cycle. The chemical composition of used powders shall be analyzed regularly, as agreed upon between component supplier and purchaser. Powder not conforming to [Table 1](#) or [7.7](#) shall not be further processed in the machine to manufacture Class A, B, and C components.

7.4.1 All used powder shall be sieved with a sieve having a mesh size appropriate for removing any agglomerates or contaminants from the build cycle.

7.5 All powder sieves used to manufacture Class A, B, and C components shall have a certificate of conformance that they were manufactured to ISO 9044 or all powder sieving shall be in conformance with Specification [E11](#).

7.6 Sieve analysis of used powder or powder lots during incoming inspection or in-process inspection shall be made in accordance with Test Method [B214](#) or as agreed between component supplier and purchaser.

7.7 The maximum percentage of any element in [Table 1](#) may be increased for virgin powder, used powder and powder blends when agreed upon between component supplier and purchaser. When component supplier and purchaser agree to an increase in the maximum percentage of any element, [9.2](#) shall apply.

7.8 Any powder lot or powder blend containing any used powder shall be considered used powder.

## 8. Process

8.1 Processing shall be conducted per applicable standards or as agreed upon between component supplier and purchaser according to an approved manufacturing plan as described in Section [6](#).

8.1.1 Test specimens for quality assurance may be required to be built and tested in accordance with Section [11](#) with each build cycle or before and after a production run as agreed upon between the component supplier and purchaser.

NOTE 2—In addition to tension test specimens, fatigue test specimens may be required by the purchaser to be built with the components at the beginning and end of each production run. Fatigue testing is described in Supplementary Requirement S6.

8.2 Permissible parameter, process changes and extent of external intervention during the build cycle shall be identified in the manufacturing plan. All process changes shall be continuously monitored and recorded. When agreed to by the purchaser, minor changes to the manufacturing plan are permissible without machine requalification.

8.3 Condition and finish of the components shall be agreed upon between the component supplier and purchaser.

8.4 Post-processing operations may be used to achieve the desired shape, size, surface finish, or other component proper-

ties. The post-processing operations shall be agreed upon between the component supplier and purchaser for Class A, B, and C components.

## 9. Chemical Composition

9.1 Except for Class E, as built components shall conform to the percentages by weight shown in [Table 1](#). Carbon, Sulfur, Nitrogen, and Oxygen shall be determined in accordance with Test Methods [E1019](#) and other elements in accordance with Test Methods [E354](#). Chemical composition shall be determined by Test Methods [E1473](#), [E1019](#), or [E1941](#), or combination thereof, as appropriate. Other analytical methods may be used if agreed upon by the component supplier and purchaser.

9.2 Chemical check analysis limits shall be in accordance with AMS 2269 or Specification [B880](#) and [Table 2](#). Chemical check analysis tolerances do not broaden the limits in [Table 1](#), but cover variations between laboratories in the measurement of chemical content. The supplier shall not ship components that are outside the limits specified in [Table 1](#).

9.3 The chemical composition requirements in this specification for UNS N06625 components are the same as specification AMS 5599 for wrought alloy.

## 10. Microstructure

10.1 The microstructural requirements and frequency of examinations shall be mutually agreed upon by the supplier and purchaser. Specimen preparation shall be in accordance with Guide [E3](#) and Practice [E407](#).

## 11. Mechanical Properties

11.1 Build platform coordinates and build platform location for test specimens shall be used in accordance with ISO/ASTM [52921](#).

11.2 Tension test specimens shall be prepared in accordance with ISO/ASTM [E8/E8M](#) either before or after thermal processing as agreed upon by component supplier and purchaser.

11.3 In accordance to with ISO/ASTM [52921](#), specimens used for tension testing shall be machined from bulk deposition, machined from bars or taken from near net shape specimens and built in X, Y, Z, or other orientations as agreed with purchaser.

**TABLE 2 Check Analysis Tolerances**

Check Analysis Tolerances (wt %)	
Element	Permissible Variation in Check Analysis
Carbon	±0.01
Manganese	±0.03
Silicon	±0.03
Phosphorus	±0.005
Sulfur	±0.003
Chromium	±0.25
Cobalt	±0.03
Molybdenum	±0.15
Niobium	±0.15
Aluminum	±0.05
Titanium	±0.03
Iron	±0.07
Nickel	±0.45

NOTE 3—Mechanical properties of the test specimens may vary because of the location of the sample on the build platform and the test specimen orientation. Whether or not the test specimens are near net shape or machined from larger blocks is a matter of preference.

11.4 Tensile properties on test specimens shall conform to **Table 3**, as determined in accordance with Test Methods **E8/E8M** at a strain rate of 0.003 to 0.007 mm/mm/min through yield and then the crosshead speed may be increased so as to produce failure in approximately one additional minute.

## 12. Thermal Processing

12.1 When required, Class A components shall be stress relieved or annealed as agreed between component supplier and purchaser. Stress relief is optional for all other classifications.

NOTE 4—Stress relief is typically performed while the components are attached to the build platform. AMS 2774 provides stress relief guidance. Some residual stress may remain depending on the stress relief processing. Components manufactured on some powder bed fusion machines may not require a stress relief procedure. Components processed to **12.1** may require further thermal processing.

12.2 Class B components shall be annealed per AMS 2774. Other classifications may be annealed as agreed between component supplier and purchaser.

12.3 Class C components shall be stress relieved and removed from the platform, hot isostatically pressed (HIP) per Section **13** and then annealed per AMS 2774.

12.4 Class D—Classification not used.

12.5 Class F—Classification not used.

## 13. Hot Isostatic Pressing

13.1 HIP is required for Class C components and optional for all other classifications.

13.1.1 Process components under inert atmosphere at not less than 100 MPa within the range of 1120 to 1175°C; hold at the selected temperature within  $\pm 15^\circ\text{C}$  for 240 min  $\pm$  60 min and cool under inert atmosphere to below 425°C, or to parameters as agreed upon between the component supplier and purchaser.

## 14. Dimensions and Permissible Variations

14.1 Tolerances on as-built components shall be agreed upon by the component supplier and purchaser.

14.2 As-built components may be machined to meet dimensional requirements.

14.3 Component repair by welding shall be approved by the purchaser.

## 15. Retests

15.1 If the results of any chemical or mechanical property test or any inspection method, including S1–S15, on a component are not in conformance with the requirements of this specification, the component may be retested at the option of the manufacturer.

15.1.1 The frequency of the retest will be double the initial number of tests. If the results of the retest conform to the requirement, then the retest values will become the test values for certification.

15.2 All test results including the original test results and the conforming retest results shall be reported to the purchaser.

15.3 If any of the results for the retest fail to conform to this specification, the material shall be rejected in accordance with Section **17**.

## 16. Inspection

16.1 Inspection criteria shall be agreed upon by the component supplier and purchaser.

## 17. Rejection

17.1 Components not conforming to this specification, or modifications to this specification that are not authorized by the purchaser, will be subject to rejection.

17.2 All rejected components shall be quarantined and reported to the component purchaser.

## 18. Certification

18.1 A certificate, including a complete test report, shall be provided by the component supplier at the time of shipment stating that the components were manufactured and tested in accordance with this specification.

18.2 If the component supplier and purchaser are one and the same, equivalent internal documentation shall be acceptable in lieu of certification.

## 19. Product Marking and Packaging

19.1 Each component shall be identified as agreed upon between the component supplier and purchaser.

**TABLE 3 Minimum Tensile Properties<sup>A,B</sup>**

Room Temperature Classification	Tensile Strength MPa X and Y Directions	Tensile Strength MPa Z Direction	Yield Strength at 0.2% Offset MPa X and Y Directions	Yield Strength at 0.2% Offset MPa Z Direction	Elongation in 5 cm or 4D (%) X and Y Direction	Elongation in 5 cm or 4D (%) Z Direction	Reduced Area X and Y Direction	Reduced Area Z Direction
A, B, C E	485 no requirement	485 no requirement	275 no requirement	275 no requirement	30 no requirement	30 no requirement	30 no requirement	30 no requirement

<sup>A</sup> A gauge length corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser (5.65 times the square root of S<sub>0</sub>, where S<sub>0</sub> is the original cross-sectional area).

<sup>B</sup> Mechanical properties conform to MIL-C-24615A Grade B.

19.2 Unless otherwise specified, components purchased under this specification shall be packaged in accordance with the manufacturer's standard practice or Practice **D3951**.

## 20. Quality Program Requirements

20.1 The component supplier and its metal powder supplier shall maintain a quality program as defined in ASQ C1 or other recognized quality management systems such as ISO 9001, AS 9100, or ISO 13485 for Class A, B and C components.

NOTE 5—To ensure full component and feedstock traceability, the component purchaser should require the component supplier to use and maintain a comprehensive manufacturing control system except for Class

E components. What constitutes a comprehensive manufacturing control system shall be agreed upon between component supplier and purchaser.

## 21. Significance of Numerical Limits

21.1 All observed or calculated values shall be rounded to the nearest unit in the last right hand digit used in expressing the specification limit, in accordance with the rounding method of Practice **E29**.

## 22. Keywords

22.1 additive manufacturing; electron beam melting; metal laser sintering; selective laser melting

## SUPPLEMENTARY REQUIREMENTS

### S1. Furnace Anneal

S1.1 Furnace anneal shall be performed to specifications as agreed between the component supplier and purchaser.

### S2. Liquid Penetrant

S2.1 Testing shall be performed on component surfaces after machining only.

S2.2 Fluorescent penetrant inspection in accordance with Practice **E1417** with the sensitivity level agreed by the component supplier and purchaser shall be performed on all components.

### S3. Radiographic Examination

S3.1 Components shall be subject to radiographic examination in accordance with Practice **F629**. Acceptance criteria and sampling plan other than 100 % inspection shall be agreed upon between component supplier and purchaser.

### S4. Hardness Test

S4.1 Hardness tests shall be performed in accordance with the requirements of ASTM **E10** or ASTM **E18** as agreed upon by component supplier and purchaser.

### S5. Fracture Toughness

S5.1 Static fracture toughness shall be tested in accordance with Test Method **E399** or Test Method **E1820**. Dynamic fracture toughness shall be tested in accordance with Test Methods **E23**. Use of other relevant methods requires prior agreement between the component supplier and purchaser.

### S6. Fatigue Testing

S6.1 It is recommended that users evaluate fatigue properties for powder bed fusion components that experience dynamic loads in service. Fatigue testing shall be in accordance with Practice **E466**, Test Method **E606**, or other relevant methods and performed as agreed between the component supplier and purchaser.

### S7. Feedstock Flow Rate

S7.1 In powder bed fusion machines, the feedstock should have a flow rate that is optimized for each process. The powder flow rate shall be measured in accordance with Test Methods **B964** or Test Methods **B213**.

NOTE S1—Physical characteristics such as inter-particle friction and particle size of UNS N06625 powder can vary significantly depending upon the process used to produce the powder. These physical variations subsequently lead to variations in powder flow characteristics. These powder flow variations can be critical in additive manufacturing powder bed fusion machines, and if not addressed properly, may lead to defects such as porosity in the components. Thus, changes in feedstock vendors may require revalidation of the process.

### S8. Component Density

S8.1 Component density shall be measured in accordance with Test Method **B311**.

### S9. Contamination from Powder Distribution System

S9.1 The powder distribution system should be non-contaminating to the feedstock for Class A, B and C components. What constitutes non-contaminating shall be agreed upon between the component supplier and purchaser.

### S10. Surface Finish

S10.1 As built surface finish can vary significantly depending on process, machine, and material parameters and orientation. Surface finish should be agreed upon between component supplier and purchaser as measured in accordance with ASME B46.1 or other relevant methods.

### S11. Compression

S11.1 Compression shall be tested in accordance with Test Methods **E9**.

### S12. Shear

S12.1 Shear shall be tested in accordance with Test Method **B769**.

### S13. Bearing

S13.1 Pin-type bearing shall be tested in accordance with Test Method **E238**.

### S14. Crack Growth

S14.1 Crack growth shall be determined by Test Method **E647** or as agreed between the component supplier and purchaser.

## **S15. Other Supplemental Requirements**

S15.1 Other tests may be performed on components as agreed upon between the component supplier and purchaser.

## **S16. Quality Assurance**

S16.1 When specified in the purchase order or contract:

S16.1.1 The components as received by the purchaser shall meet engineering tolerances and notes and other requirements of the purchaser order.

S16.1.2 Components shall be free from cracks, defects, discontinuities, foreign material, inclusions, imperfections, and porosity detrimental to the usage of the component.

S16.1.3 When agreed upon between the component supplier and purchaser, a first-article inspection shall be performed on one component for each part number.

S16.1.3.1 Multiple components may be included in a first-article production run.

S16.1.3.2 The first-article inspection shall include verification of the requirements of the engineering drawing and all test results.

S16.1.4 Manufacturing lot inspection shall be performed in accordance with the manufacturing plan. Inspection criteria shall be agreed upon between the component supplier and purchaser.

S16.1.5 The inspection and sequence of operations shall be carried out as listed in the manufacturing plan.

S16.1.6 Manufacturing lots rejected on the basis of a sampling plan, regardless of the inspection method, may be resubmitted for 100 % inspection and unacceptable components removed from the lot.

S16.1.7 Individual component rejection shall apply in those instances in which 100 % inspection is required in the manufacturing plan and any individual component fails an inspection method. Only unacceptable components need to be rejected when the balance of the components in the manufacturing lot meet inspection requirements.

## **APPENDIX**

### **(Nonmandatory Information)**

#### **X1. ADDITIVE MANUFACTURING OF METALS IN POWDER BED FUSION**

X1.1 Commercially available full-melt, powder bed additive manufacturing systems have two main heat sources: laser and electron beam. Although both heat sources produce UNS N06625 components with nearly no porosity and good mechanical properties, the technologies differ significantly in their implementation, which upon examination can show differences in microstructure and the need for furnace annealing. The purchaser should be educated as to the differences in the processes and enforce additional requirements where appropriate.

X1.2 The commercially available powder bed fusion systems that fully melt metal powders to create components are machines that typically allow the operator much latitude in terms of process parameters. Adjustments by the operator or from other sources to the process parameters can have a dramatic effect on surface finish, internal porosity, mechanical properties, and chemical composition. Therefore, the manufacturing control system will contain safeguards to prevent changes of the validated digital component files and of the process parameters and track the planned versus real process parameters. It is also a recommendation that Class A, B and C components have tension test specimens built and tested as part of the machine validation process. Components built with a robust manufacturing plan are likely to have similar properties to the test specimens. Additionally, this specification allows the purchaser to require tension test samples to be included with each component build cycle; however, this requirement should

only be enforced when lot testing is not adequate or when each process cycle has significantly different components in terms of geometry.

X1.3 Suppliers of UNS N06625 powder bed fusion components should use a validated, fixed process that takes into account and minimizes machine to machine and operator variability. The supplier and purchaser should agree upon what constitutes a validated process and ensure the manufacturing plan is accurate, comprehensive, adequate, monitored and continuously recorded for the components being procured.

X1.4 In order for this standard to be accepted internationally, ISO and ASTM reference standards were cited where applicable. In 2012 the National Institute of Standards and Technology (NIST) published an internal report, IR 7847, called Mechanical Properties Testing for Metal Parts Made via Additive Manufacturing: A Review of the State of the Art of Mechanical Property Testing. In this internal report, the authors compared ISO and ASTM testing methods for determining properties of metal materials. The following chart shows the equivalent and significantly similar test methods between ISO and ASTM as determined by IR 7847. Care should be taken when substituting test methodology and there should be agreement between component supplier and purchaser on all test methods.

**TABLE X1.1 Comparison of Similar ASTM and ISO Test Methods for Metals**

ASTM Spec	ISO Spec	Notes
<b>E8/E8M</b>	6892-1	tension test 10°C-38°C
<b>E21</b>	6892-2	tension test >38°C
<b>E1450</b>	19819	tension test <-196°C
<b>E10</b>	6506-1	Brinell hardness 10°C-35°C
<b>E18</b>	6508	Rockwell B, C hardness
<b>E384</b>	4545-1	Knoop Hardness
<b>E384</b>	6507-1	Vickers Hardness
<b>E606</b>	1099	fatigue test 10°C-35°C, strain controlled
<b>E647</b>	12108	crack growth
<b>E2368</b>	12111	fatigue, thermomechanical, strain controlled
<b>E399</b>	12737	fracture toughness, plane-strain
<b>E1820</b>	12135	fracture toughness
<b>E23</b>	148-1	Charpy and Izod tests

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>