



Standard Specification for Oxygen-Free Copper in Wrought Forms for Electron Devices¹

This standard is issued under the fixed designation F68; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for wrought and fabricated shapes made from Copper UNS² No. C10100, conforming to the chemical requirements of Specification **B170**, Grade 1, and suitable for use in electron devices.

1.2 The requirements of this specification are in addition to those prescribed in the following product specifications appropriate to the material being ordered: **B1**, **B2**, **B3**, **B75/B75M**, **B152/B152M**, **B170**, **B187/B187M**, **B188**, **B272**, and **B372**. In case of conflict, however, this specification shall take precedence.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3.1 *Exception*—grain sizes are in metric units and are standard.

1.4 The following safety hazard caveat applies to sections **17.4**, **17.5** and **18.7** of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

B1 Specification for Hard-Drawn Copper Wire

¹ This specification is under the jurisdiction of ASTM Committee **B05** on Copper and Copper Alloys and is the direct responsibility of Subcommittee **B05.02** on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Oct. 1, 2016. Published November 2016. Originally approved in 1966. Last previous edition approved in 2010 as F68 – 10. DOI: 10.1520/F0068-16.

² The UNS System for copper and copper alloys (see Practice **E527**) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

B2 Specification for Medium-Hard-Drawn Copper Wire
B3 Specification for Soft or Annealed Copper Wire
B75/B75M Specification for Seamless Copper Tube
B152/B152M Specification for Copper Sheet, Strip, Plate, and Rolled Bar
B170 Specification for Oxygen-Free Electrolytic Copper—Refinery Shapes
B187/B187M Specification for Copper, Bus Bar, Rod, and Shapes and General Purpose Rod, Bar, and Shapes
B188 Specification for Seamless Copper Bus Pipe and Tube
B193 Test Method for Resistivity of Electrical Conductor Materials
B272 Specification for Copper Flat Products with Finished (Rolled or Drawn) Edges (Flat Wire and Strip)
B372 Specification for Seamless Copper and Copper-Alloy Rectangular Waveguide Tube
B577 Test Methods for Detection of Cuprous Oxide (Hydrogen Embrittlement Susceptibility) in Copper
B846 Terminology for Copper and Copper Alloys
E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
E112 Test Methods for Determining Average Grain Size
E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 *ASTM Adjunct: Comparison Chart*⁴

3. Terminology

3.1 For definitions of terms related to this product, refer to Terminology **B846**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *rms, n*—root-mean-square, a statistical measure of surface roughness usually determined by means of a profilometer.

4. Ordering Information

4.1 Include the following specified choices when placing orders for product under this specification, as appropriate:

⁴ Available from ASTM International Headquarters. Order Adjunct No. **ADJF0068**. Original adjunct produced in 1966.

*A Summary of Changes section appears at the end of this standard

- 4.1.1 ASTM designation and year of issue of both Specification F68 and the basic product specification involved,
- 4.1.2 Temper,
- 4.1.3 Dimensions and form,
- 4.1.4 How furnished: straight lengths of coils,
- 4.1.5 Quantity: Total weight or length or number of pieces of each size,
- 4.1.6 The Specification F68 Class of material,
- 4.1.7 Intended application (for example, wave guide),

4.2 The following options are available but may not be included unless specified at the time of placing the order when required:

- 4.2.1 Heat identification or traceability details,
- 4.2.2 Certification,
- 4.2.3 Mill test report,
- 4.2.4 Special packaging,
- 4.2.5 Special marking,
- 4.2.6 If special temper requirements for sheet and strip for gasket applications are required.

5. Materials and Manufacture

5.1 *Material*—The material shall be oxygen-free electronic copper which conforms to the requirements of Specification B170, Grade 1.

5.2 *Manufacture*—The manufacturing process shall conform to the requirements of this specification and to the basic product specification to which the product was ordered.

6. Chemical Composition

6.1 The cast refinery shape shall conform to the requirements specified in Specification B170, Grade 1, Table 1.

6.1.1 Copper shall be taken as the difference between the sum of results for Grade 1 specified elements in Table 1 and 100 %.

6.2 These composition limits do not preclude the possible presence of other unnamed elements. Limits may be established and analysis required for elements not specified in Table 1 of B170 by agreement between the manufacturer and the purchaser.

7. Temper

7.1 The temper of the wrought or fabricated product supplied shall conform to the requirements of the basic product specification to which it was ordered.

8. Physical Properties

8.1 *Electrical Resistivity*—The maximum mass resistivity shall be 0.15176 ohms g/m² (conductivity 101.0 % minimum, International Annealed Copper Standard (IACS) at 20°C when tested in the annealed condition.

8.2 *Scaling*—When agreed upon between customer and supplier, the test specimens of oxygen-free copper shall show substantial surface oxide adherence when subjected to test as described in 18.7.

NOTE 1—The purpose of this test is to distinguish between oxygen-free copper and deoxidized copper. Deoxidized copper will not retain the surface oxide in this test.

9. Mechanical Properties

9.1 All products shall conform to the mechanical property requirements of the basic product specification to which the item was ordered, with the following exception:

9.1.1 Sheet and strip with a thickness of 0.125 in. or less and intended for gaskets or for deep drawing shall conform to the requirements prescribed in Table 1, and when so specified 4.2.6 of Ordering Information.

10. Hydrogen Embrittlement (Reverse Bend Test Method)

10.1 Specimens shall withstand a minimum of ten reverse bends without breaking when prepared in accordance with B577 Test Method D. Evidence of blisters, upon visual examination, shall be cause for rejection.

NOTE 2—Fractured areas of the bent samples should show some reduction in area and have a distorted, smeared surface. The ideal break will have the appearance of a cup and cone tensile failure.

11. General Examination

11.1 When examined the samples shall have:

- 11.1.1 A relatively uniform surface free of irregular rough spots sometimes termed open grains,
- 11.1.2 Edges free of seams, laps and cracks,
- 11.1.3 Cross sections free of breaks, inclusions or extrusion pipe.

12. Special Examinations

12.1 *Special Macro Examination:*

12.1.1 The samples shall show no subsurface defects in excess of the following limits:

12.1.1.1 *Tubular Products:*

(1) *Tubes for Exhaust (Pinch-off) Purposes:*

(a) For wall thickness over 0.1 in. (2.5 mm), no defects on the external surface deeper than 0.005 in. (0.13 mm).

(b) For wall thicknesses up to 0.1 (2.5 mm) inclusive, no defects on the external surface deeper than 5 % of the wall thickness.

(c) No significant defects on the inside surface when examined with fiber optics or a boroscope.

(2) *Waveguides*—No defects on the external surface deeper than 0.005 in. (0.13 mm) or 5 % of the wall thickness, whichever is smaller. No significant defects on the inside surface when examined with fiber optics or a boroscope.

(3) *Tube for Other Applications*—No defects on either the internal or external surfaces deeper than 0.020 in. (0.51 mm) or 5 % of the wall thickness, whichever is the smaller.

12.1.1.2 *Bar and Plate Products*—No defects deeper than 0.06 in. (1.6 mm) or 5 % of the thickness, whichever is the smaller.

TABLE 1 Grain Size

Thickness	Average Grain Size, max, mm	Hardness HRF ^A max
Less than 0.040 in. (1.0 mm)	0.035	75
0.040 to 0.125 in. (1.0 to 3.2 mm)	0.050	75

^A For information only.

12.1.1.3 *Sheet, Strip and Flat Wire Products*—No defects deeper than 0.005 in. (0.13 mm) or 5 % of the thickness, whichever is smaller.

12.1.1.4 *Rod and Wire Products*:

(1) *Rod and Wire less than 0.19 in. (4.8 mm) in Diameter*—No defects deeper than 0.005 in. (0.13 mm) or 5 % of the diameter, whichever is smaller.

(2) *Rod and Wire 0.19 in. (4.8 mm) and Over in Diameter*—No defects deeper than 0.06 in. (1.6 mm) or 5 % of the diameter, whichever is smaller.

12.2 *Special Microscopical Examination*:

12.2.1 Samples shall be classified by comparison to Plate 1, which is available from ASTM International Headquarters as an adjunct (see 2.2).

12.2.1.1 Product whose samples have an appearance in conforming to either Class 1 or Class 2 shall be considered acceptable.

12.2.1.2 Subsurface microporosity similar to those typical of Class 3, 4 or 5 as illustrated in Plate 1, are permissible in Class 1 and 2 material provided the microporosity does not appear below the metal surface at depths exceeding the following:

(1) *Tubular Products*:

(a) *Tubes for Exhaust Purposes and Waveguides*—No indications at any depth below the surface.

(b) *Tubes for Other Applications*—Microporosity permissible to depths of 0.020 in. (0.51 mm) or 5 % of the tube wall, whichever is smaller.

(2) *Bar and Plate*—Microporosity permissible to depths of 0.06 in. (1.5 mm) or 5 % of the thickness, whichever is smaller.

(3) *Sheet, Strip and Flat Wire*—Microporosity permissible to depths of 0.010 in. (0.25 mm) or 5 % of the thickness, whichever is smaller.

(4) *Rod and Wire Products*:

(a) *Rod and Wire less than 0.19 in. (4.8 mm) in Diameter*—Microporosity permissible to depths of 0.010 in. (0.25 mm) or 5 % of the diameter or thickness, whichever is smaller.

(b) *Rod and Wire 0.19 in. (4.8 mm) and Over in Diameter*—Microporosity permissible to depths of 0.06 in. (1.5 mm) or 5 % of the diameter or thickness, whichever is the smaller.

12.2.1.3 Product whose samples have an appearance corresponding to Class 3, 4 or 5 and not in conformance with 12.2.1.2, shall be acceptable only by agreement between the manufacturer or supplier and the purchaser.

13. Dimensions, Mass and Permissible Variations

13.1 The dimensional tolerances for the product described by this specification shall be as prescribed in the basic product specification to which it was ordered.

14. Workmanship, Finish and Appearance

14.1 The product shall be prepared and handled in such a manner as to be substantially free from surface oxide and the presence of foreign material such as metal chips, dirt and grease.

15. Sampling

15.1 The sampling practice shall be as prescribed in the basic product specification to which it was ordered.

15.1.1 The number of sample pieces to be selected, however, shall be twice the number prescribed in the basic product specification.

16. Number of Tests and Retests

16.1 *Tests*—The number of samples submitted to all tests shall be twice that required by the basic product specification to which the product was ordered.

16.2 *Retests*:

16.2.1 Retests are permitted as stated in the basic product specification to which the product was ordered for tests associated with the basic product specification.

16.2.2 Retests shall be permitted for tests and examinations required by this specification.

16.2.3 Products which fail in retest shall be rejected.

17. Specimen Preparation

17.1 *Chemical Composition*—Analytical sample preparation shall be as directed in the basic product specification to which the product was ordered.

17.2 *Electrical Resistivity*—Specimen preparation shall be as directed in the basic product specification to which the product was ordered.

17.3 *Grain Size*—Specimen preparation shall be as directed in the basic product specification to which the product was ordered.

17.4 *General and Special Macro Examination*:

17.4.1 Transverse sections of the samples shall be machined to a 63 rms or smoother surface finish and degreased.

17.4.1.1 In a properly ventilated fume hood, etch the samples for 3 to 5 min by lowering the samples into a freshly prepared etching solution and slowly agitate.

17.4.1.2 Prepare the etching solution by mixing equal parts of concentrated reagent grade nitric acid (HNO₃) and deionized or distilled water. Add 5 grams of copper for each liter of the 50 % acid solution and cool the solution to ambient temperature prior to use. The solution shall be kept free of dirt and maintained at 75 ± 5°F (24 ± 3°C) during use. (**Warning**—Do not pour the water into the acid.)

17.4.1.3 Remove the samples periodically from the etching solution and visually examine to determine whether sufficiently etched. Should the samples tend to stain, add 25 mL of concentrated reagent grade hydrochloric acid (HCl) to each liter of etching solution.

17.4.1.4 After etching, rinse the samples thoroughly with deionized or distilled water and blow dry with air for examination.

17.5 *Special Microscopical Examination*:

17.5.1 Cut and degrease longitudinal samples taken from the finished product.

17.5.2 Heat the samples to 1870 ± 40°F (1020 ± 20°C) and hold at temperature for 30 min in an atmosphere comprising

not less than 10 % hydrogen. Rapidly cool to ambient temperature by quenching in water without undue exposure to air or quickly cool the specimens in the same atmosphere.

17.5.3 Polish and etch for examination using the etching solution described in **Table 2**. (**Warning**—With constant gentle stirring or swirling of the water, slowly add the acid. Do not pour the water into the acid.)

17.6 *Hydrogen Embrittlement* (Reverse Bend Test Method)—Sample preparation shall be in accordance with Test Specimens Section of Test Methods **B577**.

17.6.1 *Tubular Products:*

17.6.1.1 For tube with an outside diameter of 0.12 in. (3 mm) or less, the samples shall be flattened by pressing or rolling.

17.6.1.2 For tube with an outside diameter greater than 0.12 in. (3 mm) but less than 1 in. (25.4 mm) the samples shall be cut longitudinally from the tube and flattened, when necessary by either pressing or rolling.

17.6.1.3 For tube with an outside diameter of 1 in. (25.4 mm) and greater, samples may be cut either parallel or transverse to the axis of the tube and then flattened.

17.6.1.4 Should the thickness of any flattened sample be greater than 0.081 in. (2.06 mm), it shall be machined to a thickness of 0.081 ± 0.001 in. (2.06 ± 0.025 mm) and at least one of the original surfaces of the finished tube shall be retained on one of the samples.

17.6.1.5 Samples shall be heated to $1560 \pm 40^\circ\text{F}$ ($850 \pm 20^\circ\text{C}$) and held at that temperature for a period of 30 min in an atmosphere containing not less than 10 % hydrogen and then rapidly cooled by quenching in ambient temperature water without undue exposure to air or quickly cool the specimens in the same atmosphere.

17.6.2 *Bar and Plate Products:*

17.6.2.1 Samples shall be machined to a thickness of 0.081 ± 0.001 in. (2.06 ± 0.025 mm) and at least one of the original surfaces of the finished product shall be retained on one of the samples.

17.6.2.2 Samples shall be heated to $1560 \pm 40^\circ\text{F}$ ($850 \pm 20^\circ\text{C}$) and held at that temperature for a period of 30 min in an atmosphere containing not less than 10 % hydrogen and then rapidly cooled by quenching in ambient temperature water without undue exposure to air or quickly cool the specimens in the same atmosphere.

17.6.3 *Sheet, Strip and Flat Wire Products:*

17.6.3.1 For products with a thickness of 0.081 in. (2.06 mm) or less, the samples shall be prepared without machining.

17.6.3.2 For products with a thickness greater than 0.081 in. (2.06 mm), the samples shall be machined to a thickness of 0.081 ± 0.001 in. (2.06 ± 0.025 mm) and at least one of the original surfaces of the finished product shall be retained on one of the samples.

17.6.3.3 Samples shall be heated to $1560 \pm 40^\circ\text{F}$ ($850 \pm 20^\circ\text{C}$) and held at that temperature for a period of 30 min in an atmosphere containing not less than 10 % hydrogen and then rapidly cooled by quenching in ambient temperature water without undue exposure to air or quickly cool the specimens in the same atmosphere.

17.6.4 *Rod and Wire Products:*

17.6.4.1 For products with a diameter or thickness of 0.081 in. (2.06 mm) and under the sample shall be prepared without machining.

17.6.4.2 For products with a diameter or thickness greater than 0.081 in. (2.06 mm) the samples shall be machined to a thickness of 0.081 ± 0.001 in. (2.06 ± 0.025 mm) and at least one of the original surfaces of the finished product shall be retained on one of the samples.

17.6.4.3 Samples shall be heated to $1560 \pm 40^\circ\text{F}$ ($850 \pm 20^\circ\text{C}$) and held at that temperature for a period of 30 min in an atmosphere containing not less than 10 % hydrogen and then rapidly cooled by quenching in ambient temperature water without undue exposure to air or quickly cool the specimens in the same atmosphere.

18. Test Methods

18.1 *Chemical Composition:*

18.1.1 The test methods used for the determination of composition shall be as specified in the basic product specification to which the material was ordered.

18.1.2 The test method(s) used for the determination of elements required by contractual or purchase order agreement shall be as agreed upon between the manufacturer or supplier and the purchaser.

18.2 *Grain Size*—Grain size shall be determined in accordance with Test Methods **E112**. In case of dispute, the intercept method shall be used.

18.3 *Electrical Resistivity*—Electrical resistivity shall be determined in accordance with Test Method **B193**. Measurement uncertainty shall not exceed $\pm 0.15\%$.

18.4 *General Examination and Special Macro Examination*—Examination shall be visually with the unaided eye or at 10× magnification.

18.5 *Special Microscopical Examination*—Examination shall be made at 100× magnification and classified by comparison to Plate 1.

18.6 *Hydrogen Embrittlement Susceptibility (Reverse Bend Test Method)*—Hydrogen embrittlement shall be determined in accordance with Test Method D of Test Methods **B577**.

18.7 *Scaling Test*—The samples shall be heated in air in a clean muffle furnace for 30 min at $1560 \pm 40^\circ\text{F}$ ($850 \pm 20^\circ\text{C}$) and immediately quenched in clean, ambient temperature water. Acceptance criteria to be by agreement between customer and supplier.

19. Significance of Numerical Limits

19.1 For the purpose of determining compliance with specified limits an observed value or calculated value shall be rounded as indicated in accordance with the rounding method of Practice **E29**.

TABLE 2 Etching Solution

Sodium Dichromate	16 grams
Sodium Chloride	12 grams
Sulfuric Acid (Conc.)	64 mL
Water (deionized or distilled)	100 mL

Property	Rounded Unit for Observed or Calculated Value
Chemical composition	Nearest unit in the last right-hand significant digit used in expressing the limiting value
Electrical resist.	
Grain size:	
Up to 0.055 mm, incl.	nearest multiple 0.005 mm
Over 0.055 to 0.160 mm	nearest 0.01 mm

20. Inspection

20.1 The manufacturer shall inspect and make tests necessary to verify that the product furnished conforms to the requirements prescribed in the basic product specification to which the product was ordered and the requirements of this specification.

20.2 Source inspection of the product by the purchaser may be agreed upon between the manufacturer or supplier and the purchaser as part of the contract or purchase order.

20.2.1 The nature of the facilities needed to satisfy the inspector representing the purchaser that the product being furnished is in accordance with the product specification shall be included in the agreement.

20.2.2 All tests and inspection shall be conducted so as not to interfere unnecessarily with the operations of the works.

20.3 The manufacturer or supplier may accomplish the final inspection simultaneously by mutual agreement.

21. Rejection and Rehearing

21.1 Rejection:

21.1.1 Product which fails to conform to the requirements of this specification when inspected or tested by the purchaser, or the purchaser's agent, may be rejected.

21.1.2 Rejection shall be reported to the manufacturer or supplier, promptly, and in writing.

21.1.3 In case of dissatisfaction with results of the test upon which rejection is based, the manufacturer, or supplier, may make claim for a rehearing.

21.2 *Rehearing*—As a result of product rejection, the manufacturer, or supplier, may make claim for a retest to be conducted by the manufacturer, or supplier, and the purchaser. Samples of the rejected product shall be taken in accordance with this specification and subjected to test by both parties using the test method(s) specified herein or, alternatively, upon agreement by both parties, an independent laboratory may be selected for the test(s) using the test methods specified in this product specification.

22. Certification

22.1 When specified in the contract or purchase order, the purchaser shall be furnished certification that samples representing each lot have been tested or inspected as directed in this specification and the requirements have been met.

23. Mill Test Report

23.1 When specified in the contract or purchase order, a report of the test results shall be furnished.

24. Packaging and Package Marking

24.1 Packaging:

24.1.1 The product shall be separated by shape, size and temper and prepared for shipment in such a manner as to afford protection from the normal hazards of transportation.

24.1.2 Special packing or packaging required shall be by agreement between the manufacturer or supplier and the purchaser at the time of the contract or purchase order.

24.2 *Package Marking*—Each shipping unit shall be legibly marked with the purchase order number, metal designation, temper, size, shape, gross and net weight, and the name of the supplier. The specification numbers shall also be shown when so specified in the contract or purchase order.

25. Keywords

25.1 oxygen-free copper; oxygen-free copper for electron devices; wrought copper forms for electron devices; wrought oxygen-free copper for electron devices

SUMMARY OF CHANGES

Committee B05 has identified the principal changes to this specification that have been incorporated since the F68 – 10 issue as follows:

- (1) Deleted term “extrusion pipe” from Section 3.
- (2) Revised Section 4 for compliance with B950-15.

- (3) Corrected reference in 9.1.1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>