



# Standard Specification for Type 101 Sealing Glass<sup>1</sup>

This standard is issued under the fixed designation F79; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers Type 101 sealing glass for use in electronic applications.

NOTE 1—This specification is primarily intended to consider glass as most generally used, this is, glass in its transparent form as normally encountered in fabricating electronic devices. X1.3 lists sealing metals and alloys that are compatible with this glass. Type 101 glass in other forms such as powdered, crushed, sintered, fibrous, etc. are excluded. The requirements of this specification, as applied to these forms, must be established in the raw glass prior to its conversion.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

C336 Test Method for Annealing Point and Strain Point of Glass by Fiber Elongation

C338 Test Method for Softening Point of Glass

C598 Test Method for Annealing Point and Strain Point of Glass by Beam Bending

D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation

D257 Test Methods for DC Resistance or Conductance of Insulating Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer

F14 Practice for Making and Testing Reference Glass-Metal Bead-Seal

F140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods

F144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by Polarimetric Methods

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.04 on Physical and Mechanical Properties.

Current edition approved May 1, 2015. Published May 2015. Originally approved in 1967. Last previous edition approved in 2010 as F79 – 69 (2010). DOI: 10.1520/F0079-69R15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Form,

3.1.2 Type of glass,

3.1.3 Dimensions,

3.1.4 Marking and packaging, and

3.1.5 Certification (if required).

## 4. Chemical Composition

4.1 The typical chemical composition of this glass is as follows (Note 2):

Major Constituents	Weight %
Silica (SiO <sub>2</sub> )	56.0
Alumina (Al <sub>2</sub> O <sub>3</sub> )	1.5
Soda (Na <sub>2</sub> O)	4.0
Potash (K <sub>2</sub> O)	8.5
Lead oxide (PbO)	29.0
Antimony trioxide (Sb <sub>2</sub> O <sub>3</sub> )	1.0, max
Arsenic trioxide (As <sub>2</sub> O <sub>3</sub> )	1.0, max
Halogens	0.2, max

NOTE 2—Major constituents may be adjusted to give the desired electrical and physical properties to the glass. However, no change shall be made that alters any of these properties without due notification of, and approval by, the user.

## 5. Physical Properties

5.1 The material shall conform to the physical properties prescribed in Table 1. For electrical properties see Table 2 and its Footnote A.

## 6. Workmanship, Finish, and Appearance

6.1 The glass shall have a finish that ensures smooth, even surfaces and freedom from cracks, checks, bubbles, and other flaws of a character detrimental to the strength or life of the component or device for which its use is intended.

## 7. Test Methods

7.1 *Softening Point*—See Test Method C338.

7.2 *Annealing Point*—See Test Methods C336 or C598.

7.3 *Thermal Expansion Coefficient*—Pretreat the specimen by heating to 10°C above the annealing point and hold it at that temperature for 15 min; then cool it from that temperature to

**TABLE 1 Physical Requirements**

Property	ASTM Test Method <sup>A</sup>	Condition <sup>A</sup>	Value
Softening point	<b>C338</b>	sec <b>7.1</b>	630 ± 10°C
Annealing point	<b>C336</b> or <b>C598</b>	sec <b>7.2</b>	435 ± 10°C
Thermal expansion coefficient	<b>E228</b>	sec <b>7.3</b> 0 to 300°C	8.95 ± 0.20 ppm/°C
Contraction coefficient	<b>E228</b>	sec <b>7.4</b> (annealing point minus 15 to 30°C)	10.10 ± 0.20 ppm/°C

<sup>A</sup> Test methods and conditions are detailed in the appropriately referenced section of this specification.

**TABLE 2 Electrical Properties<sup>A</sup>**

Property	ASTM Test Method	Condition	Value (Typical)
Volume resistivity (dc)	<b>D257<sup>B</sup></b>	25°C	log <sub>10</sub> <i>R</i> (Ω·cm) 17.0
		250°C	log <sub>10</sub> <i>R</i> (Ω·cm) 9.9
		350°C	log <sub>10</sub> <i>R</i> (Ω·cm) 7.8
Dielectric constant (1 MHz)	<b>D150<sup>B</sup></b>	20°C	6.7
Dissipation factor (1 MHz)	<b>D150</b>	20°C	0.0014
Loss index (1 MHz)	<b>D150</b>	20°C	0.009

<sup>A</sup> While having no influence on the sealing capability of the glass, electrical properties are included as information pertaining to the effect of the material on the performance of electronic devices in which it may be used.

<sup>B</sup> Test methods are cited in Section 2 of this specification.

100°C at a rate of 2 to 5°C/min. The cooling rate below 100°C is optional. Place the specimen in the dilatometer and determine the mean coefficient of linear thermal expansion for the 0 to 300°C range in accordance with Procedure A of Test Method **E228**.

**7.4 Contraction Coefficient**—Heat the specimen in a vitreous silica dilatometer to 20°C above the annealing point and hold it at that temperature for 15 min; then cool at a rate of from 1.0 to 1.5°C/min to a temperature below 200°C. The rate of cooling from the point below 200 to 100°C shall not exceed 5°C/min. The rate of cooling from 100°C to room temperature is optional. During this cooling schedule, determine the thermal contraction curve and calculate the mean coefficient of linear thermal contraction between a point 15°C below the annealing point and 30°C in accordance with Procedure B of Test Method **E228**.

**7.5 Bead Seal Test**—The thermal contraction match between the glass and a sealing alloy may be determined by preparing and testing an assembly in accordance with Practices **F14**, **F140**, or **F144**.

## 8. Test Results

8.1 Observed or calculated values obtained from measurements, tests, or analysis shall be rounded in accordance with the rounding method of Practice **E29**, to the nearest unit in the last right-hand place of figures used in expressing the specified limit.

## 9. Investigation of Claims

9.1 Where any material fails to meet the requirements of this specification, the material so designated shall be handled in accordance with the agreement mutually acceptable to the manufacturer and the purchaser.

## 10. Packaging and Package Marking

10.1 Packing shall be determined by the form in which this material shall be supplied and shall be subject to agreement between the manufacturer and the purchaser.

10.2 The material as furnished under this specification shall be identified by the name or symbol of the manufacturer. The lot size for determining compliance with the requirements of this specification shall be one day's production.

## 11. Keywords

11.1 glass; sealing

## APPENDIX

### (Nonmandatory Information)

#### X1. ADDITIONAL INFORMATION

**X1.1 Physical Properties**—The physical properties as listed in **Table X1.1**, in addition to those included as require-

ments of the specification, are presented for guidance in negotiating with a specific vendor for their imposition when particularly appropriate. These criteria are not included within the specification because their values are averages of results obtained by various methods, no one of which is presently agreed upon by the glass industry as a whole.

**TABLE X1.1 Physical Properties**

Property	Condition	Unit	Value	Tolerance
Density	...	g/cm <sup>3</sup>	3.05	±0.02
Refractive index	sodium (D) line	...	1.56	±0.02
Birefringence, constant or stress-optical coefficient	...	10 <sup>-12</sup> Pa <sup>-1</sup>	3.0	±0.2

**X1.2 Typical Values for the Mean Coefficient of Linear Thermal Contraction**—Typical values for the mean coefficient of linear thermal contraction of Type 101 glass are given in **Table X1.2** for information only. These apply to a specimen of

**TABLE X1.2 Typical Contraction Coefficients**

Temperature Range, °C	Mean Contraction Coefficient, µm/m/°C or ppm/°C
100 to 30	8.6
200 to 30	8.9
300 to 30	9.2
400 to 30	9.7
420 to 30	10.1
450 to 30	10.8

the glass when cooled during the thermal contraction test (see 7.4) from a point above the maximum temperature shown to 30°C at a rate not exceeding 1.5°C/min.

**X1.3 Type 101—Compatible Metals and Sealing Alloys—**  
The thermal expansion characteristics of Type 101 sealing glass are generally satisfactory for sealing to the metals and alloys in **Table X1.3**.

**TABLE X1.3 Metals and Sealing Alloys Compatible with Type 101 Glass**

Metal or Alloy	ASTM Specification
Platinum	...
Titanium	...
Dumet	F29, Dumet Wire for Glass to Metal Seal Applications
52 Alloy	F30, Iron-Nickel Sealing Alloys
41-6 Alloy	F31, 42 % Nickel-6 % Chromium-Iron Sealing Alloy

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*