



# Standard Specification for Portable Gasoline Containers for Consumer Use<sup>1</sup>

This standard is issued under the fixed designation F852; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This specification establishes nationally recognized performance requirements for portable gasoline containers intended for reuse by the consumer. This specification also covers reusable containers for gas/oil mixtures commonly used for two-cycle engines and reusable dual-compartment containers for separate gas and oil storage. This specification does not cover single-trip prepackaged containers.

1.2 This specification is not a fire hazard standard, but a specification for portable gasoline containers for consumer use.

1.3 The following precautionary caveat applies only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* See Section 7 for additional precautionary information.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- B117 Practice for Operating Salt Spray (Fog) Apparatus
- D471 Test Method for Rubber Property—Effect of Liquids
- D572 Test Method for Rubber—Deterioration by Heat and Oxygen
- D638 Test Method for Tensile Properties of Plastics
- D794 Practice for Determining Permanent Effect of Heat on Plastics (Withdrawn 1998)<sup>3</sup>
- D999 Test Methods for Vibration Testing of Shipping Containers
- D2561 Test Method for Environmental Stress-Crack Resistance of Blow-Molded Polyethylene Containers

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F15 on Consumer Products and is the direct responsibility of Subcommittee F15.10 on Standards for Flammable Liquid Containers.

Current edition approved July 1, 2008. Published August 2008. Originally approved in 1984. Last previous edition approved in 2006 as F852 – 99 (2006). DOI: 10.1520/F0852-08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

- D2565 Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
- F839 Specification for Cautionary Labeling of Portable Gasoline Containers for Consumer Use
- F2234 Specification for Spill Resistant Fueling Systems for Portable Fuel Containers for Consumer Use
- G23 Practice for Operating Light-Exposure Apparatus (Carbon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials (Withdrawn 2000)<sup>3</sup>

### 2.2 ANSI Standard:<sup>4</sup>

- B71.1b1977 Supplement to Safety Specifications for Power Lawn Mowers, Lawn and Garden Tractors, and Lawn Tractors

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *portable gasoline container*, *n*—single- or multi-compartment vessel designed to be carried by hand and to be used to transport gasoline or gas/oil mixtures, or separate compartments of gas and oil, from distribution point to use point.

3.1.2 *pouring vent*, *n*—part of the container enabling free entry of air to replace the liquid being poured out.

3.1.3 *rated capacity*, *n*—volume indicated on the container, may also be termed nominal capacity or maximum filling level.

3.1.4 *spout*, *n*—component through which the contents of the container can be dispensed.

3.1.5 *total volume*, *n*—rated capacity plus any remaining space within the container.

## 4. Requirements

4.1 The container shall show evidence of good workmanship and meet the following requirements:

4.1.1 All container tests shall be conducted after closures are secured with torque values specified in Specification F2234 (see Table 1).

4.2 *Color*—The container shall be predominately red in color. Pigments, coatings, or other means used to impart color shall not be affected by gasoline.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

**TABLE 1 Torque Requirements**

Outer Diameter of Closure	Closing Torque, Nm (lbf-in.)
Less than 51 mm (2 in.)	2.8 (25)
51 mm (2 in.) and greater	5.6 (50)

4.3 *Capacity*—The maximum rated capacity shall be 25 L (6.6 gal).

4.3.1 The total volume of a container shall exceed its rated capacity by at least 5 %.

4.3.2 Capacity shall be determined with the container and its contents at  $23 \pm 2^\circ\text{C}$  ( $75 \pm 3.6^\circ\text{F}$ ).

4.4 *Stability*—Each container shall not upset when tested in accordance with 8.1.

4.5 *Handle*—Each container shall be provided with a handle. The container shall not leak or evidence any handle detachment when tested in accordance with 8.2.

4.6 *Drop Strength*—Containers shall show no evidence of rupture, cracks, or leakage when tested in accordance with 8.3.

4.7 *Internal Pressure*—Containers shall show no evidence of leakage when tested in accordance with 8.4.

4.8 *Durability*:

4.8.1 *Aging*—This requirement applies only to nonmetallic containers. The material for the container shall retain at least 70 % of its original tensile strength when tested in accordance with 8.5 and 8.5.1.

4.8.2 *Permeability*—This requirement applies only to non-metallic containers. The filled container shall not have a weight loss greater than 1 % when tested in accordance with 8.6.

4.8.3 *Gasoline Resistance*—This requirement applies only to nonmetallic containers. The container material shall show no pitting, crazing, softening, bubbling, cracking, tackiness, or decomposition when tested in accordance with 8.7.1. The material shall retain at least 60 % of its tensile yield strength when tested in accordance with 8.7.2.

4.8.4 *Stress Cracking*—This requirement applies only to containers molded of polyethylene. The container shall not crack in 120 h when tested in accordance with 8.8.

4.8.5 *Corrosion Resistance*—This requirement applies only to metal containers or metal components of containers. No leakage shall be evident when tested in accordance with 8.9.

4.8.6 *Heat Resistance*—The container shall not leak when tested in accordance with 8.10. Any burning that occurs during the test specified in 8.10.1 shall not continue for more than 5 s after the heat source is removed.

4.9 *Openings*—Openings in containers shall be provided with a means of closure.

4.9.1 *Pouring*—The opening intended for pouring shall have an integral pouring spout or it shall accept a pouring spout supplied with the container. The pouring spout shall be designed to permit gasoline to be poured without leakage. The closures on the containers shall not leak when tested in accordance with 8.12.

4.9.2 *Pouring Vent*—The container shall be provided with a vented pouring spout or other means for venting the container during pouring.

4.9.3 *Filling*—The opening intended for filling the container shall have a minimum inside diameter of 31.7 mm (1.25 in.).

4.9.4 *Gasoline Resistance*—This requirement applies only to nonmetallic components. Closures, pouring spout, venting devices, and gaskets shall be resistant to aging and the action of gasoline when tested in accordance with 8.11.

## 5. Marking

5.1 The container shall be labeled in accordance with Specification F839.

5.2 The container shall be clearly marked with at least one of the following:

5.2.1 The manufacturer's name,

5.2.2 The private labeler's name, and

5.2.3 An identifying symbol.

5.3 The container shall be marked with its rated capacity in litres and in gallons.

5.4 Marking durability shall comply with the applicable requirements of ANSI B71.1b1977.

## 6. Retest and Rejection

6.1 If any failure occurs, an additional container may be tested if the failure is judged to be nonrepresentative of production.

## 7. Precautions

7.1 Gasoline is used in some of the following tests. Cautionary standards for handling and disposal of hazardous materials should be observed. Containers containing gasoline should not be opened in the presence of open flame or other sources of ignition.

## 8. Test Methods

8.1 *Stability Test*—Fill a sample container with water at  $23 \pm 2^\circ\text{C}$  ( $75 \pm 3.6^\circ\text{F}$ ) to its rated capacity by volume. Secure the closures as in transportation and storage. Place the container with its base on an inclined plane forming an angle of 0.35 rad ( $20^\circ$ ) with the horizontal. During the test, rotate the container about its vertical axis so that stability can be checked with the sample facing any direction.

8.2 *Handle Strength*—Fill a sample container with an equivalent weight of water at  $23 \pm 2^\circ\text{C}$  ( $75 \pm 3.6^\circ\text{F}$ ) to its rated gasoline capacity. Secure the closures as in transportation and storage. One end of a 9.5 mm (0.375 in) diameter manila rope about 2 m (6.5 ft) long shall be secured to a rigid point of suspension and the other end attached so as to distribute the load across the container handle. Suspend the container from the rope for 1 min then raise it 305 mm (12 in.) from the suspended position and allow it to fall freely.

8.3 *Drop Strength Test*—Fill the container to its nominal capacity with water at  $23 \pm 2^\circ\text{C}$  ( $75 \pm 5^\circ\text{F}$ ) and secure the closures. Drop it, free fall, onto a flat, solid surface. Make drops in the following sequence: one drop on the bottom, one drop on a bottom corner, and one drop on a side. The distance of fall shall be 1.8 m (6 ft). Make the same tests with another container filled with a blend of 50 % glycol and 50 % water

and with both the container and its contents cooled to  $-18 \pm 1$  °C ( $0 \pm 2$  °F). For these latter tests, the distance of fall shall be 1.2 m (4 ft).

NOTE 1—The location of the spout is considered to be the front of the container. The side is considered to be approximately 90° to either left or right of the nozzle area.

#### 8.4 Internal Pressure Test:

8.4.1 *Hydrostatic Pressure Test*—Fill the container to its total volume with water at  $23 \pm 3$ °C ( $75 \pm 5$ °F) and secure the closures. Increase the internal pressure to a gage pressure of 138 kPa (20 psi) and maintain for 2 min. Conduct the same test with a container filled to its total volume with water at  $60 \pm 3$ °C ( $140 \pm 5$ °F). For plastic containers, apply the pressure by inserting and securing an adaptor through a drilled hole in a flat, heavy section of the container wall, and not on a pinch-off or parting line. For metal containers, the pressure can be applied through a fill or pour closure.

8.5 *Aging Test*—Perform the following two tests. In both tests, determine tensile strength in accordance with the conditions outlined in Test Method **D638** using five specimens and a crosshead speed of 50 mm (2 in.) per min.

8.5.1 *Test 1*—Test the specimen for 2000 h in accordance with Procedure B of Practice **D2565** using Type B or BH apparatus, or for 1400 h in accordance with Practice **G23** using a Type E carbon-arc weathering device (Note 2). The test cycle for each method shall consist of 102 min of light followed by 18 min of light and spray. If Practice **G23** is used, the blackbody temperature shall be 62.8°C (145°F). In cases of disagreement, Practice **D2565** shall be the referee method.

NOTE 2—Limited data indicate that carbon-arc exposure is much more severe than xenon-arc exposure, and therefore, less exposure time is required when using the carbon-arc equipment.

8.5.2 *Test 2*—Test the specimen for 60 days in accordance with Practice **D794** except that the oven temperature shall be  $87 \pm 2$ °C ( $189 \pm 3.6$ °F).

8.6 *Permeability Test*—Fill the container to its rated capacity with Reference Fuel B (70 % isooctane and 30 % toluene by volume), as defined by Test Method **D471** and secure the closures. Weigh the container accurately to the nearest 5 g (0.01 lb). After storage for 30 days at  $23 \pm 2$ °C ( $75 \pm 3.6$ °F), reweigh the container and calculate the weight loss.

#### 8.7 Gasoline Resistance Test:

8.7.1 *Visual Test*—Upon completion of the permeability test in 8.6, empty the container and cut apart in a manner to allow visual inspection of all interior surfaces.

8.7.2 *Immersion Test*—Condition at least 30 specimens, taken from untested container, measuring about 125 mm (5 in.) by 16 mm (0.625 in.) at  $23 \pm 2$ °C ( $75 \pm 3.6$ °F) for 18 h. Immerse specimens in each of the following solutions at  $38 \pm 2$ °C ( $100 \pm 3.6$ °F). Use the remaining ten specimens as a control:

8.7.2.1 ASTM Reference Fuel C (mixtures of 50 % isooctane and 50 % toluene by volume), and

8.7.2.2 Blend of ASTM Reference Fuel A (isooctane and ASTM Reference Oil No. 3, considered to be representative of low aniline point automotive lubricating oils) as defined by Test Method **D471** in a ratio of 16 to 1 by volume.

8.7.2.3 Following exposure for 30 days, remove ten specimens from each solution and test to determine tensile yield strength in accordance with Test Method **D638** using a crosshead speed of 50 mm (2 in.) per min.

8.8 *Stress Cracking Test*—Test two containers in accordance with Procedure B of Test Method **D2561**, except do not expose the outside of the containers to the stress cracking agent.

8.9 *Corrosion Resistance Test*—Fill six container samples to their nominal capacity with water. Secure the closures as in transportation and storage. Test the containers in accordance with Practice **B117**. Expose the containers to a spray of 5 % salt solution for 21 days. Then allow them to dry for 4 h at room temperature.

8.10 *Container Material Flammability Test*—Determine the resistance of the container filled with water to a momentary exposure to heat and flame in accordance with 8.10.1 and 8.10.2.

NOTE 3—These test methods should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions.

8.10.1 *Test 1*—Fill a container completely with water at  $23 \pm 2$ °C ( $75 \pm 3.6$ °F). Adjust a 9.5 mm ( $\frac{3}{8}$ -in.) diameter bunsen burner, using natural gas having a calorific value of approximately 37 MJ/m<sup>3</sup> (1000 Btu/ft<sup>3</sup>) so that the outer blue flame is approximately 25 mm (1 in.) in length and the inner blue cone is approximately 9.5 mm ( $\frac{3}{8}$  in.) long. The temperature of the flame just above the inner cone shall be a minimum of 930°C (1700°F) and the temperature of the flame 19 mm ( $\frac{3}{4}$  in.) above the burner shall be a minimum of 288°C (550°F). Tilt the burner about 0.31 radians (18°) from the normal 1.57 radians (90°) impingement and hold the tip of the burner 19 mm ( $\frac{3}{4}$  in.) away from the container for 75 s. Test the container on the side, bottom and any corner. Examine for leaks. If the design of the container is such that it cannot be filled completely with water, apply the flame only to those areas which are water backed.

8.10.2 *Test 2*—Fill a container completely with water at  $23 \pm 2$ °C ( $75 \pm 3.6$ °F). Heat a 12.7-mm (0.5-in.) diameter steel rod, 150 mm (6 in.) long, to  $260 \pm 6$ °C ( $500 \pm 10.8$ °F) and immediately place on the bottom of an inverted container and allow to cool to  $23 \pm 2$ °C ( $75 \pm 3.6$ °F). Repeat this procedure, except place the heated rod on a side wall of the container. Examine the container for leaks.

#### 8.11 Components Tests:

8.11.1 A part made of an elastomer which may be affected by aging shall not crack or show visible evidence of deterioration following exposure for 96 h to oxygen at a pressure of 2.1 MPa (300 psi) and at a temperature of  $70 \pm 2$ °C ( $158 \pm 3.6$ °F) when tested in accordance with Test Method **D572**.

8.11.2 A nonmetallic part other than an elastomer, which may be affected by aging shall not crack or show visible evidence of deterioration following exposure for 168 h in an air oven at a temperature of  $100 \pm 2$ °C ( $212 \pm 3.6$ °F).

8.11.3 A nonmetallic part in contact with gasoline shall not show excessive volume change or loss of weight, when

considered on the basis of its intended function following immersion in ASTM No. 3 Swelling Oil and A and C Reference Fuels in accordance with Test Method **D471** at  $23 \pm 2^\circ\text{C}$  ( $75 \pm 3.6^\circ\text{F}$ ) for 70 h. A change in volume of not more than 25 % swelling (40 % in Reference Fuel C) or 1 % shrinkage, and a weight loss (extraction) of not more than 10 % is considered as indicating compliance with this test.

8.12 *Closure Test*—Fill the container to its nominal capacity with water at  $23 \pm 3^\circ\text{C}$  ( $75 \pm 5^\circ\text{F}$ ) and secure the closures. Test the filled container in accordance with Procedure A of Test

Methods **D999** for 2 h. After the 2 h test, invert the container for 5 min without tightening the closures.

8.13 *Precision and Bias*—Precision statements will be included in subsequent revisions after interlaboratory and intralaboratory comparisons are instituted, completed and properly evaluated.

## 9. Keywords

9.1 gasoline containers; gasoline storage; portable fuel containers

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org/COPYRIGHT](http://www.astm.org/COPYRIGHT)).*