

BS EN ISO 75-2:2013



BSI Standards Publication

Plastics — Determination of temperature of deflection under load

Part 2: Plastics and ebonite (ISO 75-2:2013)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 75-2:2013. It supersedes BS EN ISO 75-2:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 73628 5

ICS 83.060; 83.080.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2013.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Plastics - Determination of temperature of deflection under load
- Part 2: Plastics and ebonite (ISO 75-2:2013)

Plastiques - Détermination de la température de
fléchissement sous charge - Partie 2: Plastiques et ébonite
(ISO 75-2:2013)

Kunststoffe - Bestimmung der
Wärmeformbeständigkeitstemperatur - Teil 2: Kunststoffe
und Hartgummi (ISO 75-2:2013)

This European Standard was approved by CEN on 21 March 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 75-2:2013) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 75-2:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 75-2:2013 has been approved by CEN as EN ISO 75-2:2013 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Apparatus	2
5.1 Means of producing a flexural stress.....	2
5.2 Heating equipment.....	2
5.3 Weights.....	2
5.4 Temperature-measuring instrument.....	2
5.5 Deflection-measuring instrument.....	2
6 Test specimens	2
6.1 General.....	2
6.2 Shape and dimensions.....	2
6.3 Specimen inspection.....	3
6.4 Number of test specimens.....	3
6.5 Test-specimen preparation.....	3
6.6 Annealing.....	3
7 Conditioning	3
8 Procedure	3
8.1 Calculation of force to be applied.....	3
8.2 Initial temperature of the heating equipment.....	3
8.3 Measurement.....	3
9 Expression of results	4
10 Precision	4
11 Test report	4
Annex A (informative) Precision	5
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 75-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

This third edition cancels and replaces the second edition (ISO 75-2:2004), which has been technically revised. In particular, [Clause 5](#) and [Annex A](#) have been updated.

ISO 75 consists of the following parts, under the general title *Plastics — Determination of temperature of deflection under load*:

- *Part 1: General test method*
- *Part 2: Plastics and ebonite*
- *Part 3: High-strength thermosetting laminates and long-fibre-reinforced plastics*

Introduction

The first editions of ISO 75-1 and this part of ISO 75 described three methods (A, B and C) using different test loads and two specimen positions, edgewise and flatwise. For testing in the flatwise position, test specimens with dimensions 80 mm × 10 mm × 4 mm were required. These can be moulded directly or machined from the central section of the multipurpose test specimen (see ISO 20753).

The previous (i.e. second) editions of ISO 75-1 and this part of ISO 75 specified the flatwise test position as preferred, while still allowing testing in the edgewise position with test conditions given in [Annex A](#) until the next revision of ISO 75-1 and this part of ISO 75, as agreed in ISO/TC 61/SC2/WG 5. Therefore, with this revision, the edgewise test position will be removed.

Technical development of testing instruments in recent years made instruments based on a fluidized bed or air ovens available. These are especially advantageous for use at temperatures at which the common silicone oil-based heat transfer fluids reach their limit of thermal stability. The fluidized bed and air oven methods of heat transfer are introduced in ISO 75-1.

An additional precision statement covering the new heating methods is introduced in this part of ISO 75.

Plastics — Determination of temperature of deflection under load —

Part 2: Plastics and ebonite

1 Scope

This part of ISO 75 specifies three methods, using different values of constant flexural stress, which can be used for the determination of the temperature of deflection under load of plastics (including filled plastics and fibre-reinforced plastics in which the fibre length, prior to processing, is up to 7,5 mm) and ebonite:

- method A, using a flexural stress of 1,80 MPa;
- method B, using a flexural stress of 0,45 MPa;
- method C, using a flexural stress of 8,00 MPa.

The standard deflection, Δs , used to determine the temperature of deflection under load corresponds to a flexural-strain increase, $\Delta \epsilon_f$, defined in this part of ISO 75. The initial flexural strain due to the loading of the specimen at room temperature is neither specified nor measured in this part of ISO 75. The ratio of this flexural-strain increase to the initial flexural strain depends on the modulus of elasticity, at room temperature, of the material under test. This method is, therefore, only suitable for comparing the temperatures of deflection of materials with similar room-temperature elastic properties.

NOTE 1 The methods give better reproducibility with amorphous plastics than with semi-crystalline ones. With some materials, it can be necessary to anneal the test specimens to obtain reliable results. Annealing procedures, if used, generally result in an increase in the temperature of deflection under load (see 6.6).

NOTE 2 For additional information, see ISO 75-1:2013, Clause 1.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 10724-1, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles and moulding of multipurpose test specimens*

ISO 20753, *Plastics — Test specimens*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 75-1 apply.

NOTE Depending on the selected value of the flexural stress (see [Clause 1](#)), the temperature of deflection under load (see definition 3.7 in ISO 75-1:2013) is designated as $T_f 0,45$, $T_f 1,8$ or $T_f 8,0$.

4 Principle

The principle is specified in ISO 75-1:2013, Clause 4.

5 Apparatus

5.1 Means of producing a flexural stress

This is specified in ISO 75-1:2013, 5.1.

The span (distance between the lines of contact between specimen and supports) shall be (64 ± 1) mm for testing.

5.2 Heating equipment

This is specified in ISO 75-1:2013, 5.2.

5.3 Weights

This is specified in ISO 75-1:2013 5.3.

5.4 Temperature-measuring instrument

This is specified in ISO 75-1:2013, 5.4.

5.5 Deflection-measuring instrument

This is specified in ISO 75-1:2013, 5.5.

6 Test specimens

6.1 General

This is specified in ISO 75-1:2013, 6.1.

6.2 Shape and dimensions

See ISO 75-1:2013, 6.2.

The preferred test-specimen dimensions are:

length l : $(80 \pm 2,0)$ mm;

width b : $(10 \pm 0,2)$ mm;

thickness h : $(4 \pm 0,2)$ mm.

6.3 Specimen inspection

This is specified in ISO 75-1:2013, 6.3.

6.4 Number of test specimens

This is specified in ISO 75-1:2013, 6.4.

6.5 Test-specimen preparation

Test specimens shall be produced in accordance with ISO 293 (and ISO 2818, if applicable), or in accordance with ISO 294-1 or ISO 10724-1, or as agreed by the interested parties. The test results obtained on moulded test specimens depend on the moulding conditions used in their preparation. The moulding conditions shall be in accordance with the standard for the material concerned, or as agreed by the interested parties.

In the case of compression-moulded specimens, the thickness shall be in the direction of the moulding force. For materials in sheet form, the thickness of the test specimens (this dimension is usually the thickness of the sheet) shall be in the range 3 mm to 13 mm, preferably between 4 mm and 6 mm.

The specimen may be taken from the narrow central part of the multipurpose test specimen specified in ISO 20753 (specimen type A1).

6.6 Annealing

Discrepancies in test results due to variations in moulding conditions may be minimized by annealing the test specimens before testing them. Since different materials require different annealing conditions, annealing procedures shall be employed only if required by the materials standard or if agreed upon by the interested parties.

7 Conditioning

This is specified in ISO 75-1:2013, Clause 7.

8 Procedure

8.1 Calculation of force to be applied

This is specified in ISO 75-1:2013, 8.1.

The flexural stress produced shall be one of the following:

- 1,80 MPa (preferred value), in which case the method is designated method A;
- 0,45 MPa, in which case the method is designated method B;
- 8,00 MPa, in which case the method is designated method C.

8.2 Initial temperature of the heating equipment

This is specified in ISO 75-1:2013, 8.2.

8.3 Measurement

This is specified in ISO 75-1:2013, 8.3.

Apply the force required to produce one of the flexural stresses specified in [8.1](#).

Calculate the standard deflection, Δ_s , by means of Formula (4) in ISO 75-1:2013 using a value of 0,2 % for the flexural-strain increase $\Delta\varepsilon_f$.

Record the temperature at which the initial deflection of the bar has increased by the standard deflection. This temperature is the temperature of deflection under load. If the individual results for amorphous plastics or ebonite differ by more than 2 °C, or those for semi-crystalline materials by more than 5 °C, repeat tests shall be carried out.

Table 1 — Standard deflections for different test-specimen heights for a 80 mm length × 10 mm width specimen tested

Test-specimen height (thickness h of specimen) mm	Standard deflection mm
3,8	0,36
3,9	0,35
4,0	0,34
4,1	0,33
4,2	0,32

NOTE The thicknesses in [Table 1](#) reflect the acceptable variation in the test-specimen dimensions (see [6.2](#)).

9 Expression of results

This is specified in ISO 75-1:2013, Clause 9.

10 Precision

See [Annex A](#).

11 Test report

This is specified in ISO 75-1:2013, Clause 11.

The test report shall also include the following additional information:

- l) the value of the standard deflection used.

In item h) of the test report, indicate the flexural stress used by means of the following designation system: $T_{f0,45}$ for method B, $T_{f1,8}$ for method A or $T_{f8,0}$ for method C.

Annex A (informative)

Precision

A.1 General

A.1.1 Round robin studies have been performed independently and separate from each other, using different heating methods. The heating methods were heat transfer by oil, by a fluidized bed and by air.

A.1.2 A round robin study involving eight materials and 10 laboratories was conducted in 1996 in accordance with ASTM E691 to determine the precision of the method specified in this part of ISO 75. In this study, oil was used as the heat transfer medium.

All test specimens were injection moulded by one laboratory. Each material was tested twice. PP 1 and PP 2 were tested at 0,45 MPa stress loading and the rest at 1,8 MPa stress loading, with the specimen in the flatwise position.

Not every laboratory tested every material. Only four laboratories tested material 8 and the data were therefore not included in the statistical calculation. Data from laboratory 7 were significantly lower than data from the others, and laboratory 10 tested materials only once. Data from these two laboratories were, therefore, also excluded from the calculation.

Due to the limitations of the ASTM E691 software, three separate precision statements were established. The results were combined and reported as one, as shown in [Table A.1](#).

A.1.3 [Tables A.2](#) to [A.4](#) are based on a round robin test performed in 2009 involving three to six laboratories and seven to 11 materials. Three heating methods were used, being the standard method with oil as heat transfer medium, fluidized beds with aluminium oxide powder and air ovens. Test specimens were always prepared and distributed by one source. Each laboratory obtained and reported six individual test results for each material. The results reported were evaluated according to ISO 5725-2.

CAUTION — Due to the limited number of laboratories and materials, the following explanations of r and R (see A.1.4 to A.3) are only intended to present a meaningful way of considering the approximate precision of this test method. The data in [Tables A.1](#) to [A.4](#) should not be rigorously applied to acceptance or rejection of material, as those data are specific to the round robin and may not be representative of other lots, conditions, materials, or laboratories.

A.1.4 Concept of r and R :

- a) repeatability: two test results obtained within one laboratory shall be judged not equivalent if they differ by more than the r value for that material. r is the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment in the same laboratory.
- b) reproducibility: two test results obtained by different laboratories shall be judged not equivalent if they differ by more than the R value for that material. R is the interval representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.

The judgements in [Tables A.1](#) to [A.4](#) will have an approximately 95 % (0,95) probability of being correct.

A.2 Statistical properties

In [Tables A.1](#) to [A.4](#), the statistical properties used are:

s_r = within laboratory standard deviation

s_R = between laboratory standard deviation

r = 95 % repeatability limit = 2,8 s_r

R = 95 % reproducibility limit = 2,8 s_R

n_{Lab} = number of laboratories reporting results

A.3 Results using oil as heat transfer medium

Table A.1 — Heat transfer medium: oil (see A1.2)

Material	Number of lab., n_{Lab}	Flexural stress MPa	Average °C	s_r °C	s_R °C	r °C	R °C
PP 1	7	0,45	$T_{f0,45} = 81,9$	0,9	2,4	2,5	6,9
PP 2	7	0,45	$T_{f0,45} = 115,2$	1,0	3,4	2,9	9,7
ABS	8	1,8	$T_{f1,8} = 79,3$	0,3	0,7	0,9	2,0
POM 1	8	1,8	$T_{f1,8} = 91,1$	0,8	2,1	2,1	5,8
PBT	8	1,8	$T_{f1,8} = 49,7$	0,4	0,4	1,0	1,0
PET	8	1,8	$T_{f1,8} = 65,4$	0,1	1,0	0,4	2,8
POM 2	6	1,8	$T_{f1,8} = 160,5$	0,9	1,0	2,5	2,7

A.4 Results using oil, fluidized bed and air as heat transfer medium

Table A.2 — Heat transfer medium: oil (see A.1.3)

Material	Number of lab., n_{Lab}	Heating rate, 120 °C/h				
		Average $T_{f1,8}$ °C	s_r °C	s_R °C	r °C	R °C
PS	6	77,3	0,2	1,7	0,7	4,7
POM 1	5	97,9	1,1	3,3	3,1	9,2
PC	6	126,0	0,2	3,5	0,4	9,8
POM 2	6	161,4	0,4	0,9	1,1	2,6
PPE	6	187,1	0,2	1,9	0,7	5,4
PES	4	202,9	1,0	1,6	2,2	4,4
PPS	3	267,5	0,5	0,9	1,5	2,6

Table A.3 — Heat transfer: fluidized bed (see A.1.3)

Material	Number of lab., n_{Lab}	Heating rate, 120 °C/h				
		Average $T_{f1,8}$ °C	s_r °C	s_R °C	r °C	R °C
PS	3	77,1	0,0	1,1	0,1	3,1
POM 1	3	107,6	1,8	3,1	5,0	8,8
PC	3	129,3	0,5	0,8	1,3	2,4
POM 2	3	162,0	0,1	0,4	0,3	1,1
PPE	3	189,5	1,0	1,0	2,9	2,9
PES	3	209,2	1,0	1,7	2,7	4,7
PPS	3	274,5	0,3	0,5	0,9	1,5
LCP 1	3	311,8	1,1	1,1	3,1	3,1
LCP 2	3	319,5	0,6	1,2	1,8	3,2
PEEK	3	319,7	1,7	1,7	4,8	4,8
LCP 4	3	368,4	0,2	1,9	0,6	5,4

Table A.4 — Heat transfer medium: air (see A.1.3)

Material	Number of lab., n_{Lab}	Heating rate, 120 K/h				
		Average $T_{f1,8}$ °C	s_r °C	s_R °C	r °C	R °C
PS	3	78,3	0,2	1,7	0,4	4,7
POM 1	3	101,7	2,0	4,3	5,7	12,0
PC	3	131,7	0,9	3,1	2,4	8,6
POM 2	3	169,4	0,1	0,8	0,2	2,2
PPE	3	193,6	0,1	3,1	0,4	8,6
PES	3	206,5	0,5	3,7	1,3	10,2
PPS	3	273,9	0,2	1,1	0,6	3,0
LCP 1	3	308,0	1,2	1,9	3,4	5,3
LCP 2	3	315,2	0,4	1,6	1,2	4,3
PEEK	3	301,1	2,1	5,0	6,0	14,1
LCP 4	3	363,5	1,4	1,6	4,1	4,5

Bibliography

- [1] ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*
- [2] ASTM E691, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*
- [3] ISO 5725, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™