

Textiles — Tests for colour fastness

**Part B07: Colour fastness to light
of textiles wetted with artificial
perspiration (ISO 105-B07:2009)**

ICS 59.080.01,

National foreword

This British Standard is the UK implementation of EN ISO 105-B07:2009.

The UK participation in its preparation was entrusted to Technical Committee TCI/81, Colour fastness and colour measurement of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2009.

© BSI 2009

ISBN 978 0 580 54890 1

Amendments/corrigenda issued since publication

Date	Comments

EUROPEAN STANDARD

EN ISO 105-B07

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2009

ICS 59.080.01

English Version

**Textiles - Tests for colour fastness - Part B07: Colour fastness
to light of textiles wetted with artificial perspiration (ISO 105-
B07:2009)**

Textiles - Essais de solidité des teintures - Partie B07:
Solidité des teintures à la lumière de textiles mouillés par
de la sueur artificielle (ISO 105-B07:2009)

Textilien - Farbechtheitsprüfungen - Teil B07: Farbechtheit
gegen Licht von mit künstlichem Schweiß angefeuchteten
Textilien (ISO 105-B07:2009)

This European Standard was approved by CEN on 30 March 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 105-B07:2009) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2009, and conflicting national standards shall be withdrawn at the latest by November 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 105-B07:2009 has been approved by CEN as a EN ISO 105-B07:2009 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 105-B07 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

ISO 105 was previously published in 13 “parts”, each designated by a letter (e.g. “Part A”), with publication dates between 1978 and 1985. Each part contained a series of “sections”, each designated by the respective part letter and by a two-digit serial number (e.g. “Section A01”). These sections are now being republished as separate documents, themselves designated “parts” but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01 [2].

Introduction

This part of ISO 105 was developed using acid perspiration solution 1 and the exposure conditions listed in ISO 105-B02.

Textiles — Tests for colour fastness —

Part B07:

Colour fastness to light of textiles wetted with artificial perspiration

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles, of all kinds and in all forms, to the combined effect of wetting with acid or alkaline artificial perspiration solutions and an artificial light source representing natural daylight (D65).

2 Normative reference(s)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 105-E04, *Textiles — Tests for colour fastness — Part E04: Colour fastness to perspiration*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Principle

Specimens of textiles wetted with a selected artificial perspiration solution are exposed to artificial light under prescribed conditions, together with a specified blue wool reference material. When this blue wool reference material shows the prescribed change of colour, the specimens are removed and the change in colour of each specimen is assessed by comparison with the grey scale for assessing change in colour or instrumentally.

4 Apparatus, material and reagents

4.1 Balance, with a weighing accuracy of 0,01 g.

4.2 pH meter, accurate to 0,01.

4.3 Grey scale for assessing change in colour, in accordance with ISO 105-A02.

4.4 Blue wool reference material, in accordance with ISO 105-B02.

4.5 Artificial perspiration solutions, either 5.1, 5.2 or 5.3.

Alternative perspiration solutions can be used. The specific formulas should be given in the Test report [9 c)].

4.6 Water-repellent white card stock, without optical brightener.

4.7 Xenon-arc-lamp fading apparatus, in accordance with ISO 105-B02.

4.8 Grade 3 water, complying with ISO 3696.

4.9 Spectrophotometer or colorimeter for assessing change in colour, in accordance with ISO 105-A05.

5 Preparation of reagents

5.1 Acid perspiration solution 1, freshly prepared (see AATCC TM 15^[1]) using water (4.8) and containing, per litre:

- 0,25 g of L-histidine monohydrochloride monohydrate ($C_6H_9N_3O_2 \cdot HCl \cdot H_2O$);
- 10 g of sodium chloride (NaCl);
- 1 g of disodium hydrogen phosphate, anhydrous (Na_2HPO_4);
- 1 g of lactic acid 85 % ($CH_3CHOHCOOH$).

The pH of the resulting solution should be pH 4,3 ($\pm 0,2$).

5.2 Acid perspiration solution 2, freshly prepared (in accordance with ISO 105-E04) using water (4.8) and containing, per litre:

- 0,5 g of L-histidine monohydrochloride monohydrate ($C_6H_9N_3O_2 \cdot HCl \cdot H_2O$);
- 5 g of sodium chloride (NaCl);
- 2,2 g of sodium dihydrogen orthophosphate dihydrate ($NaH_2PO_4 \cdot 2H_2O$).

The solution is brought to pH 5,5 ($\pm 0,2$) with 0,1 mol/l sodium hydroxide solution.

5.3 Alkali perspiration solution, freshly prepared (in accordance with ISO 105-E04) using water (4.8) and containing, per litre:

- 0,5 g L-histidine monohydrochloride monohydrate ($C_6H_9N_3O_2 \cdot HCl \cdot H_2O$);
- 5 g of sodium chloride (NaCl); and

either

- 5 g of disodium hydrogen orthophosphate dodecahydrate ($Na_2HPO_4 \cdot 12H_2O$);

or

- 2,5 g of disodium hydrogen orthophosphate dihydrate ($Na_2HPO_4 \cdot 2H_2O$).

The solution is brought to pH 8,0 ($\pm 0,2$) with 0,1 mol/l sodium hydroxide solution.

6 Test specimen

The size of the test specimen will depend on the number of specimens to be tested and on the shape and dimensions of the specimen holders supplied with the apparatus. The minimum size for the samples is 40 mm × 10 mm. One specimen is required for each solution to be tested.

The specimen may be a strip of cloth, with the yarn wound close together on a card or laid parallel and fastened on a card, or a mat of fibres combed and compressed to give a uniform surface and fastened on a card.

7 Procedure

7.1 Weigh the specimen to $\pm 0,01\text{g}$.

7.2 Place the test specimen in a smooth flat-bottomed dish and add 50 ml of freshly prepared perspiration solution (5.1, 5.2 or 5.3, as agreed by interested parties) to be tested so as to cover the specimen. Soak the test specimen in the solution at room temperature for (30 ± 2) min with occasional agitation and squeezing to ensure complete wetting.

7.3 Remove the test specimen from the solution and blot it to remove excess solution. Reweigh the specimen to determine (100 ± 5) % wet pick-up.

7.4 Attach each specimen to a water-repellent white card (4.6).

7.5 Mount the test specimen and white card in a specimen holder suitable for the xenon-arc-lamp fading apparatus (4.7), without masking.

7.6 Mount the blue wool reference material (4.4) onto a second card and mask in accordance with ISO 105-B02. Do not wet with test solution.

7.7 The blue wool reference material and the exposure conditions should be agreed upon by the interested parties.

NOTE The different exposure conditions in ISO 105-B02 do not lead to the same results.

7.8 Expose specimens together with the blue wool reference material (4.4) in the light-fading apparatus in accordance with one of the exposure conditions agreed upon as specified in ISO 105-B02. The filter systems and irradiance level shall be in accordance with ISO 105-B02.

Expose the specimens and blue wool reference material until the prescribed degree of fading of the blue wool reference material, as indicated in ISO 105-B02, has been achieved, as determined on the grey scale for assessing the change in colour (see ISO 105-A02) or instrumentally (see ISO 105-A05).

7.9 Remove the specimens and rinse by occasionally squeezing them with grade 3 water (4.8) for 1 min. Dry them by hanging them in air at a temperature not exceeding 60 °C.

8 Evaluation

Assess the change in colour of each specimen by comparison with the grey scale for assessing change in colour (4.3), or instrumentally (4.9).

9 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for the identification of the sample tested;
- c) the perspiration solution(s) used;
- d) the blue wool reference material used;
- e) the numerical rating for change in colour of the specimen for each type of perspiration solution used;
- f) the xenon-arc-lamp apparatus used, chosen exposure condition, and machine set-up;
- g) any deviation from the test method specified;
- h) date of the test.

Bibliography

- [1] AATCC TM 15, *Colorfastness to Perspiration*
- [2] ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com