

Textiles — Tests for colour fastness —

Part C10: Colour fastness to washing with soap or soap and soda

The European Standard EN ISO 105-C10:2007 has the status of a
British Standard

ICS 59.080.01

National foreword

This British Standard was published by BSI. It is the UK implementation of EN ISO 105-C10:2007. It is identical with ISO 105-C10:2006. It supersedes BS EN 20105-C01:1993, BS EN 20105-C02:1993, BS EN 20105-C03:1993, BS EN 20105-C04:1993 and BS EN 20105-C05:1993, which are withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/81, Colour fastness and colour measurement of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2007

© BSI 2007

ISBN 978 0 580 50608 6

Amendments issued since publication

Amd. No.	Date	Comments

English Version

**Textiles - Tests for colour fastness - Part C10: Colour fastness
to washing with soap or soap and soda (ISO 105-C10:2006)**

Textiles - Essais de solidité des teintures - Partie C10:
Solidité des teintures au lavage au savon ou au savon et à
la soude (ISO 105-C10:2006)

Textilien - Farbechtheitsprüfungen - Teil C10: Farbechtheit
gegen das Waschen mit Seife oder mit Seife und Soda
(ISO 105-C10:2006)

This European Standard was approved by CEN on 1 March 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 105-C10:2006 has been prepared by Technical Committee ISO/TC 38 "Textiles" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 105-C10:2007 by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 105-C10:2006 has been approved by CEN as EN ISO 105-C10:2007 without any modifications.

INTERNATIONAL
STANDARD

ISO
105-C10

First edition
2006-06-15

Textiles — Tests for colour fastness —
Part C10:
**Colour fastness to washing with soap
or soap and soda**

Textiles — Essais de solidité des teintures —

Partie C10: Solidité des teintures au lavage au savon ou au savon et à la soude



Reference number
ISO 105-C10:2006(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 105-C10 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

ISO 105 was previously published in thirteen "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A02"). These sections are now being republished as separate documents, themselves designated "parts", but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

This first edition of ISO 105-C10 cancels and replaces ISO 105-C01:1989, ISO 105-C02:1989, ISO 105-C03:1989, ISO 105-C04:1989 and ISO 105-C05:1989, which have been technically revised.

Introduction

The test methods in this part of ISO 105 are intended to reflect the effect of washing using soap or soap and soda by domestic and commercial laundering procedures on the colour of textiles. The washes are carried out in a similar manner to the ISO 105-C08 tests, but using soap.

The general principles of testing, described in ISO 105-A01, should be understood before using this part of ISO 105.

Textiles — Tests for colour fastness —

Part C10:

Colour fastness to washing with soap or soap and soda

1 Scope

This part of ISO 105 specifies five methods intended for determining the resistance of the colour of textiles of all kinds and in all forms to washing procedures, from mild to severe, used for normal household articles.

This part of ISO 105 is designed to determine the effect of washing only on the colour fastness of the textile. It is not intended to reflect the result of the comprehensive laundering procedure.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-A04 *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-F, *Textiles — Tests for colour fastness — Part F: Standard adjacent fabrics*

ISO 105-F01, *Textiles — Tests for colour fastness — Part F01: Specification for wool adjacent fabric*

ISO 105-F02, *Textiles — Tests for colour fastness — Part F02: Specification for cotton and viscose adjacent fabrics*

ISO 105-F03, *Textiles — Tests for colour fastness — Part F03: Specification for polyamide adjacent fabric*

ISO 105-F04, *Textiles — Tests for colour fastness — Part F04: Specification for polyester adjacent fabric*

ISO 105-F05, *Textiles — Tests for colour fastness — Part F05: Specification for acrylic adjacent fabric*

ISO 105-F06, *Textiles — Tests for colour fastness — Part F06: Specification for silk adjacent fabric*

ISO 105-F07, *Textiles — Tests for colour fastness — Part F07: Specification for secondary acetate adjacent fabric*

ISO 105-F10, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre*

ISO 105-J01 *Textiles — Tests for colour fastness — Part J01: General principles for measurement of surface colour*

ISO 105-J03, *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Principle

A specimen of the textile in contact with one or two specified adjacent fabrics is mechanically agitated under specified conditions of time and temperature in a soap, or soap and soda solution, then rinsed and dried. The change in colour of the specimen and the staining of the adjacent fabric, or fabrics, are assessed with reference to the original fabric, either with the grey scales or instrumentally.

4 Apparatus

4.1 Suitable mechanical laundering device, consisting of water bath containing a rotatable shaft which supports, radially, stainless steel containers [(75 mm ± 5 mm diameter) × (125 mm ± 10 mm high)] of capacity (550 ± 50) ml, the bottom of the containers being (45 ± 10) mm from the centre of the shaft.

The shaft/container assembly is rotated at a frequency of (40 ± 2) r/min. The temperature of the water bath is thermostatically controlled to maintain the test solution at the prescribed temperature ± 2 °C.

Other mechanically devices may be used for this test, provided that the results are identical with those obtained by the apparatus described in 4.1. Be aware of possible contamination (see the note in 7.2).

4.2 Balance, accurate to ± 0,01 g (see ISO 105-A01).

4.3 Mechanical stirrer, minimum 16,667 s⁻¹ (1 000 r/min) to ensure thorough dispersion and prevent settling.

4.4 Non-corrodible (stainless) steel balls, approximately 6 mm in diameter.

4.5 Means of heating the soap solution, such as a hot plate.

5 Reagents and materials

5.1 Soap, containing not more than 5 % moisture and complying with the following requirements based upon dry mass:

- free alkali, calculated as Na₂CO₃: 0,3 % maximum;
- free alkali, calculated as NaOH: 0,1 % maximum;
- total fatty matter: 850 g/kg minimum;
- titre of mixed fatty acids, prepared from soap: 30 °C maximum;
- Iodine value: 50 maximum.

The soap shall be free from fluorescent brightening agents.

5.2 Sodium carbonate, anhydrous (Na_2CO_3).

5.3 Soap solution, containing 5 g of soap (5.1) per litre of water (5.4) for test conditions A and B and 5 g of soap (5.1) and 2 g of sodium carbonate (5.2) per litre of water (5.4), for test conditions C, D and E.

It is recommended to vigorously disperse the soap using a mixer (4.3) in grade 3 water at $(25 \pm 5)^\circ\text{C}$ and stir for (10 ± 1) min.

5.4 Grade 3 water, complying with ISO 3696.

5.5 Adjacent fabrics (see ISO 105-A01), either 5.5.1 or 5.5.2

5.5.1 Multifibre adjacent fabric, complying with ISO 105-F10, according to the temperature used:

- Type DW multifibre adjacent fabric containing wool and acetate (for tests at 40°C and 50°C and, in certain cases, to be indicated in the test report, at 60°C);
- Type TV multifibre adjacent fabric not containing wool and acetate (in certain tests at 60°C and in all tests at 95°C).

5.5.2 Two single-fibre adjacent fabrics, complying with the relevant clauses of ISO 105-F01 to ISO 105-F07.

One of the adjacent fabrics shall be made of the same kind of the fibre as that of the textile to be tested or that predominating in the case of blends. The second piece shall be made of the fibre as indicated in Table 1 or, in the case of blends, of the kind of fibre second in order of predominance or as otherwise specified.

Table 1 — Pairs of adjacent fabrics

If first piece is	Second piece	
	For test at 40°C and 50°C	For test at 60°C and 95°C
Cotton	Wool	Viscose
Wool	Cotton	—
Silk	Cotton	—
Viscose	Wool	Cotton
Acetate	Viscose	Viscose
Polyamide	Wool or cotton	Cotton
Polyester	Wool or cotton	Cotton
Acrylic	Wool or cotton	Cotton

5.6 Non-dyeable fabric, if required (e.g. polypropylene).

5.7 Grey scales, for assessing change in colour and staining (ISO 105-A02; ISO 105-A03), or a **spectrophotometer** for assessing change in colour and staining complying with ISO 105-J01, ISO 105-A04 and ISO 105-A05.

6 Test specimen

6.1 If the textile to be tested is fabric, either

- a) attach a specimen 100 mm × 40 mm to a piece of the multifibre adjacent fabric (5.5.1), also 100 mm × 40 mm, by sewing along one of the shorter edges, with the multifibre adjacent fabric next to the face side of the specimen, or
- b) attach a specimen 100 mm × 40 mm between the two single-fibre adjacent fabric (5.5.2), also 100 mm × 40 mm by sewing along one of the shorter edges.

6.2 Yarn may be knitted into fabric and tested in this form. Where yarns or loose fibres are to be tested, take a mass of the yarn or loose fibres approximately equal to one-half of the combined mass of the adjacent fabrics and either

- a) place it between a 100 mm × 40 mm piece of the multifibre fabric (5.5.1) and a piece of the non-dyeable fabric (5.6) and sew them along all four sides (see ISO 105-A01), or
- b) place it between a 100 mm × 40 mm pieces of the two specified single-fibre fabrics (5.5.2) and sew them along all four sides.

6.3 Determine the mass, in grams, of the composite specimen using the balance (4.2) to aid accurate liquor ratio volumes.

7 Test procedures

7.1 Prepare the soap solution (5.3) according to the test used.

7.2 Place the composite specimen in the container together with the specified number of steel balls (Table 2). Add the necessary amount of soap solution (5.3) preheated to the test temperature ± 2 °C, according to Table 2, to give a liquor ratio of 50:1 ml/g. Close the container and operate the machine at the temperature and for the time specified in Table 2. Begin timing as soon as the container is closed.

Table 2 — Test conditions

Test number	Temperature °C	Time	Number of steel balls	Sodium carbonate
A (1)	40	30 min	0	–
B (2)	50	45 min	0	–
C (3)	60	30 min	0	+
D (4)	95	30 min	10	+
E (5)	95	4 h	10	+

Care should be taken to differentiate clearly between containers used for testing with and without fluorescent brighteners.

NOTE Containers (see 4.1) could be contaminated by the fluorescent brightening agents present in other test detergents and in commercial detergents. This could affect the colour fastness ratings of test specimens if such contaminated containers were subsequently used for tests using a detergent without fluorescent brighteners.

7.3 For all tests, remove the composite specimen at the end of the wash and place it in a 4 l beaker half filled with grade 3 water (5.4) at ambient temperature. Gently agitate, rinse for 1 min and then place the beaker under a cold running tap for 1 min.

7.4 For all methods, extract the excess water from the composite specimen by squeezing the test specimen by hand.

Open out the composite specimen by cutting the stitching except on one of the shorter sides if necessary.

7.5 Dry the specimen by pressing it flat between new filter papers to remove excess water. Then dry by hanging it in air at a temperature not exceeding 60 °C, with the parts in contact only at the line of stitching.

7.6 Assess the change in colour of the specimen and the staining of the adjacent fabric with reference to the original specimen using either the grey scales or instrumentally. See ISO 105-A02; ISO 105-A03; ISO 105-A04; ISO 105-A05; ISO 105-J03.

8 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 105 (ISO 105-C10:2006);
- b) all details necessary for complete identification of the sample tested;
- c) the test conditions/test number used from Table 2;
- d) the numerical grey scale rating and/or instrumental assessment for the change in colour of the specimen;
- e) if single-fibre adjacent fabrics were used, the numerical rating for staining of each kind of adjacent fabric used;
- f) if a multifibre adjacent fabric was used, the staining of each type of fibre in the multifibre adjacent fabric, and the type of multifibre adjacent fabric used;
- g) any deviation, by agreement or otherwise, from the procedure specified.

Bibliography

- [1] ISO 105-C08, *Textiles — Tests for colour fastness — Part C08: Colour fastness to domestic and commercial laundering using a non-phosphate reference detergent incorporating a low temperature bleach activator*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.