

BS EN ISO 105-X16:2016



BSI Standards Publication

Textiles — Tests for colour fastness

Part X16: Colour fastness to rubbing —
Small areas (ISO 105-X16:2016)

National foreword

This British Standard is the UK implementation of EN ISO 105-X16:2016. It supersedes BS EN ISO 105-X16:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/81, Colour fastness and colour measurement of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 84916 9

ICS 59.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 105-X16

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2016

ICS 59.080.01

Supersedes EN ISO 105-X16:2002

English Version

Textiles - Tests for colour fastness - Part X16: Colour fastness to rubbing - Small areas (ISO 105-X16:2016)

Textiles - Essais de solidité des coloris - Partie X16:
Solidité des coloris au frottement - Petites surfaces
(ISO 105-X16:2016)

Textilien - Farbechtheitsprüfungen - Teil X16:
Farbechtheit gegen Reiben - Kleine Flächen (ISO 105-
X16:2016)

This European Standard was approved by CEN on 15 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 105-X16:2016) has been prepared by Technical Committee ISO/TC 38 “Textiles” in collaboration with Technical Committee CEN/TC 248 “Textiles and textile products” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2016, and conflicting national standards shall be withdrawn at the latest by December 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 105-X16:2002.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 105-X16:2016 has been approved by CEN as EN ISO 105-X16:2016 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Test specimens	2
6 Procedure	2
6.1 General	2
6.2 Dry rubbing	2
6.3 Wet rubbing	3
6.4 Drying	3
7 Evaluation	3
8 Test report	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This second edition cancels and replaces the first edition (ISO 105-X16:2001), of which it constitutes a minor revision.

ISO 105 consists of many parts designated by a part letter and a two-digit serial number (e.g. A01), under the general title *Textiles — Tests for colour fastness*. A complete list of these parts is given in ISO 105-A01.

Textiles — Tests for colour fastness —

Part X16:

Colour fastness to rubbing — Small areas

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles to rubbing off and staining other materials where the singling out of areas smaller than possible to test with the apparatus described in ISO 105-X12 is required.

Two tests may be made, one with a dry rubbing cloth and one with a wet rubbing cloth.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01:2010, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-F09, *Textiles — Tests for colour fastness — Part F09: Specification for cotton rubbing cloth*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

3 Principle

Specimens of the textile are rubbed with a dry rubbing cloth and with a wet rubbing cloth. The method is specifically designed for small areas of printed or otherwise coloured fabric where the singling out of areas smaller than possible to test with the standard rubbing device found in method ISO 105-X12 is required.

4 Apparatus

4.1 Suitable testing devices for determining the colour fastness to rubbing, using an alternating rotary motion and a single test finger of $(25 \pm 0,1)$ mm diameter mounted on a vertical weighted rod that rotates $(405 \pm 3)^\circ$ with a downward force of $(11,1 \pm 0,5)$ N.

Another device has a test finger of $(16 \pm 0,1)$ mm diameter with the same downward force.

NOTE A suitable apparatus is described in Reference [1], AATCC Test Method 116. Other devices can be used provided that the same results are obtained as with the apparatus described in 4.1. There is no known correlation of results between the device used in this method and two methods described in ISO 105-X12.

4.2 Cotton rubbing cloth, desized, bleached, without finish, cut into 50 mm squares (± 2 mm) for the finger used in 4.1 (see ISO 105-F09).

4.3 Soft-back waterproof abrasive paper, or grating of stainless steel wire 1 mm in diameter and mesh width about 20 mm.

Attention should be paid to the characteristics of the grating or abrasive paper used to hold the specimen as they may leave an imprint through the textile which would cause a false rating to be made. The use of the abrasive paper may be preferred for testing textile fabrics.

4.4 Grey scale for assessing staining, in accordance with ISO 105-A03.

Verification on the operation of the test and the apparatus should be made routinely and the results kept in a log. Use an in-house or established rubbing specimen and conduct three (3) dry tests.

5 Test specimens

5.1 If the textile to be tested is a fabric, specimens not less than 25 mm × 25 mm are required.

Additional specimens may be used when higher precision is needed.

5.2 If the textile to be tested is yarn or thread, knit it into fabric to provide specimens at least 25 mm × 25 mm or form a layer of parallel strands by wrapping it lengthways on a cardboard rectangle of suitable dimensions.

5.3 Before testing, condition the specimen and rubbing cloth for at least 4 h in the standard atmosphere as defined in ISO 139.

Alternative standard atmospheres as defined in ISO 139 may only be used if the parties agree and, in this case, the alternative atmosphere used shall be reported. Conditioning is done by laying each test specimen and each piece of rubbing cloth separately on a screen or perforated shelf. Some fabrics such as cotton or wool may require longer periods of conditioning.

5.4 For best results, testing should be conducted under standard atmosphere for testing textiles (see ISO 139).

6 Procedure

6.1 General

Tilt the upper half of the rotary vertical machine to open and expose the rotary crocking finger. Fasten the specimen at the point the vertical rod comes into contact with the base and place the rubbing square on the finger. Return the upper half of the machine back to the operating position with the rubbing cloth at the end of the shaft in contact with the test specimen. Apply weight to the vertical shaft to give $(11,1 \pm 0,5)$ N downward force.

6.2 Dry rubbing

Place the conditioned rubbing cloth (see [4.2](#) and [5.3](#)), flat over the end of rubbing finger and turn the crank 20 turns producing 40 reciprocal turns of the vertical shaft. Turn the crank at a rate of one revolution per second. Remove the test square and condition.

6.3 Wet rubbing

Establish a technique for preparing the rubbing cloth by weighing a conditioned piece of cloth, then thoroughly soak in distilled water and reweigh to ensure take-up of 95 % to 100 %. Follow the instructions for rubbing in [6.2](#).

NOTE As the level of soak of the rubbing cloth might dramatically affect ratings, other levels can be used. An example of a very commonly used level of soak is (65 ± 5) % of the conditioned mass of a dry rubbing cloth.

6.4 Drying

Air dry the test cloth.

7 Evaluation

7.1 Remove any extraneous fibrous material that might interfere with the rating.

7.2 Back each tested rubbing cloth with three layers of white rubbing cloth while evaluating.

7.3 Assess the staining of the cotton rubbing cloths with the grey scale for staining ([4.4](#)) under suitable illumination (see ISO 105-A01:2010, Clause 14).

NOTE Difficulty might be experienced in making assessments of the degree of staining on the rubbing cloth as the rotary device usually exhibits greater colour transfer near the edge of the tested circle than the centre.

8 Test report

The test report shall contain the following information:

- a) a reference to this part of ISO 105, i.e. ISO 105-X16:2016;
- b) whether dry or wet rubbing was performed along with the percentage of soak;
- c) the numerical rating for staining for each test specimen;
- d) the time of conditioning of the specimens and rubbing cloth as well as the atmospheric conditions during testing.

Bibliography

- [1] *Technical Manual of the American Association of Textile Chemists and Colorists*, www.aatcc.org
- [2] ISO 105-X12, *Textiles — Tests for colour fastness — Part X12: Colour fastness to rubbing*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK