

BS EN ISO 536:2012



BSI Standards Publication

Paper and board — Determination of grammage (ISO 536:2012)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 536:2012. It supersedes BS EN ISO 536:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 76591 9

ICS 85.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2012.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Paper and board - Determination of grammage (ISO 536:2012)Papier et carton - Détermination du grammage (ISO
536:2012)Papier und Pappe - Bestimmung der flächenbezogenen
Masse (ISO 536:2012)

This European Standard was approved by CEN on 14 July 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG**Management Centre: Avenue Marnix 17, B-1000 Brussels**

Foreword

This document (EN ISO 536:2012) has been prepared by Technical Committee ISO/TC 6 "Paper, board and pulps" in collaboration with Technical Committee CEN/TC 172 "Pulp, paper and board" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2013, and conflicting national standards shall be withdrawn at the latest by January 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 536:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 536:2012 has been approved by CEN as a EN ISO 536:2012 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Sampling	2
7 Conditioning	2
8 Procedure	2
9 Calculation and expression of results	2
10 Test report	3
Annex A (normative) Determination of grammage on an “oven-dry” and “as-taken” basis	4
Annex B (informative) Precision	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 536 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This third edition cancels and replaces the second edition (ISO 536:1995), of which it constitutes a minor revision. Mainly editorial changes have been made and precision data have been added as an informative Annex B.

Paper and board — Determination of grammage

1 Scope

This International Standard specifies a method for determining the grammage of paper and board.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

grammage

mass per unit area

mass of a unit area of paper or board determined by a specific method of test

NOTE Grammage is expressed in grams per square metre.

4 Principle

The area of the test pieces and their masses are determined and the grammage is calculated.

5 Apparatus

5.1 Cutting device, capable of repeatedly cleanly cutting test pieces of the same nominal size, whose area falls within $\pm 1,0$ % of a known area. This shall be checked frequently by measurement and, provided that the above accuracy is attained, the mean area obtained in these checks shall be used for calculating grammage.

With certain types of paper and board it will be found, after carrying out this determination of area, that test pieces cannot be cut with the accuracy just defined; in such instances, the area of every test piece shall be determined individually.

5.2 Balance, sufficiently accurate, over the range of mass for which it is used, to measure to within 0,5 % of the actual mass. It shall be sensitive enough to detect a change of $\pm 0,2$ % in the mass to be weighed and, if the balance is of the direct-reading type, it shall be graduated so that readings may be taken to this degree of accuracy.

Special sheet-weighing balances, designed to weigh test pieces of a given size and which indicate grammage directly, may be used, provided that the above conditions are fulfilled and that the area of each test piece on a single weighing is not less than 50 000 mm² (500 cm²) and not more than 100 000 mm² (1 000 cm²) (see Clause 8 and 9.2).

When in use, the balance shall be shielded from air currents.

6 Sampling

The selection of units and sheets and the taking of specimens shall be carried out in accordance with ISO 186. The number of specimens taken (at least five) shall be sufficient for at least 20 test pieces. If tests are made on another type of sample, make sure that the specimens taken are representative of the sample received.

7 Conditioning

For the determination of conditioned grammage, the specimens shall be conditioned in accordance with ISO 187.

If a determination is made in the "oven-dry" or "as-taken" condition (see Annex A), or if any other conditioning atmosphere is used, the reported results shall be qualified by a statement indicating the condition of the test pieces at the time of weighing.

8 Procedure

For the determination of conditioned grammage, prepare and weigh the test pieces in the same atmospheric conditions as used to condition the specimens.

Using the cutting device (5.1), cut at least 20 test pieces from at least five specimens, if possible taking the same number from each specimen.

Whenever possible, each test piece shall have an area of not less than 50 000 mm² (preferably 200 mm × 250 mm) and not more than 100 000 mm²; it may, if necessary, be composed of several smaller pieces.

NOTE In cases where there is only a limited sample area available and it is not possible to make up a test piece comprising several smaller pieces, a test area of not less than 10 000 mm² (100 cm²) may be used.

Determine the area of each test piece by calculation, from measurements taken to the nearest 0,5 mm.

Weigh each test piece on the balance (5.2) and express its mass to three significant figures.

It is recommended, especially when dealing with small pieces, that contact of the test piece with bare hands be avoided.

9 Calculation and expression of results

9.1 If the procedure in Clause 8 is followed, calculate the grammage, g , in grams per square metre, to three significant figures, for each test piece, using Equation (1):

$$g = \frac{m}{A} \times 10^6 \quad (1)$$

where

m is the mass, in grams, of the test piece;

A is the area, in square millimetres, of the test piece.

Alternatively, the grammage may be calculated using Equation (2):

$$g = \frac{\bar{m}}{\bar{A}} \times 10^6 \quad (2)$$

where

\bar{m} is the average mass, in grams, of the test pieces;

\bar{A} is the average area, in square millimetres, of the test pieces.

9.2 If a special sheet-weighing balance such as described in 5.2 is used, calculate the grammage, g , in grams per square metre, to three significant figures, using Equation (3):

$$g = \frac{A_1}{A} \times g_1 \quad (3)$$

where

g_1 is the indicated grammage, in grams per square metre, of the test piece;

A_1 is the area, in square millimetres, of the test piece for which the balance is calibrated;

A is the area, in square millimetres, of the weighed test piece.

9.3 Calculate the mean of the results and the standard deviation and express them to three significant figures.

10 Test report

The test report shall include the following information:

- a) a reference to this International Standard (ISO 536:2012);
- b) the date and place of testing;
- c) all the information necessary for identification of the sample;
- d) the conditioning atmosphere used;
- e) the area of the test piece used;
- f) the number of replicate tests;
- g) the mean and standard deviation of the results;
- h) if specimens have been taken from more than one position across a reel or sheet and information on grammage variation is required, the details listed in c), d), e) and f) shall be reported for each position separately;
- i) any departure from the procedure specified in this International Standard and any circumstances that may have influenced the results.

Annex A (normative)

Determination of grammage on an “oven-dry” and “as-taken” basis

A.1 Determination of grammage on an “oven-dry” basis

Determine the area of each test piece after conditioning in accordance with Clause 7. Dry the test pieces in accordance with ISO 287 and determine their mass. Calculate the grammage according to 9.1.

A.2 Determination of grammage “as-taken”

This is based on the material in the condition pertaining at the time of sampling. Select specimens and cut and weigh test pieces from them as quickly as the need for accuracy will allow. When taking specimens from a roll, cut them out from a depth such that their moisture content has remained unaffected by the ambient atmosphere.

Annex B (informative)

Precision

The precision data presented in Tables B.1 and B.2 has been obtained from CEPI-CTS, the Comparative Testing Service of the Confederation of European Paper Industries. Estimates of repeatability and reproducibility from the CEPI-CTS programme are based on round-robin work in 2011 in which 17 laboratories from 11 European countries tested three different sample materials.

The calculations have been made according to ISO/TR 24498^[1] and TAPPI T 1200^[2].

The repeatability standard deviation reported in Table B.1 is the “pooled” repeatability standard deviation; that is, the standard deviation is calculated as the root-mean-square of the standard deviations of the participating laboratories. This differs from the conventional definition of repeatability in ISO 5725-1^[3].

The repeatability and reproducibility limits reported are estimates of the maximum difference which should be expected in 19 out of 20 instances, when comparing two test results for material similar to those described under similar test conditions. These estimates may not be valid for different materials or different test conditions.

Repeatability and reproducibility limits are calculated by multiplying the repeatability and reproducibility standard deviations by 2,77.

NOTE 1 The *repeatability standard deviation* and the *within-laboratory standard deviation* are identical. However, the *reproducibility standard deviation* is NOT the same as the *between-laboratory standard deviation*. The reproducibility standard deviation includes both the between-laboratory standard deviation and the within-laboratory standard deviation, viz.:

$$s_{\text{repeatability}}^2 = s_{\text{within lab}}^2 \quad \text{but} \quad s_{\text{reproducibility}}^2 = s_{\text{within lab}}^2 + s_{\text{between lab}}^2$$

NOTE 2 $2,77 = 1,96 \times \sqrt{2}$, provided that the test results have a normal distribution and that the standard deviation s is based on a large number of tests.

Table B.1 — Estimation of repeatability of the test method from CEPI-CTS

Sample	Number of laboratories	Mean value g/m ²	Repeatability standard deviation s_r g/m ²	Coefficient of variation $C_{V,r}$ %	Repeatability limit r g/m ²
Level 1	17	51,0	0,51	1,00	1,41
Level 2	16 ^a	94,6	1,04	1,10	2,88
Level 3	17	281	1,60	0,57	4,44

^a Outlier not included.

Table B.2 — Estimation of reproducibility of the test method from CEP-CTS

Sample	Number of laboratories	Mean value g/m ²	Reproducibility standard deviation s_R g/m ²	Coefficient of variation $C_{V,R}$ %	Reproducibility limit R g/m ²
Level 1	17	51,0	0,65	1,27	1,80
Level 2	16 ^a	94,6	1,47	1,56	4,08
Level 3	17	281	3,67	1,31	10,2

^a Outlier not included.

Bibliography

- [1] ISO/TR 24498:2006, *Paper, board and pulps — Estimation of uncertainty for test methods*
- [2] TAPPI Test method T 1200 sp-07, *Interlaboratory evaluation of test methods to determine TAPPI repeatability and reproducibility*
- [3] ISO 5725-1:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™