

General methods of test for pigments and extenders —

Part 14: Determination of resistivity of aqueous extract

The European Standard EN ISO 787-14:2002 has the status of a
British Standard

ICS 87.060.10

National foreword

This British Standard is the official English language version of EN ISO 787-14:2002. It is identical with ISO 787-14:2002. It supersedes BS 3483-C5:1974 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/1, Pigments, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii to v, a blank page, pages 1 to 4, the Annex ZA page, and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, having been prepared under the direction of the Materials and Chemicals Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 19 September 2002

© BSI 19 September 2002

ISBN 0 580 40434 X

English version

**General methods of test for pigments and extenders - Part 14:
Determination of resistivity of aqueous extract (ISO 787-
14:2002)**

Méthodes générales d'essai des pigments et matières de charge - Partie 14: Détermination de la résistivité de l'extrait aqueux (ISO 787-14:2002)

Allgemeine Prüfverfahren für Pigmente und Füllstoffe - Teil 14: Bestimmung des spezifischen Widerstandes des wässrigen Extraktes (ISO 787-14:2002)

This European Standard was approved by CEN on 13 June 2002.

CEN members are bound to comply with the CEN/GENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 787-14:2002) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 298 "Pigments and extenders", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2003, and conflicting national standards shall be withdrawn at the latest by February 2003.

This document supersedes EN ISO 787-14:2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 787-14:2002 has been approved by CEN as a European Standard without any modifications.

NOTE Normative references to International Standards are listed in annex ZA (normative).

INTERNATIONAL
STANDARD

EN ISO 787-14:2002

ISO
787-14

Second edition
2002-08-01

**General methods of test for pigments and
extenders —**

Part 14:
**Determination of resistivity of aqueous
extract**

Méthodes générales d'essai des pigments et matières de charge —

Partie 14: Détermination de la résistivité de l'extrait aqueux



Reference number
ISO 787-14:2002(E)

Contents

	Page
1 Scope	1
2 Normative reference	1
3 Reagents	1
4 Apparatus	2
5 Sampling	2
6 Determination of cell constant	2
7 Procedure	3
8 Expression of results	3
9 Test report	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 787 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 787-14 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 2, *Pigments and extenders*.

This second edition cancels and replaces the first edition (ISO 787-14:1973), of which it constitutes a minor (editorial) revision.

ISO 787 consists of the following parts, under the general title *General methods of test for pigments and extenders*:

- *Part 1: Comparison of colour of pigments*
- *Part 2: Determination of matter volatile at 105 °C*
- *Part 3: Determination of matter soluble in water — Hot extraction method*
- *Part 4: Determination of acidity or alkalinity of the aqueous extract*
- *Part 5: Determination of oil absorption value*
- *Part 7: Determination of residue on sieve — Water method — Manual procedure*
- *Part 8: Determination of matter soluble in water — Cold extraction method*
- *Part 9: Determination of pH value of an aqueous suspension*
- *Part 10: Determination of density — Pyknometer method*
- *Part 11: Determination of tamped volume and apparent density after tamping*
- *Part 13: Determination of water-soluble sulphates, chlorides and nitrates*
- *Part 14: Determination of resistivity of aqueous extract*
- *Part 15: Comparison of resistance to light of coloured pigments of similar types*
- *Part 16: Determination of relative tinting strength (or equivalent colouring value) and colour on reduction of coloured pigments — Visual comparison method*
- *Part 17: Comparison of lightening power of white pigments*
- *Part 18: Determination of residue on sieve — Mechanical flushing procedure*
- *Part 19: Determination of water-soluble nitrates (Salicylic acid method)*
- *Part 21: Comparison of heat stability of pigments using a stoving medium*
- *Part 22: Comparison of resistance to bleeding of pigments*

- *Part 23: Determination of density (using a centrifuge to remove entrained air)*
- *Part 24: Determination of relative tinting strength of coloured pigments and relative scattering power of white pigments — Photometric methods*
- *Part 25: Comparison of the colour, in full-shade systems, of white, black and coloured pigments — Colorimetric method*

General methods of test for pigments and extenders —

Part 14:

Determination of resistivity of aqueous extract

1 Scope

This part of ISO 787 specifies a general method of test for determining the resistivity (specific resistance) of the aqueous extract of a pigment. The method is applicable to all pigments and extenders, except pigments that are substantially soluble in water.

It should be noted that the resistivity of the aqueous extract of a pigment should be considered as a property independent of the amount of water-soluble matter. If agreed, a cold extraction method may be used. This shall be stated in the test report, however.

The standard temperature of determination should preferably be 23 °C but a different temperature may be agreed between the parties provided that the necessary corrections are made to take account of the differences in temperature.

NOTE When this general method is applicable to a given pigment, a cross-reference to it will simply be included in the International Standard relating to that pigment, with a note of any detailed modification which may be needed in view of the special properties of the pigment in question. Only when this general method is not applicable to a particular pigment will a special method for determination of resistivity of aqueous extract be specified.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this part of ISO 787. For dated references, subsequent amendments to, or revisions of, this publication do not apply. However, parties to agreements based on this part of ISO 787 are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Reagents

All reagents used shall be of recognized analytical reagent quality.

3.1 Conductivity water, resistivity not less than 2 500 $\Omega \cdot \text{m}$.

3.2 Methanol, resistivity not less than 2 500 $\Omega \cdot \text{m}$.

3.3 Potassium chloride, 0,02 mol/l solution.

4 Apparatus

4.1 Centrifuge, or ultra-centrifuge if necessary.

4.2 Filter paper, fine textured, washed with conductivity water on a filter funnel until the filtrate gives a resistivity greater than $2\,000\ \Omega \cdot \text{m}$.

NOTE The diameter of the filter paper depends on the bulk density of the pigment. Some organic pigments require at least a 185 mm paper for satisfactory filtering.

4.3 Cylinder, approximately 35 mm wide by 125 mm deep, or other container suitable for use with the conductivity cell to be employed.

4.4 Thermometer, graduated in $0,2\ ^\circ\text{C}$ intervals.

4.5 Conductivity bridge.¹⁾

4.6 Conductivity cell,¹⁾ having a cell constant K of approximately 1.

5 Sampling

The sample of pigment used for the test shall be taken in accordance with the provisions of ISO 15528.

6 Determination of cell constant

6.1 Prepare a working standard solution of potassium chloride by diluting the potassium chloride solution (3.3) with conductivity water to a known concentration.

Measure the resistance R of the working standard solution using the conductivity cell (4.6) at $23\ ^\circ\text{C}$ (or at an alternative agreed temperature with appropriate corrections) as described in 7.2.2.

6.2 Calculate the cell constant K as follows:

$$K = \frac{R}{\rho}$$

where

R is the measured resistance, in ohms;

ρ is the resistivity at $23\ ^\circ\text{C}$ of the KCl solution of the concentration used, in ohm metres (for a $0,002\ \text{mol/l}$ solution, this is $34,4\ \Omega \cdot \text{m}$ — see Figure 1).

If a potassium chloride solution of different known concentration is used, deduce the appropriate value of ρ from Figure 1 for use in the calculation of the cell constant.

In general, the cell constant is not greatly affected by variations in the strength of the potassium chloride solution, but for greatest accuracy a concentration of the potassium chloride solution shall be used which has a resistivity similar to that of the solution being tested, and measurements shall be made at values that utilize the middle third of the scale.

¹⁾ Any commercially produced conductivity bridge and conductivity cell are likely to be satisfactory.

7 Procedure

7.1 Test for water-wettability of the pigment

Test a small amount of the pigment with boiling distilled water to see if it is water-wettable. Material which does not wet well with water is probably hydrophobic and shall be treated as described in 7.3. If the sample wets easily, proceed as described in 7.2.

7.2 Hydrophilic pigments

7.2.1 Add $(20 \pm 0,01)$ g of the pigment to 180 g of boiling conductivity water in a tared beaker of suitable capacity with a stirring rod.

NOTE A 20 g test portion is usually sufficient for pigments easily wetted with water. Usually a 250 ml beaker is sufficient for white pigments. Some white pigments, however, because of a tendency to foam and crawl, can be handled better in a 400 ml beaker. A 20 g test portion of an organic pigment usually requires a 600 ml beaker to allow adequate room for foaming when boiled.

Boil slowly for 5 min with occasional stirring. Cool to a temperature of about $60\text{ }^{\circ}\text{C}$ and add water to bring the net mass back to 200 g. Stir thoroughly. Filter directly through a fine-textured filter paper, or separate the solids using a centrifuge or ultra-centrifuge and clean dry tubes, or tubes washed with some of the slurry, followed by decanting the supernatant liquid through a filter. In either case, discard the first 10 ml of filtrate.

7.2.2 Cool the filtrate to a temperature of about $20\text{ }^{\circ}\text{C}$. Rinse the cylinder (4.3) and the conductivity cell (4.6) first with conductivity water and then with the filtrate. Fill the cylinder with the filtrate and place the conductivity cell in it. Move the cell up and down to remove all air bubbles. Adjust the temperature slowly to $23\text{ }^{\circ}\text{C}$ and, with the cell submerged so that the vent is about 10 mm below the surface of the liquid and upright in the centre of the cylinder, make at least five measurements of the resistance at a temperature of $(23 \pm 0,5)\text{ }^{\circ}\text{C}$, using the conductivity bridge (4.5) with the multiplier set to give a reading near the centre of the scale, following the instructions supplied with the instrument to obtain a balance.

Repeat the whole procedure on a further aqueous extract of the pigment.

7.3 Hydrophobic pigments

A modification of the procedure given in 7.2 is necessary for organic pigments that are not easily wetted with water.

Wet $(20 \pm 0,01)$ g of pigment with as much methanol (3.2) (4 g to 16 g) as is required to produce a smooth wet paste. Dilute with boiling conductivity water in a tared 1 000 ml beaker with a stirring rod to bring the total mass to 200 g. Then proceed as outlined in 7.2.2.

Repeat the whole procedure on a further aqueous extract of the pigment.

8 Expression of results

Calculate the resistivity ρ_t , in ohm metres, of the aqueous extract of the pigment at the agreed temperature $t\text{ }^{\circ}\text{C}$, by the equation:

$$\rho_t = \frac{\bar{R}_t}{K}$$

where

\bar{R}_t is the mean of all measured values of resistance, in ohms;

K is the cell constant, determined in accordance with 6.2.

Express the result to the nearest 1 % of the value obtained.

9 Test report

The test report shall include the following information:

- a reference to this part of ISO 787 (ISO 787-14);
- all details necessary for complete identification of the pigment under test;
- any deviation, by agreement or otherwise, from the test procedures described above;
- whether the pigment was treated as a hydrophilic pigment (7.2) or a hydrophobic pigment (7.3);
- the result of the test as indicated in clause 8;
- the date of the test.




Figure 1 — Resistivity of potassium chloride at 23 °C

Annex ZA (normative)

Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE Where an International Publication has been modified by common modifications, indicated by (mod.), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 15528	2000	Paints, varnishes and raw materials for paints and varnishes — Sampling	EN ISO 15528	2000

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.