

BS EN ISO 1141:2012



BSI Standards Publication

Fibre ropes — Polyester — 3-, 4-, 8- and 12-strand ropes (ISO 1141:2012)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 1141:2012. It supersedes BS EN ISO 1141:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/77, Ropes and cordage and fishing nets.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 74410 5

ICS 59.080.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2012.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

**Fibre ropes - Polyester - 3-, 4-, 8- and 12-strand ropes (ISO
1141:2012)**

Cordages en fibres - Polyester - Cordages à 3, 4, 8 et 12
torsions (ISO 1141:2012)

Faserseile - Polyester - 3-, 4-, 8- und 12-litzige Seile (ISO
1141:2012)

This European Standard was approved by CEN on 11 August 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 1141:2012) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2013, and conflicting national standards shall be withdrawn at the latest by February 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1141:2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 1141:2012 has been approved by CEN as a EN ISO 1141:2012 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Designation	1
5 General requirements	2
6 Physical properties	3
7 Marking	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1141 was prepared by Technical Committee ISO/TC 38, *Textiles*.

This fourth edition cancels and replaces the third edition (ISO 1141:2004), which has been technically revised.

Fibre ropes — Polyester — 3-, 4-, 8- and 12-strand ropes

1 Scope

This International Standard specifies requirements for 3-strand hawser-laid and 4-strand shroud-laid ropes, 8-strand braided ropes and 12-strand braided ropes for general service made of polyester, and gives rules for their designation.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1968, *Fibre ropes and cordage — Vocabulary*

ISO 2307, *Fibre ropes — Determination of certain physical and mechanical properties*

ISO 9554, *Fibre ropes — General specifications*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1968 apply.

4 Designation

Fibre ropes shall be designated by

- the words “fibre rope”,
- the number of this International Standard,
- the construction or type of rope (see Clause 5),
- the reference number of the rope,
- the material from which the rope is made, and
- the type of stabilization (1 or 2 in accordance with ISO 9554).

Polyester-laid ropes that are required to have a heat setting on the rope to ensure lay and dimensional stability are designated as type 1 ropes. In other cases, polyester-laid ropes that are not required to have a heat setting on the rope are designated as type 2 ropes.

EXAMPLE

Designation of a 3-strand hawser-laid rope heat set (type 1), reference number 30 (type A), corresponding to a linear density of 682 ktex and made of polyester (PES):

Fibre rope ISO 1141 – A – 30 – PES – 1

5 General requirements

5.1 Polyester ropes shall be made in one of the following constructions:

- type A: 3-strand hawser-laid rope (see Figure 1);
- type B: 4-strand shroud-laid rope (see Figure 2);
- type L: 8-strand braided rope (see Figure 3);
- type T: 12-strand braided rope (see Figure 4).




Figure 1 — Shape of a 3-strand hawser-laid rope (type A)




Figure 2 — Shape of a 4-strand shroud-laid rope (type B)




Figure 3 — Shape of an 8-strand braided rope (type L)



Figure 4 — Shape of a 12-strand braided rope (type T)

5.2 Construction, manufacture, lay, labelling, packaging, invoicing and delivery lengths shall be in accordance with ISO 9554.

6 Physical properties

Linear density and minimum breaking force shall be in accordance with Tables 1, 2 and 3.

Table 1 — Linear density and minimum breaking force (MBF) of 3-strand hawser-laid polyester ropes, type A

Reference number ^a	Linear density ^{b c}		Minimum breaking force ^{d e}	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
4	12,1	±10	2,80	2,52
4,5	15,3		3,51	3,19
5	19,0		4,25	3,82
6	27,3		6,00	5,40
8	48,5		10,6	9,54
9	61,4		13,2	11,88
10	75,8	±8	16,0	14,4
12	109		22,4	20,2
14	149		30,0	27,0
16	194	±5	40,0	36,0
18	246		50,0	45,0
20	303		60,0	54,0
22	367		71,0	63,9
24	437		85,0	76,5
26	512		100	90,0
28	594		118	106
30	682		132	119
32	776		150	135
36	982		190	171
40	1 210		236	212
44	1 470		280	252
48	1 750		335	302
52	2 050		375	338
56	2 380		425	383
60	2 730		500	450
64	3 100	560	504	

Table 1 (continued)

Reference number ^a	Linear density ^{b c}		Minimum breaking force ^{d e}	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
72	3 930	±5	710	639
80	4 850		850	765
88	5 870		1 060	954
96	6 990		1 250	1 125
104	8 200		1 400	1 260
112	9 510		1 600	1 440
120	10 900		1 900	1 710
128	12 400		2 120	1 908
136	14 000		2 360	2 124
144	15 700		2 650	2 385
160	19 400		3 350	3 015

^a The reference number corresponds to the approximate diameter, in millimetres.

^b The linear density, in kilotex, corresponds to the net mass per length of rope, expressed in grams per metre or in kilograms per thousand metres.

^c The linear density is under reference tension and is measured as specified in ISO 2307.

^d The breaking forces quoted in this table relate to new dry and wet ropes.

^e A force determined by the test methods specified in ISO 2307 is not necessarily an accurate indication of the force at which that rope might break in other circumstances and situations. The type and quality of the termination rate of force application, prior conditioning and previous force applications to the rope can significantly influence the breaking force. A rope bent around a post, capstan, pulley or sheave might break at a significantly lower force. A knot or other distortion in a rope might significantly reduce the breaking force.

Table 2 — Linear density and minimum breaking force (MBF) of 4-strand shroud-laid polyester ropes, type B

Reference number ^a	Linear density ^{b c}		Minimum breaking force ^{d e}	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
6	27,3	±10	5,60	5,04
8	48,5		9,50	8,55
10	75,8		15,0	13,5
12	109	±8	21,2	19,1
14	149		28,0	25,2
16	194		35,5	32,0
18	246	±5	45,0	40,5
20	303		56,0	50,4
22	367		67,0	60,3
24	437		80,0	72,0
26	512		90,0	81,0
28	594		106	95,4
30	682		118	106
32	776		132	119

Table 2 (continued)

Reference number ^a	Linear density ^{b c}		Minimum breaking force ^{d e}	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
36	982	±5	170	153
40	1 210		212	191
44	1 470		250	225
48	1 750		300	270
52	2 050		335	302
56	2 380		400	360
60	2 730		450	405
64	3 100		500	450
72	3 930		630	567
80	4 850		800	720
88	5 870		950	855
96	6 990		1 120	1 008
104	8 200		1 320	1 188
112	9 510		1 500	1 350
120	10 900		1 700	1 530
128	12 400		1 900	1 710
136	14 000	2 120	1 908	
144	15 700	2 360	2 124	
160	19 400	3 000	2 700	

^a The reference number corresponds to the approximate diameter, in millimetres.

^b The linear density, in kilotex, corresponds to the net mass per length of rope, expressed in grams per metre or in kilograms per thousand metres.

^c The linear density is under reference tension and is measured as specified in ISO 2307.

^d The breaking forces quoted in this table relate to new dry and wet ropes.

^e A force determined by the test methods specified in ISO 2307 is not necessarily an accurate indication of the force at which that rope might break in other circumstances and situations. The type and quality of the termination rate of force application, prior conditioning and previous force applications to the rope can significantly influence the breaking force. A rope bent around a post, capstan, pulley or sheave might break at a significantly lower force. A knot or other distortion in a rope might significantly reduce the breaking force.

**Table 3 — Linear density and minimum breaking force (MBF)
of 8-strand and 12-strand braided polyester ropes, types L and T**

Reference number ^a	Linear density ^{b c}		Minimum breaking force ^{d e}			
	Nominal ktex	Tolerance %	kN			
			8 strands		12 strands	
			Unspliced ropes	Ropes with eye-spliced terminations	Unspliced ropes	Ropes with eye-spliced terminations
12	109	±8	23,0	20,7	25,0	22,5
16	194	±5	40,0	36,0	42,5	38,3
20	304		63,0	56,7	67,0	60,3
24	437		90,0	81,0	95,0	85,5
28	595		118	106	125	113
30	683		132	119	140	126
32	777		150	135	160	144
36	984		190	171	200	180
40	1 210		236	212	250	225
44	1 470		280	252	300	270
48	1 750		335	302	355	320
52	2 050		400	360	425	383
56	2 380		450	405	475	428
60	2 730		500	450	530	477
64	3 110		560	504	600	540
72	3 930		710	639	750	675
80	4 860		900	810	950	855
88	5 880		1 060	954	1 120	1 008
96	6 990		1 250	1 125	1 320	1 188
104	8 210		1 500	1 350	1 600	1 440
112	9 520	1 700	1 530	1 800	1 620	
120	10 900	1 900	1 710	2 000	1 800	
128	12 400	2 240	2 016	2 360	2 124	
136	14 000	2 500	2 250	2 650	2 385	
144	15 700	2 800	2 520	3 000	2 700	
160	19 400	3 350	3 015	3 550	3 195	

^a The reference number corresponds to the approximate diameter, in millimetres.

^b The linear density, in kilotex, corresponds to the net mass per length of rope, expressed in grams per metre or in kilograms per thousand metres.

^c The linear density is under reference tension and is measured as specified in ISO 2307.

^d The breaking forces quoted in this table relate to new dry and wet ropes.

^e A force determined by the test methods specified in ISO 2307 is not necessarily an accurate indication of the force at which that rope might break in other circumstances and situations. The type and quality of the termination rate of force application, prior conditioning and previous force applications to the rope can significantly influence the breaking force. A rope bent around a post, capstan, pulley or sheave might break at a significantly lower force. A knot or other distortion in a rope might significantly reduce the breaking force.

NOTE The relation between the minimum breaking force (MBF) and the reference number (RN) is given by the following formula:

$$RN = 2,349 \times MBF^{0,520} \text{ for unspliced 8-strand ropes}$$

$$RN = 2,265 \times MBF^{0,520} \text{ for unspliced 12-strand ropes}$$

7 Marking

Type 1 ropes (reference number less than 14) shall be marked using a blue thread. For other ropes, the marking shall be in accordance with ISO 9554.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™