

Textile glass — Yarns — Designation

ICS 59.100.10

National foreword

This British Standard is the UK implementation of EN ISO 2078:1994+A1:2015. It is identical to ISO 2078:1993, incorporating amendment 1:2015. It supersedes BS EN ISO 2078:1995 (dual numbered as BS 946-2:1995) which is withdrawn.

Attention is drawn to BS 946:1970, *Method for the designation of yarns*, which deals also with the designation of yarns in the Tex system.

The UK participation in its preparation was entrusted to Technical Committee PRI/42, Fibre reinforced thermosetting plastics and prepreps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 May 1995

© The British Standards Institution 2016
Published by BSI Standards Limited 2016

ISBN 978 0 580 87026 2

Amendments/corrigenda issued since publication

Date	Comments
31 January 2016	Implementation of ISO amendment 1:2015 with CEN endorsement A1:2015: Table 1 updated. All forewords updated and standard renumbered to match ISO identifier and CEN publication year.

ICS 59.100.10

English Version

Textile glass - Yarns - Designation - Amendment 1 (ISO
2078:1993/Amd 1:2015)

Verre textile - Fils - Désignation - Amendement 1 (ISO
2078:1993/Amd 1:2015)

Textilglas - Garne - Bezeichnung - Änderung 1 (ISO
2078:1993/Amd 1:2015)

This amendment A1 modifies the European Standard EN ISO 2078:1994; it was approved by CEN on 3 October 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This European Standard was taken over by the Technical Committee CEN/TC 249, Plastics, from the work of ISO/TC 61, Plastics, of the International Organization for Standardization (ISO).

CEN/TC 249 had decided to submit the final draft for formal vote. The result was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 1995, and conflicting national standards shall be withdrawn at the latest by April 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

Foreword to amendment A1

This document (EN ISO 2078:1994/A1:2015) has been prepared by Technical Committee ISO/TC 61 “Plastics” in collaboration with Technical Committee CEN/TC 249 “Plastics” the secretariat of which is held by NBN.

This Amendment to the European Standard EN ISO 2078:1994 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 2078:1993/Amd 1:2015 has been approved by CEN as EN ISO 2078:1994/A1:2015 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Definition	1
4 Designation of a yarn	1
Table 1	1

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2078 was prepared by Technical Committee ISO/TC 61, *Plastics*, Sub-Committee SC 13, *Composites and reinforcement fibres*.

This fifth edition cancels and replaces the fourth edition (ISO 2078:1985), of which subclauses 4.1.1 and 4.2.7 have been technically revised and clause 2 updated.

1 Scope

This International Standard specifies a system of designating textile glass yarns [including single, multiple-wound, folded (plied), cabled and textured yarns, strands, slivers and rovings] based on their linear density expressed in the tex system.

This International Standard applies the rules of the single-to-fold designation given in ISO 1139 to these textile glass products.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 2:1973, *Textiles — Designation of the direction of twist in yarns and related products*.

ISO 472:1988, *Plastics — Vocabulary*.

ISO 1139:1973, *Textiles — Designation of yarns*.

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 2 and ISO 472 apply.

4 Designation of a yarn

4.1 Elements of the designation

According to the definition given in ISO 1139, the designation of a yarn (single yarn, strand, sliver, ..., roving) is a condensed technical description containing the following elements.

4.1.1 Glass used

One or several letters, to specify the glass used by the manufacturer (see Table 1).

4.1.2 Type of yarn

A letter to describe the type of yarn:

- C (continuous) for continuous-filament yarns,
- D (discontinuous) for staple-fibre yarns.

NOTE 1 These letters are placed in the first group, as it is of special importance in the case of textile glass to distinguish between continuous-filament yarns and staple fibre yarns; their use makes it unnecessary to indicate the number of filaments, preceded by the symbol *f*, as proposed in ISO 1139.

Table 1

Type	General indications
E	Compositions with electrical properties, strength and durability appropriate for most application
D	Compositions with a low dielectric constant
A	High alkali content compositions typically with lower electrical resistivity, strength and durability than E-glass
C	Composition resistant to corrosion by most acids
S	Compositions in the system SiO ₂ -Al ₂ O ₃ -MgO with high tensile strength and high elastic modulus
R	Compositions in the system SiO ₂ -Al ₂ O ₃ -MgO-CaO with high elastic modulus
AR	Compositions resistant to corrosion by alkali
E-CR	E-glass compositions modified for improved resistant to corrosion by most acids

4.1.3 Nominal diameter of fibre

A number, consisting of one or two figures, giving the nominal diameter, in micrometres, of the filament or staple fibre.

4.1.4 Linear density, direction and amount of twist and number of components

Some, or all, of the following elements, as in ISO 1139:

- a) a number giving the linear density expressed in the tex system. It is strongly recommended that the tex be used as the basic unit, in which case the word “tex” can be omitted from the designation (if multiples or submultiples of the tex are used, these units shall be indicated after the value given for linear density);
- b) the direction(s) of twist;¹⁾
- c) the amount(s) of twist, expressed in turns per metre, for the twist of the final stage, and (if necessary) in the full designation, for the twist of each intermediate stage;
- d) the number of components in folding (plying) or cabling.

¹⁾ If the yarn has been subjected to a twisting operation, this shall be indicated by the direction of twist followed by the degree of twist. If the designation does not include any mention of twist, this shall always be taken to signify the absence of any twisting operation.

4.1.5 *Manufacturer's code*

If desired, the designation may also include the manufacturer's code, permitting the incorporation of any complementary information that does not appear among the previous elements, for example the type of size and the overall linear density. If it is included, the manufacturer's code shall be placed either before or after the designation as defined below and never between the elements of the designation [for example in the case of folded (plied) yarns having dissimilar components].

4.2 *Designation of different types of textile glass yarn*

Subclauses 4.2.1 to 4.2.8 give the elements that shall appear in the designation of various types of glass yarn.

4.2.1 *Strands*

- a) the type of glass used;
- b) the letter C for continuous-filament yarn;
- c) the nominal diameter, in micrometres, of the filaments, followed by a space;
- d) the linear density, preferably in tex [see 4.1.4 a)].

EXAMPLE EC10 40

4.2.2 *Slivers*

- a) the type of glass used;
- b) the letter D (discontinuous) for staple-fibre yarns;
- c) the nominal diameter, in micrometres, of the staple fibres, followed by a space;
- d) the linear density, preferably in tex [see 4.1.4 a)].

EXAMPLE ED7 190

4.2.3 *Single yarns*

4.2.3.1 *Single continuous-filament yarns*

- a) the type of glass used;
- b) the letter C for continuous-filament yarn;
- c) the nominal diameter, in micrometres, of the filaments, followed by a space;
- d) the linear density, preferably in tex [see 4.1.4 a)], followed by a space;
- e) the direction of twist, followed by a space;
- f) the amount of twist, expressed in turns per metre.

EXAMPLE EC9 34 Z 40

NOTE 2 When several strands are assembled in parallel and twisted together, only the overall linear density of all the strands before twisting is given.

For example, starting with four strands of EC9 34 and twisting these together, the designation of the resulting yarn is EC9 136 Z 40.

4.2.3.2 *Single staple-fibre yarns*

- a) the type of glass used;
- b) the letter D (discontinuous) for staple-fibre yarns;
- c) the nominal diameter, in micrometres, of the staple fibres, followed by a space;
- d) the linear density, preferably in tex [see 4.1.4 a)], followed by a space;
- e) the direction of twist, followed by a space;
- f) the amount of twist, expressed in turns per metre.

EXAMPLE ED7 190 Z 160

4.2.3.3 *Textured yarns*

- a) the type of glass used;
- b) the letter C or D for the designation of the original yarn (see 4.1.2);
- c) the nominal diameter, in micrometres, of the filaments, followed by a space;
- d) the linear density, preferably in tex [see 4.1.4 a)], before texturing, followed by a space;
- e) the linear density, preferably in tex [see 4.1.4 a)], after texturing, preceded by the letter T.

EXAMPLE EC9 340 T352

4.2.4 *Folded (plied) (doubled) yarns²⁾*

4.2.4.1 *Folded (plied) yarns having identical components*

- a) Full designation:
 - 1) the designation of the single continuous-filament or staple-fibre yarns used, in accordance with 4.2.3.1 or 4.2.3.2, followed by a space;
 - 2) a multiplication sign, ×, followed by a space;
 - 3) the number of single continuous-filament or staple-fibre yarns, followed by a space;
 - 4) the direction of the folding (plying) twist, followed by a space;
 - 5) the amount of folding (plying) twist, expressed in turns per metre.

EXAMPLES

EC9 34 Z 160 × 2 S 150

ED7 190 Z 160 × 2 S 260

²⁾ This term is defined in ISO 1139.

b) Simplified designation:

- 1) the designation of the single continuous-filament or staple-fibre yarns used, in accordance with 4.2.3.1 or 4.2.3.2, without indication of the direction or amount of twist [the twist of folded (plied) yarns is generally balanced], followed by a space;
- 2) a multiplication sign, ×, followed by a space;
- 3) the number of single continuous-filament or staple-fibre yarns, followed by a space;
- 4) the direction of the folding (plying) twist, followed by a space;
- 5) the amount of folding (plying) twist, expressed in turns per metre.

EXAMPLES

EC9 34 × 2 S 150

EC9 190 × 2 S 260

4.2.4.2 *Folded (plied) yarns having dissimilar components*

- a) the designations of the single continuous-filament yarns used, in accordance with 4.2.3.1, joined by a plus sign, +, preceded and followed by a space, the whole being placed in parentheses and followed by a space;
- b) the direction of the folding (plying) twist, followed by a space;
- c) the amount of folding (plying) twist, expressed in turns per metre.

EXAMPLE (EC9 34 Z 150 + EC7 22 Z 150) S 100

4.2.5 *Cabled yarns*

a) Full designation:

The designation of the yarn used, including the direction and the amount of twist for each stage, the information for each stage being separated by a multiplication sign, ×, preceded and followed by a space.

EXAMPLE EC9 34 Z 150 × 2 S 100 × 3 Z 80

b) Simplified designation:

The twist of cabled yarns is generally balanced, and in most cases it is not necessary to know the direction and the amount of twist of each of the intermediate stages; consequently, the simplified designation for a cabled yarn shall only show the direction and the amount of final twist.

The simplified designation shall therefore consist of the following elements:

- 1) the designation of the single continuous-filament yarns, in accordance with 4.2.3.1, omitting the direction and the amount of twist, followed by a space; for each intermediate stage:
- 2) a multiplication sign, ×, followed by a space;
- 3) the number of yarns involved, followed by a space; for the final stage:
- 4) a multiplication sign, ×, followed by a space;
- 5) the number of yarns involved, followed by a space;
- 6) the direction of twist, followed by a space;
- 7) the amount of twist, expressed in turns per metre.

EXAMPLE EC9 34 × 2 × 3 Z 80

4.2.6 *Multiple wound yarns*³⁾

4.2.6.1 *Multiple wound yarns having identical components*

- a) the designation of the yarn used, followed by a space;
- b) a multiplication sign, ×, followed by a space;
- c) the number of yarns which have been wound together.

EXAMPLE EC5 11 Z 90 × 10

4.2.6.2 *Multiple wound yarns having dissimilar components*

The designations of the yarns used, joined by a plus sign, +, preceded and followed by a space, the whole being placed in parentheses.

EXAMPLE (EC9 34 Z 40 + EC7 22 Z 40)

4.2.7 *Rovings*

- a) the type of glass used;
- b) the letter C for continuous-filament yarns;
- c) the nominal diameter, in micrometres, of the filaments, followed by a space;
- d) the overall linear density, preferably in tex [see 4.1.1 a)].

EXAMPLE EC10 2400

The overall linear density as given in the designation is equal either to the sum of the linear densities of the strands (in the case of assembled rovings) or the linear density of the single strand (in the case of direct rovings).

³⁾ This term is defined in ISO 1139.

For assembled rovings, in particular rovings which are to be chopped, the specification of the roving will indicate the type of strand.

4.2.8 Chopped strands

The designation shall consist of the following elements:

- a) the designation of the strand (see 4.2.1), followed by a space;

- b) a dash, followed by a space;

- c) the nominal length, in millimetres, of the chopped strands, followed by a space and the symbol mm.

EXAMPLE EC14 75 – 6 mm

NOTE 3 In the designation of the strand, the linear density given is that of the strands before the chopping process.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™