

# Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

The European Standard EN ISO 2177:1994 has the status of a  
British Standard

# Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Surface Coatings (other than Paints) Standards Committee (SRC/-) to Technical Committee SRC/14, upon which the following bodies were represented:

Aluminium Federation  
 Association of Manufacturers of Domestic Electrical Appliances  
 Association of Metal Sprayers  
 British Anodising Association  
 British Industrial Fasteners Federation  
 British Jewellers' Association  
 British Telecommunications plc  
 City of London Polytechnic  
 Department of Trade and Industry (National Physical Laboratory)  
 Institute of Metal Finishing  
 Institution of Corrosion Science and Technology  
 Metal Finishing Association  
 Ministry of Defence  
 NDT Trade Association  
 Society of Motor Manufacturers and Traders Limited

This British Standard, having been prepared under the direction of the Surface Coatings (other than Paints) Standards Committee, was published under the authority of the Board of BSI and comes into effect on 28 February 1986

© BSI 03-2000

First published April 1977  
 First revision February 1986

The following BSI references relate to the work on this standard:  
 Committee reference SRC/14  
 Draft for comment 80/55367 DC

ISBN 0 580 14913 7

## Amendments issued since publication

Amd. No.	Date of issue	Comments
8493	April 1995	Indicated by a sideline in the margin

---

# Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
Foreword	2
Text of EN ISO 2177	3
Publications referred to	Inside back cover

---

## National foreword

This revised Part of BS 5411 has been prepared under the direction of the Surface Coatings (other than Paints) Standards Committee. It is identical with the 1985 edition of ISO 2177 “*Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*” which was prepared, with the active participation and approval of the United Kingdom, by Subcommittee 2, Methods of inspection and co-ordination of test methods, of Technical Committee 107, Metallic and other non-organic coatings, of the International Organization for Standardization (ISO). This Part of BS 5411 supersedes BS 5411-4:1977 which is now withdrawn.

In 1994 the European Committee for Standardization (CEN) accepted ISO 2177:1985 as European Standard EN ISO 2177:1994. As a consequence of implementing the European Standard this British Standard is renumbered as BS EN ISO 2177 and any reference to BS 5411-4 should be read as a reference to BS EN ISO 2177.

The first edition of this Part of BS 5411 differed in a number of respects from the first edition of ISO 2177. In the second edition of ISO 2177, dated 1985, many of the technical differences have been removed and those that remain are considered acceptable by the committee concerned. Accordingly ISO 2177:1985 has been adopted for this edition of this Part of BS 5411.

This edition of BS 5411-4 differs from the previous edition in its editorial layout and also in the following principal respects.

- a) The scope has been extended to include coatings of autocatalytic nickel and tin-lead alloys, and substrates of nickel-cobalt-iron alloys, silver and non-metals.
- b) A new clause has been included listing those factors that may affect the accuracy of coating thickness measurements.
- c) The procedure has been extended to cover measurements of undercoat thickness and of coating thicknesses on cylindrical specimens.
- d) A clause has been included specifying information to be included in the test report.

**Terminology and conventions.** The text of the International Standard has been approved as suitable for publication as a British Standard without deviation. Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker.

Where the words “International Standard” appear, referring to this standard, they should be read as “Part of BS 5411”.

In British Standards it is current practice to use the symbol “L” for litre (and its submultiples) rather than “l”, and to use the spelling “sulphur”, etc., instead of “sulfur”, etc.

### Cross-reference

International Standard	Corresponding British Standard
ISO 2064:1980	BS 5411 <i>Methods of test for metallic and related coatings</i> Part 1:1980 <i>Definitions and conventions concerning the measurement of thickness</i> (Identical)

NOTE *Textual error.* In **B.0**, paragraph 3, line 3, “settings in” should be read as “settings if”.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

#### **Summary of pages**

This document comprises a front cover, an inside front cover, pages i to iv, the EN title page, pages 2 to 14, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.



ICS 25.220.40

Descriptors: Coatings, metal coatings, tests, determination, thickness, coulometric methods

English version

# Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

(ISO 2177:1985)

Revêtements métalliques — Mesurage de  
l'épaisseur — Méthode coulométrique par  
dissolution anodique  
(ISO 2177:1985)

Metallische Überzüge —  
Schichtdickenmessung — Coulometrisches  
Verfahren durch anodisches Ablösen  
(ISO 2177:1985)

This European Standard was approved by CEN on 1994-10-26. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

## Foreword

This European Standard was taken over by the Technical Committee CEN/TC 262, Protection of metallic materials against corrosion, from the work of ISO/TC 107, Metallic and other inorganic coatings, of the International Organization for Standardization (ISO).

CEN/TC 262 has decided to submit the final draft for formal vote. The result was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 1995, and conflicting national standards shall be withdrawn at the latest by April 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

NOTE Normative references to international publications are listed in Annex ZA (normative).

## Contents

	Page
Foreword	2
1 Scope and field of application	3
2 Reference	3
3 Definitions	3
4 Principle	3
5 Instrumentation	3
6 Electrolyte	3
7 Factors affecting the measuring accuracy	4
8 Procedure	5
9 Expression of results	6
10 Measurement uncertainty	6
11 Test report	7
Annex A Types of instrument	8
Annex B Typical electrolytes	9
Annex ZA (normative) Normative references to international publications with their relevant European publications	13
Table 1 — Typical combinations of coatings and substrates which can be tested by the coulometric method	4
Table 2 — Cell sizes for measurements on curved surfaces	8
Table 3 — Applicability of electrolytes	9



## 1 Scope and field of application

This International Standard specifies a coulometric method by anodic dissolution for measuring the thickness of metallic coatings.

Typical combinations of coatings and substrates that can be tested by this method are given in Table 1. Other combinations may be tested with electrolytes in current use (see Annex B), or new electrolytes may be developed for them, but, in both cases, it is necessary to verify the suitability of the complete system.

The method is also applicable to multi-layer systems, for example Cu/Ni/Cr (see also 8.6).

This method may be used to measure the thickness of coatings applied by various means, if due account is taken of special features, such as the presence of an alloy layer. In some cases, the presence and thickness of diffusion layers can also be measured. It can also be used to measure the thickness of coatings on cylindrical specimens and wires (see 8.8).

## 2 Reference

ISO 2064, *Metallic and other non-organic coatings — Definitions and conventions concerning the measurement of thickness.*

## 3 Definitions

For the purpose of this International Standard, the definitions of ISO 2064, and the following, apply.

### 3.1

#### measuring area

the area of the significant surface over which a single measurement is made

the measuring area for this method is the area enclosed by the sealing ring of the cell

## 4 Principle

Anodic dissolution of a well-defined area of the coating using a suitable electrolyte. Detection of the virtually complete dissolution of the coating by a rapid change in cell voltage. Calculation of the coating thickness from the quantity of electricity (in coulombs) used, which may in turn be calculated from

- a) the time interval between the start and the end of the test, if it is conducted at constant current density;
- b) the integrated quantity of electricity used in dissolving the coatings.

## 5 Instrumentation

5.1 Suitable instruments may be constructed from readily available components but proprietary instruments are usually used (see Annex A).

5.2 Proprietary direct reading instruments are available for use with electrolytes recommended by the manufacturer. Other instruments record the quantity of electricity, in coulombs, used in dissolving the coating from the measuring area (see clause 3), usually in arbitrary units, from which the thickness is calculated using factors or tables.

With direct reading instruments, the calculation of thickness from current density is made electronically.

5.3 The performance of the instrument shall be checked using specimens of known coating thickness. If the instrument readings agree to  $\pm 5\%$  of the known thicknesses of the specimens, the instrument may be used without further adjustment. Otherwise, the cause of the discrepancy shall be removed. Proprietary instruments shall always, however, be calibrated in accordance with the manufacturer's instructions.

Suitable specimens of known coating thickness shall consist of the same type of coating and substrate as the specimen to be measured, and they shall have an accuracy of 5 % or better. If measuring alloy coatings, the use of correct specimens is of particular importance.

## 6 Electrolyte

The electrolyte shall have a known, adequate shelf-life and shall be such that:

- a) there is no reaction with the coating metal in the absence of an impressed flow of current;
- b) the coating dissolves anodically at an efficiency as close to 100 % as possible;
- c) a detectable sharp change in electrode potential occurs as the coating is penetrated and an increasing area of substrate is exposed;
- d) the test area exposed in the test cell is completely wetted.

**Table 1 — Typical combinations of coatings and substrates which can be tested by the coulometric method**

Coating	Substrate (basis material)							
	Aluminium <sup>a</sup>	Copper and copper alloys	Nickel	Nickel-cobalt-iron alloys (such as Kovar)	Silver	Steel	Zinc	Non-metals
Cadmium	X	X	X	—	—	X	—	X
Chromium	X	X	X	—	—	X	—	X
Copper	X	Only on brass and copper-beryllium	X	—	—	X	X	X
Lead	X	X	X	X	X	X	—	X
Nickel	X	X	—	X	—	X	—	X
Nickel, autocatalytic <sup>b</sup>	X	X	X	X	—	X	—	X
Silver	X	X	X	—	—	X	—	X
Tin	X	X	X	—	—	X	—	X
Tin-lead alloys <sup>c</sup>	X	X	X	X	—	X	—	X
Zinc	X	X	X	—	—	X	—	X

<sup>a</sup> The detection of the change in the cell voltage may be difficult with some aluminium alloys.  
<sup>b</sup> The coulometric method can only be used if the phosphorus or boron contents of these coatings are within certain limits.  
<sup>c</sup> The method is sensitive to alloy composition.

The electrolyte shall be chosen in relation to the coating and substrate materials, the current density and electrolyte circulation within the test cell. Typical electrolytes that have been found satisfactory for use with one type of test apparatus for testing various electrodeposited coatings on specific substrates are described in Annex B.

For proprietary instruments, the electrolytes shall normally be chosen on the recommendations of the manufacturer.

## 7 Factors affecting the measuring accuracy

The following factors may affect the accuracy of coating thickness measurements.

### 7.1 Coating thickness

Generally, the accuracy is lower than optimum for coating thicknesses greater than 50 µm and less than 0,2 µm, unless special equipment is used.

With coatings thicker than 50 µm, there may be an appreciable amount of bevelling or undercutting as the anodic dissolution proceeds. The amount of bevelling is largely dependent on the method employed for stirring the electrolyte. Undercutting may be eliminated, or reduced, by increasing the rate of dissolution, i.e. by increasing the current density used in the test.

### 7.2 Current variation

For instruments using the constant current and time measuring technique, current variation will cause errors. For instruments using a current-time integrator, too large a change in current may change the anode current efficiency or interfere with the end-point causing an error.

### 7.3 Area variation

The accuracy of the thickness measurement will be no better than the accuracy to which the measuring area is known. Area variations due to gasket wear, gasket pressure, etc., may lead to measurement errors. Much greater accuracy can be obtained if the electrolytic cells are so designed that sealing rings consistently give well-defined measuring areas.<sup>1)</sup> In some cases it may be advantageous to measure the area after it has been depleted and compensate accordingly.

<sup>1)</sup> Error due to variations of the measuring area may, in some instances, be minimized by modifying the instrument calibration using coating thickness calibration standards. Such standards should create similar test conditions to those during actual tests, particularly if testing curved surfaces.

**7.4 Agitation** (if required)

Inadequate agitation can cause a false end-point.

**7.5 Alloy layer between coating and substrate**

The measurement of coating thickness by the coulometric method assumes implicitly that a sharply defined interface exists between the coating and the substrate. If an alloy layer exists between the coating and the substrate as, for example, in the case of coatings applied by hot dipping<sup>2)</sup>, the coulometric end-point may occur at some point within the alloy layer, thus giving a high value for the thickness of the unalloyed coatings.

**7.6 Purity of coatings**

Materials that co-deposit with a coating metal (including alloying metals) may change the effective electrochemical equivalent of the coating metal, the anode current efficiency, and the coating density.

**7.7 Condition of test surface**

Oil, grease, paint, corrosion products, polishing ingredients, conversion coatings, passivity of nickel coatings, etc., may interfere with the test.

**7.8 Density of coating material**

Because the coulometric method measures intrinsically mass per unit area, variations in density from the normal density of the coating metal will cause corresponding variations in linear thickness measurements. Normal variations of the composition of an alloy result in small, but significant changes in alloy density and its electrochemical equivalent.

**7.9 Cleanliness of the cell**

Deposition of metal may take place on the cathode in some electrolytes. This deposit can alter the cell voltages or block the cell aperture. It is, therefore, essential to keep the cathode clean.

**7.10 Cleanliness of electrical connections**

In the case of instruments other than the constant current type, if the electrical connections are not clean, the current/potential relationship will be disturbed and false end-points obtained.

**7.11 Calibration standards** (if used)

Measurements made using calibration standards are subject to the additional error of the standards. If the thickness of alloy coatings is being determined, it is usually necessary to use coating standards and to test them using the same procedure.

**7.12 Non-uniform dissolution**

If the rate of dissolution is not uniform over the measuring area, a premature end-point may be obtained, and yield low results. Hence, one should examine the surface after the test to verify that most of the coating has dissolved. On some substrates, however, a visible, but insignificant, portion of the coating may remain.

The presence of other material in the coating, the roughness of the coating surface and interface and the presence of porosity in the coating can cause fluctuation of the cell voltage. Such fluctuations can prematurely affect the end-point.

**8 Procedure****8.1 General**

If commercial equipment is used, follow the manufacturer's instructions with respect to the operating procedure for measurement, the electrolytes and, if necessary, calibration (see 5.3). Appropriate attention shall be given to the factors listed in clause 7.

**8.2 Pre-set voltage**

If using instruments that require a pre-set voltage, it should be noted that the actual value is dependent on the particular metallic coating, current density, electrolyte concentration and temperature, and circuit resistance, for example lead-out connections. For these reasons, it is considered advisable to first perform an evaluation test.

**8.3 Preparation of test surface**

If necessary, clean the test surface (see 7.7) with a suitable organic solvent. It may also be necessary to activate the test surface by mechanical or chemical means, but care should then be taken to avoid removal of metal.

**8.4 Cell application**

Press the electrolytic cell, fitted with its flexible sealing ring, on to the coating so that a known area is exposed to the test electrolyte. If the cell body is metallic, for example stainless steel, it normally forms the cell cathode, but, otherwise, insert a suitable cathode (incorporated in some instruments as part of the electrolyte agitation mechanism).

<sup>2)</sup> See the footnote to clause A.1.

### 8.5 Electrolysis

Introduce the appropriate electrolyte and make sure that no air bubbles occur on the measuring surface. If required, put the agitation mechanism into the cell. Make the electrical connections, and operate the agitator as appropriate. Continue electrolysis until dissolution of the coating is complete, as indicated by a sharp change in the anode potential or cell voltage, or by the operation of the automatic cut-out.

### 8.6 Undercoats

When one or more undercoats are to be measured, after measuring the top coating ensure that the top coat has first been completely removed from the whole of the measuring area. Remove the electrolyte from the cell with a suitable suction device, and thoroughly rinse out the cell with distilled or demineralized water.

Do not disturb the cell at any time during these operations. Abandon the test if the slightest displacement has occurred.

Reset the instrument controls for the next coating, introduce the appropriate electrolyte and continue the test as before.

### 8.7 Examination after test

After completion of the test(s), remove the electrolyte from the cell, rinse out with water, lift off the cell and examine the specimen to ensure that the removal of the coating is complete over the area enclosed by the seal (see 7.12).

### 8.8 Coatings on cylindrical specimens

If the surface area is too small to use the normal cell with a flexible gasket, replace it by an electrolyte container and an appropriate holding device, using an agitator if necessary. This device shall be adjustable and shall be pre-set to allow a known length of specimen to be immersed. For direct reading instruments, especially those with alternative cell sizes, calculate the length of specimen to be immersed so that the same known surface area is presented to the cathode as for a test cell.

In the majority of applications, the same electrolyte can be used but, in order to obtain the optimum instrument sensitivity and accuracy, the operating conditions may have to be modified, for example the cut-off voltage and deplating current.

NOTE An exact deplating area is necessary for accuracy and the main source of error is due to the meniscus and current field at the electrolyte surface.

## 9 Expression of results

The coating thickness,  $d$ , in micrometres, is given by the equation

$$d = 100k \frac{QE}{AQ}$$

where

$k$  is the current efficiency of the dissolution process (equal to 100 in the case of 100 % efficiency);

$E$  is the electrochemical equivalent, in grams per coulomb, of the coating metal for the conditions of the test;

$A$  is the area, in square centimetres, from which the coating is dissolved, i.e. the measuring area;

$\rho$  is the density, in grams per cubic centimetre, of the coating;

$Q$  is the quantity of electricity, in coulombs, passed in dissolving the coating; if an integrating meter is not used, calculate  $Q$  from the equation

$$Q = It$$

where

$I$  is the current, in amperes,

$t$  is the test duration, in seconds.

The thickness may also be expressed as:

$$XQ$$

where  $X$  is a constant for a given metal coating, electrolyte and cell. The value of  $X$  can either be calculated theoretically from the area of the test specimen exposed by the sealing ring, the efficiency of anodic dissolution (usually 100 %) and the electrochemical equivalent and density of the coating metal, or can be determined experimentally by measuring a coating of known thickness.

With most commercial instruments, the thickness is either read directly from the instrument or the instrument reading is converted to thickness by applying a factor appropriate to the measuring area exposed by the cell and the coating metal.

## 10 Measurement uncertainty

The test equipment and the procedure shall be such that the coating thickness can be measured to within 10 % of its true thickness.

## 11 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) an identification of the test specimen;
- c) the area, in square centimetres, over which the measurements were made;
- d) the location of the reference area;
- e) the location(s) on the coated item at which the tests were carried out;
- f) the identity of the electrolyte used;
- g) the measured thickness in micrometres at each area at which the tests were carried out; the number of measurements averaged for each reported measurement;
- h) the name of the operator and testing laboratory;
- j) the date;
- k) any deviation from the method specified;
- m) any factor that may have influenced the result;
- n) an identification of the instrument used.

## Annex A Types of instrument

(This annex is for information only and does not form part of this International Standard.)

### A.1 General

The instrument may operate on either of two principles:

- a) measurement of the time of anodic dissolution at constant cell current;
- b) measurement of the quantity of electricity consumed during the test by current-time integration.

With the former, the current passed through the test cell has to be controlled at a constant value, a timer then being used to measure the time interval between the start and the end-point of the test. With the latter, an integrating meter is used to measure the quantity of electricity passed, in which case accurate knowledge of the magnitude of the current and separate measurement of the time interval are unnecessary.

The results may be displayed as single time units, as the product of current and time (quantity of electricity) units or, more frequently with recent designs of apparatus, directly as thicknesses.

The end-point can be determined by observing the marked change in cell voltage on a suitable voltmeter, or a cut-out can be used to terminate the test automatically. In the latter case, the cut-out is set to operate at a predetermined value<sup>3)</sup> of either the cell voltage or the rate of increase of cell voltage.

Other non-mandatory, but advantageous, features of coulometric instruments may include digital results display, electronic timing and switching for greater accuracy of end-point determination, and the capability to accept different test cell sizes or use different current densities. The test cell sealing ring should be capable of being interchanged rapidly.

Many modern instruments display results as direct thickness measurements and may incorporate initial automatic setting of the cut-out at the start of each test to terminate the test at the correct end-point.

### A.2 Electrolytic cell

The electrolytic cell consists of a container, usually cylindrical, applied to the article under test through an intermediate non-conductive and elastic seal made, for example, of rubber or plastics material. The cell itself, if it is made of metal, for example stainless steel, can serve as the cathode, in which case the seal will also serve as insulation between the cathode and anode.

If the cell is of insulating material, a separate cathode is used and immersed in the electrolyte before starting the test.

The area of surface enclosed by the seal has to be well defined and small enough to permit its application to a curved surface. Smaller cells may be required for measuring the thickness of coatings on intricately shaped substrates, but these pose problems connected with the definition and measurement of the area of the seal. With any cell, the accuracy of the method is largely controlled by the accuracy of measurement of the area over which the thickness measurement is made. Inaccuracies can occur if the seal defining the test area is applied on a curved surface. A further inaccuracy can also arise from the wear or distortion of the end of seal. This can be assessed visually by examination of the periphery of the circle of stripped coating.

For substantially flat surfaces, a typical deplated area is 0,2 cm<sup>2</sup>, but curved surfaces can be measured with cells of the sizes indicated in Table 2, depending on the diameters of the deplated areas.

**Table 2 — Cell sizes for measurements on curved surfaces**

Diameter of deplated area	Deplated area	Minimum diameter of curved surfaces
cm	cm <sup>2</sup>	cm
0,32	0,080	3,0
0,22	0,038	1,0
0,15	0,018	0,4

<sup>3)</sup> In the case of hot-dipped coatings, or other coatings where a diffusion layer may have developed between the coatings and the basis metal, this predetermined value may be either that at which the main coating has been removed to expose the diffusion layer or that at which the diffusion layer has been removed to expose completely the basis metal.

## Annex B Typical electrolytes

(This annex is for information only and does not form part of this International Standard.)

### B.0 Introduction

Although it is possible to use higher current densities with some proprietary electrolytes (and possibly with some of the electrolytes listed in this annex), the following electrolytes (**B.1** to **B.16**) were formulated to give substantially 100 % anodic efficiency with current densities ranging from 100 to 400 mA/cm<sup>2</sup>. However, a few electrolytes were found only to be suitable when used towards the lower or upper ends of this current density range and these electrolytes are marked with an asterisk.

These electrolytes dissolve the metallic coatings at substantially 100 % anodic efficiency. Therefore, the thickness, in micrometres, can be calculated with satisfactory accuracy from the expression

$$10\,000 \frac{QE}{A\rho}$$

or from instrument factors calculated from this expression. (See clause 9 for definitions of the symbols.) There is no need to use coating standards when using these electrolytes. Direct calculation from the above expression will normally give more accurate results than those based on calibration of coulometric instruments with coating standards.<sup>4)</sup>

The solutions given in **B.1** to **B.4** should preferably be made up from reagents of recognized analytical grade and using distilled or demineralized water. Small variations in concentration of the solutions will not affect the accuracy of the results, but may affect the voltage settings in an automatic cut-out mechanism, based on a pre-set voltage, is employed. All the electrolytes, except **B.9**, have shelf-lives in excess of 6 months.

The instrument manufacturer's advice or instructions shall be followed regarding whether any of these electrolytes may be used with their instruments or whether it is necessary to use proprietary electrolytes for any particular coating/substrate combination. A summary of the applicability of the electrolytes described in clauses **B.1** to **B.16** is given in Table 3.

### B.1 Electrolyte for cadmium coatings on steel, copper or brass

Prepare a solution containing 30 g of potassium chloride (KCl) and 30 g of ammonium chloride (NH<sub>4</sub>Cl) per litre.

This electrolyte requires a critical pre-set voltage.

Table 3 — Applicability of electrolytes

Coating	Substrate (basis material)					
	Aluminium	Copper and copper alloys (such as brass)	Nickel	Steel	Zinc	Non-metals
Cadmium	—	<b>B.1</b>	—	<b>B.1</b>	—	<b>B.1</b>
Chromium	<b>B.2</b> and <b>B.4</b>	<b>B.3</b>	<b>B.2</b> and <b>B.4</b>	<b>B.2</b>	—	<b>B.2</b> and <b>B.4</b>
Copper	<b>B.5</b> and <b>B.6</b>	—	<b>B.6</b>	<b>B.5</b>	<b>B.7</b>	<b>B.5</b> , <b>B.6</b> and <b>B.7</b>
Lead	—	<b>B.8</b>	<b>B.8</b>	<b>B.8</b>	—	<b>B.8</b>
Nickel	<b>B.9</b>	<b>B.10</b>	—	<b>B.9</b>	—	<b>B.9</b> and <b>B.10</b>
Silver	—	<b>B.11</b>	<b>B.11</b>	—	—	<b>B.11</b>
Tin	<b>B.13</b>	<b>B.12</b>	<b>B.12</b>	<b>B.12</b>	—	<b>B.12</b> and <b>B.13</b>
Tin-nickel alloys	—	<b>B.16</b>	—	<b>B.15</b>	—	<b>B.15</b> and <b>B.16</b>
Zinc	—	<b>B.14</b>	—	<b>B.14</b>	—	<b>B.14</b>

<sup>4)</sup> Both direct calculation and use of calibration standards have inherent errors which have to be considered, for example an error in the diameter of the test cell of 3 % will give a 9 % error in measurement.

**B.2 Electrolyte for chromium coatings on steel, nickel or aluminium\***

Dilute 95 ml of orthophosphoric acid ( $\text{H}_3\text{PO}_4$ ) solution,  $\rho = 1,75$  g/ml, to 1 000 ml with water and add 25 g of chromium(VI) oxide ( $\text{CrO}_3$ ).

**WARNING — Orthophosphoric acid causes burns: avoid contact with eyes and skin.**

**Chromium(VI) oxide may cause fire on contact with combustible material and causes severe burns: avoid inhaling dust and prevent contact with eyes and skin.**

This solution is only suitable for use at a current density of about 100 mA/cm<sup>2</sup> and for coatings up to 5 µm thick, when the accuracy of measurement is probably  $\pm 10$  %.

NOTE Anodic dissolution of chromium in this electrolyte — and in electrolytes **B.3** and **B.4** — produces hexavalent chromium ions Cr(VI) and the electrochemical equivalent for Cr(VI) shall be used when calculating the thickness.

**B.3 Electrolyte for chromium coatings on copper or brass\***

Prepare a solution containing 100 g of sodium carbonate ( $\text{Na}_2\text{CO}_3$ ) per litre.

This electrolyte is only suitable for use at a current density of about 100 mA/cm<sup>2</sup>, and for coatings up to 5 µm thick.

**B.4 Electrolyte for chromium coatings on nickel or aluminium\***

Dilute 64 ml of orthophosphoric acid ( $\text{H}_3\text{PO}_4$ ) solution,  $\rho = 1,75$  g/ml, to 1 000 ml with water.

**WARNING — See clause B.2.**

This electrolyte is best used at a current density at about 100 mA/cm<sup>2</sup> and is, therefore, particularly useful on thin or decorative chromium coatings. (See also the note to clause **B.2**.)

**B.5 Electrolyte for copper coatings on steel or aluminium**

Dissolve 800 g of ammonium nitrate ( $\text{NH}_4\text{NO}_3$ ) in water, dilute to 1 000 ml and add 10 ml of ammonia solution ( $\text{NH}_3$ ),  $\rho = 0,88$  g/ml.

**WARNING — Ammonium nitrate may cause fire on contact with combustible material. Keep out of contact with all combustible material.**

**Ammonia causes burns and is irritating to eyes, respiratory system and skin: avoid breathing vapour and prevent contact with eyes and skin.**

This electrolyte gives thickness results that are about 1 to 2 % lower than the correct value.

**B.6 Electrolyte for copper coatings on nickel or aluminium**

Dissolve 100 g of potassium sulfate ( $\text{K}_2\text{SO}_4$ ) in water, dilute to 1 000 ml and then add 20 ml of orthophosphoric acid ( $\text{H}_3\text{PO}_4$ ) solution,  $\rho = 1,75$  g/ml.

**WARNING — See clause B.2.**

**B.7 Electrolyte for copper coatings on zinc or zinc die-cast alloys**

Use pure hexafluorosilicic acid ( $\text{H}_2\text{SiF}_6$ ), of concentration not lower than approximately 30 % (*m/m*).

**WARNING — Hexafluorosilicic acid causes burns and is toxic by inhalation, in contact with skin and if swallowed: avoid inhaling vapour and prevent contact with eyes and skin.**

This solution dissolves copper coatings with 100 % efficiency at quite low voltages, with practically no anodic attack on the zinc substrate exposed at the end of the test. There is, however, a tendency to leave slight traces of copper, as spots, on the zinc, in the test area but, although noticeable, they are normally too small to affect significantly the accuracy of the results.

It is important to note that:

- a pure grade of hexafluorosilicic acid is required, substantially free from impurities such as chlorides and sulfates which would allow anodic attack on the zinc substrate when it is exposed at the end of the test;
- the acid should not have too high a water content, which would lead to an effect similar to that described in a). If the water content of the available acid is too great, its deleterious effect can sometimes be overcome by dissolving a little magnesium hexafluorosilicate in the acid.

**B.8 Electrolyte for lead coatings on steel, copper or nickel (with or without tin undercoats)**

Prepare a solution containing 200 g of sodium acetate ( $\text{CH}_3\text{COONa}$ ) and 200 g of ammonium acetate ( $\text{CH}_3\text{COONH}_4$ ) per litre.

This electrolyte tends to give slightly lower than 100 % efficiency, but will probably give results that are not more than about 5 % higher than the correct value.

**B.9 Electrolyte for nickel coatings on steel or aluminium**

Dissolve 800 g of ammonium nitrate ( $\text{NH}_4\text{NO}_3$ ) (see the warning to clause **B.5**) in water, dilute to 1 000 ml and add 50 ml of a 76 g/l thiourea [ $\text{CS}(\text{NH}_2)_2$ ] solution.



This mixed solution has rather a short shelf-life and should thus be made up not more than 5 days before use, preferably from stock solutions of 800 g/l ammonium nitrate solution and 76 g/l thiourea solution, which have shelf-lives of at least 6 months.

**NOTE** The efficiency of this electrolyte is reduced by passivity of nickel coatings: it will not dissolve nickel with 100 % efficiency if its surface is passive. Nickel surfaces can also become passive by the anodic action of phosphoric acid electrolyte used to remove chromium top coats before measuring the thickness of the nickel coating.

The cell voltage during the test can serve as a guide to this behaviour. If testing at about 400 mA/cm<sup>2</sup>, the cell voltage for dissolving nickel with 100 % efficiency is normally less than 2,4 V, while a cell voltage of 2,5 V or more usually indicates either that the nickel is dissolving at much less than 100 % efficiency, usually accompanied by electropolishing of the nickel, or that oxygen is being evolved without any dissolution of the nickel.

If necessary, the nickel can be activated before the test by introducing a little dilute hydrochloric acid [ $1 \text{ mol/l} \leq c(\text{HCl}) \leq 2 \text{ mol/l}$ ]<sup>5)</sup> solution into the cell, removing it after about 0,5 to 1 min and rinsing well before introducing the ammonium nitrate/thiourea electrolyte to test for nickel thickness.

#### **B.10 Electrolyte for nickel coatings on copper, brass or other copper alloys or on stainless steel\***

Dilute 100 ml of hydrochloric acid (HCl),  $\rho = 1,18 \text{ g/ml}$ , to 1 000 ml with water.

**WARNING — Hydrochloric acid causes burns and is irritating to the respiratory system: avoid breathing the vapour and prevent contact with eyes and skin.**

This electrolyte is only satisfactory for nickel coatings on copper or copper alloys when used at current densities of about 400 mA/cm<sup>2</sup>, but not when used at about 100 mA/cm<sup>2</sup>.

**NOTE** Electrolytes **B.9** and **B.10** are also suitable for testing the thickness of cobalt, cobalt-nickel or nickel-iron alloy coatings. The electrochemical equivalents of cobalt and iron are very close to that of nickel, thus no significant error occurs when the thicknesses of alloys of these metals are calculated as though they were nickel alone.

#### **B.11 Electrolyte for silver coatings on copper, copper alloys or nickel**

Prepare a 100 g/l potassium fluoride (KF) solution.

**WARNING — Potassium fluoride is toxic by inhalation, in contact with skin and if swallowed: avoid inhalation of dust and prevent contact with eyes and skin.**

This electrolyte is satisfactory for dull silver coatings or bright silver coatings incorporating sulfur-containing brighteners, but is not as satisfactory for bright silver alloy coatings containing small percentages of antimony or bismuth.

**NOTE** When testing silver coatings with electrolyte **B.11**, there is a tendency for the silver to be deposited as metal on the inside of stainless steel cells. The deposit is, however, in the form of a uniform coating, that does not block the aperture, but it can lower the cell voltage needed for dissolution of the silver coatings. It is, therefore, desirable to dissolve away the silver deposit from stainless steel cell bodies with nitric acid after each determination.

#### **B.12 Electrolyte for tin coatings on steel, copper alloys or nickel**

Dilute 170 ml of hydrochloric acid (HCl),  $\rho = 1,18 \text{ g/ml}$ , to 1 000 ml with water.

**WARNING — See clause B.10.**

This solution dissolves tin coatings at very low cell voltages at which there is no anodic attack on the substrates when they are exposed at the end of the test. There is, however, a tendency for the tin to be deposited out of this solution during the test as a spongy deposit on the cathode, for example on a stainless steel cell body, and this deposit can block the cell aperture after a while and thus prematurely stop the test when testing very thick tin coatings or a number of thinner ones. The aperture of the cell should therefore be cleaned of these growths at fairly frequent intervals.

**NOTE** The electrolyte is believed to have 100 % efficiency.

#### **B.13 Electrolyte for tin coatings on aluminium\***

Dilute 50 ml of sulfuric acid (H<sub>2</sub>SO<sub>4</sub>),  $\rho = 1,84 \text{ g/ml}$ , with water to 1 000 ml by carefully adding the acid, in small portions, to the water, and dissolve 5 g of potassium fluoride (KF) in this solution.

**WARNING — See clause B.11. (Sulfuric acid causes severe burns: prevent contact with skin and eyes and do not add water to sulfuric acid.)**

#### **B.14 Electrolyte for zinc coatings on steel, copper or brass**

Prepare a 100 g/l potassium chloride (KCl) solution.

This electrolyte requires a fairly critical pre-set voltage, but not quite as critical as that for testing cadmium coatings (clause **B.1**).

#### **B.15 Electrolyte for tin-nickel alloys on steel\***

Mix 100 ml of orthophosphoric acid (H<sub>3</sub>PO<sub>4</sub>) solution,  $\rho = 1,75 \text{ g/ml}$ , with 50 ml of hydrochloric acid (HCl),  $\rho = 1,18 \text{ g/ml}$ , and 50 ml of a solution of oxalic acid dihydrate (C<sub>2</sub>H<sub>2</sub>O<sub>4</sub> · 2H<sub>2</sub>O), saturated at room temperature.

**WARNING — See clauses B.2 and B.10. (Oxalic acid is harmful in contact with skin and if swallowed: avoid contact with eyes and skin.)**

<sup>5)</sup> Hitherto expressed as "1 N to 2 N".

This electrolyte was formulated for use at a current density of about 100 mA/cm<sup>2</sup> and at this current density the tin in the alloy was found to dissolve as tin(II) ions. The correct electrochemical equivalent for a 65/35 tin-nickel alloy, with tin in the divalent form, i.e. 0,505 mg/C, should be used for calculating the thickness. For greater accuracy the factor should be adjusted for the actual composition of the alloy (see 7.8).

**B.16 Electrolyte for tin-nickel alloys on copper or brass\***

Prepare a solution containing 12 g of nickel chloride hexahydrate (NiCl<sub>2</sub>·6H<sub>2</sub>O), 13 g of anhydrous tin(IV) chloride (SnCl<sub>4</sub>), 200 ml of water, 40 ml of hydrochloric acid (HCl),  $\rho = 1,18$  g/ml, and 50 ml of orthophosphoric acid (H<sub>3</sub>PO<sub>4</sub>) solution,  $\rho = 1,75$  g/ml.

**WARNING** — See clauses B.2 and B.10. (Nickel chloride has a harmful dust and is irritating to skin and eyes: avoid breathing dust and avoid contact with eyes and skin.)

**Tin(IV) chloride causes burns and is irritating to the respiratory system: avoid contact with eyes and skin and do not allow to come into contact with water inadvertently.**

This electrolyte was formulated for use at a current density of about 400 mA/cm<sup>2</sup> and at this current density the tin in the alloy was found to dissolve as tin(IV) ions. The correct electrochemical equivalent for a 65/35 tin-nickel alloy, with tin in the quadrivalent form, i.e. 0,305 mg/C, should be used for calculating the thickness. For greater accuracy the factor should be adjusted for the actual composition of the alloy (see 7.8).

**Annex ZA (normative)****Normative references to international publications with their relevant European publications**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

Publication	Year	Title	EN/HD	Year
ISO 2064		<i>Metallic and other non-organic coatings — Definitions and conventions concerning the measurement of thickness</i>	EN ISO 2064	



## Publications referred to

See national foreword.

---

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.