

BS EN ISO 2376:2010



BSI Standards Publication

Anodizing of aluminium and its alloys — Determination of electric breakdown potential (ISO 2376:2010)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 2376:2010. It supersedes BS EN 12373-17:2001 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/32, Anodic oxidation coatings on aluminium.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 66004 7

ICS 25.220.20; 77.120.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2010.

Amendments issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

English Version

Anodizing of aluminium and its alloys - Determination of electric breakdown potential (ISO 2376:2010)

Anodisation de l'aluminium et de ses alliages -
Détermination de la tension électrique de claquage (ISO
2376:2010)

Anodisieren von Aluminium und Aluminiumlegierungen -
Bestimmung der elektrischen Durchschlagspannung (ISO
2376:2010)

This European Standard was approved by CEN on 14 July 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2376 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 2, *Organic and anodic oxidation coatings on aluminium*.

This second edition cancels and replaces the first edition (ISO 2376:1972), which has been technically revised.

Anodizing of aluminium and its alloys — Determination of electric breakdown potential

1 Scope

This International Standard specifies test methods for the determination of the electric breakdown potential of anodic oxidation coatings on aluminium and its alloys, on flat or near-flat surfaces and on round wire. The methods are applicable to anodic oxidation coatings used primarily as electrical insulators.

The methods are not applicable to coatings in the vicinity of cut edges, the edges of holes, or sharp changes of angle on, for example, extruded shapes.

NOTE 1 The methods described do not give satisfactory results for unsealed coatings.

NOTE 2 Electric breakdown potential is affected by relative humidity.

2 Principle

The electric voltage at which current first passes through an anodic oxidation coating is measured; this breakdown potential is a function of the dielectric characteristics and the insulation properties of the oxidation coatings. The breakdown potential depends upon the thickness of the coating, as well as on many other factors, particularly the composition of the basis metal, its surface condition, the effectiveness of sealing, the dryness of the sample and the degree of ageing.

3 Apparatus

3.1 Power supply, from a suitable 50 Hz or 60 Hz source.

3.2 Transformer (a.c.), having an output with a waveform as nearly sinusoidal as possible, capable of producing the potential required.

3.3 Voltage regulator, enabling the test potential to be increased gradually from any point without interruption, and providing an essentially undistorted waveform so that the peak potential is within the limit $\sqrt{2} \pm 5\%$ (i.e. 1,34 to 1,48) of the root-mean-square (r.m.s.) potential.

3.4 Current limiting resistor, 0,5 M Ω , in series with secondary winding of the transformer and the test electrode probe (3.6).

3.5 Potential-measuring device, which gives r.m.s. values, expressed in volts.

3.6 Electrode probe, made from conducting material, suitably insulated for handling purposes, free to move as required and adequately supported. The contact surface shall be spherical with a diameter of 3 mm to 8 mm and shall be maintained in a smooth, untarnished condition. The design of the probe shall be such that, when the spherical surface is placed on the surface of the anodized test specimen, the total force exerted on the coating is 0,5 N to 1,0 N (a probe of mass 50 g to 100 g is suitable).

3.7 Contact plate, for testing flat test specimens, having a smooth, bright, metallic surface, or a **contact probe** or **clip** which is capable of breaking through to the basis metal (see 4.2.1).

3.8 Twisting machine, for testing round wire, having two sets of jaws 400 mm apart, with one set of jaws fixed, while the other set is free to rotate. The jaws shall be mounted so as to prevent lateral movement of the jaws when the twisting operation is carried out (see 4.2.2).

4 Procedure

4.1 Test specimen

The test specimen shall normally consist of a production component (or a part thereof). It shall be sealed, dry and clean and, if required, shaped to correspond to its ultimate use in service.

Unsealed items may be tested but only under conditions of known, recorded and controlled relative humidity.

NOTE The use of specially prepared test specimens, processed at the same time and in the same manner as production articles, can lead to erroneous results.

4.2 Determination

4.2.1 Flat or near-flat surfaces

Unless otherwise specified, carry out the determination at room temperature. Measure and record the relative humidity of the environment in which the test is taking place. Place the test specimen on the contact plate (3.7) in good electrical contact with it, for example by using an earthing clip. Alternatively, make contact to the basis metal using the contact probe or clip.

Connect the contact plate or contact probe or clip (3.7) and the electrode probe (3.6) to opposite poles of the secondary winding of the transformer (3.2), and place the probe on the test specimen so that the force exerted on the coating is 0,5 N to 1,0 N (see 3.6).

Starting at zero, increase the potential uniformly at a rate not exceeding 25 V/s until the specified potential is reached or the potential drops suddenly (indicating electric breakdown of the coating). It is necessary to clean the contact surface of the probe after any breakdown has occurred, and it is essential to return the potential to zero after each determination and particularly before cleaning the probe.

Carry out a minimum of five tests and record the lowest value and the mean value obtained. Alternatively, ascertain whether or not any value falls below a predetermined electric breakdown potential.

4.2.2 Round wire

Unless otherwise specified, carry out the determination at room temperature. Measure and record the relative humidity of the environment in which the test is taking place.

Twist together two suitable lengths of wire using the twisting machine (3.8) so that the number of twists per 50 mm specified in Table 1 is achieved.

Ensure that the two lengths of wire are of equal length between the jaws, are under equal tension and are touching in the jaws.

Remove the wires from the twisting machine, separate the wires for about 50 mm at each end, and remove the anodic coating from one pair of ends. Join the opposite poles of the secondary winding of the transformer to these exposed ends.

Table 1 — Number of twists for round wire test specimens

| Diameter of wire, d mm | Number of twists per 50 mm |
|-----------------------------|----------------------------|
| $0,2 \leq d \leq 0,3$ | 5 |
| $0,3 < d \leq 0,5$ | 4 |
| $0,5 < d \leq 0,75$ | 3 |
| $0,75 < d \leq 1,25$ | 2 |
| $1,25 < d \leq 3,25$ | 1 |
| $3,25 < d \leq 6,5$ | 0,5 |

Starting at zero, increase the potential uniformly at a rate not exceeding 25 V/s until the specified potential is reached or the potential drops suddenly (indicating electric breakdown of the coating). It is essential to return the potential to zero after each determination, and to maintain the contacts between the transformer and test specimen.

Carry out a minimum of five tests and record the lowest value and the mean value obtained. Alternatively ascertain whether or not any value falls below a predetermined electric breakdown potential.

5 Expression of results

Express the electric breakdown potential, in volts, as the lowest value recorded and the mean value.

6 Test report

The test report shall include at least the following information:

- a) a reference to this International Standard;
- b) the type and identification of the product tested;
- c) the anodizing specification, when applicable;
- d) the electric breakdown potential (see Clause 5) and, where appropriate, a statement as to whether the electric breakdown potential conformed to that specified for the product;

NOTE The minimum acceptable breakdown potential will normally be specified in the relevant product specification.

- e) the relative humidity of the environment at the time of the test;
- f) any other relevant information on the tests or the results, including the test temperature, if it is different from room temperature;
- g) the date of the test.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™