

Flexible and rigid cellular polymeric materials — Accelerated ageing tests

ICS 83.100

National foreword

This British Standard is the UK implementation of EN ISO 2440:1999+A2:2014. It is identical to ISO 2440:1997, incorporating amendment 1:2010 and amendment 2:2014. It supersedes BS EN ISO 2440:1999+A1:2010 which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to ISO text carry the number of the ISO amendment. For example, text altered by ISO amendment 1 is indicated by \square_{A1} \square_{A1} .

The UK participation in its preparation was entrusted to Technical Committee PRI/24, Testing of rigid and flexible cellular materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 November 2000

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 84006 7

Amendments/corrigenda issued since publication

Date	Comments
30 April 2010	Implementation of ISO amendment 1:2010 with CEN endorsement A1:2010; alignment of BSI and CEN publication dates
30 November 2014	Implementation of ISO amendment 2:2014 with CEN endorsement A2:2014

ICS 83.100

English version

Flexible and rigid cellular polymeric materials - Accelerated
ageing tests (ISO 2440:1997)

Matériaux polymères alvéolaires souples et rigides - Essais
de vieillissement accéléré (ISO 2440:1997)

Weich- und Hartschaumstoffe - Schnellalterungsprüfung
(ISO 2440:1997)

This European Standard was approved by CEN on 21 June 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard from Technical Committee ISO/TC 45 "Rubber and rubber products" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2000, and conflicting national standards shall be withdrawn at the latest by May 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 2440:1997 has been approved by CEN as a European Standard without any modification.

Foreword to amendment A1

This document (EN ISO 2440:1999/A1:2010) has been prepared by Technical Committee ISO/TC 45 "Rubber and rubber products" in collaboration with Technical Committee CEN/TC 249 Plastics the secretariat of which is held by NBN.

This Amendment to the European Standard EN ISO 2440:1999 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2010, and conflicting national standards shall be withdrawn at the latest by August 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 2440:1997/Amd 1:2010 has been approved by CEN as a EN ISO 2440:1999/A1:2010 without any modification.

Foreword to amendment A2

This document (EN ISO 2440:1999/A2:2014) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This Amendment to the European Standard EN ISO 2440:1999 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2015, and conflicting national standards shall be withdrawn at the latest by April 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 2440:1997/Amd 2:2014 has been approved by CEN as EN ISO 2440:1999/A2:2014 without any modification.

Flexible and rigid cellular polymeric materials – Accelerated ageing tests

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies, for flexible and rigid cellular polymeric materials, laboratory procedures which are intended to imitate the effects of naturally occurring reactions such as oxidation or hydrolysis by humidity. The physical properties of interest are measured before and after the application of the specified treatments.

Test conditions are only given for open cellular latex, both open- and closed-cell polyurethane foams, and closed-cell polyolefin foams. Conditions for other materials will be added as required.

The effect of the ageing procedures on any of the physical properties of the material may be examined, but those normally tested are either the elongation and tensile properties, or the compression or indentation hardness properties.

These tests do not necessarily correlate either with service behaviour or with ageing by exposure to light.

A₂ If desired, the ageing conditions contained in this International Standard can be applied to composite structures containing any of the above types of cellular material. This can be helpful in the investigation of possible interactions between cellular materials and other substrates. Composite constructions can be in the form of complete finished products or representative small specimens cut there-from. **A₂**

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

A₁ ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*. **A₁**

3 Apparatus

3.1 For heat ageing

A₁ **3.1.1 Oven**, with forced circulation, capable of maintaining the required temperature to within ± 3 °C. **A₁**

NOTE — It is recommended that a device be used to record the temperature, preferably continuously.

3.2 For humidity ageing

3.2.1 Ageing apparatus, of such a size that the total volume of the test pieces does not exceed 10 % of the free air space, and such that the test pieces are free of strain, freely exposed to the ageing atmosphere on all sides and not exposed to light.

A1 3.2.2 **Steam autoclave** or similar vessel, capable of maintaining the required temperature to within ± 3 °C and of withstanding absolute pressures up to 300 kPa. **A1**

A1 3.2.3 **Glass vessel**, with a suitable closure, and a **water-bath** or **drying oven** for heating the vessel, capable of maintaining the required temperature to within ± 3 °C. **A1**

3.3 For physical-property measurements

Use apparatus appropriate to the measurements of the physical property to be examined.

4 Test pieces

4.1 Number, size and shape

The number of test pieces, and their size and shape, shall be appropriate to the property being examined. They shall be prepared, before ageing, to the dimensions used in the particular test.

4.2 Conditioning

Material shall not be tested less than 72 h after manufacture, unless at either 16 h or 48 h after manufacture it can be demonstrated that the mean result does not differ by more than ± 10 % from those obtained after 72 h. Testing is permitted at either 16 h or 48 h if, at the specified time, the above criterion has been satisfied.

A1 Prior to the test, the test pieces shall be conditioned, undeflected and undistorted, for at least 16 h in one of the following atmospheres as given in ISO 23529. **A1**

23 °C \pm 2 °C, (50 \pm 5) % relative humidity;

27 °C \pm 2 °C, (65 \pm 5) % relative humidity.

This period can form the latter part of the period following manufacture.

NOTE — It is recommended that for reference purposes the test be performed 7 days or more after the cellular material has been manufactured.

5 Procedure

5.1 General

After conditioning, the test of the required physical property shall be performed and the test pieces shall be brought rapidly to the ageing condition. If the test to be performed is destructive, for example the examination of tensile properties, it is recommended that the tests on both reference and aged material be performed at the same time, that is after the exposure of the latter to the ageing conditions.

The ageing conditions shall be chosen from the following alternatives which should be appropriate to the material under test. It is recommended that materials differing in chemical composition should not be aged in the same enclosure. **A2** If a finished product is being studied for interaction effects, ensure that the test enclosure contains only that finished product test specimen. **A2**

5.2 Dry heat ageing

5.2.1 Temperatures

Polyolefin 70 °C

Latex 70 °C or 100 °C

A1 Polyurethane 80 °C, 125 °C or 140 °C **A1**

NOTE — The use of the non-standard temperature of 140 °C is included for the following technical reason: the temperature of the ageing test should be as high as possible to enable results to be obtained in the minimum time, but above this critical temperature the changes which occur when polyurethane foam is tested are not those which are found in service, so that the ageing test will no longer discriminate between foams of different behaviour in service.

5.2.2 Duration of ageing

Use 16 h, 22 h, 72 h, 96 h, 168 h, 240 h or some multiple of 168 h, with a tolerance $\pm 5\%$, but not more than ± 4 h.

5.3 Humidity ageing

5.3.1 Humidity

Use 100 % relative humidity or saturated steam.

5.3.2 Temperatures and duration of ageing

Material	Conditions
Polyurethane (all types)	85 °C for 20 h or 105 °C for 3 h
Polyurethane (polyether only)	120 °C for 5 h

A_1 Tolerance on temperature: ± 3 °C A_1

Tolerance on duration of ageing: $\pm 5\%$ but not more than ± 2 h, the time being measured from the time when the air in the vessel has been replaced by water vapour or steam.

NOTE – In this test for resistance to hydrolysis, the use of the non-standard temperatures of 105 °C and 120 °C is included for the following technical reasons: 105 °C is used because this temperature requires the use of a closed vessel so that control of the conditions is better than at the alternative of 100 °C; 120 °C is used because much experimental evidence has been accumulated at this temperature, but little or none at the alternative of 125 °C. Until these background data are collected it is not considered possible to change to 125 °C.

5.4 Reconditioning

A_1 After exposure to the ageing conditions, test pieces undergoing humidity ageing shall be dried at 70 °C \pm 3° C for 3 h per 25 mm of thickness, subject to a minimum of 3 h. The humidity-aged test pieces shall then be reconditioned in the atmosphere specified in 4.2 for 3 h per 25 mm of thickness. Dry-heat-aged test pieces shall merely undergo the reconditioning procedure. A_1

After reconditioning, the properties of the aged test pieces shall be tested.

6 Expression of results

6.1 Calculation

The percentage change in the property being examined is given by the formula

$$\frac{\bar{X}_a - \bar{X}_0}{\bar{X}_0} \times 100$$

where

\bar{X}_0 is the average value of the property before ageing;

\bar{X}_a is the average value of the property after ageing.

6.2 Format

The value of the percentage change shall be stated, followed by the test condition in parentheses, in order time, temperature and method.

EXAMPLE

Value % (16 h, 70 °C, dry heat).

7 Test report

The test report shall contain the following information:

- a) a reference to this International Standard;
- b) a description of the material $\boxed{A_2}$ or composite construction; $\boxed{A_2}$
- c) the procedure and conditions used;
- d) the average final value of the property $\boxed{A_2}$ of the cellular material; $\boxed{A_2}$
- e) the percentage change in property, expressed as indicated in clause 6;
- f) the date of the test;
- g) any deviations from this International Standard.

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com