

Thermoplastics pipes — Longitudinal reversion — Test method and parameters

The European Standard EN ISO 2505:2005 has the status of a
British Standard

ICS 23.040.20

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

National foreword

This British Standard is the official English language version of EN ISO 2505:2005. It is identical with ISO 2505:2005. It supersedes BS EN 743:1995 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee PRI/88, Plastic piping systems, to Subcommittee PRI/88/4, Method of tests for plastic piping systems and components, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii and iii, a blank page, pages 1 to 5 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 5 December 2005

© BSI 5 December 2005

ISBN 0 580 47367 8

English version

Thermoplastics pipes - Longitudinal reversion - Test method and parameters (ISO 2505:2005)

Tubes en matières thermoplastiques - Retrait longitudinal à chaud - Méthode d'essai et paramètres (ISO 2505:2005)

Rohre aus Thermoplasten - Längsschrumpf - Prüfverfahren und Kennwerte (ISO 2505:2005)

This European Standard was approved by CEN on 12 May 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2005 CEN. All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 2505:2005: E



EN ISO 2505:2005

Foreword

This document (EN ISO 2505:2005) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2005, and conflicting national standards shall be withdrawn at the latest by November 2005.

This document supersedes EN 743:1994.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 2505:2005 has been approved by CEN as EN ISO 2505:2005 without any modifications.



INTERNATIONAL
STANDARD

ISO
2505

Second edition
2005-05-15

**Thermoplastics pipes — Longitudinal
reversion — Test method and parameters**

*Tubes en matières thermoplastiques — Retrait longitudinal à chaud —
Méthode d'essai et paramètres*

Reference number
ISO 2505:2005(E)



**This document is now
PUBLIC**

© British Standards Institution 2011



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2505 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces ISO 2505-1:1994 and ISO 2505-2:1994, of which it constitutes a technical revision.

**This document is now
PUBLIC**



Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

blank

Not for Resale

Thermoplastics pipes — Longitudinal reversion — Test method and parameters

1 Scope

This International Standard specifies a method for determining the longitudinal reversion of thermoplastics pipes, to be carried out in either a liquid or in air. In case of dispute, heated liquid is used as the reference.

This International Standard is applicable to all thermoplastics pipes with smooth internal and external walls of constant cross-section. It is not applicable to non-smooth structured-wall thermoplastics pipes.

The parameters appropriate to the pipe material and recommendations for the maximum levels of reversion as a function of the pipe material are given in Annex A.

NOTE Measurement of longitudinal reversion is not considered relevant for pipe wall thickness greater than 16 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

3 Abbreviations

The abbreviations used for the plastic materials are as specified in ISO 1043-1. The following abbreviations are used in this International Standard.

ABS	acrylonitrile/butadiene/styrene
PA	polyamide (nylon)
ASA	acrylonitrile/styrene/acrylate
PB	polybutene
PE 32/40	polyethylene MRS 3,2/4
PE 50/63	polyethylene MRS 5/6,3
PE 80/100	polyethylene MRS 8/10
PE-X	cross-linked polyethylene
PVC-C	chlorinated poly(vinyl chloride)
PVC-U	unplasticized poly(vinyl chloride)
PVC-HI	high-impact poly(vinyl chloride)
SAN + PVC	styrene/acrylonitrile plus poly(vinyl chloride)

PP-H	polypropylene homopolymer
PP-B	polypropylene block copolymer
PP-R	polypropylene random copolymer

4 Principle

A pipe of specified length is placed in a liquid bath or air oven at a specified temperature for a specified time. A marked length of this portion of pipe is measured, under identical conditions, before and after heating. The reversion is calculated as a percentage of the change in length in relation to the initial length. The surface appearance of the test piece shall not be changed after heating.

5 Apparatus

5.1 Heated liquid bath, thermostatically controlled at the temperature, T_R , as specified in Table 1, unless otherwise specified by a referring standard.

The volume and agitation of the bath shall be such that the temperature remains within the specified temperature range when the test piece is immersed.

The liquid chosen should be stable at the specified temperature and should not otherwise affect the plastics material.

NOTE Glycerine, glycol, mineral oil free from aromatic hydrocarbons, or a solution of calcium chloride are suitable, but any other liquid in line with these recommendations can be used.

5.2 Air oven, thermostatically controlled such that it operates at the temperature, T_R , as specified in Table 1, unless otherwise specified, and capable of re-establishing this temperature within 15 min of the introduction of the test pieces. The oven shall be equipped with a thermostat capable of maintaining T_R to a permissible deviation of ± 2 °C.

5.3 Ancillary equipment

5.3.1 Device to hold the test piece(s) within the heating bath or oven in accordance with Clause 7.

5.3.2 Thermometer, with an accuracy to within $\pm 0,5$ °C.

6 Preparation

6.1 Test piece

Immediately after extrusion, the sample of pipe to be tested shall be stored at (23 ± 2) °C, or conditioning in accordance with 6.2 shall commence.

If the test is carried out immediately after production of the pipe, a pessimistic result may be obtained. In case of dispute, carry out the test at least 24 h after production and storage at (23 ± 2) °C.

Take as a test piece a pipe (200 ± 20) mm long.

Using, for example, a scribe, trace on this test piece two circumferential marks 100 mm apart, corresponding to the test area, at equal distances from the two ends.

Prepare a total of three similar test pieces per pipe sample.

Pipes of diameter 250 mm or larger may be cut into four even segments for production of test pieces.

Table 1 — Parameters for the determination using a liquid bath or air oven

Thermoplastics material ^a	Temperature of bath or air oven T_R °C	Duration of exposure min	Length of test piece mm
PVC-U	150 ± 2	For liquid bath: 15 for $e \leq 8$ 30 for $8 < e \leq 16$ For air oven: 60 for $e \leq 8$ 120 for $8 < e \leq 16$	200 ± 20
PVC-C	150 ± 2		
PVC-HI	150 ± 2		
SAN+PVC	150 ± 2		
PA	150 ± 2 (air oven only)		
PE 32/40	100 ± 2		
PE 50/63	110 ± 2		
PE 80/100			
PE-X	120 ± 2		
PB	110 ± 2		
PP-H et PP-B	150 ± 2		
PP-R	135 ± 2		
ABS et ASA	150 ± 2		
<i>e</i> mean wall thickness, in millimetres.			
^a Symbols in accordance with ISO 1043-1.			

6.2 Conditioning

Condition the test pieces at (23 ± 2) °C for a period of time according to the wall thickness of the pipe as follows:

≥ 1 h, for $e < 3$ mm

≥ 3 h, for $3 \text{ mm} \leq e < 8$ mm

≥ 6 h, for $8 \text{ mm} \leq e \leq 16$ mm

where e is the mean wall thickness in millimetres.

7 Procedure

At a temperature of (23 ± 2) °C, measure the distance L_0 between the marks to within 0,25 mm.

Set the temperature of the heating bath or air oven to the temperature T_R , as specified in Table 1, unless otherwise specified.

Suspend the test pieces allowing free movement in the heating bath or air oven so that they touch neither the walls nor the base of the bath or oven, and in the case of the bath so that there is a minimum distance of 30 mm between the upper boundary of the test area (see 6.1) and the fluid–air interface. Alternatively the test piece may be supported providing this does not inhibit reversion.

Leave the test pieces for the duration specified in Table 1, unless otherwise specified. Maintain the specified test temperature in the zone between the circumferential marks on the test piece.

Remove the test pieces from the bath or oven and allow them to hang freely in the same position. After they have cooled to (23 ± 2) °C, measure the maximum and minimum distance, L , between marks (diametrically opposed), following any curvature of the marked surfaces.

8 Expression of results

For each test piece, calculate the longitudinal reversion, $R_{L,i}$, as a percentage, using the following equation:

$$R_{L,i} = \frac{\Delta L}{L_0} \times 100$$

where

$$\Delta L = L_0 - L;$$

L_0 is the distance between the marks before the immersion, in millimetres;

L is the distance between the marks after the immersion, measured along the generatrices, in millimetres.

Choose those measurements of L which give the greatest value of ΔL , with ΔL being either positive or negative.

When the test piece has been cut into four even segments (see 6.1), the longitudinal reversion of the test piece, $R_{L,i}$, is calculated as the average of the three highest of the four results.

Calculate, as the value for the longitudinal reversion R_L of the pipe, the arithmetic mean of the values obtained for each of the three test pieces.

9 Test report

The test report shall include the following information:

- a) reference to this International Standard;
- b) full identification of the pipe;
- c) the nature of the heating fluid used;
- d) the duration of the test and the temperature T_R of the bath or oven;
- e) the change in length of each test pipe ΔL , indicating whether it is positive or negative;
- f) any change in the appearance of the test pieces during the immersion, or immediately afterwards, for example, bubbles or cracking;
- g) the value of the longitudinal reversion R_L of the pipe, calculated in accordance with Clause 8;
- h) all operating details not specified in this method, as well as any incidents likely to have influenced the results;
- i) the date of the test.

This document is now
PUBLIC

Annex A (informative)

Recommended basic specifications for longitudinal reversion

Using either a liquid bath or an air oven, the calculated value of the longitudinal reversion should conform to the recommended value given in Table A.1.

Table A.1 — Basic specifications of longitudinal reversion

Thermoplastics material	Reversion %	Thermoplastics material	Reversion %
PVC-U	≤ 5	PB	≤ 2
PVC-C	≤ 5	PP-H	≤ 2
PVC-HI	≤ 5	PP-B	≤ 2
SAN+PVC	≤ 5	PP-R	≤ 2
PE	≤ 3	PA	≤ 2
PE-X	≤ 3	ABS et ASA	≤ 5

For applications requiring more stringent specifications, a value smaller than the applicable limit given in Table A.1 may be adopted.



BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.

BSI

389 Chiswick High Road
London
W4 4AL