

BS EN ISO 2811-3:2011



BSI Standards Publication

Paints and varnishes — Determination of density

Part 3: Oscillation method (ISO
2811-3:2011)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 2811-3:2011. It supersedes BS EN ISO 2811-3:2001 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 66283 6

ICS 87.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2011.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

**Paints and varnishes - Determination of density - Part 3:
Oscillation method (ISO 2811-3:2011)**

Peintures et vernis - Détermination de la masse volumique
- Partie 3: Méthode par oscillation (ISO 2811-3:2011)

Beschichtungsstoffe - Bestimmung der Dichte - Teil 3:
Schwingungsverfahren (ISO 2811-3:2011)

This European Standard was approved by CEN on 19 February 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 2811-3:2011) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2011, and conflicting national standards shall be withdrawn at the latest by September 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2811-3:2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 2811-3:2011 has been approved by CEN as a EN ISO 2811-3:2011 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Temperature	2
6 Apparatus	2
7 Sampling	2
8 Procedure	2
8.1 General	2
8.2 Determination	2
9 Calculation	3
10 Precision	3
10.1 General	3
10.2 Repeatability limit, r	3
10.3 Reproducibility limit, R	3
11 Test report	3
Annex A (normative) Calibration of the apparatus — Determination of the apparatus constants	5
Annex B (informative) Density values for damp air, air-free water and tetrachloroethylene	6
Annex C (informative) Calculation of density at the reference temperature from measurements at other temperatures	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2811-3 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 2811-3:1997), which has been technically revised.

The main changes are:

- a) The unit for the density has been changed from grams per millilitre to grams per cubic centimetre, because this is the more common SI unit.
- b) The determination in duplicate has been changed to a single determination.
- c) The precision data has been corrected.
- d) The normative references have been updated.

ISO 2811 consists of the following parts, under the general title *Paints and varnishes — Determination of density*:

- *Part 1: Pycnometer method*
- *Part 2: Immersed body (plummet) method*
- *Part 3: Oscillation method*
- *Part 4: Pressure cup method*

Paints and varnishes — Determination of density —

Part 3: Oscillation method

1 Scope

This part of ISO 2811 specifies a method for determining the density of paints, varnishes and related products using an oscillator.

The method is suitable for all materials, including paste-like coatings. If a pressure-resistant type of apparatus is used, the method is also applicable to aerosols.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 density

ρ

mass divided by the volume of a portion of a material

NOTE This is expressed in grams per cubic centimetre.

4 Principle

A glass or stainless-steel U-tube is filled with the product under test. The tube is clamped at both ends and then subjected to oscillation. The resonance frequency of the filled tube varies with the mass contained in the tube, i.e. the density of the product under test.

5 Temperature

The effect of temperature on density is highly significant with respect to filling properties, and varies with the type of product.

Carry out the test at $(23,0 \pm 0,5)$ °C.

NOTE For some purposes a different temperature, for example $(20,0 \pm 0,5)$ °C, might be needed.

The test sample, tube and oscillator shall be conditioned to the specified or agreed temperature, and it shall be ensured that the temperature variation does not exceed 0,5 °C during testing.

6 Apparatus

Ordinary laboratory apparatus and glassware, together with the following.

6.1 Oscillator, consisting of a glass or stainless-steel U-tube and apparatus to cause the U-tube to oscillate. One model displays the resonance frequency; another calculates and displays the density.

6.2 Thermometer, accurate to 0,2 °C and graduated at intervals of 0,2 °C or finer.

6.3 Temperature-controlled chamber, capable of maintaining the oscillator and test sample at the specified or agreed temperature (see Clause 5).

6.4 Disposable plastic syringe, of sufficient capacity to fill the U-tube.

7 Sampling

Take a representative sample of the product under test, as described in ISO 15528. Examine and prepare the sample as described in ISO 1513.

8 Procedure

8.1 General

Carry out a single determination on a fresh test sample.

8.2 Determination

Ensure that the apparatus is clean, both by inspection and by checking that the display indicates the density of air (or the corresponding period of oscillation at resonance).

Fill the U-tube with the product under test (about 2 cm³) in accordance with the oscillator manufacturer's instructions (i.e. until the level is above the upper of the two clamps holding the U-tube). Avoid introducing air bubbles, which cause unsteady readings.

NOTE The presence of non-visible air bubbles becomes apparent due to the fact that the measured values vary considerably.

Close the upper filler-hole. Using the thermometer (6.2), check that the temperature of the temperature-controlled chamber is within the specified limits.

Start up and operate the oscillator in accordance with the manufacturer's instructions.

If using an apparatus which displays the period of oscillation at resonance, take at least three readings of the period of oscillation, T , and at least two of the temperature. The values of T shall not differ by more than 0,000 1 ms. If they do, make three more measurements.

If using an apparatus which displays the density directly, take at least three readings of the density and at least two of the temperature. The density values shall not differ by more than 0,000 2 g/cm³. If they do, make three more measurements.

After the measurements, clean the apparatus in accordance with the manufacturer's instructions. It is essential to leave it clean and dry, and to check that the display indicates the density of air (or the corresponding period of oscillation).

9 Calculation

If the period of oscillation, T , has been read, calculate the density, ρ , using Equation (1):

$$\rho = \frac{1}{A} \times (T^2 - B) \quad (1)$$

where A and B are two apparatus constants (see Annex A).

If the temperature used is not the reference temperature, the density can be calculated using Equation (C.1).

10 Precision

10.1 General

The precision of the method depends on the characteristics of the product to be tested. For materials which contain no entrapped air, the values in 10.2 and 10.3 are valid.

10.2 Repeatability limit, r

The value below which the absolute difference between two single test results, obtained on identical material by one operator in one laboratory using the same equipment within a short interval of time using the standardized test method, may be expected to lie, with a 95 % probability, is 0,001 g/cm³.

10.3 Reproducibility limit, R

The value below which the absolute difference between two test results, obtained on identical material by operators in different laboratories using the standardized test method, may be expected to lie, with a 95 % probability, is 0,002 g/cm³.

11 Test report

The test report shall include at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 2811, i.e. ISO 2811-3:2011;
- c) the type (model) of apparatus used;
- d) the test temperature;

- e) the density measurement determined in accordance with 8.2, or the density calculated in accordance with Clause 9, in grams per cubic centimetre, rounded to the nearest 0,001 g/cm³;
- f) any deviation from the test method specified;
- g) any unusual features (anomalies) observed during the test;
- h) the date of the test.

Annex A (normative)

Calibration of the apparatus — Determination of the apparatus constants

A.1 General

If using an apparatus which displays the period of oscillation at resonance, the apparatus constants need to be determined for use in Equation (A.1). If using an apparatus which displays the density directly, the constants are entered into the memory of the data-processing unit of the apparatus.

The apparatus constants have to be determined and regularly checked by the user. They are usually obtained by measurements in air and in distilled or deionized water of at least grade 2 purity, as defined in ISO 3696.

A.2 Procedure

Make several measurements with air and water over a period of several minutes in each case, as described in 8.2. If the values obtained are not constant, repeat the measurements.

The apparatus constants are valid only at temperatures which do not differ from the temperature, t_T , at which they were determined by more than 0,5 °C. For other test temperatures, the constants shall be determined again.

The apparatus constants shall be determined at the beginning of each series of measurements and checked at the end.

NOTE Differences can occur in the period of oscillation due to the presence of impurities.

A.3 Calculation of apparatus constants

Calculate the mean values of the period of oscillation for water, T_W , and for air, T_A . Use these mean values to calculate the two apparatus constants, A and B, as given by Equation (A.1):

$$\rho = \frac{1}{A} \times (T^2 - B) \quad (\text{A.1})$$

Annex B (informative)

Density values for damp air, air-free water and tetrachloroethylene

Table B.1 — Density of damp air

Temperature	Pressure								Relative humidity
	mbar								
°C	900	920	940	960	980	1 000	1 013,25	1 050	%
	Density								
	ρ_A								
	g/cm ³								
15	0,001 08	0,001 11	0,001 13	0,001 15	0,001 18	0,001 20	0,001 22	0,001 26	89
20	0,001 06	0,001 09	0,001 11	0,001 13	0,001 16	0,001 18	0,001 20	0,001 24	65
25	0,001 05	0,001 07	0,001 09	0,001 12	0,001 14	0,001 16	0,001 18	0,001 22	48
30	0,001 03	0,001 05	0,001 07	0,001 10	0,001 12	0,001 14	0,001 16	0,001 20	35,8
35	0,001 01	0,001 03	0,001 06	0,001 08	0,001 10	0,001 12	0,001 14	0,001 18	27
40	0,001 00	0,001 02	0,001 04	0,001 06	0,001 08	0,001 11	0,001 12	0,001 16	20,6
45	0,000 98	0,001 00	0,001 02	0,001 05	0,001 07	0,001 09	0,001 10	0,001 14	15,9
50	0,000 96	0,000 99	0,001 01	0,001 03	0,001 05	0,001 07	0,001 09	0,001 13	12,3

Table B.2 — Density of pure, air-free water

Temperature <i>t</i> °C	Density ρ_W g/cm ³	Temperature <i>t</i> °C	Density ρ_W g/cm ³	Temperature <i>t</i> °C	Density ρ_W g/cm ³
10	0,999 7	22	0,997 77	25	0,997 04
11	0,999 6				
12	0,999 5	22,1	0,997 75	25,1	0,997 02
13	0,999 38	22,2	0,997 72	25,2	0,996 99
14	0,999 24	22,3	0,997 7	25,3	0,996 97
15	0,999 1	22,4	0,997 68	25,4	0,996 94
16	0,998 94	22,5	0,997 65	25,5	0,996 91
17	0,998 77	22,6	0,997 63	25,6	0,996 89
18	0,998 59	22,7	0,997 61	25,7	0,996 86
19	0,998 4	22,8	0,997 58	25,8	0,996 83
		22,9	0,997 56	25,9	0,996 81
20	0,998 2	23	0,997 54	26	0,996 78
				27	0,996 51
20,1	0,998 18	23,1	0,997 51	28	0,996 23
20,2	0,998 16	23,2	0,997 49	29	0,995 94
20,3	0,998 14	23,3	0,997 46	30	0,995 65
20,4	0,998 12	23,4	0,997 44	31	0,995 34
20,5	0,998 1	23,5	0,997 42	32	0,995 02
20,6	0,998 08	23,6	0,997 39	33	0,994 7
20,7	0,998 05	23,7	0,997 37	34	0,994 37
20,8	0,998 03	23,8	0,997 34	35	0,994 03
20,9	0,998 01	23,9	0,997 32		
21	0,997 99	24	0,997 29	36	0,993 68
				37	0,993 33
21,1	0,997 97	24,1	0,997 27	38	0,992 96
21,2	0,997 95	24,2	0,997 24	39	0,992 59
21,3	0,997 92	24,3	0,997 22	40	0,992 21
21,4	0,997 9	24,4	0,997 19		
21,5	0,997 88	24,5	0,997 17		
21,6	0,997 86	24,6	0,997 14		
21,7	0,997 84	24,7	0,997 12		
21,8	0,997 81	24,8	0,997 09		
21,9	0,997 79	24,9	0,997 07		

Table B.3 — Density of tetrachloroethylene

Temperature <i>t</i> °C	Density ρ g/cm ³
0	1,655 8
15	1,631 1
20	1,622 8
25	1,614 6
30	1,606 4
35	1,598 3

Annex C (informative)

Calculation of density at the reference temperature from measurements at other temperatures

If the density of the product under test is determined at a temperature different from the reference temperature, the density, ρ_C , in grams per cubic centimetre, at the reference temperature can be calculated using Equation (C.1):

$$\rho_C = \frac{\rho_t}{[1 + \gamma_m(t_C - t_T)]} = \rho_t [1 - \gamma_m(t_C - t_T)] \quad (\text{C.1})$$

where

ρ_t is the density, in grams per cubic centimetre, of the product at the test temperature;

γ_m is the volume coefficient of thermal expansion of the product under test, the approximate value of γ_m being $2 \times 10^{-4} \text{ }^\circ\text{C}^{-1}$ for waterborne paints and $7 \times 10^{-4} \text{ }^\circ\text{C}^{-1}$ for other paints;

t_C is the reference temperature, in degrees Celsius;

t_T is the test temperature, in degrees Celsius.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™